Magnetic COFs as satisfied support for lipase immobilization and recovery to effectively achieve the production of biodiesel by great maintenance of enzyme activity.

Zi-Wen Zhou

Sichuan University

Xiu Xing

Sichuan University

Jun Li

Sichuan University

Zu-E Hu

Sichuan University

Zong-Bo Xie

East China University of Technology

Na Wang

Sichuan University

Xiao-Qi Yu (✉ xqyu@scu.edu.cn)

Sichuan University

Research

Keywords: COFs, Covalent-Organic Frameworks, biodiesel

Posted Date: November 19th, 2020

DOI: <https://doi.org/10.21203/rs.3.rs-110352/v1>

License: This work is licensed under a Creative Commons Attribution 4.0 International License.

[Read Full License](#)

Version of Record: A version of this preprint was published at Biotechnology for Biofuels on July 14th, 2021. See the published version at <https://doi.org/10.1186/s13068-021-02001-0>.

Abstract

Background: Production of biodiesel from renewable sources such as non-edible vegetable oils by enzymatic catalysis has been a hotspot but remains a challenge on the efficient use of an enzyme. COFs featuring large surface area and porosity should be applied as an ideal support to impede aggregation of lipase and methanol. However, the naturally low density limits its application. In this work, we reported a facile synthesis of core-shell magnetic COF composite ($\text{Fe}_3\text{O}_4@\text{COF-OMe}$) to immobilize RML (*Rhizomucor miehei* lipase), in order to achieve its utilization in biodiesel production.

Result: This strategy gives extrinsic magnetic property, and the magnetic COFs is much heavier and could disperse in water medium well, facilitating the attachment with enzyme. The resultant biocomposite exhibited an excellent capacity of RML due to its high surface area and fast response to the external magnetic field, as well as good chemical stability. The core-shell magnetic COF-OMe structure not only achieved highly efficient immobilization and recovery processes, but also maintained the activity of lipase to a great extent. $\text{RML}@\text{Fe}_3\text{O}_4@\text{COF-OMe}$ performed well in practical applications, while free lipase did not. The biocomposite successfully achieved the production of biodiesel from *Jatropha curcas* Oil with a yield of about 70% in the optimized conditions.

Conclusion: Magnetic COFs ($\text{Fe}_3\text{O}_4@\text{COF-OMe}$) for RML immobilization greatly improved catalytic performance in template reaction and biodiesel preparation. The magneticity makes it easily recovered and separated from system. This first successful attempt of COFs-based immobilized enzyme broadened the prospect of biodiesel production by COFs with some inspiration.

Background

With the character of biodegradability, biodiesel from renewable sources such as vegetable oils and animal fat produced by enzymatic transesterification has attracted the interest of scientists.^{1, 2} Immobilized lipase received incredible interest among the biotechnology community for the production of biodiesel with the advantages of absence of side reactions, low energy requirement and free pollutions, compared to basic chemical catalysts.³ A range of carriers such as microemulsion-based organogels (MBGs),⁴ carbon nanotube,^{3, 5} silica nanoparticles⁶ and organic polymers⁷ have been successfully utilized. However, such common supports usually affect the enzymatic activity and the relatively small surface area limits its loading capacity.

In recent years, porous materials have been developed and applied to integrate enzyme based on their excellent features of high surface area and porosity which facilitate immobilization process and preservation of biomolecules.⁸ Metal-Organic Frameworks (MOFs) with high surface area, pore channels and chemical functionality^{9–11} has been reported to entrap lipase for biodiesel.^{12–14} However, MOFs is chemical stability and metal toxicity unsatisfactory, since some are water-sensitive or easily digested.^{15–17} And the leakage of unwanted metal ions may have a negative impact on biomolecule conformation. As a sister material of MOFs, Covalent-Organic Frameworks (COFs) featuring long-term water/chemistry

stability and no toxic metal ion are highly desirable.^{18, 19} This emerging porous nanomaterial are prepared by linkage of organic building units covalently into extended structures to make crystalline materials, whose backbones are composed of light elements (B, C, N, O, Si).^{20, 21} Since the constituents of COFs do not undergo significant change when covalently linked, the structures of resulting COFs with desired composition, pore size, and aperture could be predicted and prepared by the programming of monomers.^{20, 22} Its tunability and stability enable it to apply in gas storage,^{23, 24} sensing,^{25, 26} and catalysis^{27, 28}, as well as immobilization of enzyme. This is because COFs could provide appropriate abundant micro and mesopore channels, affording large surface area for infiltrating biomolecules. Through design, the good matched pore size could impede the aggregation of enzymes and facilitate the rapid transportation of reagents at the same time.²⁹ In addition, there are also specific sites on the interface for weak interaction or covalent binding,^{30, 31} so that the immobilization process varies with a practical need.³²

Since Kandambeth et al. reported the first example to utilize COFs for enzyme immobilization,³³ a few COF-based immobilized enzyme are reported for applications, such as kinetic resolution of secondary alcohols by Sun et al(TPB-DMTP-COF@Lipase PS)³⁴ and chiral separation by Zhang et al(lysozyme@COF 1).³⁵ As one of the common substrates (methanol) itself has an adversely effect on the lipase,³⁶ COFs featuring large surface area and porosity can be an ideal carrier for lipase adsorption and reagents transportation, which impedes the aggregation of enzyme and the effect of methanol, indicating a potential utility for enzyme immobilization and biodiesel production. However, there are also some challenges for highly efficient use of COFs as a carrier. One of the matters is attributed to the backbone consisted of light elements. For one thing, the naturally low density³⁷ hinders its dispersion in water solution, which is not conducive to the enzyme enrichment on the support. For another, the strong electrostatic interaction between nanoparticles and containers (such as plastic tubes) make it adhere to the surface, which is not convenient to gather and preserve. Therefore, it has not been reported for COFs-based immobilized lipase to achieve the transition of biodiesel and these inconveniences hinder its applied research in industrial production.

Our group has reported several works about immobilized enzyme in applications such as biomass conversion and biodiesel production³⁸⁻⁴⁰. During these processes, we have introduced Fe₃O₄ nanoparticles to facilitate recovery. Thus, we conceived a magnetic strategy to give extrinsic magnetic property to COFs to overcome these factors mentioned before. The resultant composite is much heavier and could disperse in water medium well, facilitating the attachment with enzyme. Combining the characters of COFs and magnetism, the magnetic COFs is not only beneficial to reduce the aggregation of lipase and influence of methanol by the uniform pore channels, but also to recovery by an external magnetic fields,⁴¹⁻⁴⁴ which lays a good foundation for its efficient industrial production of biodiesel. Here, we reported core-shell magnetic COFs (Fe₃O₄@COF-OMe), which Fe₃O₄ nanoparticles is wrapped by COF-shell. This composite can be dispersed in PBS buffer and recovered easily due to the introduction of magnetism. The prepared composite is used to immobilized RML (*Rhizomucor miehei* lipase, EC 3.1.1.3,

a kind of lipase, triacylglycerol hydrolases) by physical absorption, with a high enzyme uptake capacity of and good maintenance of activity in harsh conditions. The resultant immobilized RML finally achieved the production of biodiesel from a renewable source, *Jatropha curcas* Oil (non-edible vegetable oil) with a satisfactory yield after optimizing the conditions of template reactions.

(See Scheme 1 in the Supplementary Files)

Results And Discussion

Preparation and characterization of Fe_3O_4 @COF-OMe nanoparticles and immobilized RML.

The facile synthesis of magnetic core-shell COFs is based on the room-temperature synthesis of COF-OMe (Fig S1-S4). The detail preparation and immobilization process is illustrated in Fig. 1, which involved two main steps: (1) coprecipitation synthesis of magnetic Fe_3O_4 nanoparticles and rapid room-temperature synthesis of the core-shell structured magnetic Fe_3O_4 @COF-OMe composites in a one-pot process by mixing Fe_3O_4 nanoparticles (30 mg, 0.13 mmol) as the magnetic core and 2,5-dimethoxyterephthalaldehyde benzidine (DMTP, 0.24 mmol) and 1,3,5-tris(4-aminophenyl)-benzene (TPB, 0.16 mmol) as building units of COF-OMe in the acetonitrile according to the result of morphology (Fig. S5). (2) immobilization process of RML by physical absorption in PBS buffer. The as-prepared biocomposites could be applied in the production of biodiesel.

The morphologies of COF-OMe, Fe_3O_4 @COF-OMe and RML@ Fe_3O_4 @COF-OMe are verified by scanning electron microscopy (SEM) and transmission electron microscopy (TEM), shown in Fig. 2. It can be seen that COF-OMe has good dispersity and exhibits a uniform nanosphere structure (Fig. 2(A)) with a size of 500–600 nm. The core-shell structure of Fe_3O_4 @COF-OMe with the thickness of COF shell about 70 nm is confirmed by the TEM image (Fig. 2(B)). The Fe_3O_4 @COF-OMe particles display similar spherical morphology as COF-OMe (Fig. 2(C)). And after enzyme immobilization, the composite morphology remains unchanged, only the surface becomes rough (Fig. 2(D)).

Fourier transforms infrared (FT-IR) spectroscopy is carried out to prove that the successful synthesis of Fe_3O_4 @COF-OMe. As shown in Figure S6, The FTIR spectrum of Fe_3O_4 contains a band at 579 cm^{-1} , which is assigned to characteristic Fe-O-Fe stretch. The characteristic absorption bands of monomer 2,5-dimethoxyterephthalaldehyde (DMTP) at 2868 cm^{-1} , 2760 cm^{-1} and 1677 cm^{-1} demonstrate the existence of aldehyde groups, where the 1677 cm^{-1} is assigned to the C=O stretching. The bands at 1207 cm^{-1} , 1025 cm^{-1} attributed to the aromatic =C-O-C asymmetric and symmetric vibration respectively and the peak at 1610 cm^{-1} assigned to the C=N stretch mode are observed in the curve of Fe_3O_4 @COF-OMe, which means the successful synthesis of COF-OMe by condensation of aldehydes and amines. Along with the characteristic Fe-O-Fe stretch found in the curve of biocomposite, the combination of COF-shell and magnetic Fe_3O_4 was proved, demonstrating the successful preparation of Fe_3O_4 @COF-OMe.

The crystalline structure of $\text{Fe}_3\text{O}_4@\text{COF-OMe}$ is examined by PXRD patterns (Fig. 3(A)). XRD image exhibits 6 peaks with 2θ at 30.12° , 35.42° , 43.18° , 53.64° , 56.96° , and 62.60° , corresponding to (220), (311), (400), (422), (511) and (440),⁴¹ which matches well with magnetite, indicating that the $\text{Fe}_3\text{O}_4@\text{COF-OMe}$ are well crystallized after coating COFs. As to COFs, the characteristic peak appears about 2.0° of 2θ (Cu K α 1), attributed to the (100) facet of a primitive hexagonal lattice.²⁹ This is found in the PXRD image of COF-OMe pattern, shown inset. The peak at 2.75° is attributed to the plane (100) of COF-OMe. The other planes, like (110), (200), (210), (220) corresponds to peaks at 4.8° , 5.5° , 7.3° and 9.2° .⁴⁵ This pattern confirms the formation of the crystalline form of COF-OMe. These successful and facile preparation represents it an alternative way of traditional synthesis of them, which provides guidance for the exploration of other COFs.

Thermogravimetry analysis (TGA) expounds the thermal stability and different components of biocomposites, shown in Fig. 3(B) and Fig. S7 (DTG). For COF-OMe, there is a distinct decrease in weight that occurs at $300\text{--}400^\circ\text{C}$, which means its structure begins to disintegrate. In other words, a long plateau under 419°C demonstrates the high thermal stability of COF-OMe. As for $\text{RML}@\text{Fe}_3\text{O}_4@\text{COF-OMe}$, the weight loss at about 280°C can be attributed to the removal of lipase. The two parts of mass losses occurred at 48°C and 410°C is consistent with it of bare Fe_3O_4 (4% at 48°C) and COF-OMe (12% at 410°C) respectively. The sharp weight-loss at over 700°C may due to the reaction between melt COF-OMe and Fe_3O_4 of core-shell structure. In a word, the support $\text{Fe}_3\text{O}_4@\text{COF-OMe}$ displays such satisfactory thermal stability as COF-OMe, where the TG curve runs smoothly under 400°C . At the same time, the core-shell structure doesn't react mutually under 700°C , which means it is qualified to be a good carrier of an enzyme.

The magnetic property of these nanospheres is characterized by a vibrating sample magnetometer (VSM). The magnetic hysteresis curve (Fig. 3(C)) of nanomagnetic Fe_3O_4 has an excellent magnetic property, with a saturated magnetization value of 46.07 emu g^{-1} . There is a drop observed in $\text{Fe}_3\text{O}_4@\text{COF-OMe}$ ($\sim 20\text{ emu g}^{-1}$) and $\text{RML}@\text{Fe}_3\text{O}_4@\text{COF-OMe}$ ($\sim 6\text{ emu g}^{-1}$), which are attributed to the loading of COF shell and enzyme. Despite this, rapid aggregation of biocomposites from the suspension is obtained with the help of an external magnet, which could reduce the desorption of the enzyme by the centrifugation in this way.

Nitrogen sorption isotherms measured at 77 K indicates the BET surface of $\text{Fe}_3\text{O}_4@\text{COF-OMe}$ decreases from $232\text{ cm}^2\text{ g}^{-1}$ to $28\text{ cm}^2\text{ g}^{-1}$ after immobilization of RML (Fig. 3(D)). The pore-size distribution analyses of $\text{Fe}_3\text{O}_4@\text{COF-OMe}$ and $\text{lipase}@\text{Fe}_3\text{O}_4@\text{COF-OMe}$ calculated by the density functional theory have shown that both of the samples have a pore size centered at about 3.1 nm, whereas the pore volume drops from 0.223 cc g^{-1} to 0.036 cc g^{-1} after RML absorption (Figure S8 & Table S1). The result indicates the successfully loading of lipase, and it suggests that the magnetic COFs may serve as a promising carrier for lipase immobilization.

To further verify the distribution of RML on the support, the Fluorescein-labelled enzyme is an optical way to prove its existence and determine its distribution. Fluorescent probe fluorescein isothiocyanate (FITC) is used to label the enzyme molecules (green) generally.^{44, 46} However, it is not available to use in RML@COF-OMe in this work. This is because the support, COF-OMe itself, is fluorescent. Under an excitation $\lambda = 488$ nm (the parameter of FITC-labelled protein), the long emission at $\lambda = 490\text{--}690$ nm is got by the COF-OMe itself, which interferes with the detection of FITC-labelled enzyme, so it is incapable to prove the existence of enzyme on the surface of the carrier and determine its distribution (Figure S9). In this case, Rhodamine B isothiocyanate (RBITC)-labeled RML was prepared. The RBITC-labelled RML (red) is present throughout Fe_3O_4 @COF-OMe (green), which is observed by CLSM analysis at excitation wavelengths of 488 nm for Fe_3O_4 @COF-OMe and 543 nm for RBITC-RML, demonstrating that the enzyme accommodated in this composite (Figure S10).

Immobilized RML activity assay

To facilitate recycling in the application, we employed the core-shell magnetic COFs (Fe_3O_4 @COF-OMe) to enhance the recovery efficiency. Here, we first compared this strategy with the common mixing method. This tactic is to make COFs magnetic by mixing COFs and magnetic Fe_3O_4 nanoparticles in solutions (Fe_3O_4 -COF-OMe), where the Fe_3O_4 nanoparticles are attached on the surface of COFs, shown in Fig. 4. The SEM & EDS mapping images display these two magnetic strategies in detail. In Fig. S11, the element Fe (purple pots) gather in some specific places. Compared with the morphology image left, it can be attributed to smaller particles (magnetic Fe_3O_4). This is the evidence that the Fe_3O_4 is adhering to the surface of COFs. However, element Fe (the yellow pots in Fig. S12) are averagely distributed on the image with other color dots, which represents nanoparticles Fe_3O_4 are wrapped.

Both immobilized enzyme uptake capacities were calculated by the method of Coomassie blue staining (Table S1). And the enzymatic activity was tested as followed.

The activity of immobilized RML was studied by hydrolysis of p-NPA (see details in Support information). The catalytic activities, stability in a different environment (such as pH, heat) of an immobilized enzyme, were shown in Fig. 5. After immobilized, there was a shuttle decrease in activity in hydrolysis of p-NPA of both immobilized RML (Fig. 5(A)). The best outcome could recover to 60% of the free enzyme (Fe_3O_4 @COF-OMe) as the time prolonged. The Fe_3O_4 @COF-OMe also showed good thermal and pH stability. The stability of the activity for both free RML and immobilized enzyme in different pH ranging from 5.0 to 10.0 was studied and plotted in Fig. 5(B). The result showed that the optimal pH altered slightly, from about 7.0 to 8.0. Thermal stability was investigated, which the biocomposites were stored at 60 °C overnight ahead of tests. It was observed that there is a decrease in activity for all of them, but the range of decrease was not significant for Fe-COFs immobilized RML (Fig. 5(C)). We found that although the Fe_3O_4 -COF-OMe has a higher RML uptake, the enzyme activity of it did not perform well. It is due to the non-uniform and solid two-phase in framework prepared by physical mixing and adhesion strategy, which was not enough to maintain the RML activity.

Based on the outcomes of activity assay, $\text{Fe}_3\text{O}_4@\text{COF-OMe}$ can indeed be optimal support to maintain RML activity for the subsequent transesterification reaction.

Optimization of transesterification conditions

The preparation process of biodiesel is a kind of transesterification reaction which belongs to a specific catalytic reaction of lipase. So here, we studied the catalytic performance of immobilized RML on transesterification of 2-phenol with vinyl acetate as a template reaction and improved the yields by optimizing conditions (Figure S13). First of all, both $\text{Fe}_3\text{O}_4@\text{COF-OMe}$ and $\text{Fe}_3\text{O}_4\text{-COF-OMe}$ were adapted to catalyze under the same feeding ratio (20 μL of 2 phenol, 40 μL of vinyl acetate, 2 mL of solvents and 0.1 mg of RML). We found that this result was consistent with it of enzyme activity. It was $\text{RML}@\text{Fe}_3\text{O}_4@\text{COF-OMe}$ that performed best (Fig. 6(A)). At the same time, the yields of the immobilized RML were better than that of free RML, nevertheless, the activities were lower than it. This proved that in the application, the protection functioning was far greater than the loss of enzyme activity.

The solvent effect of the reaction in which n-Hexane functioned as a solvent was shown in Fig. 6(B), with the highest yield up to 80%. Interestingly, according to the results, we found that the yields altered by the trends of the polarity of different solvents. In detail, the hydrophobic the solvent was, the higher yields we got. As for the optimized solvent, whose log P value was largest, the yield was much higher than the others at the same time. Carbon tetrachloride, trichloroethylene and toluene, whose polarity was similar, had almost the same yields of 20%. However, if the solvent was hydrophile, such as THF, acetone, the transesterification didn't happen in it. To furtherly verify the hydrophobic solvents were conducive to this reaction, several homologous liquids of n-Hexane were adapted (Fig. S14). n-Hexane, c-Hexane and n-Heptane had similar yields, which indicated the hydrophobic solvents were beneficial in this work.

Then we investigated the influence of temperature on the reaction (Fig. 6(C)). Apparently immobilized RML did better in the transesterification than the free enzyme. With the rise of temperature, the yield of the immobilized enzyme increased gradually and reached a peak at about 50 $^{\circ}\text{C}$, while it of liquid enzyme decreased continuously. The loss of activity may due to the conformation change of RML caused by high temperature, which affected the binding of the active center and substrate. It demonstrated that the carrier could effectively protect the enzyme from heat and kept its catalytic activity.

The dosage of RML has also played an important role in a transesterification reaction, where excessive enzyme not only causes waste but also reduces the rate due to the aggregation. So here, in Figure, we studied the yields of the reaction with different amount of enzyme. As we can see, in Fig. 6(D), the yield of free RML still went up along with the increase of amount. For Immobilized RML, the yield didn't show a significant rise when the enzyme added from 0.5 to 0.8 mg. Considering the efficiency and economy of this reaction, 0.5 mg of free and immobilized RML was used in every single sample assay. At the optimal conditions, n-Hexane as a solvent, the transesterification yield can reach to about 80% with 0.5 mg of immobilized RML at 50 $^{\circ}\text{C}$.

The preservation of activity by the protection of support in organic solvents and high temperature were shown above, where the immobilized RML always did better in different organic solvents and at over 30 °C than free lipase. To furtherly assess the function of COFs in protecting the catalytic ability of RML, the tolerance of immobilized RML against ultrasonic operation was investigated. As shown in Figure S15, the yields of immobilized RML did not change significantly after ultrasonic treatment, and always higher than that of free RML at the same time. Here we also studied the leakage ratio of RML by washing the immobilized lipase (Fig. 7). As we can see, the amount loss of RML for every single wash was about 2% and the total leakage ratio was less than one-fifth after 8 wash cycle, which indicated a good ability to preserve the lipase from washing operation.

Production of biodiesel

Having established the efficiency of RML@Fe₃O₄@COF-OMe in the templet reaction, then we studied its catalytic ability in the production of biodiesel from non-edible *Jatropha curcas* Oil (Table 1). The outcomes^a catalyzed by immobilized RML are much better than it by free RML, with a yield of 67.8% and 5.1% respectively. It is noticed that there is an obvious loss in enzymatic activity when the amount of methanol exceeds the stoichiometric ratio (3:1). This is due to the inhibitory effect of methanol, and the activity is irreversibly inactivated.³⁶ Compared to free RML, magnetic Fe₃O₄ nanoparticles could protect RML from the methanol, as the product could be detected with a satisfactory yield. It is noticed that the protective effect is not permanent although the activity could be maintained if the concentration of methanol is doubled (Entry 4, Table 1). But If the amount of methanol is excessive too much (15:1 and 30:1), there is a huge loss in yield. In a word, the nanoparticle efficiently improved the stability and maintained the activity of the enzyme in practical application.

Table. 1 RML@Fe₃O₄@COF-OMe-catalyzed production of Biodiesel by *Jatropha curcas* Oil^a.

Entry	Enzyme	Methanol (μL)	Yield (%)
1	Free RML	10	5.1
2	Free RML	20	trace
3	RML@Fe ₃ O ₄ @COF-OMe	10	67.8
4	RML@Fe ₃ O ₄ @COF-OMe	20	72.3
5	RML@Fe ₃ O ₄ @COF-OMe	50	trace
6	RML@Fe ₃ O ₄ @COF-OMe	100	trace

^aReaction conditions: *Jatropha curcas* Oil (0.15 mmol), methanol (0.45 mmol, 10 μL), n-Hexane (3 mL), RML@Fe₃O₄@COF-OMe/RML (0.5 mg), and 50 °C at 100 rpm for 48 h. The yields were determined by GC.

Conclusion

In summary, we successfully prepared a core-shell magnetic COFs structure (Fe₃O₄@COF-OMe) in a facile way. The resultant magnetic COFs exhibited a great uptake of RML and facilitated the separation taking advantage of features of high surface area, porosity, good chemical stability and strong magnetic response. The support could maintain the activity of RML and perform well in practical applications. We applied the immobilized RML into the production of biodiesel from un-editable *Jatropha curcas* Oil and obtained a satisfactory yield. This first successful attempt of COFs-based immobilized lipase demonstrates their promising applications in the production of biodiesel.

Materials And Methods

Materials

All chemicals and reagents were commercially available and used without further purification. 2,5-dimethoxyterephthalaldehyde benzidine (DMTP), 1,3,5-tris(4-aminophenyl)-benzene (TPB) were purchased from Shanghai KaiYuLin pharmaceutical technology co., LTD. *Rhizomucor miehei* lipase (RML) was supplied by Sigma-Aldrich. Iron(II) chloride tetrahydrate (FeCl₂·4H₂O), Iron chloride hexahydrate (FeCl₃·6H₂O) were obtained by Chengdu HuaXia Chemical Reagents Co., LTD. Rhodamine B isothiocyanate (RBITC), 4-Nitrophenyl acetate (p-NPA) were purchased by Aladdin Chemistry Co., Ltd (Shanghai, China). Methanol (HPLC), Tetrahydrofuran (anhydrous, HPLC) were supplied by Thermo Fisher Scientific (China) Co., LTD. Bradford Protein Assay Kit was obtained by Beyotime Biotech Inc, Shanghai, China. The other chemical reagents and solvents were purchased by Chengdu Chron Chemicals. Co., LTD. *Jatropha curcas* Oil was bought from market Liangzhou, Sichuan province.

Characterization

Powder X-ray diffraction (PXRD) data were collected on X'Pert Pro MPD DY129 X-ray diffractometer (40 kV, 40 mA) using Cu K α ($\lambda = 1.5406 \text{ \AA}$) radiation. The gas adsorption isotherms were collected on a surface area analyzer, Quantachrome Instruments version 3.01 Autosorb Station 2. The N₂ sorption isotherms were measured at 77 K using a liquid N₂ bath. Scanning electron microscopy (SEM) images were collected using a JSM-5900LV (JEOL, Japan). Transmission electron microscopy (TEM) images were collected using a HITACHI H-600, operating at 75 kV. IR spectra were recorded on a Nicolet Impact 410 FTIR spectrometer. The confocal laser scanning microscopy (CLSM) data were collected on a Leica SP5 under an excitation $\lambda_{\text{ex}} = 488 \text{ nm}$ and $\lambda_{\text{ex}} = 543 \text{ nm}$. The vibrating sample magnetometer (VSM) data were measured by LakeShore7404. Thermal Gravity analysis (TG/TGA) was tested and analyzed by METTLER TOLEDO TGA/DSC2/1600.

Preparation of magnetic Fe₃O₄ nanoparticles

The magnetic Fe₃O₄ was prepared by a facile coprecipitation method. Firstly, FeCl₂·4H₂O (0.74 g, 3.7 mmol) and FeCl₃·6H₂O (1.22 g, 7.5 mmol) were dissolved in deionized water (25 mL) by vigorous stirring. Then 30% (w/v) NaOH solutions (7 mL) was added dropwise, keeping stirring for another 1–2 h. The obtained black magnetic precipitate was washed by deionized water several times until the pH values decrease to 7.0. With the help of the external magnetic field, the nanoparticles were separated and dried under vacuum.

Preparation of core-shell magnetic COFs (Fe₃O₄@COF-OMe)

The preparation of magnetic COFs was similar to the preparation of COF-OMe, addition the magnetic Fe₃O₄ particles along with monomers, The COF-OMe shell is shaped and formed core-shell structure. In brief, to a 50 mL of acetonitrile solution containing DMTP (0.24 mmol) and TPB (0.16 mmol), Fe₃O₄ nanoparticles (30 mg) was added. After sonicated for 5 min. acetic acid (17.5 M, 3 mL) was dropped into the suspension. The reaction proceeded at room temperature for 2 h. The grey-yellow precipitates can be separated by the external help of a magnet. After washed by methanol 3 times, the remaining monomers were cleared from reaction mixtures by anhydrous tetrahydrofuran using Soxhlet extraction for 2 days. The product was dried under vacuum at 50 °C for 24 h to afford Fe₃O₄@COF-OMe.

Preparation of RBITC-labelled RML (RBITC-RML).

RBITC (0.5 mg) and RML solution (3 mL) were added into 4 mL of PBS buffer solution (pH 7.4) and left in darkness overnight under gentle stirring. The RBITC-tagged RML (RBITC-RML) was obtained by dialysis for 2 days in PBS buffer.

Immobilization of RML

The RML was immobilized by physical adsorption in PBS buffer. The support material was first immersed into PBS buffer. 0.1 mg/mL of RML was then added. Keep the mixture in a rolling incubator overnight at 20 rpm. The composite and supernatant were collected by centrifugation and magnet to observe the activity and immobilization efficiency. The uptake capacity was measured by the method of Coomassie

blue staining with the use of Bradford Protein Assay Kit (see details in Support Information). The enzyme uptake capacity is calculated by:

$$Ca = (C_0 - C) V / M_s$$

C_0 represents the initial concentration of RML solutions, while C is the concentration of supernatant after immobilization. V is the total volume of the system. M_s is the mass of support.

The enzyme activity assay

To a tube, p-NPA (500 μ L, 2 μ mol/mL) and PBS buffer (2 mL, pH = 7.4) with immobilized RML (or 2 mL total volume of free enzyme and PBS buffer solution) were added. The absorbance at 405 nm was detected. Finally, the product concentrations were corrected for the auto-hydrolysis of p-NPA and also the absorbance of p-NPA left in the solution. (See details in Support Information).

Transesterification Reaction.

The transesterification of 2-phenylethanol and vinyl acetate were chosen as a template reaction. Generally, 2-phenylethanol (20 μ L) and vinyl acetate (40 μ L) were added into a tube with 2 mL of solvent. Different bio-complex, solvent, temperature, and amount of immobilized enzyme were optimized. The yields of transesterification were determined by HPLC analysis with a Waters-HPLC on C18 columns using methanol/water (70:30) as the eluent.

Production of Biodiesel

In the experiment of production of Biodiesel, to a tube of 3 mL of the solvent containing *Jatropha curcas* Oil (0.15 mmol) and methanol (0.45 mmol), immobilized RML was mixed. Then the system was put into a shaker for 48 h at conditions optimized by template reactions. The yields were determined by GC-analysis.

Abbreviations

COFs: Covalent-Organic Frameworks; MOFs: Metal-Organic Frameworks; RML: *Rhizomucor miehei* lipase; PXRD: Powder X-ray diffraction; BET: Brunauer–Emmett–Teller; FTIR: Fourier transform infrared; RT: Room temperature; $Fe_3O_4@COF-OMe$: COF-OMe coated Fe_3O_4 nanoparticles to form core-shell structure. Fe_3O_4 -COF-OMe: Physically mixtures; GC: Gas chromatography; SEM: Scanning electron microscopy; TG(TGA): Thermal Gravity analysis; TEM: Transmission electron microscopy; CLSM: Confocal laser scanning microscopy; VSM: Vibrating sample magnetometer; HPLC: High performance liquid chromatography; RBITC: Rhodamine B isothiocyanate; FITC: Fluorescein isothiocyanate; PBS: Phosphate buffer saline; p-NPA: 4-Nitrophenyl acetate.

Declarations

Acknowledgements

We acknowledge support by Key laboratory of Green Chemistry & Technology (Sichuan University), Ministry of Education. We are also grateful to Analytical & Testing Center, Sichuan University and Comprehensive Training Platform of Specialized Laboratory, College of Chemistry, Sichuan University for help.

Authors' contribution

ZZ carried out the experimental studies and drafted the manuscript. XX and JL helped with the experimental analysis. ZH and ZX helped with the data processing. NW and XY participated in the experimental design, coordination and helped to draft the manuscript. All authors read and approved the final manuscript.

Availability of data and material

All data generated or analyzed during this study are included in this published article and its additional file.

Competing interest

The authors declare that they have no competing interests.

Consent for publication

Not applicable.

Ethics approval and consent to participate

Not applicable.

Funding

This work was supported by National Key R&D Program of China (Grant No. 2018YFA0901600) and Science and Technology Project of Jiangxi Province (No. 20192BBH80012).

References

1. Qi D-H, Geng L-M, Chen H, Bian Y-Z, Liu J, Ren X-C. Combustion and performance evaluation of a diesel engine fueled with biodiesel produced from soybean crude oil. *Renew Energ.* 2009;34:2706-13.
2. Knothe G. Analyzing biodiesel: standards and other methods. *J Am Oil Chem Soc.* 2006;83: 823–33.
3. Zhong L, Feng Y, Wang G, Wang Z, Bilal M. Lv H, Jia S, Cui J. Production and use of immobilized lipases in/on nanomaterials: A review from the waste to biodiesel production. *Int J Biol Macromol.* 2020;152:207-22.
4. Zhang W-W, Wang N, Zhou Y-J, He T, Yu X-Q. Enhancement of activity and stability of lipase by microemulsion-based organogels (MBGs) immobilization and application for synthesis of arylethyl

- acetate. *J Mol Catal B: Enzym.* 2012;78:65-71.
5. Bencze LC, Bartha-Vári JH, Katona G, Toşa MI, Paizs C, Irimie F-D. Nanobioconjugates of *Candida antarctica* lipase B and single-walled carbon nanotubes in biodiesel production. *Bioresour Technol.* 2016;200:853-60.
 6. Babaki M, Yousefi M, Habibi Z, Mohammadi M, Yousefi P, Mohammadi J, Brask J. Enzymatic production of biodiesel using lipases immobilized on silica nanoparticles as highly reusable biocatalysts: effect of water, t-butanol and blue silica gel contents. *Renew Energ.* 2016;91:196-206.
 7. Li Y, Gao F, Wei W, Qu J-B, Ma G-H, Zhou W-Q. Pore size of macroporous polystyrene microspheres affects lipase immobilization. *J Mol Catal B: Enzym.* 2010;66:182-9.
 8. Samui A, Happy H, Sahu SK. Integration of α -amylase into covalent organic framework for highly efficient biocatalyst. *Microporous Mesoporous Mater.* 2020;291:109700-8.
 9. Samui A, Chowdhuri AR, Mahto TK, Sahu SK, Fabrication of a magnetic nanoparticle embedded NH₂-MIL-88B MOF hybrid for highly efficient covalent immobilization of lipase. *RSC Adv.* 2016;6:66385-93.
 10. Ye N, Kou X, Shen J, Huang S, Chen G, Ouyang G. Metal-Organic Frameworks: A New Platform for Enzyme Immobilization. *Chembiochem.* 2020;21:2585-90.
 11. Nadar SS, Rathod VK. Magnetic-metal organic framework (magnetic-MOF): A novel platform for enzyme immobilization and nanozyme applications. *Int J Biol Macromol.* 2018;120:2293-302.
 12. Hu Y, Dai L, Liu D, Du W. Hydrophobic pore space constituted in macroporous ZIF-8 for lipase immobilization greatly improving lipase catalytic performance in biodiesel preparation. *Biotechnol Biofuels.* 2020;13:86-94.
 13. Adnan M, Li K, Xu L, Yan Y. X-Shaped ZIF-8 for Immobilization *Rhizomucor miehei* Lipase via Encapsulation and Its Application toward Biodiesel Production. *Catalysts.* 2018; doi:10.3390/catal8030096.
 14. Rafiei S, Tangestaninejad S, Horcajada P, Moghadam M, Mirkhani V, Mohammadpoor-Baltork I, Kardanpour R, Zadehahmadi F. Efficient biodiesel production using a lipase@ZIF-67 nanobioreactor. *Chem Eng J.* 2018;334:1233-41.
 15. Tranchemontagne DJ, Hunt JR, Yaghi OM. Room temperature synthesis of metal-organic frameworks: MOF-5, MOF-74, MOF-177, MOF-199, and IRMOF-0. *Tetrahedron.* 2008;64:8553-7.
 16. Jeremias F, Fröhlich D, Janiak C, Henninger SK. Water and methanol adsorption on MOFs for cycling heat transformation processes. *New J Chem.* 2014;38:1846-52.
 17. Li M-M, Qiao S, Zheng Y-L, Andaloussi Y-H, Li X, Zhang Z-J, Li A, Cheng P, Ma S-Q, Chen Y. Fabricating Covalent Organic Framework Capsules with Commodious Microenvironment for Enzymes. *J Am Chem Soc.* 2020;142:6675-81.
 18. Wang H, Jiao F, Gao F, Zhao X, Zhao Y, Shen Y, Zhang Y, Qian X. Covalent organic framework-coated magnetic graphene as a novel support for trypsin immobilization. *Anal Bioanal Chem.* 2017;409:2179-87.

19. Zhao F, Liu H, Mathe SDR, Dong A, Zhang J. Covalent Organic Frameworks: From Materials Design to Biomedical Application. *Nanomaterials*. 2017;8:doi:10.3390/nano8010015.
20. Waller PJ, Gandara F, Yaghi OM. Chemistry of Covalent Organic Frameworks. *Acc Chem Res*. 2015;48:3053-63.
21. Zhang X, Li G, Wu D, Zhang B, Hu N, Wang H, Liu J, Wu Y. Recent advances in the construction of functionalized covalent organic frameworks and their applications to sensing. *Biosens Bioelectron*. 2019;145:111699-717.
22. Ding S-Y, Wang W. Covalent organic frameworks (COFs): from design to applications. *Chem Soc Rev*. 2013;42:548-68.
23. Yu J-T, Chen Z, Sun J, Huang Z-T, Zheng Q-Y. Cyclotricatechylene based porous crystalline material: Synthesis and applications in gas storage. *J Mater Chem*. 2012;22:5369-73.
24. Li Y, Yang R-T. Hydrogen storage in metal-organic and covalent-organic frameworks by spillover. *AIChE J*. 2008;54:269-79.
25. Wang P, Zhou F, Zhang C, Yin S-Y, Teng L, Chen L, Hu X-X, Liu H-W, Yin X, Zhang X-B. Ultrathin two-dimensional covalent organic framework nanoprobe for interference-resistant two-photon fluorescence bioimaging. *Chem Sci*. 2018;9:8402-8.
26. Li M, Cui Z, Pang S, Meng L, Ma D, Li Y, Shi Z, Feng S. Luminescent covalent organic framework as a recyclable turn-off fluorescent sensor for cations and anions in aqueous solution. *J Mater Chem C*. 2019;7:11919-25.
27. Ding S-Y, Gao J, Wang Q, Zhang Y, Song W-G, Su C-Y, Wang W. Construction of covalent organic framework for catalysis: Pd/COF-LZU1 in Suzuki-Miyaura coupling reaction. *J Am Chem Soc*. 2011;133:19816-22.
28. Sarkar P, Riyajuddin S, Das A, Hazra Chowdhury A, Ghosh K, Islam SM. Mesoporous covalent organic framework: An active photo-catalyst for formic acid synthesis through carbon dioxide reduction under visible light. *Mol Catal*. 2020;484:110730-8.
29. Sun Q, Aguila B, Lan PC, Ma S. Tuning Pore Heterogeneity in Covalent Organic Frameworks for Enhanced Enzyme Accessibility and Resistance against Denaturants. *Adv Mater*. 2019;31:doi:10.1002/adma.201900008.
30. Su D, Feng B, Xu P, Zeng Q, Shan B, Song Y. Covalent organic frameworks and electron mediator-based open circuit potential biosensor for in vivo electrochemical measurements. *Anal Methods*. 2018;10:4320-8.
31. Zhang T, Song Y, Xing Y, Gu Y, Yan X, Liu H, Lu N, Xu H, Xu Z, Zhang Z, Yang M. The synergistic effect of Au-COF nanosheets and artificial peroxidase Au@ZIF-8(NiPd) rhombic dodecahedra for signal amplification for biomarker detection. *Nanoscale*. 2019;11:20221-7.
32. Li M, Qiao S, Zheng Y, Andaloussi YH, Li X, Zhang Z, Li A, Cheng P, Ma S, Chen Y. Fabricating Covalent Organic Framework Capsules with Commodious Microenvironment for Enzymes. *J Am Chem Soc*. 2020;142:6675-81.

33. Kandambeth S, Venkatesh V, Shinde DB, Kumari S, Halder A, Verma S, Banerjee R, Self-templated chemically stable hollow spherical covalent organic framework. *Nat Commun*. 2015;6:doi:10.1038/ncomms7786.
34. Sun Q, Fu C-W, Aguila B, Perman J, Wang S, Huang H-Y, Xiao F-S, Ma S. Pore Environment Control and Enhanced Performance of Enzymes Infiltrated in Covalent Organic Frameworks. *J Am Chem Soc*. 2018;140:984-92.
35. Zhang S, Zheng Y, An H, Aguila B, Yang C-X, Dong Y, Xie W, Cheng P, Zhang Z, Chen Y, Ma S. Covalent Organic Frameworks with Chirality Enriched by Biomolecules for Efficient Chiral Separation. *Angew Chem Int Ed*. 2018;57:16754-59.
36. Shimada Y, Watanabe Y, Samukawa T, Sugihara A. Conversion of Vegetable Oil to Biodiesel Using Immobilized *Candida antarctica* Lipase. *J Am Oil Chem Soc*. 1999;76:789-93.
37. El-Kaderi H, Hunt J, Mendoza-Cortés J, Côté A, Taylor R, O'Keeffe M, Yaghi O. Designed Synthesis of 3D Covalent Organic Frameworks. *Science*. 2007;316:268-72.
38. Jia J, Zhang W, Yang Z, Yang X, Wang N, Yu X. Novel Magnetic Cross-Linked Cellulase Aggregates with a Potential Application in Lignocellulosic Biomass Bioconversion. *Molecules*. 2017;22:doi:10.3390/molecules22020269.
39. Zhang W, Yang H, Liu W, Wang N, Yu X. Improved Performance of Magnetic Cross-Linked Lipase Aggregates by Interfacial Activation: A Robust and Magnetically Recyclable Biocatalyst for Transesterification of *Jatropha* Oil. *Molecules*. 2017;22:doi:10.3390/molecules22122157.
40. Zhang W-W, Yang X-L, Jia J-Q, Wang N, Hu C-L, Yu X-Q. Surfactant-activated magnetic cross-linked enzyme aggregates (magnetic CLEAs) of *Thermomyces lanuginosus* lipase for biodiesel production. *J Mol Catal B: Enzym*. 2015;115:83-9.
41. Gao C, Lin G, Lei Z, Zheng Q, Lin J, Lin Z. Facile synthesis of core-shell structured magnetic covalent organic framework composite nanospheres for selective enrichment of peptides with simultaneous exclusion of proteins. *J Mater Chem B*. 2017;5:7496-503.
42. Zhong C, Lei Z, Huang H, Zhang M, Cai Z, Lin Z. One-pot synthesis of trypsin-based magnetic metal-organic frameworks for highly efficient proteolysis. *J Mater Chem B*. 2020;8:4642-7.
43. Lin G, Gao C, Zheng Q, Lei Z, Geng H, Lin Z, Yang H, Cai Z. Room-temperature synthesis of core-shell structured magnetic covalent organic frameworks for efficient enrichment of peptides and simultaneous exclusion of proteins. *Chem Commun*. 2017;53:3649-52.
44. Chen L, He Y, Lei Z, Gao C, Xie Q, Tong P, Lin Z. Preparation of core-shell structured magnetic covalent organic framework nanocomposites for magnetic solid-phase extraction of bisphenols from human serum sample. *Talanta*. 2018;181:296-304.
45. Lu G, Huang X, Wu Z, Li Y, Xing L, Gao H, Dong W, Wang G. Construction of covalently integrated core-shell TiO₂ nanobelts@COF hybrids for highly selective oxidation of alcohols under visible light. *Appl Surf Sci*. 2019;493:551-60.
46. Sun Q, Pan Y, Wang X, Li H, Farmakes J, Aguila B, Yang Z, Ma S. Mapping out the Degree of Freedom of Hosted Enzymes in Confined Spatial Environments. *Chem*. 2019;5:3184-95.

Figures

Figure 1

The synthesis of core-shell magnetic nanoparticles and immobilization process.

Figure 1

The synthesis of core-shell magnetic nanoparticles and immobilization process.

Figure 2

SEM image of (A) COF-OMe; TEM image (B) and SEM image (C) of core-shell structure Fe₃O₄@COF-OMe; SEM image (D) of RML@Fe₃O₄@COF-OMe.

Figure 2

SEM image of (A) COF-OMe; TEM image (B) and SEM image (C) of core-shell structure Fe₃O₄@COF-OMe; SEM image (D) of RML@Fe₃O₄@COF-OMe.

Figure 3

(A) PXRD patterns of Fe₃O₄ and Fe₃O₄@COF-OMe particles (the inset shows the patterns of crystalline COF-OMe). (B) TGA curves, (C) The magnetic hysteresis curve and (D) the N₂ adsorption–desorption isotherms of the magnetic support Fe₃O₄@COF-OMe and the immobilized enzyme RML@Fe₃O₄@COF-OMe.

Figure 3

(A) PXRD patterns of Fe₃O₄ and Fe₃O₄@COF-OMe particles (the inset shows the patterns of crystalline COF-OMe). (B) TGA curves, (C) The magnetic hysteresis curve and (D) the N₂ adsorption–desorption isotherms of the magnetic support Fe₃O₄@COF-OMe and the immobilized enzyme RML@Fe₃O₄@COF-OMe.

Figure 4

The scheme of two magnetic composites by different strategies: physical mixing and core-shell structure.

Figure 4

The scheme of two magnetic composites by different strategies: physical mixing and core-shell structure.

Figure 5

(A) The catalytic activity, (B) The pH effect to and (C) the thermal stability of free and immobilized RML.

Figure 5

(A) The catalytic activity, (B) The pH effect to and (C) the thermal stability of free and immobilized RML.

Figure 6

The yields of template reaction by optimizing different conditions. (A) The outcomes catalyzed by immobilized enzymes and free RML. (B) The reaction catalyzed by RML@Fe₃O₄@COF-OMe in different solvents. (C) The temperature effect on the reactions. (D) Yields by a different dosage of enzymes.

Figure 6

The yields of template reaction by optimizing different conditions. (A) The outcomes catalyzed by immobilized enzymes and free RML. (B) The reaction catalyzed by RML@Fe₃O₄@COF-OMe in different solvents. (C) The temperature effect on the reactions. (D) Yields by a different dosage of enzymes.

Figure 7

The leakage of the enzyme by washing operations in different cycles. The value of Wash 1, 2, 4, 8 means the concentration of RML in the supernatant.

Figure 7

The leakage of the enzyme by washing operations in different cycles. The value of Wash 1, 2, 4, 8 means the concentration of RML in the supernatant.

Supplementary Files

This is a list of supplementary files associated with this preprint. Click to download.

- [ESI.docx](#)
- [ESI.docx](#)
- [Scheme1.jpg](#)
- [Scheme1.jpg](#)