Electrochemical activation of C–H by electron-deficient W₂C nanocrystals for simultaneous alkoxylation and hydrogen evolution

Xiu Lin

School of Chemistry and Chemical Engineering, Shanghai Jiao Tong University

Shi-Nan Zhang

School of Chemistry and Chemical Engineering, Shanghai Jiao Tong University, Shanghai 200240

Dong Xu

School of Chemistry and Chemical Engineering, Shanghai Jiao Tong University

Jun-Jun Zhang

Shanghai Jiao Tong University <https://orcid.org/0000-0002-3068-0874>

Yun-Xiao Lin

Shanghai Jiao Tong University <https://orcid.org/0000-0002-1375-5360>

Guang-Yao Zhai

School of Chemistry and Chemical Engineering, Shanghai Jiao Tong University, Shanghai 200240, P. R. China. <https://orcid.org/0000-0002-1527-5387>

Hui Su

Shanghai Jiao Tong University <https://orcid.org/0000-0002-2257-4342>

Zhong-Hua Xue

Shanghai Jiao Tong University

Xi Liu

Shanghai Jiao Tong University

Markus Antonietti

Department of Colloid Chemistry, Max-Planck Institute of Colloids and Interfaces

Jie Sheng Chen

Shanghai Jiao Tong University

Xin-Hao Li (✉ xinhaoli@sjtu.edu.cn)

Shanghai Jiao Tong University <https://orcid.org/0000-0003-1643-4631>

Article

Keywords: Organic Chemistry, Retro-synthesis, Nanocrystal-based Electrodes, Heterogeneous Electrocatalytic Strategy, Schottky Heterojunctions, Direct Deprotonation Process

Posted Date: December 14th, 2020

DOI: <https://doi.org/10.21203/rs.3.rs-113168/v1>

License: This work is licensed under a Creative Commons Attribution 4.0 International License.
[Read Full License](#)

Version of Record: A version of this preprint was published at Nature Communications on June 23rd, 2021. See the published version at <https://doi.org/10.1038/s41467-021-24203-8>.

Abstract

Activation of C – H bonds is maybe the central challenge in organic chemistry and usually the key step for the retro-synthesis of functional natural products and medicines from abundant hydrocarbons due to the high chemical stability of C – H bonds. Electrochemical methods are now recognized as a powerful alternative for C – H activation, but this approach usually requires high overpotential and homogeneous mediators. Here, we designed electron-deficient W₂C nanocrystal-based electrodes to boost the heterogeneous activation of C – H bonds under mild conditions via an additive-free, purely heterogeneous electrocatalytic strategy. The electron density of W₂C nanocrystals was tuned by constructing Schottky heterojunctions with nitrogen-doped carbon support to facilitate the preadsorption and activation of benzylic C – H bonds of ethylbenzene on the W₂C surface, enabling a high turnover frequency (18.8 h⁻¹) at a comparably low work potential (2 V versus SCE). The pronounced electron deficiency of the W₂C nanocatalysts substantially facilitates the direct deprotonation process to ensure long-term electrode durability without self-oxidation. The efficient oxidation process also boosts the balancing hydrogen production from as-formed protons on the cathode by a factor of 10 compared to an inert reference electrode. The whole process meets the requirements of atomic economy and electric energy utilization in terms of sustainable chemical synthesis.

Introduction

Direct activation of C–H bonds via selective oxidation of *hydrocarbons* is of great interest for organic hydrocarbons^{1,2}. As a typical and important transformation path of C–H bonds, selective dehydrogenation of C–H bonds has been widely used for the production of high value-added compounds such as alcohols, and ketones and ethers³⁻⁵. However, the chemical stability of C–H bonds without activating neighborhood effects makes C–H activation quite challenging, and either extreme and rather toxic oxidants as chromium or selenium compounds or noble-metal-catalysts (based on rhodium or palladium) at high temperatures have to be applied to obtain acceptable conversions⁶⁻⁸. Moreover, the as-formed side product water from the cleavage of C–H bonds via oxydehydrogenation is free of value. As a result, novel and sustainable strategies are highly desirable to further decrease the economic and environmental footprints of C–H activation processes.

Electrochemical transformation is recognized as an environmentally friendly method for the production of various functional molecules driven by electricity under mild conditions⁹⁻¹¹. Pioneering works of electrochemical synthesis using homogeneous catalysts have demonstrated the advantages of this technique for C–H activation¹¹, which includes selective oxidation¹², amination¹³, epoxidation¹⁴ and dehydrogenative coupling reactions¹⁵. Most of these reactions have high atom economy and excellent compatibility with flow reactors for continuous synthesis^{16,17}. The current strategies to boost the transformation of specific substrates mainly rely on the involvement of functional additives¹¹ (e.g., organic ligands, bases and mediators), a high work potential and/or sacrificial transition metal electrodes¹⁸, which all will severely limit real-industry applications. Principally, the preparation of cost-

effective and active electrode materials is at least as important as the development of a new methodology for selective C–H bonds activation¹⁹⁻²⁶, and only non-targeted, commercial first generation electrodes (such as carbon rod, platinum and reticulated vitreous carbon) are applied as the current collectors in electrochemical organic synthesis at the moment. The significant progress reported using well-designed reaction-specified electrodes in improving the catalytic activity for water splitting, nitrogen reduction reactions and even carbon dioxide reduction reactions²⁷⁻³⁰ further manifests the huge gap between the design of novel electrode materials and the requirements of sustainable electrochemical organic synthesis.

Herein, we present the proof-of-concept application of electron-deficient W₂C nanocrystal-based electrodes for the highly efficient electrochemical activation of C–H bonds, highlighting the key importance of the modified physicochemical properties of electrode materials in boosting additive-free C–H activation reactions. A nanoheterojunction composed of W₂C nanocrystals and nitrogen-doped carbons has been rationally designed to control the number of electrons flowing from W₂C nanocrystals to nitrogen-doped carbons by increasing the doping concentration in the carbon supports to enhance the interfacial Schottky effect. The as-formed electron-deficient W₂C nanocrystal-based electrode acts as a functional anode to simultaneously facilitate the alkoxylation of ethylbenzene with methanol on the anode and the balancing hydrogen evolution reaction on the cathode. Both the experimental and theoretical results indicate the key role of the electron deficiency of the W₂C nanocrystals in capturing ethylbenzene on the anode to substantially increase the reaction rates of alkoxylation and hydrogen evolution reaction processes simultaneously and ensure the long-term stability of the anode without scarifying the current collector.

The W₂C/NC catalysts were prepared via a modified nanoconfinement method (Supplementary Fig. 1) from a mixture of dicyandiamide and ammonium tungstate, followed by N₂-protected thermal pyrolysis at high temperatures. The nitrogen contents (x at.%) of the W₂C/N_xC samples could be tuned from 3.0 via 2.3 to 1.4 at.% (Supplementary Fig. 2 and Table 1) by elevating the condensation temperatures from 1000 to 1200 °C (for experimental details please see the experimental section). The morphology (Supplementary Fig. 3), surface area (Supplementary Fig. 4) and W content (Supplementary Table 1) of W₂C/N_xC samples are well maintained, as reflected by their scanning electron microscopy (SEM) images. Transmission electron microscopy (TEM) observations (Fig. 1a-c and Supplementary Fig. 5-7) further reveal the presence of few-layer-graphene-supported W₂C nanocrystals with a mean size of 2.5 nm (Fig. 1a and Supplementary Fig. 8) and a typical lattice fringe of 0.24 nm (Fig. 1b), which corresponds to the (002) plane of α-W₂C^{31,32}. The formation of W₂C is doubly confirmed by its X-ray diffraction (XRD) pattern (Supplementary Fig. 9), matching well with that of typical α-W₂C (JCPDS# 35-776)³¹. Detailed elemental mapping images (Fig. 1c) exhibit nanometer-sized W-rich areas with a homogeneous distribution of N atoms along with the whole carbon support, indicating an integrated structure of W₂C nanocrystals on the nitrogen-doped carbons.

The highly coupled structure of W_2C/NC dyads makes it possible to form a rectifying interface for modulation of the electron density of W_2C nanocrystals. The density functional theory (DFT) calculation results (Supplementary Fig. 10,11) predict electron transfer from W_2C to nitrogen-doped carbons, resulting in more pronounced electron-deficient regions in W_2C nanocrystals suggested by the charge density difference (CDD) stereograms (Fig. 1d) of the same W_2C model supported on pristine carbons (W_2C/C). The mean number of electrons transferred from the W_2C nanocrystal to the nitrogen-doped carbon support (Fig. 1e) increases from 0.338 to 0.397 as more nitrogen atoms (from 1.4 to 3.0 at.%) are doped into the carbon support models (Supplementary Fig. 12), which were constructed based on the X-ray photoelectron spectroscopy (XPS) analysis results³³. As depicted in Fig. 1f, the nanoheterojunction of W_2C and NC has a rectifying contact, with electrons flowing from the W_2C side with a lower Fermi level (E_F) to the NC side, generating electron-deficient W_2C due to the interfacial Schottky barrier^{34,35}. Indeed, the electron donation from the W_2C nanocrystals to the nitrogen-rich carbon supports is experimentally confirmed by the gradual shift in W 4f XPS peaks to higher energy (Fig. 1g) from 34.2 via 34.4 to 34.5 eV for $W_2C/N_{1.4}C$, $W_2C/N_{2.3}C$ and $W_2C/N_{3.0}C$, respectively, resulting in gradually increased work functions (Fig. 1h and Supplementary Fig. 13) from 5.4 via 5.6 to 5.7 eV. A similar trend for the electron density of W_2C nanocrystals in W_2C/N_xC samples is also demonstrated by the most positive W M4,5 peak (Supplementary Fig. 14) of the $W_2C/N_{3.0}C$ materials among all samples³⁶. All of the above results indicate the formation of electron-deficient W_2C nanocrystals and the successful further enhancement of electron deficiencies by increasing the nitrogen contents in the carbon supports.

Inspired by the success in modifying the electron density of W_2C nanocrystals, we further evaluated the possible catalytic activity of W_2C/N_xC catalysts for electrochemical alkoxylation of ethylbenzene with methanol under mild conditions as a model reaction. Considering that the reported methods for alkoxylation of C–H bonds usually require highly active additives/oxidants and/or a high reaction temperature, we initially tested the possibility of additive-free alkoxylation of ethylbenzene with methanol using only a simple electrolyte containing lithium perchlorate and W_2C/N_xC -based electrodes under ambient conditions (Fig. 2 and Supplementary Fig. 15). No product was detected without applying a working potential for various electrodes in our electrochemical system (Supplementary Fig. 16), illustrating that the methoxylation reaction cannot proceed spontaneously. Surprisingly, a complete conversion of ethylbenzene can be achieved on the $W_2C/N_{3.0}C$ electrode with high selectivity to the target product (1-methoxyethyl)benzene (Fig. 2a,b and Supplementary Fig. 17) and a total carbon balance of approximately 95%, confirming the possibility of highly efficient alkoxylation of C–H bonds on a well-designed heterogeneous electrode without sacrificing additives. The fact that control electrodes with the same amount of bare NC sample, W_2C catalyst or a mechanical mixture of the two components (Fig. 2e) give much lower conversions of ethylbenzene than the $W_2C/N_{3.0}C$ electrode under fixed conditions further indicates a synergistic effect between W_2C and $N_{3.0}C$ components in facilitating the transformation of ethylbenzene.

Unlike the oxidative alkoxylation reaction of C–H bonds by using various oxidants for dehydrogenation to generate water³⁷, our heterogeneous electrochemical system could achieve the full use of as-formed protons from the activation of C–H bonds and methanol for subsequent hydrogen evolution reactions, generating hydrogen gas bubbles on the cathode (Supplementary Fig. 18). Moreover, the calculated Faradaic efficiencies (Fig. 2d and Supplementary Fig. 19) are similar for the conversion of ethylbenzene to (1-methoxyethyl)benzene on the $W_2C/N_{3.0}C$ anode (F_E : 42-46%) and hydrogen production on the Ti cathode (F_E : 42-55%), implying a cascade transformation of protons generated from the anode into hydrogen gas on the cathode. Even with an excess amount of methanol in the reactor, only a trace amount of formaldehyde (0.006 mmol) formed during the conversion of 0.5 mmol of ethylbenzene (Supplementary Fig. 20), well explaining the comparable Faradaic efficiencies for the reactions on anode and cathode without the obvious contribution of methanol dehydrogenation to the total F_E for hydrogen evolution reactions. Remarkably, the electron-deficient W_2C in the $W_2C/N_{3.0}C$ -based electrode substantially promotes the hydrogen evolution rate on the Ti cathode to 880 μmol (Fig. 2c), which is above 10 times that on the same Ti cathode (85 μmol) when using bare carbon cloth as the anode. The constant current density of the $W_2C/N_{3.0}C$ anode under fixed conditions with different cathodes (Fig. 2f), including Pt mesh, Ti mesh and carbon rod, further demonstrates that the activation and deprotonation of ethylbenzene on the $W_2C/N_{3.0}C$ electrode is the rate dominating step for the whole reaction. Indeed, the alkoxylation reaction could be selectively quenched by butylated hydroxytoluene (BHT) (Supplementary Fig. 21), indicating a radical-based pathway on the $W_2C/N_{3.0}C$ anode, as indicated in Fig. 2a¹⁸.

The role of the electron-deficient W_2C nanocrystals and the interfacial effect of the heterojunction catalysts on the electrochemical alkoxylation of C–H bonds were simulated via theoretical calculations and then validated by experimental evidence (Fig. 3). The optimized geometry (Fig. 3a,c) of ethylbenzene presents preferred adsorption of benzylic C–H bonds on the W_2C surface dependent of the electron-deficiency of W_2C , indicating the feature role of W_2C as an active component. This role was further validated by more negative onset potentials (<1.4 V versus SCE) for the electrochemical alkoxylation reaction on W_2C/N_xC anodes than that (>1.6 V versus SCE) of the bare carbon cloth electrode (Supplementary Fig. 22). However, the polarization of adsorbed C–H bonds is enhanced by the electron-deficient surface of the $W_2C-0.08e^-$ model, as reflected by the more pronounced electron density difference (Hirshfeld charge) of the preadsorbed C–H bonds (Fig. 3c and Supplementary Fig. 23) and a much lower calculated adsorption energy for ethylbenzene (Fig. 3e). Such strong adsorption of ethylbenzene molecules over the electron-deficient W_2C surface was then experimentally validated by the temperature-programmed desorption (TPD) analysis results (Fig. 3f), exhibiting gradually elevated adsorption capacities over those of more electron-deficient W_2C/N_xC samples with similar surface areas. It should be noted that the bare carbon support (NC sample in Fig. 3f) provides a low adsorption capacity, only 21% of the best-in-class $W_2C/N_{3.0}C$ sample (Supplementary Fig. 24). More importantly, the electron deficiency-induced adsorption behavior of ethylbenzene on the final W_2C/N_xC -based anodes under a fixed bias in the electrochemical reactor was well expressed with the same trend in adsorption capacities (Fig. 3g) as that revealed by TPD results, making successive C–H dissociation process more favorable.

Indeed, the stronger interaction between preadsorbed ethylbenzene molecules and electron-deficient W_2C significantly reduces the Gibbs free energy of each step of the whole alkoxylation reaction pathway (Fig. 3e). The dissociation of C–H bonds of ethylbenzene on the electron-deficient W_2C catalyst ($W_2C-0.08e^-$ model) is the rate-limiting step with a free energy change of only 0.34 eV, and the subsequent coupling of $*C_8H_9$ and $*CH_3O^*$ ($*C_8H_9^* + *CH_3O^*$) and desorption of as-formed (1-methoxyethyl)benzene ($*C_9H_{12}O$) proceed automatically. With similar configurations, the last three steps for the catalytic conversion of preadsorbed ethylbenzene molecules on the pristine W_2C catalyst (W_2C model) are thermodynamically uphill with a larger free energy change of 0.4 eV for the ($*C_8H_9^* + *CH_3O^*$) step, again indicating the key role of electron density in facilitating the whole reaction and desorption processes on the W_2C surface. This electron-deficiency-dependent promotion effect on the activity of W_2C was then unambiguously confirmed by the gradually increased catalytic activities (Fig. 3h) and F_E values (Fig. 3i) for producing (1-methoxyethyl)benzene on more electron-deficient W_2C/N_xC -based anodes under fixed work potential.

The $W_2C/N_{3.0}C$ anode also shows excellent electrochemical stability for long-term use. The composition (Supplementary Fig. 25) and morphology (Supplementary Fig. 26) of the used $W_2C/N_{3.0}C$ materials were maintained well. Most importantly, the $W_2C/N_{3.0}C$ anode can be recycled at least four times without an obvious decrease in F_E (41-46%) (Fig. 4b and Supplementary Fig. 27). It should be noted that inert metal anodes for alkoxylation of ethylbenzene, including stable metals (exemplified by Ti mesh) and active metals (exemplified by Ni plate), decompose rapidly within 5 h (Fig. 4a and Supplementary Fig. 28), illustrating the key importance of the high activity of the $W_2C/N_{3.0}C$ anode to keep itself from corroding. As a durable anode, the electron-deficient W_2C electrode exhibits satisfying activity for electrochemical alkoxylation of various aromatic C–H bonds using a series of aliphatic alcohols (Supplementary Table 2) with good to high conversions and high selectivity in 18 h, suggesting an excellent tolerance of our electrode material to various functional groups. As the best-in-class anode in this work, the $W_2C/N_{3.0}C$ electrode provides a high turnover frequency (TOF) value of 18.8 h^{-1} , which is comparable to or even higher than the reported values, mostly of homogeneous catalysts, for similar alkoxylation reactions (Fig. 4c and Supplementary Table 3-5)^{38,39}.

In summary, we have demonstrated the key role of electron-deficient W_2C nanocrystals as electrode materials in boosting the activity and durability for electrochemical activation of C–H bonds via a heterogeneous pathway. We successfully tuned the electron density of W_2C nanocrystals by constructing Schottky heterojunctions with nitrogen-doped carbons to achieve preferred adsorption of benzylic C–H bonds of ethylbenzene on the W_2C surface and facilitate subsequent C–H activation, which is the rate-limiting step. Unlike conventional oxidative alkoxylation to generate water, the as-formed protons on the W_2C anode could be simultaneously converted to hydrogen gas in our additive-free electrochemical

reactor under mild conditions. This two-birds-with-one-stone strategy illustrates the significant potential of powerful designer electrode materials to substantially increase catalytic efficiency, atomic economy and electricity utilization for organic electrosynthesis and hydrogen energy production in one electrocatalytic system. In addition to the hydrogen evolution reaction, the reduction process might be compatible with other important reactions (e.g. carbon dioxide reduction reaction or N_2/NO_x reduction reactions) to create novel or more complex cascade reaction pathways for the production of high value-added compounds from abundant hydrocarbons and even waste gases. This work may also boost the development of zero-additive and zero-emission electrosynthesis systems through the design of novel electrode materials.

Methods

Synthesis of $\text{W}_2\text{C}/\text{N}_x\text{C}$: All chemicals were analytical grade and used as received without further purification. A homogenous mixed solution including $(\text{NH}_4)_6\text{H}_2\text{W}_{12}\text{O}_{40} \cdot n\text{H}_2\text{O}$ (0.75 g), DCDA (15 g) and deionized water (150 mL) was heating at 80 °C, and the mixed solution was evaporated at a constant temperature with stirring. The obtained mixture after evaporating water was transferred into a cylindrical crucible with lid, and heated at 1000, 1100 and 1200 °C for 2 h with a heat rate of 2.5 °C min⁻¹ under high purity nitrogen atmosphere. The final products after cooling down to room temperature were named $\text{W}_2\text{C}/\text{N}_x\text{C}$ (x represents the nitrogen contents) and used for further experiments and characterizations.

The control group of nitrogen-doped carbon (NC) was prepared with the same procedure as $\text{W}_2\text{C}/\text{N}_x\text{C}$ without metal precursor. And W_2C and NC mixture was obtained by mixing W_2C powder and NC mechanically.

Materials Characterization: Powder X-ray diffraction patterns (XRD) was performed using a Bruker D8 Advance X-ray diffractometer equipped with a Cu K α radiation source ($\lambda = 1.5418 \text{ \AA}$) and operated at a scan rate of 6° min⁻¹. Scanning electron microscopy (SEM) were operated on FEI Nova NanoSEM 450 field emission scanning electron microscope. Transmission electron microscopy (TEM), high-resolution transmission electron microscopy (HRTEM) and energy dispersive X-ray (EDX) analysis were measured on a JEM-2100F microscope with an acceleration voltage of 200 kV. Temperature programmed desorption (TPD) was carried out on a Micromeritics Autochem II chemisorption analyzer with ethylbenzene probe molecules at 110 °C. Nitrogen adsorption-desorption isotherms were acquired on Quantachrome NOVA-2200e at 77 K. Prior to the measurement, the samples were degassed at 200 °C for 12 h with a gas flow of nitrogen. X-ray photoelectron spectroscopy (XPS) and ultraviolet photoelectron spectroscopy (UPS) experiments were recorded at a Kratos Axis Ultra DLD spectrometer and ESCALAB 250 photoelectron spectrometer (Thermo Fisher Scientific), respectively. The inductively coupled plasma atomic emission spectroscopy (ICP-AES) measurement was conducted on an iCAP6300 spectrometer for tungsten element analysis.

Electrochemical measurements: All of the electrochemical experiments were performed in a standard three-electrode system on an electrochemical station (CHI 660E, Shanghai CH Instruments Company).

Working electrodes were composed of catalysts supported by carbon cloth. The catalyst ink was prepared by sonicating and dispersing 5 mg of catalyst into a solution containing 700 μL of ethanol, 350 μL of deionized water and 160 μL of 5% Nafion solution. The working electrodes were prepared by evenly dipping 150 μL of ink onto carbon cloth ($1 \times 1 \text{ cm}$) and dried at 120°C for 1 h in the oven. Titanium (Ti) mesh with a size of $1 \times 1 \text{ cm}$ and saturated calomel electrode (SCE) were employed as counter and reference electrode, respectively. The control electrodes with different sample loading were prepared by dipping 50, 100 and 200 μL of ink on carbon cloth, respectively. The electrocatalytic reactions were conducted in 15 mL of methanol with 61 μL of ethylbenzene (0.5 mmol) and 0.106 g of lithium perchlorate (1 mmol) at room temperature in a home-made electrolyzer, in which methanol was not only used as solvent, but also simultaneously used as reactant. The electrocatalytic stability tests of catalyst for the reaction between ethylbenzene and methanol were evaluated using the same reaction potential for four consecutive cycles, and electrodes would have to dry at 120°C before the next reaction.

Electrode adsorption experiments were conducted in electrolyzer containing 1.5 mmol of ethylbenzene, 15 mL of methanol and 1 mmol of lithium perchlorate with $\text{W}_2\text{C}/\text{N}_x\text{C}$ anodes, Ti mesh cathode and saturated calomel electrode. To accurately measure the adsorption volume of ethylbenzene before transforming (1-methoxyethyl)benzene, we performed at 2 V versus SCE for 10 min. After the completion of adsorption, the residual volume of ethylbenzene in solution was obtained by extraction and analyzed in gas chromatography-mass spectrometry (GC-MS, Shimadzu QP2010SE) with dodecane as internal standard. And the adsorption volume for ethylbenzene on $\text{W}_2\text{C}/\text{N}_x\text{C}$ (C_{ads}) was calculated using the equation of $n_{\text{ads}} = n_{\text{ini}} - n_{\text{res}}$ (n_{ini} and n_{res} represent the initial and residual contents in solution, respectively)⁴⁰.

Products analysis: After the reaction, 500 μL of solution was firstly taken from electrolyzer and transferred into an extracted solution containing 500 μL of dichloromethane, 500 μL of deionized water and 0.2 μL of dodecane, and then dried by magnesium sulfate anhydrous. Finally, the extracted solution was analyzed in GCMS to determine the components of products and calculate the conversion and selectivity.

The Faradaic efficiency (F_E) was calculated as follow:

$$F_E = \frac{N_i \cdot n \cdot F}{Q}$$

where N_i is the number of moles for the specific product (mole); n is the number of electrons exchanged for product formation, which is 2 e in this reaction; F is the Faradaic constant of 96487 C mol^{-1} ; Q is the passed charge.

Turnover frequency (TOF) was defined by the following equation:

$$TOF = \frac{n}{N \cdot h}$$

where n is the number of moles for product; N is the number of moles of active metal sites determined from ICP-AES.

Theoretical calculation: The Spin polarization density functional theory (DFT) calculations were performed by the DMol3 program on Materials Studio. The generalized gradient approximation method with Perdew-Burke-Ernzerhof functional (GGA-PBE) was used for describing the exchange-correlation interaction among electrons⁴¹. The double numerical plus polarization (DNP) basis set was employed, while an accurate DFT semi-core pseudopotentials (DSPP) was adapted to describe the metal atoms^{42,43}. The $6 \times 6 \times 1$ k-points was used for sampling the Brillouin zone. Hexagonal W_2C (0001) facets were modeled in terms of the slabs of 5×5 supercells with $14.76 \times 14.76 \text{ \AA}$ and 120° and W_2C cluster model was placed above a 6×6 supercell of graphene lattice⁴⁴. The vacuum slab was set as $20 \text{ \AA}$ to calculate all periodical models. The contents of graphitic N and pyridinic N in the graphene lattice were estimated according to the XPS elements analysis results.

The Gibbs free energy change (ΔG) for each step of ethylbenzene activation was calculated as follows:

$$\Delta G = \Delta E + \Delta ZPE - T\Delta S (T = 298.15 \text{ K})$$

where ΔE , ΔZPE and ΔS are the changes in the reaction energy, zero-point energy and entropy, respectively.

Data availability

The data that support the findings of this study are available from the corresponding authors upon request.

Declarations

Acknowledgments

This work was supported by the National Natural Science Foundation of China (21722103, 21931005, 21720102002, and 21673140), Shanghai Science and Technology Committee (19JC1412600) and the SJTU-MPI partner group.

Author contributions

X.-H.L. and X.L. designed the experiments. X.L. conducted the preparation of the W_2C/N_xC catalysts and electrodes and carried out all of the corresponding characterizations and performance tests. X.-H.L. and X.L. co-wrote the original manuscript. X.L. and S.-N.Z. helped to conduct theoretical calculations and results analysis. D.X., J.-J.Z., Y.-X.L., G.-Y.Z., H.S., Z.-H.X. and X.L. helped to conduct the experiments and

characterizations. X.-H.L., J.-S.C. and M.A. oversaw all of the research phases and revised the manuscript. All of the authors discussed the results and commented on the manuscript.

Competing interests

The authors declare no competing interests.

References

1. Labinger, J. A. & Bercaw, J. E. Understanding and exploiting C–H bond activation. *Nature* **417**, 507–514 (2002).
2. Liu, M. et al. Photocatalytic methylation of non-activated sp^3 and sp^2 CH bonds using methanol on GaN. *ACS Catal.* **10**, 6248–6253 (2020).
3. Li, T. et al. Photoelectrochemical oxidation of organic substrates in organic media. *Nat. Commun.* **8**, 390 (2017).
4. Li, X.-H., Chen, J.-S., Wang, X., Sun, J. & Antonietti, M. Metal-free activation of dioxygen by graphene/g- C_3N_4 nanocomposites: functional dyads for selective oxidation of saturated hydrocarbons. *J. Am. Chem. Soc.* **133**, 8074–8077 (2011).
5. Tundo, P., Arico, F., Rosamilia, A. E. & Memoli, S. Synthesis of dialkyl ethers by decarboxylation of dialkyl carbonates. *Green Chem.* **10**, 1182–1189 (2008).
6. Weidmann, V. & Maison, W. Allylic oxidations of olefins to enones. *Synthesis* **45**, 2201–2221 (2013).
7. Hashiguchi, B. G., Bischof, S. M., Konnick, M. M. & Periana, R. A. Designing catalysts for functionalization of unactivated C–H bonds based on the CH activation reaction. *Acc. Chem. Res.* **45**, 885–898 (2012).
8. Dhakshinamoorthy, A., Asiri, A. M. & Garcia, H. Formation of C–C and C–heteroatom bonds by C–H activation by metal organic frameworks as catalysts or supports. *ACS Catal.* **9**, 1081–1102 (2018).
9. Horn, E. J. et al. Scalable and sustainable electrochemical allylic C–H oxidation. *Nature* **533**, 77–81 (2016).
10. Sperry, J. B. & Wright, D. L. The application of cathodic reductions and anodic oxidations in the synthesis of complex molecules. *Chem. Soc. Rev.* **35**, 605–621 (2006).
11. Wang, H., Gao, X., Lv, Z., Abdelilah, T. & Lei, A. Recent advances in oxidative R_1 -H/ R_2 -H cross-coupling with hydrogen evolution via photo-/electrochemistry: focus review. *Chem. Rev.* **119**, 6769–6787 (2019).
12. Das, A., Nutting, J. E. & Stahl, S. S. Electrochemical C–H oxygenation and alcohol dehydrogenation involving Fe-oxo species using water as the oxygen source. *Chem. Sci.* **10**, 7542–7548 (2019).
13. Sauermann, N., Mei, R. & Ackermann, L. Electrochemical C–H amination by cobalt catalysis in a renewable solvent. *Angew. Chem. Int. Ed.* **57**, 5090–5094 (2018).

14. Hollmann, F., Hofstetter, K., Habicher, T., Hauer, B. & Schmid, A. Direct electrochemical regeneration of monooxygenase subunits for biocatalytic asymmetric epoxidation. *J. Am. Chem. Soc.* **127**, 6540–6541 (2005).
15. Song, L. et al. Dual electrocatalysis enables enantioselective hydrocyanation of conjugated alkenes. *Nat. Chem.* **12**, 747–754 (2020).
16. Kong, W.-J. et al. Flow rhodaelectro-catalyzed alkyne annulations by versatile C–H activation: mechanistic support for rhodium (III/IV). *J. Am. Chem. Soc.* **141**, 17198–17206 (2019).
17. Leow, W. R. et al. Chloride-mediated selective electrosynthesis of ethylene and propylene oxides at high current density. *Science* **368**, 1228–1233 (2020).
18. Yan, M., Kawamata, Y. & Baran, P. S. Synthetic organic electrochemical methods since 2000: on the verge of a renaissance. *Chem. Rev.* **117**, 13230–13319 (2017).
19. Couper, A. M., Pletcher, D. & Walsh, F. C. Electrode materials for electrosynthesis. *Chem. Rev.* **90**, 837–865 (1990).
20. Sherbo, R. S., Delima, R. S., Chiykowski, V. A., MacLeod, B. P. & Berlinguette, C. P. Complete electron economy by pairing electrolysis with hydrogenation. *Nat. Catal.* **1**, 501–507 (2018).
21. Lu, Y. et al. Identifying the geometric site dependence of spinel oxides for the electrooxidation of 5-hydroxymethylfurfural. *Angew. Chem. Int. Ed.* **59**, 19215–19221 (2020).
22. Liu, C., Han, S., Li, M., Chong, X. & Zhang, B. Electrocatalytic deuteration of halides with D₂O as the deuterium source over a copper nanowire arrays cathode. *Angew. Chem. Int. Ed.* **132**, 18527–18531 (2020).
23. Chong, X., Liu, C., Huang, Y., Huang, C. & Zhang, B. Potential-tuned selective electrosynthesis of azoxy-, azo- and amino-aromatics over a CoP nanosheet cathode. *Nat. Sci. Rev.* **7**, 285–295 (2020).
24. Yin, Z. et al. CuPd nanoparticles as a robust catalyst for electrochemical allylic alkylation. *Angew. Chem. Int. Ed.* **59**, 15933–15936 (2020).
25. Liu, W.-J. et al. Efficient electrochemical production of glucaric acid and H₂ via glucose electrolysis. *Nat. Commun.* **11**, 265 (2020).
26. Jin, K. et al. Epoxidation of cyclooctene using water as the oxygen atom source at manganese oxide electrocatalysts. *J. Am. Chem. Soc.* **141**, 6413–6418 (2019).
27. Roger, I., Shipman, M. A. & Symes, M. D. Earth-abundant catalysts for electrochemical and photoelectrochemical water splitting. *Nat. Rev. Chem.* **1**, 0003 (2017).
28. Xue, Z.-H. et al. Electrochemical reduction of N₂ into NH₃ by donor–acceptor couples of Ni and Au nanoparticles with a 67.8% Faradaic efficiency. *J. Am. Chem. Soc.* **141**, 14976–14980 (2019).
29. Vasileff, A. et al. Electrochemical reduction of CO₂ to ethane through stabilization of an ethoxy intermediate. *Angew. Chem. Int. Ed.* **59**, 19649–19653 (2020).
30. Chen, C. et al. Coupling N₂ and CO₂ in H₂O to synthesize urea under ambient conditions. *Nat. Chem.* **12**, 717–724 (2020).
31. Pol, S. V., Pol, V. G. & Gedanken, A. Synthesis of WC nanotubes. *Adv. Mater.* **18**, 2023–2027 (2006).

32. Diao, J. et al. Interfacial engineering of W_2N/WC heterostructures derived from solid-state synthesis: a highly efficient trifunctional electrocatalyst for ORR, OER, and HER. *Adv. Mater.* **32**, 1905679 (2020).
33. Xue, Z. H. et al. Tuning the adsorption energy of methanol molecules along Ni-N-doped carbon phase boundaries by the Mott–Schottky effect for gas-phase methanol dehydrogenation. *Angew. Chem. Int. Ed.* **130**, 2727–2731 (2018).
34. Lin, Y.-X. et al. Boosting selective nitrogen reduction to ammonia on electron-deficient copper nanoparticles. *Nat. Commun.* **10**, 4380 (2019).
35. Liu, Y.-X. et al. Schottky barrier induced coupled interface of electron-rich N-doped carbon and electron-deficient Cu: in-built lewis acid–base pairs for highly efficient CO_2 fixation. *J. Am. Chem. Soc.* **141**, 38–41 (2018).
36. Milojevic, T., Albu, M., Blazevic, A., Konrad, L. & Cyran, N. Nanoscale tungsten-microbial interface of the metal immobilizing thermoacidophilic archaeon *metallostaphila sedula* cultivated with tungsten polyoxometalate. *Front. Microbiol.* **10**, 1267 (2019).
37. Shaikh, T. M. & Sudalai, A. $NaIO_4$ -mediated C–H activation of alkylbenzenes and alkanes with LiBr. *Tetrahedron Lett.* **46**, 5589–5592 (2005).
38. Hu, H. et al. Copper-catalysed benzylic C–H coupling with alcohols via radical relay enabled by redox buffering. *Nat. Catal.* **3**, 358–367 (2020).
39. Lee, B. J., DeGlopper, K. S. & Yoon, T. P. Site-selective alkoxylation of benzylic C–H bonds by photoredox catalysis. *Angew. Chem. Int. Ed.* **59**, 197–202 (2020).
40. Zhao, T.-J. et al. Biomimetic design of 3D transition metal/carbon dyad for one-step hydrodeoxygenation of vanillin. *ChemSusChem* **13**, 1900–1905 (2020).
41. Perdew, J. P., Burke, K. & Ernzerhof, M. Generalized gradient approximation made simple. *Phys. Rev. Lett.* **77**, 3865–3868 (1996).
42. Delley, B. An all-electron numerical method for solving the local density functional for polyatomic molecules. *J. Chem. Phys.* **92**, 508–517 (1990).
43. Delley, B. From molecules to solids with the DMol3 approach. *J. Chem. Phys.* **113**, 7756–7764 (2000).
44. Shi, N. et al. Strongly coupled W_2C atomic nanoclusters on N/P-codoped graphene for kinetically enhanced sulfur host. *Adv. Mater. Interfaces* **6**, 1802088 (2019).

Figures

Figure 1

Physical characterizations of the electron-deficient W₂C nanocrystals on the N_xC. **a**, High-resolution TEM image of W₂C/N_{3.0}C. **b**, A HAADF-STEM image of W₂C/N_{3.0}C. **c**, Energy-dispersive X-ray elemental mapping of W₂C/N_{3.0}C. **d**, Charge density difference stereograms of W₂C/C and W₂C/N_{3.0}C models (electron-deficient area (δ⁻), blue; electron-rich area (δ⁺), red); Colour code: C, grey; N, blue; W, purple. **e**, The numbers of electrons flowing from W₂C nanocrystals to various N_xC support models. **f**, Schematic diagrams of the rectifying interface of W₂C and N_{3.0}C. **g**, W 4f XPS spectra of W₂C/N_xC. **h**, Work functions (Φ) of W₂C/N_xC.

Figure 1

Physical characterizations of the electron-deficient W₂C nanocrystals on the N_xC. **a**, High-resolution TEM image of W₂C/N_{3.0}C. **b**, A HAADF-STEM image of W₂C/N_{3.0}C. **c**, Energy-dispersive X-ray elemental mapping of W₂C/N_{3.0}C. **d**, Charge density difference stereograms of W₂C/C and W₂C/N_{3.0}C models (electron-deficient area (δ⁻), blue; electron-rich area (δ⁺), red); Colour code: C, grey; N, blue; W, purple. **e**, The numbers of electrons flowing from W₂C nanocrystals to various N_xC support models. **f**, Schematic diagrams of the rectifying interface of W₂C and N_{3.0}C. **g**, W 4f XPS spectra of W₂C/N_xC. **h**, Work functions (Φ) of W₂C/N_xC.

Figure 2

Catalytic performance of the electron-deficient W_2C nanocrystal-based anode. a, Schematic illustration of electrolyzer and proposed reaction pathway. b, The time courses of conversion (red) of ethylbenzene and selectivity (black) to (1-methoxyethyl)benzene on the $\text{W}_2\text{C}/\text{N}_{3.0}\text{C}$ anode. c, The hydrogen production at the cathode when $\text{W}_2\text{C}/\text{N}_{3.0}\text{C}$ and CC were used as anode. d, The time courses of Faradaic efficiencies for conversion of ethylbenzene on the anode and hydrogen production on the cathode, respectively. e, Conversions of ethylbenzene on $\text{W}_2\text{C}/\text{N}_{3.0}\text{C}$ and control anodes under standard conditions within 3 h. f,

Cyclic voltammetry curves of typical cathodes (Ti mesh, Pt mesh and C rod) with the same W₂C/N_{3.0}C anode. Standard reaction conditions: ethylbenzene (0.5 mmol), lithium perchlorate (1 mmol), methanol (15 mL), W₂C/N_{3.0}C anode and Ti mesh cathode at 2.0 V versus SCE at room temperature in a home-made electrolyzer (Supplementary Fig. 15).

Figure 2

Catalytic performance of the electron-deficient W₂C nanocrystal-based anode. a, Schematic illustration of electrolyzer and proposed reaction pathway. b, The time courses of conversion (red) of ethylbenzene and

selectivity (black) to (1-methoxyethyl)benzene on the W₂C/N_{3.0}C anode. c, The hydrogen production at the cathode when W₂C/N_{3.0}C and CC were used as anode. d, The time courses of Faradaic efficiencies for conversion of ethylbenzene on the anode and hydrogen production on the cathode, respectively. e, Conversions of ethylbenzene on W₂C/N_{3.0}C and control anodes under standard conditions within 3 h. f, Cyclic voltammetry curves of typical cathodes (Ti mesh, Pt mesh and C rod) with the same W₂C/N_{3.0}C anode. Standard reaction conditions: ethylbenzene (0.5 mmol), lithium perchlorate (1 mmol), methanol (15 mL), W₂C/N_{3.0}C anode and Ti mesh cathode at 2.0 V versus SCE at room temperature in a home-made electrolyzer (Supplementary Fig. 15).

Figure 3

Effect of the electron deficiency of W2C nanocrystals on the conversion of ethylbenzene. a and c, Charge density difference stereograms of benzylic C–H bonds of ethylbenzene on the surface of W2C model (a) and electron-deficient W2C model (W2C-0.08e-) (b). The slice is perpendicular to the plane of benzylic C–H bonds, and electron-rich (red) and electron-deficient (blue) areas are presented. Colour code: C, grey; N, blue; H, white; W, purple. c and d, Calculated absorption configurations of each step of the ethylbenzene activation process on W2C (c) and W2C-0.08e- (d). e, Gibbs free energy diagrams of each step of the ethylbenzene activation process on W2C (black and top) and W2C-0.08e- (red and bottom). f, Ethylbenzene-TPD results of the W2C/NxC and NC samples. g, Adsorption capacities of ethylbenzene molecules on the surface of the W2C/NxC electrodes with fixed catalyst loadings (0.66 mg/cm²) at 2.0 V versus SCE for 10 min. h, Conversions of ethylbenzene on W2C/NxC electrodes at 2.0 V versus SCE for 3 h. i, Faradaic efficiencies for ethylbenzene conversion on W2C/NxC electrodes at 2.0 V versus SCE for 3 h.

Figure 3

Effect of the electron deficiency of W2C nanocrystals on the conversion of ethylbenzene. a and c, Charge density difference stereograms of benzylic C–H bonds of ethylbenzene on the surface of W2C model (a) and electron-deficient W2C model (W2C-0.08e⁻) (b). The slice is perpendicular to the plane of benzylic C–H bonds, and electron-rich (red) and electron-deficient (blue) areas are presented. Colour code: C, grey; N, blue; H, white; W, purple. c and d, Calculated absorption configurations of each step of the ethylbenzene activation process on W2C (c) and W2C-0.08e⁻ (d). e, Gibbs free energy diagrams of each step of the ethylbenzene activation process on W2C (black and top) and W2C-0.08e⁻ (red and bottom). f, Ethylbenzene-TPD results of the W2C/NxC and NC samples. g, Adsorption capacities of ethylbenzene molecules on the surface of the W2C/NxC electrodes with fixed catalyst loadings (0.66 mg/cm²) at 2.0 V versus SCE for 10 min. h, Conversions of ethylbenzene on W2C/NxC electrodes at 2.0 V versus SCE for 3 h. i, Faradaic efficiencies for ethylbenzene conversion on W2C/NxC electrodes at 2.0 V versus SCE for 3 h.

Figure 4

Stability and efficiency of C–H alkoxylation. a, Current density change of W₂C/N_{3.0}C, Ti mesh and Ni plate electrodes during the reaction. b, Reusability of W₂C/N_{3.0}C under standard conditions within 3 h. c, TOF values (for details, please see Supplementary Table 3) for methoxylation of benzylic C–H bonds on W₂C/N_{3.0}C-based heterogeneous system (solid sphere) and by state-of-the-art homogeneous catalyst (Ir* (III) complex, black circle) and photocatalyst (CuCl, blue circle).

Figure 4

Stability and efficiency of C–H alkoxylation. a, Current density change of W₂C/N_{3.0}C, Ti mesh and Ni plate electrodes during the reaction. b, Reusability of W₂C/N_{3.0}C under standard conditions within 3 h. c, TOF values (for details, please see Supplementary Table 3) for methoxylation of benzylic C–H bonds on W₂C/N_{3.0}C-based heterogeneous system (solid sphere) and by state-of-the-art homogeneous catalyst (Ir* (III) complex, black circle) and photocatalyst (CuCl, blue circle).

Supplementary Files

This is a list of supplementary files associated with this preprint. Click to download.

- [SupplementaryInformation.docx](#)
- [SupplementaryInformation.docx](#)
- [SupplementaryVideo1.mp4](#)
- [SupplementaryVideo1.mp4](#)