A Multi-step In Vitro Hemocompatibility Testing Protocol Recapitulating the Foreign Body Reaction to Nanocarriers

Valeria Perugini

University of Brighton School of Applied Sciences

Ruth Schmid

SINTEF

Yrr Morch

SINTEF

Isabelle Texier

CEA-Leti: Commissariat à l'énergie atomique et aux énergies alternatives Laboratoire d'électronique et de technologies de l'information

Martin Brodde

OxProtec

Matteo Santin (✉ m.santin@brighton.ac.uk)

University of Brighton <https://orcid.org/0000-0002-5260-7088>

Research Article

Keywords:

Posted Date: January 27th, 2022

DOI: <https://doi.org/10.21203/rs.3.rs-1276497/v1>

License: © ⓘ This work is licensed under a Creative Commons Attribution 4.0 International License.

[Read Full License](#)

A Multi-step *In Vitro* Hemocompatibility Testing Protocol Recapitulating the Foreign Body Reaction to Nanocarriers

Valeria Perugini¹, Ruth Schmid², Ýrr Mørch², Isabelle Texier³, Martin Brodde⁴, Matteo Santin¹

¹Centre for Regenerative Medicine and Devices, School of Applied Sciences, University of Brighton - Huxley Building, Lewes Road, Brighton, BN2 4GJ, United Kingdom

²Department of Biotechnology and Nanomedicine, SINTEF, Trondheim, Norway

³Univ. Grenoble Alpes, CEA, LETI-DTBS, F-38000 Grenoble, France

⁴OxProtect GmbH, Munster, Germany

Corresponding author: Matteo Santin, m.santin@brighton.ac.uk

Graphical Abstract

Abstract

The development of drug nanocarriers based on polymeric, lipid and ceramic biomaterials has been paving the way to precision medicine where the delivery of poorly soluble active compounds and personalised doses are made possible. However, the nano-size character of these carriers has been demonstrated to have the potential to elicit pathways of the host response different from those of the same biomaterials when engineered as larger size implants and of the drugs, when administered without carrier. Therefore, a specific regulatory framework needs to be made available that can offer robust scientific insights and provide safety data by reliable tests of these novel nano-devices. In this context, the present work presents a multi-step protocol for the *in vitro* assessment of the hemocompatibility of nanocarriers of different physicochemical properties. Poly (EthylButyl Cyanoacrylate) nanoparticles and lipid-based (LipImage™ 815) nanoparticles of comparable hydrodynamic diameter were tested through a battery of assays using human peripheral blood samples and recapitulating the main pathways of the host response upon systemic administration; i.e. protein interactions, fibrinogen-platelet binding, cytotoxicity and inflammatory response. The data showed the sensitivity and reproducibility of the methods adopted that were also demonstrated to determine individual variability as well as to discriminate between activation of pathways of inflammation and unintended release of inflammatory signalling caused by loss of cell integrity. Therefore, this multi-step testing is proposed as a reliable protocol for NP development and emerging regulatory frameworks.

Introduction

The clinical availability of nanocarriers, for the delivery of therapeutic agents to target diseased tissues more efficaciously, depends on the accurate assessment of their biocompatibility [1]. It is widely accepted that nanocarriers, typically not exceeding 200 nm, induce interactions with the biochemical and cellular components that are different from those of relatively larger particles or implants made of biomaterials bearing the same chemical moieties (e.g. hydrophobic domains, electrostatic charges) [2]. These differences can be ascribed to the nanoparticle (NP) size that increases the surface available to the adsorption and conformational changes of proteins and that is in the range favourable to their internalisation by immunocompetent and tissue cells [3-5]. Indeed, a rapid protein adsorption and contact with different types of cells take place soon after entering the body, regardless of the route of administration, upon contact with body fluids. Likewise, although different cell phenotypes may be encountered depending on the route of administration, immune cells are present in blood

and most tissues, while a range of tissue cells have been demonstrated to be capable of nanoparticle internalization [4, 6].

Intravenous administration has the advantage of delivering systemically thus bypassing first-pass metabolism and improving the therapeutic profile [7]. However, through this route, the immunological response to the injected nanocarriers is increased significantly by their direct exposure to the circulating humoral and cellular elements key to the host response to a foreign body. Protein adsorption and cell contacts may activate pathways of the host response such as thrombogenicity and inflammation which may be due either to the direct recognition of the nano-biomaterials or as result of the unintended release of pro-inflammatory cytokines caused by cytotoxicity and consequent loss of cell integrity [8].

The regulatory approval of novel nanocarriers depends on the successful demonstration of their biocompatibility through a sequence of *in vitro* and *in vivo* tests [8]. *In vitro* tests are particularly important to optimise nanocarriers as they enable scientists in both academia and industry to screen a wide range of formulations before progressing the best candidates to the pre-clinical animal models. To this end, the availability of a range of relatively rapid and operator-friendly *in vitro* tests able to recapitulate the main biochemical and cellular pathways characterising the host response to nano-biomaterials is advocated.

In those cases where a systemic administration is pursued, hemocompatibility tests are required. In particular, many *in vitro* models and assays have been published where polymeric, lipid, metallic and ceramic nanocarriers and nanoparticles have been incubated in whole blood and tested for their thrombogenicity, immunological potential and cytotoxicity [9-11]. While offering valuable scientific insights, these tests tend to focus on specific pathways of hemocompatibility and they are not always designed to provide a clear overview informing scientists and regulators about the hemocompatibility of a nano-biomaterial in a manner that recapitulates the sequence of the main events triggered by its systemic administration [10]. It is also argued that the reliability of any *in vitro* model of hemocompatibility does not rely only on its reproducibility, but also on its potential to provide data of individual variability as well as adaptability to nano-biomaterials with different physicochemical properties.

In this work, a series of interrelated tests based on incubation of either whole human blood or platelet rich plasma (PRP) with nano-biomaterials is proposed. The combined tests aimed to recapitulate the sequence of events occurring upon systemic administration; from the early protein adsorption to the overall cytotoxicity, to thrombogenicity potential and to the release of pro-inflammatory cytokines evaluated in terms either of active release from immunocompetent cells or of passive release caused by the loss of cell integrity.

The resulting multi-step hemocompatibility protocol was validated by the use of nano-biomaterials with different physicochemical properties; i.e. polymeric (Poly(EthylButyl Cyanoacrylate, PEBCA) and lipid (LipImage™ 815) nanocarriers were selected because of their previously defined physicochemical and biocompatibility properties [12-15].

PEBCA-based NP are biodegradable drug nanocarriers that have been exhaustively characterised *in vitro* as well as by pre-clinical *in vivo* models and clinical trials [12-14]. PEBCA NP used in this study typically show a hydrodynamic diameter ranging between 100 and 200 nm with a polydispersity index ranging between 0.1 and 0.18. Their cytotoxic effects have been assessed at concentration ranging from 0.3 to 285 µg/mL within 24h showing large variations between different cell lines and showing to be internalized by various cell lines.

LipImage™ 815 are lipid nanoparticles with a hydrodynamic diameter of approximately 50 nm, a polydispersity index lower than 0.25 and carrying the IR780 fluorophore [15]. Their proposed use for tumor imaging has been supported by *in vitro* cytotoxicity studies on fibroblast cell lines as well as by *in vivo* imaging determining their biodistribution [16, 17]. The assessment of the cytotoxicity showed that fibroblasts well tolerate these nanoparticles with half-maximal inhibitory concentration being 1 mg/mL (i.e. 1.5×10^{13} particles/mL), while a higher accumulation in liver than other organs was observed within 24h.

These data were considered suitable benchmarks for the validation of a multi-step, operator-friendly *in vitro* hemocompatibility testing protocol based on the use of freshly isolated human peripheral blood. The protocol sequential steps aimed to provide interrelated information about the main checkpoints of the host response to NP without the need to undergo more convolute methods of protein adsorption and cell isolation. In addition, the use of donors' blood made the protocol suitable to discriminate individual host response variability.

Materials and Methods

Tests were designed to study the hemocompatibility of the nanocarriers to reflect their early (minutes) and protracted (24 h) interaction with blood proteins and cells. An assay of platelet-fibrinogen binding was used as early thrombogenic potential, while cell lysis and pro-inflammatory cytokine release was measured over a longer period of time.

Nanocarrier preparation.

PEBCA and LipImage suspensions were prepared as previously reported [12].

Briefly, PEBCA nanoparticles were synthesized under aseptic conditions at SINTEF (Trondheim, Norway) by mixing an oil phase consisting of poly (ethylbutyl cyanoacrylate) (PEBCA) containing 0.2 % w/v Nile Red with an aqueous phase consisting of 0.1 M HCl containing the two PEG stabilizers (Brij®L23 and Kolliphor®HS15). The oil in water mini-emulsion was prepared using a tip sonifier. The polymerization was then carried out overnight and unreacted monomer and surplus of surfactants were removed by extensive dialysis.

Batches of LipImage™ 815 were prepared by high pressure homogenization (HPH), the lipid phase comprising soybean oil, Suppocire™ NB, lecithin, and IR-870 oleyl. The aqueous phase comprised Myrj™ S40 and NaCl. Mixtures of lipid and aqueous phases were pre-emulsified and then processed with a High-Pressure Homogenizer (Panda Plus 2000, GEA Niro Soavi, Italy) operated for 16 cycles with a total pressure of 1250 bars. NP were then purified through a 5-µm filter followed by tangential flow filtration, dispersed to a concentration of 100 mg/mL and filter-sterilised through a 0.22 µm Millipore membrane before storage and use.

Both NP types were pre-equilibrated at room temperature for 15 minutes and re-suspended by careful vortexing to prepare standards. These were prepared by the serial dilution of the mother solution in sterile phosphate buffered saline (PBS) pH=7.2 at different concentrations in the range of 1 to 1000 µg/mL. Samples were stored at room temperature and used within 2h from preparation.

Human peripheral blood collection

Human peripheral blood (4 mL) was collected from 6 healthy volunteers from both genders using the Vacutain system into heparinized tubes (BD Vacutainer™ UK). In the case of platelet-fibrinogen binding experiments, blood was collected by Monovette tubes containing sodium citrate. Blood collection was authorized by the University of Brighton Ethics Committee and performed under the Human Tissue Act license n. 12583.

Protein concentration

Protein concentration levels in donors' blood samples incubated with different NP concentrations (6.25, 12.5, 25, 50, 100, 250, 500, 1000 µg/mL) were performed as an indirect method to assess the early interactions between NP and blood components. Samples (50 µL) of freshly isolated human peripheral blood were added to the wells of a 96-well tissue culture plates (TCP, Corning UK) and spiked with 10 µL of NP at different concentrations within 2h from phlebotomy. Each concentration was tested in duplicate for each donor. Samples were incubated in a humidified 37°C, 5% CO₂ cell incubator for 24 hours under static conditions. After 24 hours, blood was removed and the supernatants were immediately tested for protein concentration. Protein concentrations were measured by a Bradford assay (BioRad, UK) on 5 µL of blood supernatant and data expressed as µg/mL mean $\pm$ standard deviation from n=6 as calculated by a bovine serum albumin standard curve.

Thrombogenicity

A method for the measurement of platelet-fibrinogen binding was adopted to assess the thrombogenicity potential of the tested nano-biomaterials. PRP was prepared from 5mL of whole blood by centrifugation at 200 x g for 10 minutes. Fluorisoithiocyanate (FITC)-labeled fibrinogen (OxProtec, Germany) was added to the PRP to a final concentration of 150 µg/mL and the platelet count was adjusted to 25,000/µL to get the stock solution. A volume (10 µL) of either NP at different concentrations or positive controls (i.e. 2µg/mL collagen in PBS, OxProtec) were added to 100µL of the stock solution and incubated for exactly 5 minutes. PBS was used as negative control. The reaction was stopped by adding 110µL of 1% (v/v) formaldehyde solution to fix the platelets for 30 minutes. After a washing step, the binding of FITC-labeled fibrinogen to the platelets was measured by flow cytometry by a BD Accuri C6 flow cytometer and results analyzed using the instrument software. Data were expressed as a percentage of the positive control.

Cytotoxicity

Overall blood cell toxicity induced by the different concentrations of NP was assessed both in the blood supernatants and on cells deposited on the bottom of the well. The former was quantitatively determined by the

release of the lactate dehydrogenase enzyme (LDH) activity, while the latter was qualitatively assessed by a hematoxylin/eosin (HE) staining method.

LDH activity was measured on aliquots obtained from the same blood samples tested for protein concentration levels. Aliquots of 50 µl were tested by the CytoTox 96® Non-Radioactive Cytotoxicity Assay (Promega, UK) and data were expressed as mean percentage of the positive control $\pm$ standard deviation from n=6 according to the formula

$$\text{LDH activity (\% O.D 490nm)} = [(\text{Experimental sample} - \text{Background}) / (\text{Positive Control} - \text{Background})] \times 100$$

Where the maximum LDH release is the enzymatic activity measured in the supernatant of samples treated with 10 µL of manufacturer's lytic solution for 45 min prior to addition of the kit substrate solution.

Blood basal LDH activity and the LDH activity of blood samples treated with the lytic solution (positive control) were expressed as arbitrary units_{Abs490nm}/mL.

Cells deposited at the bottom of the wells used for protein concentration and LDH activity measurements were washed twice in 50 µL of PBS, fixed by 50 µL of 3.7 % v/v paraformaldehyde for 10 minutes at room temperature, washed three times with PBS and stained by hematoxylin solution (Sigma, UK) adding 50 µL of dye into each well for 5 minutes at room temperature. Samples were rapidly rinsed three times with distilled water and in 0.5 % v/v acetic acid for 40 seconds, washed again in distilled water and counterstained in 50 µL eosin solution (Sigma, UK) for 2 minutes at room temperature. The samples were finally rinsed three times in water. Light microscopy images were taken from samples of the two types of nanoparticles at x20 magnification and qualitatively analysed for their area coverage.

Inflammatory cell levels and response

The levels and activation of inflammatory cells involved in the early inflammatory response, granulocytes and monocytes/macrophages, were assessed in the whole blood samples challenged by different concentrations of NP (1, 2, 5, 10, 100 and 1000 µg/mL) by flow cytometry. In particular, the analysis of typical cell membrane markers as well as the release of pro-inflammatory agents, including myeloperoxidase enzyme activity for granulocytes and cytokines for monocytes/macrophages was performed.

Granulocyte levels and myeloperoxidase (MPO) activity. PBS (10 µL) was used as negative control, while the TSP-1 peptide RFYVVMWK (10 µL, 200 µM in PBS) was used as positive control. NP were added to flow cytometer vials, to which 100 µL of whole blood from individual donors was added and incubated, at room temperature, for 30 minutes. Samples were fixed by the addition of 110 µL of 0.4% (v/v) formaldehyde solution for 30 minutes. Samples were washed by the addition of 1 mL of PBS followed by centrifugation for 10 minutes at 500 × g. The supernatants were discarded leaving approximately 100 µL volume including the cell pellet. Anti-Myeloperoxidase PE-labelled antibodies (5 µL, Becton Dickinson) were added to each sample and incubated for 1 hour at room temperature and washed twice. Lysing solution (1 mL) was added for 10 minutes at room temperature. PBS (2 mL) was added and samples were centrifuged at 500 × g for 10 min. The supernatants were aspirated and the cell pellets suspended in 500 µL of PBS prior to analysis by flow cytometry (Accuri C6, BD, UK).

Monocyte/macrophage levels and cytokine release. For each 100 µL of whole blood required, 5 µL of FITC-labelled mouse anti-human CD14 (Becton Dickinson) and 5 µL of PE-labelled anti-human CD11b antibody (BioLegend) were added. Aliquots of 10 µL of either NP, or TSP-1 peptide (positive control) or PBS (negative control) were added to 100 µL of antibody-labelled whole blood and incubated for 30 minutes, room temperature. Samples were fixed by the addition of 110 µL of 0.4% (v/v) formaldehyde solution (Sigma Aldrich) to the cultures for 30 minutes. Samples were washed by the addition of 1 mL of PBS followed by centrifugation for 10 minutes at 500 × g. The supernatants were discarded leaving approximately 100 µL volume including the cell pellet. Lysing solution (1 mL, Beckman Coulter) was added for 10 minutes at room temperature. Two washes in PBS (2 mL) were performed. The supernatants were aspirated and the cell pellets suspended in 500 µL of PBS prior to analysis by flow cytometry (Accuri C6, BD, UK).

Human Th1/Th2 cytokine standards (Cytometric Bead Array, CBA, BD, UK) were reconstituted in assay diluent and incubated for 15 minutes at room temperature (0 – 2500 pg/mL). After incubation, 6 human Th1/Th2 cytokine capture beads were treated with 50 µL PE-conjugated detection antibodies (BD, UK) before being mixed with 10 µL plasma/standards diluted in 40 µL of serum enhancement (BD, UK). Both samples and standards were then incubated for 3 hours. After 3 washing steps with 1 mL of washing buffer, samples and

standards were assessed by BD Accuri C6 flow cytometer and results analysed using a specific BD analysis software. Data of blood samples from individual donors after spiking with different concentrations of NP were assessed for relative levels of cytokines compared to the control.

Statistical analysis

Statistical analysis was performed by ANOVA t test (Tukey Kramer test) from n=6 blood donors. Significant differences of samples treated with different concentrations of NP from those of each donor's control were tested at $p < 0.05$.

Results and Discussion

Protein interactions with biomaterial surfaces is known to take place in milliseconds after the exposure of biomaterial surfaces to body fluids [18]. However, over a longer period of time, the so called Vroman's effect takes place, whereby proteins with a relatively high molecular weight displace those with low molecular weight, leading to the formation of a stable protein layer [18]. The consequent adsorption of this protein film at the biomaterial surface is also considered the main cause of the host response to implants, including thrombogenicity and inflammatory response [3]. Therefore, the measurement of the protein levels in the blood samples exposed to different concentrations of PEBCA and LipImage™ 815 was adopted as an indirect testing of these interactions. Protein levels in freshly isolated whole heparinised human peripheral blood showed a statistically significant reduction of protein levels in all donors when relatively high concentrations (≥ 100 $\mu\text{g/mL}$) of both PEBCA and LipImage™ 815 were tested (Fig. 1 A and B). These decreased levels indicated a possible adsorption of blood proteins onto the NP surface or the possible precipitation of proteins induced by high concentrations of NP. Indeed, serum protein depletion by NP incubation has been previously demonstrated, particularly in the case of NP with a negatively charged surface [19].

Among the proteins relevant to the host response and able to adsorb onto biomaterial surfaces, fibrinogen plays a key role in the clot activation upon NP systemic administration [20]. Fibrinogen binding to NP with different physicochemical properties has been widely documented and related to both the NP surface electrostatic charges and size [21, 22]. In the present protocol, the assay adopted assessed the binding of fibrinogen to platelets by spiking freshly isolated PRP with labelled fibrinogen. The assay provides indications of: (i) the NP-induced activation of platelets leading to a higher expression of their receptors for fibrinogen and consequently of thrombogenicity through fibrinogen-platelet complex formation, (ii) the binding of the formed fibrinogen to the surface of the NP that may also triggers thrombogenicity through complexation with the platelets.

The data showed that fibrinogen-platelet binding was dependent on the type of NP tested, but not exceeding 40% of the positive control (Fig. 2 A and B). In the case of PEBCA, a binding level of ca 40% was observed in all donors in the range of concentrations 1 to 100 $\mu\text{g/mL}$ (Fig. 2 A). This binding significantly dropped to ca 20% at 1000 $\mu\text{g/mL}$ following a pattern similar to that observed for the protein concentration levels. It can therefore be speculated that, in the case of these polymeric NP, the binding of platelets is limited and possibly reduced by the reduced concentrations of adsorbed fibrinogen. It is also observed that in such a case, the presence of PEG surfactants in the PEBCA NP formulation did not prevent the adsorption of fibrinogen and consequent platelet binding. These findings are corroborated by previous studies showing that PEG reduces but does not completely prevent the formation of a protein corona and of fibrinogen binding at the surface of NP and that it is rather change its composition and it is the cause of serum protein depletion as that observed in the experiments of protein concentration [23-26]. In addition, the formation of a protein corona at the surface of NP has been linked to their longer stability *in vivo* [26].

A different behaviour was observed when different concentrations of LipImage™ 815 NP were studied (Fig. 2 B). This lipid-based nanocarrier showed a slight increase of fibrinogen-platelet binding at increasing NP concentrations, but never exceeding the 30% level. In addition, higher individual variability was observed with two out of 6 donors showing significantly lower levels of binding up to concentrations of 100 $\mu\text{g/mL}$. These observations are supported by previous studies that have demonstrated that the binding of fibrinogen sequences to liposomes induces the binding and activation of platelets [25, 26].

Platelet activation measured as expression of CD63 and CD62b antibodies was negligible for both NP types until concentrations of 1000 mg/mL were tested were levels of ca 30% of the positive controls were observed (data not shown). Therefore, it is suggested that the adsorption of fibrinogen rather than a direct activation of the platelets by NP may determine mild thrombogenicity potential.

It may be speculated that the different profiles of fibrinogen-platelet binding on the two types of NP could be linked to their different physicochemical properties. The data suggest that the fibrinogen adsorbed within the

PEBCA NP protein corona favours platelet binding at low NP concentrations and that only the alleged depletion of proteins observed at relatively high concentrations ($>100 \mu\text{g/mL}$) slightly reduces this binding. Conversely, the intrinsically more unstable nature of the lipid-based LipImageTM 815 appears to induce a reduced and more variable formation of the fibrinogen-platelet complex [26].

In the proposed NP testing protocol, the combination of the simple and relatively rapid Bradford's protein concentration assay and the flow cytometry study of fibrinogen-platelet binding highlights the different hemocompatibility of NP under investigation, particularly in relation to the early interaction of these NP with blood components following systemic administration.

The availability of relatively large volumes (5 mL) of blood samples also enabled a further assessment of the host response to the tested NP in relation to their cytotoxicity and inflammatory response.

To this end, aliquots of the same samples used for the protein concentration measurements were used to assess the NP cytotoxicity. Indeed, these samples provided the opportunity to test the loss of cell integrity by released LDH specific activity (Figg. 3 A and B) in the blood volume and that of cells, mainly erythrocytes, deposited at the bottom of the well (Figg. 4 A and B).

The basal LDH activity of the tested blood donors, measured as absorbance at 490nm, was 0.534 ± 0.044 , while the average LDH activity released by induced cell lysis (positive control) was 1.651 ± 0.270 . An increase in the LDH activity was observed only at concentrations of $100 \mu\text{g/mL}$ and above for both NP types (Figg. 3 A and B) with clear individual donor's variations. The loss of cell integrity was qualitatively confirmed by HE staining of the well surface that showed a reduced staining of deposited cells, mainly erythrocytes, at the same concentrations for both types of NP (Figg. 4 Panels A and B) in line with previously published data of erythrocyte toxicity by NP [29].

Whole human blood samples enabled the assessment of the inflammatory response to NP, another key parameter in the study of the biomaterial hemocompatibility. This last batch of experiments of the multi-phase protocol was linked to the data of protein concentrations and cytotoxicity to indicate whether the incubation with the two types of NP was affecting the mononuclear cell population and its role in inducing an inflammatory response either by cell activation or by unintended release of pro-inflammatory cytokines through loss of cell integrity.

As the inflammatory response to biomaterials is triggered by the early activation of granulocytes followed by that of monocytes/macrophages [30, 31], the flow cytometry analysis of this study focussed on the markers of these two types of cells as well as on the release of pro-inflammatory macromolecules.

In this part of the protocol, the flow cytometry tests focussed on the presence of cells in the human blood expressing CD14 and CD11b, cell surface markers common to both granulocytes and monocytes/macrophages [32, 33]. The levels of CD14 observed at increasing concentration of PEBCA NP showed a gradual reduction of the levels of these cells suggesting that relatively high concentrations of NP, consistently with the data of cytotoxicity, led to loss of cell integrity (Fig. 5 A). Similar results were observed for LipImageTM 815 (Fig. 5 B).

It has been reported that under inflammatory conditions, CD11b (also known as Mac-1) expression is upregulated and differential CD11b can distinguish between the peak and resolution of acute lung inflammation, respectively. Mac-1 is expressed on monocytes, neutrophils, peritoneal B-1 cells, CD8⁺ dendritic cells, NK cells and a subset of CD8⁺ T cells [33]. It functions in cellular adhesion, phagocytosis and extravasation, and it may play a role in chemotaxis. Mac-1 binds a diverse group of ligands, which include inactivated complement component C3b (iC3b), fibrinogen, coagulant factor X and the intercellular adhesion molecule ICAM-1. In this work, CD11b expression induced by the tested NP never exceeded 20% of the positive control and a trend towards its reduction at higher concentrations was related to the demonstrated loss of blood cell integrity (Figures 5 C and D). Hence, the combination of the CD14 and CD11b data seem to indicate relatively low levels of inflammatory cells' activation by the tested NP.

However, the study of the release of soluble pro-inflammatory pathways seemed to suggest that an inflammatory insult could derive from the cell death detected at the relatively high NP concentrations. Indeed, granulocyte MPO activity [34] increased with the increase of NP concentrations, with a higher release being observed in the case of PEBCA NP where the MPO activity ranged from approximately 20% to 50% of the positive control (Fig. 6 A). In the case of LipImageTM 815, MPO activity was relatively low reaching a

maximum of approximately 20% at the highest concentrations tested and being not significantly different from the negative control up to 50 µg/mL (Fig. 6 B).

Finally, flow cytometry was applied to test the Th1/Th2 pathway that is shared by most of the blood immunocompetent cells (i.e monocytes/macrophages and lymphocytes) [35] thus enabling to evaluate the immune response to NP more comprehensively. The flow cytometry analysis was performed by commercially available antibody-functionalized microbead arrays to study the release of other relevant pro-inflammatory factors at different NP concentrations (Fig. 7, Panels A and B). The flow cytometry panels for both PEBCA NP and LipImage™ 815 NP showed release of the tested cytokines at levels not significantly different from the negative control (blood samples not challenged by NP) when the tested NP concentrations were below the determined cytotoxic threshold. Only a slight and donor's dependent higher release of some of the tested cytokines was observed at the cytotoxic concentrations. As observed in the case of other assays of the multi-step protocol, the testing of blood samples from individual donors highlighted that the levels of release of the cytokines of Th1/Th2 pathway showed, once again, the importance of assessing NP hemocompatibility in the context of individual variability.

Taken together, the data obtained by this multi-step protocol demonstrates its ability to discriminate between different components of the host response, different doses and different NP physico-chemical properties as well as individual variability. The comparable size of the NP and the same range of concentration tested in this study also corroborates the comparative value offered by the protocol. The tested NP were not showing a significant activation of the host response in most of its measured parameters. The thrombogenic potential seemed to be affected slightly by both the type of NP tested and their ability to induce blood protein depletion. At the same time, while a pronounced lysis of erythrocytes was observed, the integrity of the remaining blood cell population seemed to be compromised only when by very high NP concentrations were tested resulting in low levels of release of pro-inflammatory cytokines.

Conclusions

Future developments and regulatory approval of nanoparticulate carriers will depend on the definition of reliable testing protocols able to identify in a user-friendly, cost-effective and relatively fast manner the host response triggered upon administration. At the same time, it is argued that these tests should also provide reassurance about the variability of the host response of individual patients. The present work shows that a multi-step protocol obtained from single collections of peripheral blood from different donors may provide a first level of safety check of NP with different physico-chemical properties during their phase of product development and provide batches of *in vitro* data suitable for regulatory approval. In addition, this sequence of tests could be adopted to predict any adverse effect occurring on single patients and help to establish personalised safety assessments and dose regimes of nanomedicines.

Ethical Statement

Ethics approval and consent to participate: This study was approved by the University of Brighton Ethics committee and consents to participate were obtained in the form of signed document from all blood donors.

Consent for publication: Blood donors have consented the use of the data for publication. All authors have reviewed the data and the manuscript and consented to their publication.

Availability of data and materials: Raw data are stored in the University of Brighton repository and made available upon request.

Competing interests: The authors declare no competing interest in relation to the data of this research.

Authors contribution

Valeria Perugini contributed to the design of the protein and cytotoxicity studies, performed all the hemocompatibility experiments and collected and reviewed data.

Isabelle Texier contributed with the synthesis the LipImage™ 815 NP

Yrr Mørch contributed with the design and synthesis of PEBCA NP and revision of the manuscript

Ruth Schmid and Martin Brodde contributed to the experimental design and revision and interpretation of data and manuscript

Matteo Santin contributed to the experimental design, data analysis and interpretation and drafting of the manuscript.

Acknowledgements

The work has been supported by the EC Horizon 2020 project 'Regulatory Science Framework for Nano(bio)material-based Medical Products and Devices' REFINE, contract n. 751104.

References

1. Rout GK, Shin HS, Gouda S, Sahoo S, Das G, Fraceto LF, Patra JK Current advances in nanocarriers for biomedical research and their applications, *Artif Cells Nanomed Biotechnol.* 2018; 46:sup2, 1053-62, doi: 10.1080/21691401.2018.1478843
2. Ernst LM., Casals E, Italiani P, Boraschi D, Puntès V. The Interactions between Nanoparticles and the Innate Immune System from a Nanotechnologist Perspective. *Nanomaterials.* 2021; 11, 2991. <https://doi.org/10.3390/nano11112991>
3. Mishra RK, Ahmad A , Vyawahare A , j Alam P , Khan TH , Rehan Khan R. Biological effects of formation of protein corona onto nanoparticles. *Int J Macromol.* 2021; 175:1-18
4. Liu L, Bai X, Martikainen MV, Kårlund A, Roponen M, Xu W, Hu G, Tasciotti E, Lehto VP. Cell membrane coating integrity affects the internalization mechanism of biomimetic nanoparticles. *Nat Commun.* 2021; 30;12(1): 5726. doi: 10.1038/s41467-021-26052-x.
5. Di Maggio N, Martella M, Meikle S, Columbaro M, Lucarelli E, Santin M, Banfi A. Rapid and efficient magnetization of mesenchymal stem cells by dendrimer-functionalized magnetic nanoparticles. *Nanomedicine.* 2016; 11(12): 1519-34 , doi 10.2217/nnm-2016-0085.
6. Varol C, Mildner A, Jung S. Macrophages: development and tissue specialization *Annu Rev Immunol.* 2015; 33:643-75. doi: 10.1146/annurev-immunol-032414-112220.
7. Boraschia D, Italiani P, Palombab R, Decuzzib P, Duschlc A, Fadeeld B, Moghimie SM. Nanoparticles and innate immunity: new perspectives on host defence. *Semin Immunol.* 2017; 34:33-51. doi: 10.1016/j.smim.2017.08.013.
8. Saha AK, Zhen MYS, Erogbogbo F, Anand K. Ramasubramanian AK. Design Considerations and Assays for Hemocompatibility of FDA-Approved Nanoparticles. *Semin Thromb Hemost.* 2020; 46(05): 637-52 doi: 10.1055/s-0039-1688491
9. de la Harpe KM , Kondiah PPD, Choonara YE, Marimuthu T, du Toit LC, Pillay V. The Hemocompatibility of Nanoparticles: A Review of Cell–Nanoparticle Interactions and Hemostasis. *Cells* 2019; 8: 1209 doi:10.3390/cells8101209
10. Guildford A, Poletti T, Osbourne LH, Di Cerbo A, Gatti AM, Santin M. Nanoparticles of a different source induce different patterns of activation in key biochemical and cellular components of the host response *Interface* 2009 6 (41):1213-21.
11. Lewinski N, Colvin V, Drezek R. Cytotoxicity of Nanoparticles. *Small* 2008; 4(1): 26 – 49 doi: 10.1002/sml.200700595
12. Sulheim E, Iversen TG, Nakstad VT, Klinkenberg G, Sletta H, Schmid R, Hatletveit AR, Wågbø AM1, Sundan A, Skotland T, Sandvig K, Mørch Y. Cytotoxicity of Poly(Alkyl Cyanoacrylate) Nanoparticles *Int J Mol Sci.* 2017; 18:2454 doi:10.3390/ijms18112454
13. Snipstad S, Westrøm S, Mørch Y, Afadzi M, Åslund AKO, de Lange Davies SC. Contact-mediated intracellular delivery of hydrophobic drugs from polymeric nanoparticles. *Cancer Nanotechnology* 2014; 5:1-8
14. Snipstad S, Hak S, Baghirov H, Sulheim E, Mørch Y, Eva von Haartman E, Marcus Beack M,6 Nilsson KPR, Klymchenko AS, de Lange Davies SC, Andreas K. O. Åslund AKO. Labeling Nanoparticles: Dye Leakage and Altered Cellular Uptake. *Cytometry Part A* 2017; 91A: 760-66, doi: 10.1002/cyto.a.22853
15. Jacquart A, Kéramidas M, Vollaie J, Boisgard R, Pottier G, Rustique E, rique Mittler F, Navarro FP, Boutet J, Coll JL, Isabelle Texier I. LipImage™ 815: novel dye-loaded lipid nanoparticles for long-term and sensitive in vivo near-infrared fluorescence imaging. *J Biomed Optics* 2013; 18(10), 101311, doi: 10.1117/1.JBO.18.10.101311
16. Sayag D, Cabon Q, Texier I, Navarro FP, Boisgard R, Virieux-Watrelet D, Carozzo C, Ponce F. Phase-0/phase-I study of dye-loaded lipid nanoparticles for near-infrared fluorescence imaging in healthy dogs, *Eur J Pharm Biopharm* 2016; 100, 85-93
17. Cabon Q, Sayag D, Texier I, Navarro FP, Boisgard R, Virieux-Watrelet D, Ponce F, Carozzo C. Evaluation Of Intra-Operative Fluorescence Imaging Guided Surgery In Cancer-Bearing Dogs : A Prospective Proof-Of-Concept Phase II Study in 9 cases, *Trans Res* 2016; 170, 73-88 doi: 10.1016/j.trsl.2015.12.001

18. Hirsha SL, McKenzia DR, Nosworthy NJ, Denman JA, Sezerman OU, Bilek MMM. The Vroman effect: Competitive protein exchange with dynamic multilayer protein aggregates. *Coll Surf B: Biointerf* 2013; 103: 395–404 <http://dx.doi.org/10.1016/j.colsurfb.2012.10.039>
19. Zhang B, Xie M, Bruschweiler-Li L, Bruschweiler R. Nanoparticle-assisted removal of protein in human serum for metabolomics studies. *Anal Chem*. 2016; 88(1): 1003–07 doi:10.1021/acs.analchem.5b03889.
20. Mosesson MW. Fibrinogen and fibrin structure and functions. *Thromb Haemost*. 2005; 3(8):1894-904. doi: 10.1111/j.1538-7836.2005.01365.x.
21. Horbett TA Fibrinogen adsorption to biomaterials, *J Biomed Mater Res A*. 2018; 106(10): 2777–2788. doi:10.1002/jbm.a.36460.
22. Hyltegren K, Hulander M, Andersson M, Skepö M. Adsorption of Fibrinogen on Silica Surfaces-The Effect of Attached Nanoparticles Biomolecules. 2020; 10(3):413. doi: 10.3390/biom10030413
23. Nonckreman CJ, Fleith S, Rouxhet PG, Dupont-Gillain CC. Competitive adsorption of fibrinogen and albumin and blood platelet adhesion on surfaces modified with nanoparticles and/or PEO. *Colloids Surf B Biointerf*. 2010;77(2):139-49. doi: 10.1016/j.colsurfb.2010.01.014.
24. Peracchia MT, Harnisch S, Pinto-Alphandary H, Gulik A, Dedieu JC, Desmaële D, d'Angelo J, Müller RH, Couvreur P. Visualization of in vitro protein-rejecting properties of PEGylated stealth polycyanoacrylate nanoparticles. *Biomaterials* 1999; 20(14):1269-75. doi: 10.1016/s0142-9612(99)00021-6.
25. Partikel K, Korte R, Stein NC, Mulac D, Herrmann FC, Humpf HU, Langer K. Effect of nanoparticle size and PEGylation on the protein corona of PLGA nanoparticles. *Eur J Pharmaceut Biopharmaceut* 2019; 141: 70-80 <https://doi.org/10.1016/j.ejpb.2019.05.006>
26. Suka JS, Xua Q, Kima N, Hanesa J, Ensign LM. PEGylation as a strategy for improving nanoparticle-based drug and gene delivery. *Adv Drug Deliv Rev*. 2016; 99(Pt A): 28–51. doi:10.1016/j.addr.2015.09.012.
27. Suzuki H, Okamura Y, Ikeda Y, Takeoka S, Handa M. Ultrastructural analysis of thrombin-induced interaction between human platelets and liposomes carrying fibrinogen γ -chain dodecapeptide as a synthetic platelet substitute. *Thromb Res* 2011; 128: 552–559 doi:10.1016/j.thromres.2011.07.031
28. Hernández MR, Urbán P, Casals E, Estelrich J, Escolar G, Galán AM. Liposomes bearing fibrinogen could potentially interfere with platelet interaction and procoagulant activity. *Int J Nanomed* 2012; 7:2339–2347
29. Ran Q, Xiang Y, Liu Y, Xiang L, Li F, Deng X, Xiao Y, Chen L, Chen L, Li Z. Eryptosis Indices as a Novel Predictive Parameter for Biocompatibility of Fe₃O₄ Magnetic Nanoparticles on Erythrocytes. *Scientific Reports* ; 5:16209 doi: 10.1038/srep16209
30. Anderson JM. Trans Inflammatory response to implants ASAIO 1988; 34(2):101-7. doi: 10.1097/00002480-198804000-00005.
31. Roy A, Kumara S, Tripathi A, Dasa M, Dwivedi PD. Interactive threats of nanoparticles to the biological system. *Immunology Letters* 2014; 158 79–87 <http://dx.doi.org/10.1016/j.imlet.2013.11.019>
32. Zanon I, Granucci F. Role of CD14 in host protection against infections and in metabolism regulation. *F Front Cell Infect Microbiol*. 2013; 3:32. doi: 10.3389/fcimb.2013.00032.
33. Duan M, Steinfort DP, Smallwood D, Hew M, Chen W, Ernst M, Irving LB, Anderson GP, Hibbs ML. CD11b immunophenotyping identifies inflammatory profiles in the mouse and human lungs. *Nature* 2016; 9(2): 550-63 doi:10.1038/mi.2015.84
34. Khan AA, Alsahli MA, Rahmani AH. Myeloperoxidase as an Active Disease Biomarker: Recent Biochemical and Pathological Perspectives. *Med Sci*. 2018; 6: 33 doi:10.3390/medsci6020033
35. Mills CD, Kincaid K, Alt JM, Heilman MJ, Hill AM. M-1/M-2 Macrophages and the Th1/Th2 J *Immunol* 2000; 164:6166-73 doi: 10.4049/jimmunol.164.12.6166

Figures Legends

Figure 1. Levels of protein concentrations in human donors' peripheral blood incubated with increasing concentrations of PEBCA (A) and LipImage™ 815 (B) NP. Protein levels are expressed as mean μ g/mL from n=6 donors each tested in duplicate. Statistical annotations: ns=not significant, * $p \leq 0.05$.

Figure 2. Levels of fibrinogen-platelet binding in human donors' peripheral blood incubated with increasing concentrations of PEBCA (A) and LipImage™ 815 (B) NP. Data are expressed as mean $\pm$ standard deviation of the percentage of the positive control from n=6 donors each tested in duplicate. Statistical annotations: ns=not significant, * $p \leq 0.05$.

Figure 3. Levels of cytotoxicity in human blood induced by increasing concentrations of PEBCA (A) and LipImage™ 815 (B) NP. Release LDH activity is expressed as mean $\pm$ standard deviation of the percentage of

the positive control from n=6 donors each tested in duplicate. Statistical annotations: ns=not significant, * $p \leq 0.05$.

Figure 4. Cytotoxicity of deposited human blood cells induced by increasing concentrations of PEBCA (Panel A) and LipImageTM 815 (Panel B) NP. Cells were stained by HE method and photos taken by light microscopy at x20 magnification.

Figure 5. Expression of blood inflammatory cells' membrane markers upon spiking with increasing concentrations of PEBCA (A, C) and LipImageTM 815 (B, D) NP. Flow cytometry data for CD14 (A and B) and CD11b (C and D) expression are expressed as mean $\pm$ standard deviation of the percentage of the positive control from n=6 donors each tested in duplicate. Statistical annotations: ns=not significant, * $p \leq 0.05$.

Figure 6. Levels of MPO activity released by granulocytes in human blood spiked by increasing concentrations of PEBCA (A) and LipImageTM 815 (B) NP. Flow cytometry data are expressed as mean $\pm$ standard deviation of the percentage of the positive control from n=6 donors each tested in duplicate. Statistical annotations: ns=not significant, * $p \leq 0.05$.

Figure 7. Semi-quantitative assessment of the levels of cytokine released inflammatory cells (granulocytes and mononuclear cells) in human blood spiked by increasing concentrations of PEBCA (Panel A) and LipImageTM 815 (Panel B). Flow cytometry plot of control sample from Donor n. 1 reports the Th1/Th2 signalling markers analysed in the assay; IFN- γ , TNF, IL-10, IL-5, IL-4.

Figures

Figure 1

Levels of protein concentrations in human donors' peripheral blood incubated with increasing concentrations of PEBCA (A) and LipImageTM 815 (B) NP. Protein levels are expressed as mean $\mu\text{g/mL}$ from n=6 donors each tested in duplicate. Statistical annotations: ns=not significant, * p < 0.05.

Figure 2

Levels of fibrinogen-platelet binding in human donors' peripheral blood incubated with increasing concentrations of PEBCA (A) and LiplImageTM 815 (B) NP. Data are expressed as mean + standard deviation of

the percentage of the positive control from n=6 donors each tested in duplicate. Statistical annotations: ns=not significant, * p <0.05.

Figure 3

Levels of cytotoxicity in human blood induced by increasing concentrations of PEBCA (A) and LipImageTM 815 (B) NP. Release LDH activity is expressed as mean + standard deviation of the percentage of the positive control from n=6 donors each tested in duplicate. Statistical annotations: ns=not significant, * p < 0.05.

Figure 4

Cytotoxicity of deposited human blood cells induced by increasing concentrations of PEBCA (Panel A) and LiplImage™ 815 (Panel B) NP. Cells were stained by HE method and photos taken by light microscopy at x20 magnification.

Figure 5

Expression of blood inflammatory cells' membrane markers upon spiking with increasing concentrations of PEBCA (A, C) and LiplImage™ 815 (B, D) NP. Flow cytometry data for CD14 (A and B) and CD11b (C and D) expression are expressed as mean + standard deviation of the percentage of the positive control from n=6 donors each tested in duplicate. Statistical annotations: ns=not significant, * p < 0.05.

Figure 6

Levels of MPO activity released by granulocytes in human blood spiked by increasing concentrations of PEBCA (A) and LiplImageTM 815 (B) NP. Flow cytometry data are expressed as mean + standard deviation of

the percentage of the positive control from n=6 donors each tested in duplicate. Statistical annotations: ns=not

significant, * $p < 0.05$.

Figure 7

Semi-quantitative assessment of the levels of cytokine released inflammatory cells (granulocytes and mononuclear cells) in human blood spiked by increasing concentrations of PEBCA (Panel A) and LipImageTM

815 (Panel B). Flow cytometry plot of control sample from Donor n. 1 reports the Th1/Th2 signalling markers analysed in the assay; IFN-g, TNF, IL-10, IL-5, IL-4.