Surface Functionalization of Organosilica Nanoparticles with Au Nanoparticles inhibits Cell Proliferation and Induces Cell Death in 4T1 Mouse Mammary Tumor Cells for DNA and Mitochondrial-synergized Damage in Radiotherapy

Chihiro Mochizuki

Yamaguchi University

Yukihito Kayabe

Yamaguchi University

Junna Nakamura

Yamaguchi University

Shigeki Kato

Yamaguchi University

Masaya Igase

Yamaguchi University

Takuya Mizuno

Yamaguchi University

Michihiro Nakamura (✉ nakam@yamaguchi-u.ac.jp)

Yamaguchi University

Research Article

Keywords: organosilica nanoparticles, Au nanoparticles, radiotherapy, X-ray sensitizer, imaging assay

Posted Date: February 24th, 2022

DOI: <https://doi.org/10.21203/rs.3.rs-1390318/v1>

License: © ⓘ This work is licensed under a Creative Commons Attribution 4.0 International License. [Read Full License](#)

Abstract

Radiotherapy is one of the most effective cancer treatments. Au nanoparticles (NPs) are one of the most used X-ray sensitizing materials however the effective small sub-nm size of Au NPs used for X-ray sensitizers is disadvantageous for cellular uptake. Here, we propose the surface functionalization of organosilica NPs (OS) with Au NPs (OS/Au), which combined the 100 nm size of OS and the sub-nm size of Au NPs, and synthesized effective Au materials as an X-ray sensitizer. The X-ray sensitizing potential for 4T1 mouse mammary tumor cells was revealed using a multifaceted evaluation combined with a fluorescence microscopic cell imaging assay. The number of polyethyleneimine (PEI)-modified OS (OS/PEI) and OS/Au (OS/Au/ PEI) uptake per 4T1 mouse mammary tumor cell was the same; however, 4T1 cells treated with OS/Au/PEI exhibited significant inhibition of cell proliferation and increases in cell death by X-ray irradiation at 8Gy. The non-apoptotic death of OS/Au/PEI-treated 4T1 cells was increased by DNA and mitochondrial-synergized damage increase and showed potential applications in radiotherapy.

1. Introduction

Radiotherapy is one of the most effective cancer treatments.[1] The common types of tumors have been treated with radiotherapy and combined with surgery, chemotherapy, or immunotherapy. Radiotherapy uses ionizing radiation (IR), which refers to electromagnetic waves such as X-ray and γ ray, and particle radiation such as α , β particles, and neutron beams.[2] The mechanism of cell death induced by IR is as follows: The IR interaction with biomolecules causes ionization and excitation to produce reactive oxygen species (ROS) such as hydroxyl radicals ($\cdot\text{OH}$);[3][4] these ROS quickly react with cellular components and damage them. DNA is a primary target for determining the effects of IR on cells. After IR irradiation, the damaged cells are repaired through a series of cellular processes; if this repair is unsuccessful, cell death occurs within seconds to days.[5] The selectivity of tumor cells is not sufficiently high in radiotherapy, and exposure to IR can directly damage normal cells and tumor cells. Because of the lower selectivity, the dose of IR has been often limited in clinical applications.[6]

A variety of Au nanoparticle (NPs) systems have been tested for their radiosensitization properties by examining their physical properties such as the size, shape, and composition of the surface ligands of NPs in vitro.[7] Several studies have reported the use of 1.9 nm Au NPs (AuroVist™) protected by thiol derivatives.[8][9][10][11][12][13] The radiosensitization of several tens of nanometers of Au NPs protected by citrate,[14][15][16] glucose,[17][18][19] and PEG,[20][21][22][23] and the precise mechanism behind the increase in IR effects attributed to Au NPs is yet to be fully elucidated. One of the most widely believed mechanisms is that of physical enhancement, which is caused by the increased X-ray photoelectric absorption of Au.[24] Precious-metal-enhanced IR is an attractive method in X-ray sensitizers because the precious metal absorption of X-rays is based on the high-Z materials theory that produces secondary electrons (e.g., Auger electrons) which react with intracellular water and generate $\cdot\text{OH}$. [25][26][27] Previous studies have reported on the use of small-sized Au NPs (sub-5-nm) as radiosensitizers for producing ROS for the large surface area of Au.[28] This study showed that the turnover frequency (TOF) values, which is the number of catalytic reactions by a surface Au per second, of the hydroxylation of coumarin carboxylic acid for 3 nm Au NPs appeared to be better than that of the 30 nm Au NPs by a factor of 2 for the lowest surface areas. This size

dependence was different from that of simple Au NPs catalytic reactions, which increased the number of surface atoms of Au NPs by small Au NPs for the oxidation reaction,[29] indicating chemical enhancement. For these reasons, it is predicted that the X-ray sensitization of Au NPs will be highly effective for the sub-nm size. Au [Z (atomic number) = 79] has been investigated as an X-ray sensitizer owing to its biocompatibility and low cytotoxicity. In the previous study, polymer-supported Au NPs exhibited increased cellular uptake for the DU145 human prostate cancer cell line because of their increased stability under biological conditions compared to that of free Au NPs.[30] Thus, Au NPs supported on stable materials in biological conditions will be highly effective as X-ray sensitizers.

The enhanced permeability and retention (EPR) effect can be utilized to apply Au NPs in radiotherapy based on the drug delivery system (DDS). The EPR effect is attributed to the increased vascular permeability caused by the incomplete neovascularization around the tumor and the lack of excretory function by lymphatic capillaries in the tumor tissues.[31][32] The appropriate NP size for the EPR effect is approximately 5–200 nm; 100 nm NPs are widely used. Thus, the size control of approximately 100 nm NPs is essential for DDS.

Therefore, to achieve more effective Au-enhanced radiotherapy, it is necessary to combine the sub-nm Au NPs (for increased X-ray sensitization) and the 100 nm sized NPs (to target tumor cells). Thus, X-ray sensitizing and targeting tumor cells for DDS, and effective nano-drug for radiotherapy could be achieved by the functionalization of 100 nm NPs with sub-nm sized Au NPs. Among DDS NPs, OS NPs are among the most attractive NPs to realize easy size control to exploit the EPR effect and simple surface functionalization with biomolecules for the preferential accumulation of NPs in the tumor.[33][34][35]

One of the most common methods used in the evaluation of the effect of IR for the quantitative analysis of IR cell death is a colony-forming assay.[36] Cells form single cell colonies when they continue to proliferate. The cells that proliferate and die divide only a few times when they are irradiated; therefore, they do not form large colonies even after culturing for a certain period. However, colony-forming assays require long experimental periods, and therefore, they are not suitable for multiple samples. Water Soluble Tetrazolium Salts (WST-1) and 3-(4,5-dimethylthiazol-2-yl)-2,5-diphenyl-2H-tetrazolium bromide (MTT) assays are commonly used for cell viability assays in IR cell death.[37] WST-1 is more convenient than MTT because of its water solubility and storage conditions; however, the WST-1 assay does not observe cell death. IR cell death is characterized by its characteristic morphology, and thus, the multifaceted evaluation of IR cell death in vitro needs to be investigated. Fluorescence microscopic cell imaging is a popular method for observing living cells and the structure of organelles with a fluorophore stain; this method can observe cell dynamics in living cells with the fluorophore stain, and its sensitivity allows quantifying the expression of biomolecules such as proteins. A detailed observation of the preserved cells can be realized if cells are fixed to halt cell metabolism before the addition of a fluorophore.[38] Thus, multifaceted evaluation combined with fluorescence microscopic cell imaging can provide efficient tools for IR cell death based on morphology.

We report on the surface functionalization of OS with Au NPs (OS/Au) and evaluate the X-ray sensitizing potential of OS/Au. The OS/Au, which combined sub-nm sized Au NPs and 100 nm sized OS, was synthesized to assess the effect of Au as an X-ray sensitizer. OS/Au showed high $\cdot\text{OH}$ producing ability

compared to that of OS. Further, we evaluate a mouse mammary tumor cell line as an X-ray sensitizer of 4T1 cells (mouse mammary tumor cell line). The NPs uptake was quantified as the number per 4T1 cells. The uptake number for polymer polyethyleneimine (PEI)-modified OS (OS/PEI) and OS/Au (OS/PEI) were similar, and the effect of Au as an X-ray sensitizer could be evaluated. We also reveal how to damage cells taken up by X-ray irradiation by multifaceted evaluation combined with fluorescence microscopic cell imaging. The OS/Au/PEI-treated 4T1 cells exhibited significantly low cell viability and inhibition of cell proliferation and increases in cell death by X-ray irradiation at 8Gy. The death of OS/Au/PEI-treated 4T1 cells was induced by DNA and mitochondrial-synergized damage. The OS/Au/PEI will provide an effective model for NPs as X-ray sensitizers and the multifaceted evaluation helped us understand cell death in radiotherapy.

2. Results And Discussion

2.1 Surface Functionalization of Organosilica NPs (OS) with Au NPs (OS/Au)

Figure 1A shows a schematic of the synergistic radiation enhancement of the surface functionalization of organosilica NPs (OSs) with Au NPs (OS/Au) for DNA and mitochondrial damage. Au NPs have gained considerable research interest as radiosensitizers because of the increased absorption of X-rays and the production of locally damaging surroundings.[7][24][28] Further, the small size of the Au NPs, which have a large surface area, is more favorable for X-ray sensitizing.[28] However, the stability of electrostatically stabilized Au NPs is an important consideration in biological environments.[39] In our previous reports, OS was synthesized using only MPMS with SH groups as the silica source; therefore, it was easy to control the size of the NPs.[40][41] The OS exhibited high stability in a biological environment, and the functionalization of the small Au NPs on OS helped realize the stability of NPs and efficiency of the X-ray sensitizing ability. The targeting capabilities of OS have been improved, and these systems have been applied for labeling tumor cell lines.[34][35] Thus, OS/Au (the combination of OS and Au NPs) are a viable candidate for achieving increased cellular uptake and cell death with radiation enhancement.

We prepared OS containing fluorescein isothiocyanate (FITC) based on our previous report.[42] The synthesized OS has a spherical shape and narrow size distribution (i.e., mean diameter of 107.0 ± 10.3 nm); further, the OS surface is functionalized with Au NPs, as shown in Fig. 1B. First, OS is mixed and stirred with HAuCl_4 as the Au precursor; the Au and SH groups interact well on the OS surface. Next, NaBH_4 is added to form Au NPs on the OS surface. The formation of Au NPs with a mean diameter of 4.7 ± 1.6 nm on the OS surface is observed and measured using scanning transmission electron microscopy (STEM) (Fig. 1C). The Au content is calculated by thermogravimetric analysis (TGA) (Fig. 1D). The profiles of OS and OS/Au obtained in a flow of air exhibit drastic weight loss attributed to the thermal decomposition in air. For OS, the fraction of weight loss in the temperature range of 200–800°C was 51.3% (w/w) (SD = 7.1, n = 3); this value is close to the 52.8% (w/w) theoretical weight loss from OS to SiO_2 . The weight loss of OS/Au is 41.0% (w/w) (SD = 3.4, n = 3), and the fraction of weight loss by OS/Au is 10.3% (w/w) lower than that of OS. We calculated the Au content of OS/Au as 20.1% (w/w), which is high compared to those in previous reports

such as that for the Au NPs composite. Since the OS was synthesized using only MPMS with SH groups as the silica source, the abundant SH groups of OS contributed to the functionalization of the high concentration of Au NPs. In addition, the OS has a high specific surface area because its diameter is approximately 100 nm; it is believed to increase the surface area of the Au-NP-functionalized scaffold. Regarding the yields obtained of Au NPs, the traditional Turkevich method[43] for Au NPs has required a diluted reaction solution (0.25 mM of Au), thus necessitating large quantities of water. The Burst method[44] uses a higher concentration of Au (5 mM) but uses water – toluene solvents. Therefore, highly economical and green methods will be needed. This method used 2 mM of Au as the final concentration and the reaction temperature was 37°C. The large-scale synthesis would be applied for application study in vivo and clinical use.

The radiolysis of water generates ROS, i.e., $\cdot\text{OH}$. We evaluated the X-ray sensitizing ability of OS and OS/Au by measuring the $\cdot\text{OH}$ production. Further, one of the primary pathways of IR cell death indirectly causes cellular damage by inducing oxidative stress.[45] The quantity of $\cdot\text{OH}$ is measured using the fluorescence intensity of an aminophenyl fluorescein (APF) derivative, which interacts with $\cdot\text{OH}$ and APF (Fig. 1E).[4][46] The fluorescence intensity of the APF derivative increases from the NP (-) condition. Initially, we investigated the effect of the NP concentration at 4 Gy irradiation, and the fluorescence intensity of the APF derivative for OS and OS/Au increased from 0.4 to 0.8 and 2.6 to 3.8, respectively, compared to that in the absence of NPs because the NP concentration increased from 25 to 50 $\mu\text{g mL}^{-1}$. At 16 Gy irradiation, the fluorescence intensity of the APF derivative of OS and OS/Au increased from 4.8 to 6.2 and from 10.2 to 12.8, respectively, compared to the fluorescence intensity exhibited in the absence of NPs because the NP concentration increased from 25 to 50 $\mu\text{g mL}^{-1}$. The increase in the fluorescence intensity of the APF derivative indicated its dose-dependent effect on OS and OS/Au.

Subsequently, we investigated the dose-dependent effects of X-ray irradiation. For 25 $\mu\text{g mL}^{-1}$ of OS, the fluorescence intensities of the APF derivatives increased by 0.4, 1.6, and 4.8 as the X-ray irradiation dose increased from 4 to 8 Gy and then to 16 Gy, respectively. For 25 $\mu\text{g mL}^{-1}$ of OS/Au, the fluorescence intensities of the APF derivatives increased by 2.6, 5.2, and 10.2 as the X-ray irradiation doses increased from 4 to 8 and to 16 Gy, respectively. For 50 $\mu\text{g mL}^{-1}$ of OS and OS/Au, the fluorescence intensities of the APF derivatives exhibited an X-ray dose-dependent behavior. These results indicate that both OS/Au and OS exhibited X-ray sensitizing properties. The hydroxyl radical-generating ability of OS/Au appeared to be stronger than that of OS.

The extinction spectra of OS/Au shows new peaks at 527 nm compared to those of OS, which is a good assignment to the surface plasmon resonance (SPR) band of the silica-supported Au NPs (**Figure S1**). The fluorescence peak of OS excited at 488 nm was observed at approximately 530 nm; it originated from the fluorescence of FITC in OS. The fluorescence of OS/Au exhibited a marked decrease caused by absorption because of the formation of Au NPs on the surface of the OS (Figure S1). The fluorescence signal of OS/Au was detected by fluorescence microscopy (FM) imaging.

2.2 Quantification of the Cellular Uptake of NPs

The cellular uptake of NPs is an important factor for achieving highly efficient nanodrugs.[47] NPs can passively uptake macrophages via endocytosis. For macrophages, NPs can be applied for superior active targeting by functionalization with antibodies binding on their surface, which is based on the interaction between the antibodies and receptors on cells. As another active targeting approach, the positively charged NPs need to be taken up to the negatively charged cell surface through electrostatic interaction with the negatively charged cell surface.[34] In this study, OS was easily functionalized with the positively charged polymer PEI. This PEI model is applied as the positive control for cellular uptake and is efficient for evaluating NPs as a drug using cells isolated in vitro.[48] Therefore, we modified OS/Au with PEI to accelerate the cellular uptake of NPs by 4T1 cells.

The results of the dynamic light scattering (DLS) measurements are presented in Table 1. For the hydrodynamic diameter, the diameter of the OS was found to be larger than that measured by STEM; OS/PEI exhibited a larger diameter than OS. These results are similar to those reported previously.[49] OS/Au exhibited a slightly larger hydrodynamic diameter of 136 ± 11 nm than that of an OS of 132 ± 7 nm; OS/Au/PEI had a larger diameter (145 ± 10 nm) than that of OS/Au. The surface functionalization of OS with Au NPs had a negligible effect on the hydrodynamic diameter compared with that of PEI. The zeta potential of the OS was negative because of the thiol and silanol residues present on the surface. OS/PEI exhibited a positive zeta potential because of the functionalization of OS with the intramolecular amino group moiety of PEI on their surface. For the surface functionalization of OS with Au NPs, OS/Au exhibited negative zeta potentials. The surface of the thiol residue, which interacted with the Au NPs, was removed from the OS by the Au NPs. The surface-functionalized Au NPs on OS were capped with the carbonyl group, which originated from sodium citrate as a stabilizer for the Au NPs. Thus, the negative zeta potential of OS/Au was attributed to the carbonyl and silanol residues. OS/Au/PEI exhibited a positive zeta potential (9.1) upon the functionalization of OS/Au with PEI; however, this value is smaller than that of OS/PEI (36.2). These results suggest that the interaction of PEI and OS/Au is weaker than that of OS, which indicates that the interaction of PEI with the carbonyl group is weaker than that with the thiol group.

The efficiency of the cellular uptake of NPs is evaluated using FM and flow cytometry (FCM) analysis, as shown in Fig. 2. The 4T1 cells (a mouse mammary tumor cell line) were treated with OS, OS/PEI, OS/Au, and OS/Au/PEI. The FM observations indicated that the OS uptake was not observed in 4T1 cells. In contrast, positively charged OS/PEI and OS/Au/PEI were observed in almost all 4T1 cells. A small quantity of OS/Au was observed because of the low intensity of the fluorescent signal of OS/Au in a few 4T1 cells.

Next, we performed FCM to evaluate the cellular uptake efficacy; the evaluated values are summarized in Table 1. The cellular uptake efficacy was evaluated using the uptake population (uptake cells per all cells (%)) and uptake level fluorescence intensity of the uptake cells. Cells with a geometric mean above 14 on FL1 were defined as uptake cells; the uptake intensity was calculated based on the geometric mean of the uptake cells. As summarized in Table 1, the uptake of OS by the 4T1 cells was low; they exhibited 96.1% and 84.1% higher uptake ratios of OS/PEI and OS/Au/PEI, respectively. The evaluation of the fluorescence intensity was not discussed because of the difference in the fluorescence intensities of the OS and OS/Au. Further, for OS/Au (without PEI), 27% of the 4T1 cells took up OS/Au. The uptake fluorescence intensity of

OS/Au and OS/Au/PEI for the uptake cells was dissimilar; the cellular uptake fluorescence intensity of OS/Au/PEI was 4.1-fold higher than that of OS/Au alone.

The cellular uptake of NPs by 4T1 cells was quantified using inductively coupled plasma optical emission spectroscopy (ICP-OES). The quantity of NPs taken up (pg cell^{-1}) was calculated from the results of ICP-OES; the number of cells was counted before cell lysis, and the uptake ratio was determined by flow cytometry. The number of NPs taken up was calculated from the results of the quantities of NPs taken up (pg cell^{-1}) and the value (g NPs^{-1} (density: 2.3)) of the single NPs. The OS uptake to the cells was 875 per single cell; however, the uptake population of OS was only 3% according to the results of FCM. A total of 733 OS/PEI and 750 OS/Au/PEI were used up to 4T1. The PEI modification of OS and OS/Au markedly enhanced the uptake of NPs for both OS and OS/Au. Furthermore, although the number of OS/Au taken up by the 4T1 cells was lower than that of OS/Au/PEI, 181 OS/Au were taken up by the 4T1 cells. The uptake of OS/Au/PEI was 4.5-fold higher than that of OS/Au; this result was in good agreement with the FCM results. These results indicate that PEI modification accelerates the cellular uptake of 4T1 cells, and Au functionalization promotes the uptake by 4T1 cells compared to that by the naked OS. This detailed quantification of the number of NPs clearly showed that the cellular uptake ability of OS/PEI and OS/Au/PEI was comparable. Thus, it is possible to evaluate the X-ray sensitizing effect of Au modification on OS/PEI and OS/Au/PEI.

2.3 Cell Viability of 4T1 Cells with X-ray Irradiation in vitro

We investigated the viability of the 4T1 cells in the presence of NPs with X-ray irradiation using a combination of the imaging assay of the occupied nucleus area and WST-1 assay; the assays were conducted in parallel. The advantages of the imaging assay of the occupied nucleus area are:

- (1) the occupied nucleus area refers to the number of cells and,
- (2) the types of death by X-ray irradiation are morphologically recognized from the nucleus shape of the structure.

The WST-1 assay is commonly used to evaluate cell viability as a measure of mitochondrial activity.

Figure 3B illustrates the results of the imaging assay calculated from Fig. 3A. For the imaging assay at 0 Gy, none of the NPs (OS, OS/PEI, OS/Au, OS/Au/PEI) exhibited cytotoxicity up to $25 \mu\text{g mL}^{-1}$. For OS/PEI, OS/Au, and OS/Au/PEI marginally affected cell viability at concentrations greater than $50 \mu\text{g mL}^{-1}$.

The cell viability decreased markedly to 18%, even without NP treatment, with X-ray irradiation (8 Gy). Furthermore, OS/Au and OS/Au/PEI caused dose-dependent cell death at the NP concentrations. OS/Au/PEI significantly exhibited cytotoxicity (8.8% cell viability, a 52% decrease compared with the cytotoxicity without NPs) even at the $6.25 \mu\text{g mL}^{-1}$ concentration of the NPs. In contrast, OS and OS/PEI did not induce dose-dependent cell death at the NP concentrations.

From Fig. 3C, it is evident that the results of the WST-1 assay without X-ray irradiation (0 Gy) of all NPs (OS, OS/PEI, OS/Au, OS/Au/PEI) did not exhibit cytotoxicity up to $25 \mu\text{g mL}^{-1}$. Even at concentrations of up to

100 $\mu\text{g mL}^{-1}$, no cytotoxicity was observed except for OS/PEI. For OS/PEI, the high concentrations of 50 and 100 $\mu\text{g mL}^{-1}$ resulted in a slight decrease in cell viability; OS/Au can activate 4T1 cells. The results of the WST-1 assay exhibited a higher cell viability for OS/Au/PEI compared to the results of the imaging assay. The occupied nucleus area could only be inferred from the adhered cells in the well, and therefore, the non-adhered cells could not be counted. Adherent cells float as they become weaker; therefore, the results of the imaging assay from the occupied nuclear area were lower than the results obtained from the WST-1 assay.

The cell viability from the WST-1 assay showed good agreement with the results of the imaging assay with the X-ray irradiation (8 Gy). The cell viability decreased noticeably to 18% even without NP treatment. Furthermore, OS/Au and OS/Au/PEI caused dose-dependent cell deaths at NP concentrations. For OS/Au, cytotoxicity was gradually observed at a concentration of 6.25 $\mu\text{g mL}^{-1}$ of NPs. The OS/Au/PEI significantly exhibited cytotoxicity (11% cell viability, a 38% decrease compared with that of the cytotoxicity without NPs) even for a concentration of 1.56 $\mu\text{g mL}^{-1}$ of the NPs. The cell viability at 12.5 and 100 $\mu\text{g mL}^{-1}$ of OS/Au/PEI were 7% and 5%, respectively; this means that cytotoxicity was observed at 12.5 $\mu\text{g mL}^{-1}$ and at the high concentration of 100 $\mu\text{g mL}^{-1}$ of OS/Au/PEI. In contrast, OS and OS/PEI did not induce dose-dependent cell death at the NP concentrations. The sensitivity of the detectable WST-1 assay was higher than that of the imaging assay with an 8 Gy irradiation. In the imaging assay, the cell viability would become larger than that in the WST-1 assay because some of the cells of the nucleus became larger after the 8 Gy irradiation.[50]

The morphology of the nuclei in the imaging assay (IA) assay wells was observed (Fig. 3D). The process of radiation-induced cell death in cancer cells can be classified into mitotic and non-mitotic deaths in terms of the cell cycle.[51] Mitotic death is a state in which the cell loses its ability to proliferate or death occurs through cell division; the morphological characteristics of the nucleus are split nucleus, fusion, or macronucleus. The death of a non-proliferating cell that occurs during interphase without division is defined as non-mitotic death; the morphological characteristics of the nucleus are observed as a rounded shape instead of the oval shape of the normal nuclei.

At 0 Gy, the morphology of the nuclei was similar to that of a normal cell, with flat oval nuclei fluorescing uniformly blue under all conditions, with or without NP. At 8 Gy, we focused on normal nuclei observed in NP (-), OS, and OS/PEI; normal nuclear morphology is rare in PEI. Mitotic (mito-nuclei) and non-mitotic nuclei (non-mitotic nuclei) were frequently observed in OS/Au and OS/Au/PEI, more especially in OS/Au/PEI.[52] The high doses of IR are required for non-mitotic death. From the morphology of the nuclei, 4T1 cells treated with OS/Au/PEI exhibited damaged nuclei structure and high sensitivity to X-ray irradiation; the OS/Au/PEI uptake by the 4T1 cells provides selective radiosensitivity by controlling the NP uptake.

The results of the IA and WST-1 assays showed a similar trend, although the sensitivity of the WST-1 assay was marginally higher. In addition, the IA assay was calculated from the occupied nucleus area of the full wells, and the results reflect all populations of the full wells. Furthermore, IA was not limited to evaluating cell viability but could also observe morphological changes in cells. The IA assay has the potential to be developed with more multifaceted information through further detailed analysis because marked morphological changes could be observed by cell death with X-ray irradiation. In addition, the IA assay can

be performed in parallel with the WST-1 assay. This combined assay will allow for a more detailed evaluation of the X-ray sensitizing ability.

2.4 Inhibition of Cell Proliferation and Increases in Cell Death by OS/Au/PEI with X-ray Irradiation

Cell counts and cell viability counts obtained using the trypan blue method clearly showed the effect of X-rays during the very early stages (Fig. 4); at DAY1 after X-ray irradiation, approximately 40% of the cells were counted by X-ray irradiation with or without NP treatment. In addition, for the 8 Gy irradiation, the cell death ratio of those cells treated with OS/Au/PEI was 20% and significantly higher than those treated with NP (-) and OS/PEI, even at DAY1 after X-ray irradiation. At DAY4 after X-ray irradiation, less than 40% of the cells were counted by X-ray irradiation with or without NP treatment. In addition, the cell death ratio under all conditions was higher than that for DAY1. These results indicated that X-ray irradiation suppressed cell division. In addition, OS/PEI and OS/Au/PEI induced an increase in the rate of cell death as X-ray sensitizers. The number of live cells treated with OS/Au/PEI was significantly lower than that of cells treated with OS/PEI. A low live cell count is expected to be useful in radiotherapy. The evaluation of cell death by X-irradiation by conventional methods is time-consuming,[36] however, the evaluation of cell death by cell counting showed a significant increase in cell death in OS/Au/PEI as early as DAY 1 after X-irradiation. Cell counting, which can evaluate cytotoxic activity at an early stage, is a useful evaluation method.

2.5 DNA Damage by OS/Au/PEI with X-ray Irradiation

IR can cause direct and indirect DNA damage, including by the radiolysis of the surrounding water and the generation of a cluster of $\cdot\text{OH}$. In a previous report, indirect DNA damage from $\cdot\text{OH}$ accounted for approximately 65% of the radiation-induced DNA damage.[45] DNA double-strand breaks (DSBs) are considered the most lethal among the various types of DNA damage. In the early stages of the cellular DSBs, the histone H2A variant, H2AX, is phosphorylated at the site of DNA damage, which gives rise $\gamma\text{-H2AX}$ (phosphorylated H2AX) at the site of the DNA damage. Thus, we evaluated DNA damage by immunofluorescence staining for $\gamma\text{-H2AX}$.

Figure 5A illustrates the FM images of the 4T1 cells in which the cell nuclei that stained blue with DAPI and $\gamma\text{-H2AX}$ are viewed as magenta Cy5 fluorescence after 1 h of X-ray irradiation. For untreated NP (-) cells (treated with 0 Gy as the negative control), little $\gamma\text{-H2AX}$ was observed in the cell nuclei. However, a magenta Cy5 fluorescence of $\gamma\text{-H2AX}$ was observed in the nucleus in NP (-), OS/PEI, and OS/Au/PEI for cells treated with 8 Gy X-ray irradiation. In addition, the area of the magenta Cy5 fluorescence of $\gamma\text{-H2AX}$ decreased in the order NP (-) < OS/PEI < OS/Au/PEI.

The percentage of stained $\gamma\text{-H2AX}$ cells per cell is calculated as shown in Fig. 5B. NP (-) treated with 0 Gy, 6% cells showed $\gamma\text{-H2AX}$ positive. The cells treated with NP (-), OS/PEI, and OS/Au/PEI showed 54, 58, and 72% $\gamma\text{-H2AX}$ expression, respectively, after 1 h of 8 Gy X-ray irradiation. This implies that 8 Gy X-ray irradiation induced DNA damage, and the DNA damage increased with NP treatment. The rate of DNA damage increased with increasing $\cdot\text{OH}$ production (Fig. 1E). The repair of DSBs is essential for maintaining genomic stability in all cells.[53][45] Previous studies reported no influence of AuNPs on the DNA repair

kinetics while some studies demonstrated the inhibition of radiation-induced DNA damage repair with AuNPs.[7] The involvement of Au NPs in the inhibition of DNA repair remains inconclusive. We evaluated the γ -H2AX expression in the cells 6 h after 8 Gy X-ray irradiation. The γ -H2AX expression in cells treated with NP (-), OS/PEI, and OS/Au/PEI was 14, 11, and 13%, respectively. The γ -H2AX expression in NP (-) and OS/Au/PEI cells was slightly higher than that in NP (-) cells treated with 0 Gy as the negative control. The ability to repair DNA damage did not differ; however, the rate of cell death (Fig. 4) reflects the result of the DNA damage effected. Therefore, DNA damage caused by X-ray irradiation and NP treatment affects cell survival.

2.6 Deactivated Mitochondrial Activity by OS/Au/PEI

Previous studies demonstrated that AuNPs induced ROS formation.[54][55] Further, the resulting oxidative stress has been discussed as an important mechanism of inorganic and metallic NPs-induced cytotoxicity.[56] In in vitro systems, the AuNP-induced elevation of intracellular ROS levels elicits a multitude of biological effects that ultimately lead to cell death. The cellular response of 1.4 nm triphenylphosphine monosulfonate-capped AuNPs (Au1.4MS) was reported; the AuNPs treatment was associated with the increased ROS production and loss of the mitochondrial potential, which resulted in necrotic cell death.[54] The mechanism of AuNPs triggered ROS generation remains uncertain. However, it is believed to occur through the impairment of mitochondrial function as a consequence of the elevated intracellular ROS.[13] [57] Therefore, we evaluated the mitochondrial activity using the mitochondrial membrane potential by tetramethylrhodamine methyl ester (TMRE) staining. Positively charged TMRE readily accumulates in active mitochondria because of its relatively negative charge. In contrast, depolarized or inactive mitochondria exhibit decreased membrane potential and fail to sequester TMRE.

Figure 6A illustrates the FM images of the 4T1 cells of NP (-), OS/PEI, and OS/Au/PEI-treated with 0 Gy and 8 Gy at DAY1 after X-ray irradiation. The 4T1 cells were stained with TMRE, and the fluorescence intensity of TMRE was reflected in the mitochondrial activity. After irradiation with 8 Gy, the fluorescence intensity of TMRE decreased under all conditions. The fluorescence intensity of TMRE for the OS/PEI-treated 4T1 cells with or without X-ray irradiation was strong. We performed FCM analyses to evaluate mitochondrial activity (Fig. 6C).

Figure 6B illustrates the time-dependence of the mitochondrial activity without NP treatment [NP (-)]. A constant (although, perhaps minimally increased) mitochondrial activity was observed from 0 h to DAY1 and DAY2. Further, a significant decrease in the mitochondrial activity was observed from DAY3 to DAY4, which suggests that the cells were debilitated because they were unable to supply the nutrients necessary for survival under long-term incubation conditions.

The order of mitochondrial activity was higher for OS/PEI, NP (-), and OS/Au/PEI at 0 Gy, 8 Gy, and at all time points (Fig. 6C). At 0 h and DAY1 after X-ray irradiation, we compared the mitochondrial activity after treatment with NP (-), OS/PEI, and OS/Au/PEI at 0 Gy. The mitochondrial activity of the cells treated with OS/Au/PEI was weaker than that of cells treated with NP (-). Further, mitochondrial activity of the cells treated with OS/PEI exhibited a slight upward trend in mitochondrial activity compared with that of NP (-). For the cells in DAY1, the mitochondrial activity of OS/Au/PEI was significantly weaker than that of OS/PEI.

Further, the 8 Gy X-ray irradiation decreased the mitochondrial activity in NP (-), OS/PEI, and OS/Au/PEI. At DAY4, the mitochondrial activity markedly decreased in all cells. The mitochondrial activity after treatment with OS/Au/PEI with 8 Gy X-ray irradiation was lower than that of OS/PEI; however, the difference in the mitochondrial activity between the treated and untreated cells was small.

The mitochondrial damage levels for OS/Au/PEI may not be sufficient to induce cell death without X-ray irradiation; the viability of the 4T1 cells treated with OS/Au/PEI did not decrease (Fig. 3). In addition, the OS/PEI-treated 4T1 cells did not exhibit X-ray sensitizer ability for the NP dose-dependent decrease in cell viability (Fig. 3). These results indicate that OS/Au/PEI showed a synergistic effect by the combined damage to DNA and mitochondria.

2.7 Non-Apoptotic Cell Death Increased by OS/Au/PEI with X-ray Irradiation

Figure 7A shows the FM images of the 4T1 cells for apoptotic and necrotic cells by annexin V-Cy5 / DAPI staining on DAY4. The cells were classified as apoptotic or necrotic by staining with annexin V-Cy5 and DAPI, respectively. Among the annexin V-positive apoptotic cells, the early apoptotic cells did not stain with DAPI, whereas the late apoptotic cells were DAPI-positive. The necrotic cells were DAPI-positive but negative for annexin V-Cy5. Few annexin V-Cy5 positive cells (magenta arrow; early apoptosis) were observed for the untreated cells treated with 0 Gy as the negative control. In addition, some annexin V-Cy5 positive cells were stained with DAPI (yellow arrows; late apoptosis). Early and late apoptotic cell deaths were observed under these conditions. In addition, the morphology shrunk, which was a good assignment to stereotypical morphological changes in the cellular architecture of apoptosis. DAPI-positive and annexin V-Cy5 negative cells (cyan arrow; necrosis) were observed for cells with 8 Gy X-ray irradiation; this morphology was flat and expansive, and the nuclei were large. The morphology was similar to that of senescent cells, which flattened and appeared enlarged, developed cytoplasmic vacuolization, and underwent large-scale chromatin remodeling.[50] IR can induce cellular senescence, which is a state of prolonged growth arrest with a permanent loss of proliferative potential. Figure 7B shows the evaluated annexin V-Cy5 and DAPI staining areas, which were divided by the occupied cell area; this indicated the late expression of annexin V-Cy5 and DAPI in all 4T1 cells. At DAY1, there was no considerable difference between annexin V-Cy5 and DAPI, and they occupied all the cell areas. At DAY4, the annexin V-Cy5 area for OS/PEI and OS/Au/PEI with 8 Gy increased significantly for NP (-) treated with 0 Gy. For OS/Au/PEI, it increased significantly for NP (-) at 8 Gy. Further, the DAPI area for OS/Au/PEI increased significantly for NP (-) treated with 0 Gy, and for NP (-) and OS/PEI-treated with 8 Gy. Late apoptotic cells were seldom observed in the FM images; therefore, the significant increase in the DAPI area was caused by an increase in the non-apoptotic cell death. Non-apoptotic cell death for OS/Au/PEI-treated 4T1 cells was promoted, but apoptotic cell death did not promote sufficiently to compare with OS/PEI-treated 4T1 cells by X-ray irradiation. This increase of non-apoptotic cell death is similar to the death due to mitochondrial damage by oxidative stress for the small Au NPs:[54] the contribution of mitochondria is required for the induction of apoptosis upon X-ray irradiation.[58][59] A previous report showed that mitochondrial deactivation by mitochondrial inhibitors reduces the demand for oxygen by the tumor cells, leading to increased oxygenation and radiation response.[60] The mitochondrial activity for the 4T1 cells treated with OS/Au/PEI decreased with or without X-irradiation (Fig. 6C). Therefore,

it is suggested that OS/Au/PEI has an X-ray sensitizing effect because of the Z-metal theory of Au, and an increase in X-ray sensitizing activity because of the deactivation of mitochondria.

3. Conclusions

We demonstrated the X-ray sensitizing potential of OS/Au/PEI in 4T1 cells. The number of OS/Au/PEI particles taken up per 4T1 cell was precisely evaluated using ICP-OES. The number of OS/PEI and OS/Au/PEI was similar, however, the 4T1 cells treated with OS/Au/PEI decreased cell viability and inhibited cell proliferation upon X-ray irradiation compared with that exhibited by OS/PEI (without Au NPs). The OS/Au/PEI-treated 4T1 cells exhibited increased DNA damage attributed to X-ray irradiation and the deactivation of mitochondrial activity; this occurred even without X-ray irradiation. The OS/Au/PEI would affect DNA damage by X-ray irradiation as an X-ray sensitizer and by mitochondrial deactivation as an oxidant. The synergistic effect increased non-apoptotic cell death which was achieved by the combination of OS and the small size of the Au NPs in the application of radiotherapy. Furthermore, the imaging assay of the occupied nucleus area was slightly lower selectivity but revealed to observe the characterized nucleus shape of the structure. The low selectivity was overcome by the combination of the WST-1 assay. We believe the functionalization of Au NPs on OS would gain greater use as an X-ray sensitizer model to application study.

4. Experimental Section

Chemicals and reagents

3-Mercaptopropyltrimethoxysilane (MPMS), 3-aminopropyltrimethoxysilane (APS), fluorescein isothiocyanate isomer (FITC), rhodamine B, bisbenzimidazole H 33342 trihydrochloride (Hoechst 33342), and the branched polyethyleneimine solution (MW = 2.0k) were purchased from Sigma-Aldrich Chemical Co. (St. Louis, MO, USA). Ammonium hydroxide (NH₄OH, 28%) and ethanol were purchased from Kishida Chemicals (Osaka, Japan). All other reagents and solvents were of analytical grade.

Synthesis of OS and OS/Au NPs

OS was prepared using a one-pot procedure described previously.[42] OS/Au was synthesized using the following procedure: First, 1 mL of 10 mg mL⁻¹ OS was added to 0.8 mL of 50 mM HAuCl₄ (aq.) and incubated at 37°C for 3 days with stirring. Second, the mixture was added to 14.9 mL of water, 1.5 mL of 50 mM sodium citrate, and 0.6 mL of 200 mM NaBH₄. Third, the solution was incubated at 37°C for three days with stirring. Fourth, the mixture was centrifuged (20,000 × *g*, 30 min) and OS/Au was purified by washing three times with distilled water (DW) to remove excess residues.

Surface Functionalization of OS with Polyethylenimine (PEI)

OS or OS/Au (1 mg mL⁻¹) was allowed to react with 10% PEI2.0k in DW and incubated with mixing for 24 h at 37°C. After incubation, the mixture was centrifuged (20,000 × *g*, 4°C, 20 min) to remove the unbound PEI; the pellet was washed three times with DW.

Electron microscopic observation

The OS and OS/Au were dried and fixed on a 400-mesh copper grid (Nisshin EM Co., Tokyo, Japan) coated with polyvinyl alcohol. STEM and scanning electron microscopy (SEM) images of the NPs were obtained using a Quanta 3D FEG electron microscope (FEI, Hillsboro, OR, USA).

Thermal gravimetric analysis (TGA)

The thermal gravimetric analyses of the NPs was performed using a STA7200 thermal analysis system (Hitachi, Tokyo, Japan) in the temperature range of 30–800°C at a heating rate of 10°C min⁻¹ under a 200 mL min⁻¹ flow in air.

X-ray irradiation

X-rays were generated using an X-ray generator ([filter: 0.1 mm Cu and 0.5 mm Al] MBR-1520R-4, Hitachi, Japan). The X-ray dose was controlled automatically by the instruments.

Detection of hydroxyl radical

The detection of hydroxyl radicals (•OH) is based on the reaction between aminophenyl fluorescein (APF) and •OH. The assays were performed in black microplates, and the signals were detected using a microplate reader (FlexStation 3, Molecular Devices, United Kingdom). The OS and OS/Au in DW were mixed with APF to achieve a final concentration of 5 µM. The mixtures were excited at 480 nm and fluorescence was detected at 520 nm before and after X-ray irradiation. The increase in the fluorescence intensity was calculated by subtracting the fluorescence intensity from that without NPs.

Dynamic light scattering (DLS)

The DLS was performed to analyze the size distribution and ζ potential of the NPs using a DelsaMax PRO light scattering analyzer (Beckman Coulter, Brea, CA, USA) at 20°C. The analyte NPs were prepared by dispersing them in DW (0.2 mg mL⁻¹).

Evaluation of cellular uptake of NPs by flow Cytometry

A total of 2.5×10^5 4T1 cells were plated on 35 mm dishes and incubated at 37°C for 24 h. The cells were incubated with media containing OS, OS/PEI, OS/Au, or OS/Au/PEI (final concentration: 10 µg mL⁻¹) for 24 h. The NPs in the medium were well suspended by sonication before treatment. After incubation, all cells were washed with PBS (-), retrieved from the culture dish, and subjected to flow cytometry. Flow cytometric analysis was performed using aa FACSCalibur™ flow cytometer with Cell Quest software (Becton Dickinson, San Jose, CA, USA) and 488 nm excitation lasers. The fluorescence was detected in the FL1 channel (530/30 nm bandpass filter); a total of 5,000 cells was analyzed for each repetition.

Quantification of cellular uptake of NPs by ICP-OES

Cell incubation and sample preparation: For analysis by ICP-OES, a total of 0.5×10^6 4T1 cells were plated on 10 cm dishes and incubated at 37°C for 24 h. The cells were treated with 10 mL of a medium containing OS, OS/PEI, OS/Au, or OS/Au/PEI (final concentration: $10 \mu\text{g mL}^{-1}$) for 24 h. The NPs in the medium were well suspended by sonication before treatment. After incubation, all cells were carefully washed three times with PBS (-) to remove excess NPs and dispersed in 2 mL of PBS (-). The concentration (cells mL^{-1}) of the dispersed cell samples was determined before the cells were lysed ($2.5\text{--}3.1 \times 10^6$ cells mL^{-1}). The samples were centrifuged, and the supernatant was removed after cell counting. The cell pellets were lysed in 2 mL of cell lysis solution.

ICP-OES analysis of cell lysates

ICP-OES (5100 ICP-OES, Agilent Technologies, Mulgrave, Australia) was used to analyze the number of NPs in the cell lysates. Calibration curves were measured using several NPs in the cell lysate solution (2.0×10^6 cells mL^{-1}). Before the analysis, the NP-containing cell lysate samples were homogenized by vortexing.

Cell viability assay (WST-1 and Imaging assay of occupied nucleus area)

Cell culture and X-ray irradiation for cell viability assay: 4T1 cells were seeded into 96-well plates at a density of 1000 cells per well under 100% humidity and cultured at 37°C with 5% CO_2 for 24 h. Different concentrations (final concentration: $0\text{--}100 \mu\text{g mL}^{-1}$) of NPs (OS, OS/PEI, OS/Au, OS/Au/PEI) were added to the wells. After 24 h, the NPs were irradiated with 8 Gy of X-ray to NPs up-taken 4T1 cells, and the cells were subsequently incubated for 4 days with and without X-ray irradiation.

WST-1 assay

The viability of the 4T1 cells was evaluated using the WST-1 (2-(2-methoxy-4-nitrophenyl)-3-(4-nitrophenyl)-5-(2,4-disulfophenyl)-2H-tetrazolium) cell proliferation assay reagent (Dojin Chemical Co., Kumamoto, Japan). The WST-1 reagent was added 4 days after X-ray irradiation, and the absorbance was measured for each well immediately after the addition of the WST-1 reagent and after incubation at 37°C. The former signal was subtracted from the latter to obtain only the signals derived from the formazan dye (produced by viable cells).

Imaging assay of the occupied nucleus area

The occupied nucleus area was evaluated after the WST-1 assay. The media was removed to evaluate the occupied nucleus area, and it was fixed with 1% paraformaldehyde (PFA) solution and stained with Hoechst33342 after the WST-1 assay. All regions of the well images in the 96-well plate were obtained by FM (BZ-X800, Keyence, Osaka, Japan) using a 4× objective with stitching. The occupied nucleus area in all wells was analyzed using the Hybrid Cell Count BZ-H4C analyzer software (Keyence, Osaka, Japan).

Evaluation of cell count and cell viability

A total of 0.4×10^5 4T1 cells were plated on 35 mm dishes and incubated at 37°C for 24 h. The cells were incubated with a medium containing OS/PEI or OS/Au/PEI (final concentration: $30 \mu\text{g mL}^{-1}$) for 24 h. The NPs in the medium were well suspended by sonication before treatment. After 24 h, 8 Gy of X-ray was irradiated to NPs up-taken 4T1 cells and incubated at 37°C for the desired time. After incubation, all cells were collected at the desired time; the cells in the supernatant carefully separated by trypsin were collected by centrifugation ($1,000 \times g$, 25°C, 10 min) and re-dispersed in 500 μL of the medium. Automated cell counts were performed using a Vi-CELL® (Beckman, Fullerton, CA, USA). No manual mixing of the samples with trypan blue was required because it was performed automatically by the instrument.

Evaluation of mitochondrial activity

Cell culture and X-ray irradiation were performed to evaluate cell counts and viability. All cells were collected after incubation. The cells in the supernatant were carefully separated by trypsin, collected by centrifugation ($1,000 \times g$, 25°C, 10 min), re-dispersed, stained with tetramethylrhodamine ethyl ester perchlorate (TMRE, Invitrogen, Eugene, OR, USA), and subjected to flow cytometric analysis. Flow cytometric analysis was performed using a FACSCalibur™ flow cytometer with Cell Quest (Becton Dickinson, San Jose, CA, USA) and 488 nm excitation lasers. A total of 5,000 cells were analyzed for each repeat. Fluorescence was detected on the FL2 channel (filter with a passband of 543–627 nm).

Imaging assay (DNA double-strand breaks and Annexin V/DAPI assay)

Cell culture and X-ray irradiation for imaging assays (DNA DSBs and Annexin V/DAPI assay)

The 4T1 cells were seeded in a 96-well plate and incubated at 37°C for 24 h. Thereafter, the NPs (OS/PEI and OS/Au/PEI) were added to the 96-well plate at a final concentration of $30 \mu\text{g mL}^{-1}$. After 24 h, 8 Gy of X-ray was irradiated to NPs up-taken 4T1 cells, which were incubated at 37°C for the desired time.

DNA double-strand breaks

The DNA DSBs were measured by the immunofluorescence staining of γ -H2AX to evaluate the DNA damage caused by X-ray irradiation. The immunofluorescence staining of γ -H2AX was performed using a DNA damage detection kit (Dojin Chemical Co., Kumamoto, Japan) after 1 or 6 h of X-ray irradiation. DAPI was used to stain the cell nuclei. The images were obtained in 3×3 stitching areas at a $10 \times$ magnification, which were selected in the central part of the well and contained more than 1000 cells by BZ-X800 (Keyence, Osaka, Japan). The quantification was performed using Hybrid Cell Count BZ analyzer software (Keyence, Osaka, Japan). The percentage of stained γ -H2AX expression cells per cell was calculated.

Annexin V-Cy5/DAPI assay

At the desired time, the cells were stained using the Annexin V-Cy5 apoptosis detection kit (Bio-Vision, Inc. Milpitas, CA, USA), followed by DAPI staining. Images were obtained in 3×3 stitching areas at $10 \times$ magnification, which were selected in the central part of the well and contained more than 1000 cells by BZ-X800 (Keyence, Osaka, Japan). Quantification was performed using the Hybrid Cell Count BZ analyzer software (Keyence, Osaka, Japan). The percentage of the stained area of annexin V-Cy5 and DAPI per cell

per nucleus was calculated. Thereafter, the area of Annexin V-Cy5 and DAPI per cell was calculated as [area of Annexin V-Cy5 or DAPI] / [area of cell by bright field images (μm^2)].

Statistical analysis

The data are presented as mean $\pm$ standard deviation from three replicates and analyzed by one-way analysis of variance (ANOVA) followed by the Tukey–Kramer test in Microsoft Excel; statistical significance was set at * $P < 0.05$ and ** $P < 0.01$.

Declarations

Author Contributions

C.M. performed the synthesis and characterization of NPs with M.N.; Y.K. performed flow cytometric analysis with C.M.; C.M. performed cell experiments with J.N. and S.K.; C.M. drafted the manuscript with M.N.; The idea was generated by M.N. The work was initiated by M.N., and supervised by M.I, T.M, and M.N.

Acknowledgments

We appreciate the assistance provided by Dr. Koichi Udo and Dr. Azumi Yoshimura with the electron microscopic observations. This study was supported in part by JSPS KAKENHI (Grant-in-Aid for Early-Career Scientists (No. 20 K15322), Grant-in-Aid for Scientific Research (B) (No. 20H03625), Grant-in-Aid for Scientific Research (C) (Nos. 21500409, 25350530, and 16 K01358), Grant-in-Aid for Challenging Research (Exploratory) (No. 19 K22534), Research for Promoting Technological Seeds and Adaptable and Seamless Technology Transfer Program through target-driven R&D from the Japan Science and Technology Agency, and JSPS Bilateral Programs.

References

1. Delaney G, Jacob S, Featherstone C, Barton M. The role of radiotherapy in cancer treatment. *Cancer*. 2005;104:1129–37.
2. Wang H, Mu X, He H, Zhang X-D. *Cancer Radiosensitizers*. Trends Pharmacol Sci. Elsevier Ltd; 2018;39:24–48.
3. Kurzyp M, Girard HA, Cheref Y, Brun E, Sicard-Roselli C, Saada S, et al. Hydroxyl radical production induced by plasma hydrogenated nanodiamonds under X-ray irradiation. *Chem Commun. Royal Society of Chemistry*; 2017;53:1237–40.
4. Moriyama A, Hasegawa T, Jiang L, Iwahashi H, Mori T, Takahashi J. Screening of X-ray responsive substances for the next generation of radiosensitizers. *Sci Rep. Springer US*; 2019;9:1–10.
5. Mah LJ, El-Osta A, Karagiannis TC. γ H2AX: A sensitive molecular marker of DNA damage and repair. *Leukemia*. Nature Publishing Group; 2010;24:679–86.

6. Moding EJ, Kastan MB, Kirsch DG. Strategies for optimizing the response of cancer and normal tissues to radiation. *Nat Rev Drug Discov.* 2013;12:526–42.
7. Her S, Jaffray DA, Allen C. Gold nanoparticles for applications in cancer radiotherapy: Mechanisms and recent advancements. *Adv Drug Deliv Rev.* Elsevier B.V.; 2017;109:84–101.
8. Rahman WN, Bishara N, Ackerly T, He CF, Jackson P, Wong C, et al. Enhancement of radiation effects by gold nanoparticles for superficial radiation therapy. *Nanomed Nanotechnol, Biol Med.* Elsevier Inc.; 2009;5:136–42.
9. Butterworth KT, Coulter JA, Jain S, Forker J, McMahon SJ, Schettino G, et al. Evaluation of cytotoxicity and radiation enhancement using 1.9 nm gold particles: potential application for cancer therapy. *Nanotechnology.* 2010;21:295101.
10. Jain S, Coulter JA, Hounsell AR, Butterworth KT, McMahon SJ, Hyland WB, et al. Cell-Specific Radiosensitization by gold nanoparticles at megavoltage radiation energies. *Int J Radiat Oncol Biol Phys.* 2011;79:531–9.
11. Coulter J. Cell type-dependent uptake, localization, and cytotoxicity of 1.9 nm gold nanoparticles. *Int J Nanomed.* 2012;7:2673.
12. Jain S, Coulter JA, Butterworth KT, Hounsell AR, McMahon SJ, Hyland WB, et al. Gold nanoparticle cellular uptake, toxicity and radiosensitisation in hypoxic conditions. *Radiother Oncol.* Elsevier Ireland Ltd; 2014;110:342–7.
13. Taggart LE, McMahon SJ, Currell FJ, Prise KM, Butterworth KT. The role of mitochondrial function in gold nanoparticle mediated radiosensitisation. *Cancer Nanotechnol.* 2014;5:1–12.
14. Chang MY, Shiau AL, Chen YH, Chang CJ, Chen HHW, Wu CL. Increased apoptotic potential and dose-enhancing effect of gold nanoparticles in combination with single-dose clinical electron beams on tumor-bearing mice. *Cancer Sci.* 2008;99:1479–84.
15. Chithrani DB, Jelveh S, Jalali F, Van Prooijen M, Allen C, Bristow RG, et al. Gold nanoparticles as radiation sensitizers in cancer therapy. *Radiat Res.* 2010;173:719–28.
16. Liu Y, Liu X, Jin X, He P, Zheng X, Dai Z, et al. The dependence of radiation enhancement effect on the concentration of gold nanoparticles exposed to low- and high-LET radiations. *Phys Medica.* Elsevier Ltd; 2015;31:210–8.
17. Kong T, Zeng J, Wang X, Yang X, Yang J, McQuarrie S, et al. Enhancement of Radiation Cytotoxicity in Breast-Cancer Cells by Localized Attachment of Gold Nanoparticles. *Small.* 2008;4:1537–43.
18. Kaur H, Pujari G, Semwal MK, Sarma A, Avasthi DK. In vitro studies on radiosensitization effect of glucose capped gold nanoparticles in photon and ion irradiation of HeLa cells. *Nucl Instrum Methods Phys Res, Sect B.* Elsevier B.V.; 2013;301:7–11.
19. Wang C, Li X, Wang Y, Liu Z, Fu L, Hu L. Enhancement of radiation effect and increase of apoptosis in lung cancer cells by thio-glucose-bound gold nanoparticles at megavoltage radiation energies. *J Nanoparticle Res.* 2013;15:1–12.
20. Zhang XD, Wu D, Shen X, Chen J, Sun YM, Liu PX, et al. Size-dependent radiosensitization of PEG-coated gold nanoparticles for cancer radiation therapy. *Biomaterials.* 2012;33:6408–19.

21. Chattopadhyay N, Cai Z, Kwon YL, Lechtman E, Pignol J-P, Reilly RM. Molecularly targeted gold nanoparticles enhance the radiation response of breast cancer cells and tumor xenografts to X-radiation. *Breast Cancer Res Treat.* 2013;137:81–91.
22. Joh DY, Sun L, Stangl M, Al Zaki A, Murty S, Santoiemma PP, et al. Selective Targeting of Brain Tumors with Gold Nanoparticle-Induced Radiosensitization. Castro MG, editor. *PLoS One.* 2013;8:e62425.
23. Wolfe T, Chatterjee D, Lee J, Grant JD, Bhattarai S, Tailor R, et al. Targeted gold nanoparticles enhance sensitization of prostate tumors to megavoltage radiation therapy in vivo. *Nanomed Nanotechnol, Biol Med.* Elsevier B.V.; 2015;11:1277–83.
24. Regulla DF, Hieber LB, Seidenbusch M. Physical and biological interface dose effects in tissue due to X-Ray- Induced release of secondary radiation from metallic gold surfaces. *Radiat Res.* 1998;150:92–100.
25. Chen X, Song J, Chen X, Yang H. X-ray-activated nanosystems for theranostic applications. *Chem Soc Rev.* Royal Society of Chemistry; 2019;48:3073–101.
26. Tamanoi F, Matsumoto K, Doan TLH, Shiro A, Saitoh H. Studies on the exposure of gadolinium containing nanoparticles with monochromatic x-rays drive advances in radiation therapy. *Nanomaterials.* 2020;10:1–13.
27. Kuncic Z, Lacombe S. Nanoparticle radio-enhancement: principles, progress and application to cancer treatment. *Phys Med Biol.* IOP Publishing; 2018;63:02TR01.
28. Cheng NN, Starkewolf Z, Davidson RA, Sharmah A, Lee C, Lien J, et al. Chemical enhancement by nanomaterials under X-ray irradiation. *J Am Chem Soc.* 2012;134:1950–3.
29. Ishida T, Murayama T, Taketoshi A, Haruta M. Importance of Size and Contact Structure of Gold Nanoparticles for the Genesis of Unique Catalytic Processes. *Chem Rev.* 2020;120:464–525.
30. Bennie L, Belhout SA, Quinn SJ, Coulter JA. Polymer-Supported Gold Nanoparticle Radiosensitizers with Enhanced Cellular Uptake Efficiency and Increased Cell Death in Human Prostate Cancer Cells. *ACS Appl Nano Mater.* 2020;3:3157–62.
31. Matsumura Y, Maeda H. A New Concept for Macromolecular Therapeutics in Cancer Chemotherapy: Mechanism of Tumor-tropic Accumulation of Proteins and the Antitumor Agent Smancs. *Cancer Res.* 1986;46:6387–92.
32. Maeda H, Nakamura H, Fang J. The EPR effect for macromolecular drug delivery to solid tumors: Improvement of tumor uptake, lowering of systemic toxicity, and distinct tumor imaging in vivo. *Adv Drug Deliv Rev.* Elsevier B.V.; 2013;65:71–9.
33. Tang L, Cheng J. Nonporous silica nanoparticles for nanomedicine application. *Nano Today.* Elsevier Ltd; 2013;8:290–312.
34. Nakamura M. Organosilica Nanoparticles and Medical Imaging. *Enzymes.* 1st ed. Elsevier Inc.; 2018;44:137–73.
35. Mochizuki C, Nakamura J, Nakamura M. Development of Non-Porous Silica Nanoparticles towards Cancer Photo-Theranostics. *Biomedicines.* 2021;9:73.
36. Puck TT, Morkovin D, Marcus PI, Cieciura SJ. ACTION OF X-RAYS ON MAMMALIAN CELLS. *J Exp Med.* 1957;106:485–500.

37. Arab-Bafrani Z, Shahbazi-Gahrouei D, Abbasian M, Fesharaki M. Multiple MTS assay as the alternative method to determine survival fraction of the irradiated HT-29 colon cancer cells. *J Med Sig Sens.* 2016;6:112–6.
38. Evanko D. Focus on fluorescence imaging. *Nat Methods.* 2005;2:901–901.
39. Westcott SL, Oldenburg SJ, Lee TR, Halas NJ. Formation and adsorption of clusters of gold nanoparticles onto functionalized silica nanoparticle surfaces. *Langmuir.* 1998;14:5396–401.
40. Nakamura M, Ishimura K. Synthesis and characterization of organosilica nanoparticles prepared from 3-mercaptopropyltrimethoxysilane as the single silica source. *J Phys Chem C.* 2007;111:18892–8.
41. Nakamura M, Ozaki S, Abe M, Doi H, Matsumoto T, Ishimura K. Size-controlled synthesis, surface functionalization, and biological applications of thiol-organosilica particles. *Colloids Surf B. Elsevier B.V.*; 2010;79:19–26.
42. Nakamura M, Hayashi K, Nakano M, Kanadani T, Miyamoto K, Kori T, et al. Identification of polyethylene glycol-resistant macrophages on stealth imaging in vitro using fluorescent organosilica nanoparticles. *ACS Nano.* 2015;9:1058–71.
43. Turkevich J, Stevenson PC, Hillier J. A study of the nucleation and growth processes in the synthesis of colloidal gold. *Discuss Faraday Soc.* 1951;11:55–75.
44. Brust M, Walker M, Bethell D, Schiffrin DJ, Whyman R. Synthesis of thiol-derivatised gold nanoparticles in a two-phase Liquid–Liquid system. *J Chem Soc, Chem Commun.* 1994;801–2.
45. Vignard J, Mirey G, Salles B. Ionizing-radiation induced DNA double-strand breaks: A direct and indirect lighting up. *Radiother Oncol. Elsevier Ireland Ltd*; 2013;108:362–9.
46. Nakayama M, Sasaki R, Ogino C, Tanaka T, Morita K, Umetsu M, et al. Titanium peroxide nanoparticles enhanced cytotoxic effects of X-ray irradiation against pancreatic cancer model through reactive oxygen species generation in vitro and in vivo. *Radiat Oncol. Radiation Oncology*; 2016;11:1–11.
47. van der Meel R, Sulheim E, Shi Y, Kiessling F, Mulder WJM, Lammers T. Smart cancer nanomedicine. *Nat Nanotechnol. Springer US*; 2019;14:1007–17.
48. Zimmermann TS, Lee ACH, Akinc A, Bramlage B, Bumcrot D, Fedoruk MN, et al. RNAi-mediated gene silencing in non-human primates. *Nature.* 2006;441:111–4.
49. Doura T, Tamanoi F, Nakamura M. Miniaturization of thiol-organosilica nanoparticles induced by an anionic surfactant. *J Colloid Interface Sci. Elsevier Inc.*; 2018;526:51–62.
50. Cho KA, Sung JR, Yoon SO, Ji HP, Jung WL, Kim HP, et al. Morphological adjustment of senescent cells by modulating caveolin-1 status. *J Biol Chem.* © 2004 ASBMB. Currently published by Elsevier Inc; originally published by American Society for Biochemistry and Molecular Biology.; 2004;279:42270–8.
51. Forrester HB, Vidair CA, Albright N, Ling CC, Dewey WC. Using computerized video time lapse for quantifying cell death of X-irradiated rat embryo cells transfected with c-myc or c-Ha-ras. *Cancer Res.* 1999;59:931–9.
52. Kobayashi D, Shibata A, Oike T, Nakano T. One-step Protocol for Evaluation of the Mode of Radiation-induced Clonogenic Cell Death by Fluorescence Microscopy. *JoVE (Journal of Visualized Experiments).* 2017;128:1–6.

53. Qin L, Fan M, Candas D, Jiang G, Papadopoulos S, Tian L, et al. CDK1 Enhances Mitochondrial Bioenergetics for Radiation-Induced DNA Repair. *Cell Rep.* Elsevier Ltd; 2015;13:2056–63.
54. Pan Y, Leifert A, Ruau D, Neuss S, Bornemann J, Schmid G, et al. Gold nanoparticles of diameter 1.4 nm trigger necrosis by oxidative stress and mitochondrial damage. *Small.* 2009;5:2067–76.
55. Li JJ, Hartono D, Ong CN, Bay BH, Yung LYL. Autophagy and oxidative stress associated with gold nanoparticles. *Biomaterials.* Elsevier Ltd; 2010;31:5996–6003.
56. Nel A, Xia T, Mädler L, Li N. Toxic Potential of Materials at the Nanolevel. *Science.* 2006;311:622–7.
57. Ghita M, McMahon SJ, Taggart LE, Butterworth KT, Schettino G, Prise KM. A mechanistic study of gold nanoparticle radiosensitisation using targeted microbeam irradiation. *Sci Rep.* Nature Publishing Group; 2017;7:1–12.
58. Daugas E, Nochy D, Ravagnan L, Loeffler M, Susin SA, Zamzami N, et al. Apoptosis-inducing factor (AIF): a ubiquitous mitochondrial oxidoreductase involved in apoptosis. *FEBS Lett.* 2000;476:118–23.
59. Kang MH, Reynolds CP. Bcl-2 Inhibitors: Targeting Mitochondrial Apoptotic Pathways in Cancer Therapy. *Clin Cancer Res.* 2009;15:1126–32.
60. Benej M, Hong X, Vibhute S, Scott S, Wu J, Graves E, et al. Correction for Benej et al., Papaverine and its derivatives radiosensitize solid tumors by inhibiting mitochondrial metabolism. *Proc Natl Acad Sci.* 2018;115:E11561–E11561.

Supporting Information

Supporting Information is available from the Wiley Online Library or from the author.

Tables

Table 1. Hydrodynamic diameters and zeta potentials of NPs by DLS measurement and the evaluation of cellular uptake of NPs by FCM and ICP-OES measurements.

	DLS ^{a)}		FCM		ICP-OES	
	Hydrodynamic diameter	Zeta potential	Uptake population	Uptake level	NPs weight ^{b)} /cell	NPs number/cell
	(nm)	(mV)	(%)	(F.I.)	(pg)	(number)
OS	132±7	−36	2.5±1.6	25.1±2.0	1.05	875
OS/PEI	143±14	36	96.9±1.9	381.8±120.7	0.88	733
OS/Au	136±11	−28	21.9±8.0	21.3±0.9	0.22	181
OS/Au/PEI	145±10	9	84.1±8.9	96.0±17.3	0.90	750

^{a)} NPs were dispersed in water solution. ^{b)} The quantities of up-taken NPs per particle uptake-positive cell determined from FCM uptake rate.

Figures

Figure 1

Strategy for X-ray sensitizer and characterization of OS/Au. (A) Schematic of the strategy for X-ray sensitizer as cancer cell therapy. (B) Detailed overview of the surface functionalization of OS with the Au NPs (OS/Au) of OS/Au. The STEM of OS (C-1) and OS/Au (C-2). Scale bar = 100 nm. (D) TGA data of OS and OS/Au. (E) Increase in the fluorescence intensity of the APF derivative.

Figure 2

Fluorescence microscopic observation of the cellular uptake of NPs. The cells treated with OS, OS/PEI, OS/Au, and OS/Au/PEI were observed by fluorescence microscopy. Scale bar = 100 μ m.

Figure 3

Cell viabilities for 4T1 cells treated with various concentrations of OS, OS/PEI, OS/Au, and OS/Au/PEI as determined via the IA [A; representative imaging of FM for IA assay (Scale bar = 2 mm), and B] and WST-1 assays (C). Each value represents mean $\pm$ SD, where $n = 9$ (three replicates for three independent experiments). * Significantly different from the 4T1 cells treated with 0 $\mu\text{g mL}^{-1}$ of NPs. (D) FM images [left (Scale bar = 500 μm)] and high-resolution FM images [right (Scale bar = 500 μm)] of 4T1 cells. The 4T1 cells

were treated with 10 $\mu\text{g mL}^{-1}$ of NP (-), OS, OS/PEI, OS/Au/PEI, and 0 Gy and 8 Gy, respectively. Images of blue fluorescence from Hoechst 33342 staining.

Figure 4

Cell counts and cell viability of 4T1 cells treated with 30 $\mu\text{g mL}^{-1}$ of NP (-), OS, OS/PEI, and OS/Au/PEI with X-ray irradiation. * Significantly different from the 4T1 cells treated with 0 Gy NP (-). # Significantly different from the 4T1 cells treated with 8 Gy NP (-). † Significantly different from the 4T1 cells treated with 8 Gy OS/PEI.

Figure 5

(A) FM images of 4T1 cells stained blue with DAPI (indicates the cell nucleus) and stained magenta with Cy5 (indicates the γ -H2AX) treated with $30 \mu\text{g mL}^{-1}$ of NP (-), OS, OS/PEI, and OS/Au/PEI with X-ray irradiation after 1 h. Scale bar = $50 \mu\text{m}$. (B) γ -H2AX expression in 4T1 cells treated with $30 \mu\text{g mL}^{-1}$ of NP (-), OS, OS/PEI, and OS/Au/PEI with X-ray irradiation after 1 h and 6 h. * Significantly different from the 4T1 cells treated with 0 Gy NP (-). # Significantly different from the 4T1 cells treated with 8 Gy NP (-). † Significantly different from the 4T1 cells treated with 8 Gy OS/PEI.

Figure 6

(A) TMRE stained FM images of 4T1 cells at DAY1 after X-ray irradiation. 4T1 cells were treated with NP (-), OS, OS/PEI, OS/Au/PEI, and 0 Gy and 8 Gy, respectively. Scale bar = 50 μ m. (B) Time-dependence of flow cytometric analysis of 4T1 cells with NP (-) and stained with TMRE. (Upper) The SSC values of cells stained with and without TMRE are presented on the left and right sides, respectively. (Lower) Increases in FL2 were calculated by subtracting the fluorescence intensity (geo mean) of cells treated with NPs and stained with TMRE from the control cells treated with NPs but not stained with TMRE. Each value represents mean SD, where n = 3 replicates. * Significantly different from the 4T1 cells at 0 h. # Significantly different from the 4T1 cells at DAY1. † Significantly different from the 4T1 cells at DAY2. ‡ Significantly different from the 4T1 cells at DAY3. (C) Time-dependence of flow cytometric analysis of 4T1 cells with NP (-), OS/PEI, and OS/Au/PEI with or without X-ray irradiation, and stained with TMRE. * Significantly different from the 4T1 cells treated with 0 Gy NP (-). # Significantly different from the 4T1 cells treated with 0 Gy OS/PEI. † Significantly different from the 4T1 cells treated with 0 Gy OS/Au/PEI. ‡ Significantly different from the 4T1 cells treated with 8 Gy NP (-). § Significantly different from the 4T1 cells treated with 8 Gy OS/PEI.

Figure 7

(A) FM image of 4T1 cells for apoptotic and necrotic cell determination by Annexin V/DAPI staining treated with $30 \mu\text{g mL}^{-1}$ of NP (-), OS, OS/PEI, and OS/Au/PEI with X-ray irradiation after DAY4. Scale bar = $50 \mu\text{m}$. (B) The FM image analysis of 4T1 cells for apoptotic and necrotic cell determination by Annexin V/DAPI staining treated with $30 \mu\text{g mL}^{-1}$ of NP (-), OS, OS/PEI, and OS/Au/PEI with X-ray irradiation after DAY1 and DAY4. * Significantly different from the 4T1 cells treated with 0 Gy NP (-). # Significantly different from the 4T1 cells treated with 8 Gy NP (-). † Significantly different from the 4T1 cells treated with 8 Gy OS/PEI.

Supplementary Files

This is a list of supplementary files associated with this preprint. Click to download.

- [SupportingInformation.docx](#)
- [TableofContents.docx](#)