Resonant tunneling driven metal-insulator transition in double quantum-well structures of strongly correlated oxide

Ryu Yukawa

High Energy Accelerator Research Organization (KEK) <https://orcid.org/0000-0002-5066-9445>

Masaki Kobayashi

University of Tokyo

Daisuke Shiga

Tohoku University

Kohei Yoshimatsu

Tokyo Institute of Technology

Shoji Ishibashi

National Institute of Advanced Industrial Science and Technology

Makoto Minohara

High Energy Accelerator Research Organization (KEK)

Miho Kitamura

High Energy Accelerator Research Organization (KEK)

Koji Horiba

Condensed Matter Research Center and Photon Factory, Institute of Materials Structure Science, High Energy Accelerator Research Organization (KEK)

Andres Santander-Syro

University of Paris-Saclay <https://orcid.org/0000-0003-3966-2485>

Hiroshi Kumigashira (✉ kumigashira@tohoku.ac.jp)

Tohoku University <https://orcid.org/0000-0003-4668-2695>

Article

Keywords: Correlated Materials, Semiconductor Transistors, Wave-function Engineering, Mott-transistors, Angle-resolved Photoemission Spectroscopy,

Posted Date: February 24th, 2021

DOI: <https://doi.org/10.21203/rs.3.rs-153757/v1>

License: © ⓘ This work is licensed under a Creative Commons Attribution 4.0 International License.

[Read Full License](#)

Version of Record: A version of this preprint was published at Nature Communications on December 1st, 2021. See the published version at <https://doi.org/10.1038/s41467-021-27327-z>.

Resonant tunneling driven metal-insulator transition in double quantum-well structures of strongly correlated oxide

R. Yukawa^{1,†}, M. Kobayashi^{1,†}, D. Shiga^{1,2}, K. Yoshimatsu², S. Ishibashi³, M. Mihohara¹,
M. Kitamura¹, K. Horiba¹, A. F. Santander-Syro⁴, and H. Kumigashira^{1,2,*}

¹ Photon Factory, Institute of Materials Structure Science, High Energy Accelerator Research Organization (KEK), Tsukuba, 305–0801, Japan

² Institute of Multidisciplinary Research for Advanced Materials (IMRAM), Tohoku University, Sendai, 980–8577, Japan

³ Research Center for Computational Design of Advanced Functional Materials, National Institute of Advanced Industrial Science and Technology (AIST), Tsukuba, Ibaraki 305-8568, Japan

⁴ Université Paris-Saclay, CNRS, Institut des Sciences Moléculaires d’Orsay, 91405, Orsay, France

[†] These authors contributed equally to this work.

* e-mail: kumigashira@tohoku.ac.jp

Abstract

The metal-insulator transition (MIT), a fascinating phenomenon occurring in some strongly correlated materials, is of central interest in modern condensed-matter physics. Controlling the MIT by external stimuli is a key technological goal for applications in future electronic devices. However, the standard control by means of the field effect, which works extremely well for semiconductor transistors, faces severe difficulties when applied to the

MIT. Hence, a radically different approach is needed. Here, we report an MIT induced by resonant tunneling (RT) in double quantum well (QW) structures of strongly correlated oxides. In our structures, two layers of the strongly correlated conductive oxide SrVO_3 (SVO) sandwich a barrier layer of the band insulator SrTiO_3 (STO). The top QW is a marginal Mott-insulating SVO layer, while the bottom QW is a metallic SVO layer. Angle-resolved photoemission spectroscopy experiments reveal that the top QW layer becomes metallized when the thickness of the tunneling barrier layer is reduced. An analysis based on band structure calculations indicates that RT between the quantized states of the double QW induces the MIT. Our work opens avenues for realizing the Mott-transistor based on the wave-function engineering of strongly correlated electrons.

Controlling the quantum ground state of a system is essential for applications. The best-known example is semiconductor technology, where the state (conductive or not conductive) of a semiconductor is driven by the so-called field-effect transistor (FET). In the FET, the number of electric charge carriers is controlled by an external voltage¹.

Some strongly correlated electron materials naturally show a metal-to-insulator transition (MIT)^{2,3}. It would be thus highly desirable to control such a MIT in the same way as it is done for semiconductors. However, despite intensive effort, the FET control of the MIT in strongly correlated materials has been so far unsuccessful⁴⁻⁸. In fact, such approach faces fundamental difficulties. One is the insufficient carrier density that can be induced by the electric field to cause a filling-controlled MIT (Mott transistor operation)^{4,5}. The other is the shortness of the Thomas-Fermi screening length due to $10^{22} - 10^{23} \text{ cm}^{-3}$ mobile carriers, which limits the conductive area where MIT occurs⁹. Thus, realistic future applications of the Mott transistor call for a different principle of controlling the MIT¹⁰.

Now, according to the Mott-Hubbard theory¹¹, the ground state in strongly-correlated materials is described by the ratio of the Coulomb interaction (U) to the bandwidth (W)^{2,3,11}. When $U < W$, the material is metallic, but it becomes insulating when $U > W$. Therefore, tuning the U/W ratio by some external perturbation would control the MIT, and the practical realization of this idea has been one of the central goals in modern condensed matter physics⁴⁻⁸.

Here we propose a new approach for the tuning of the U/W ratio, hence the control of the MIT,

using the resonant-tunneling (RT) effects¹ in double quantum well (QW) structures of strongly correlated oxides. The concept is schematically illustrated in Fig. 1(a). The double QW structure consists of two strongly correlated oxide layers and a barrier layer (insulator). The top QW is a “marginal” Mott insulator, i.e., a material in the insulating Mott phase but in close proximity (U slightly larger than W ; $U \gtrsim W$) to the metallic one, while the bottom QW is a correlated metal. In the marginal Mott-insulating QW, the quantized electron states are localized due to $U \gtrsim W$, leading to a Mott insulating state, but the QW exhibits a transition to a metallic state by applying a small external stimulus. If the RT occurs between the marginal Mott-insulating QW and metallic QW states, the QW states that are energetically close to each other are hybridized. In this situation, the resultant envelope wave functions extend over the whole double QW structure and consequently electrons in the top QW states may achieve additional spatial freedom through the RT effects, leading to the reduction in effective Coulomb potential. As a result, the marginal Mott insulator is expected to be metallized owing to U becoming smaller than W . Since the MIT is caused by the quantum tunneling phenomena, the MIT control avoids the fundamental problems of the FET approach^{4–10}, and is also advantageous over conventional filling (bandwidth) control by chemical doping (pressure) in the bulk².

To demonstrate the MIT driven by the RT effects, we fabricate double QW structures where layers of the strongly-correlated conductive oxide SrVO_3 (SVO) sandwich a barrier layer of SrTiO_3 (STO), a band insulator. Being a highly correlated Fermi-liquid (FL) metal with simple $3d(t_{2g})^1$ configuration^{12–14}, SVO in ultrathin film grown onto STO is known to form QW states^{15,16}, and to undergo a thickness-dependent transition from the FL metal to a Mott insulator at a critical film thickness of 2–3 monolayers (ML)^{17,18}. A recent theoretical study has predicted that the 2 ML of SVO is at the verge of the Mott insulator, and it can easily become a metal by applying a small perturbation¹⁹. Thus, as the top marginal Mott-insulating QW, we used a 2-ML SVO layer. As a counterpart, for the bottom metallic QW layer we used a 6-ML SVO, so as to induce the RT effect between two energetically close QW states (Supplementary Note 5). Thereafter, the (2-ML SVO)/(L -ML STO)/(6-ML SVO) double QW structure is denoted as $\text{V}_2\text{T}_L\text{V}_6$, where L is the thickness of the STO barrier layer. Thus, based on the previously reported structure plot of quantization energies as a function of SVO layer thickness^{15–17,20,21}, the first quantization level of the top (2-ML SVO) QW states matches the second quantization level of the bottom (6-ML SVO) QW. Furthermore, in the $\text{V}_2\text{T}_L\text{V}_6$ structure, the transition probability of electrons between the

top and bottom QWs is also controlled as a function of the STO barrier layer thickness L , as schematically presented in Fig. 1.

The transition from the marginal Mott-insulating QW states to the metallic QW states induced by the RT effects is visualized by *in situ* angle-resolved photoemission spectroscopy (ARPES). Figure 2a presents a series of ARPES images of the $V_2T_LV_6$ double QW structures with varying the STO barrier layer thickness ($L = 2, 4, 10$, and ∞ ML). Because these band dispersions have been taken along the Γ -X direction, the ARPES images consist of only the d_{zx} bands of V $3d t_{2g}$ states in the present experimental geometry (see also Supplementary Note 2)^{15–17,22,23}. Here, the series of ARPES images are normalized to the incident photon flux; hence, the color scale reflects the change in spectral weight as a function of L . Thus, the metallization of top QW will be evidenced by the appearance of a parabolic band at the Γ point near the Fermi level (E_F).

As can be seen in the ARPES images of the $V_2T_\infty V_6$ structure, there are no discernible states near E_F , reflecting the Mott-insulating nature of the 2-ML SVO films. The Mott-insulating state of the top 2-ML QW of $V_2T_\infty V_6$ is further confirmed by the appearance of the lower Hubbard band at a binding energy of 1.5 eV (see Supplementary Fig. S9)^{17,18}. In the $V_2T_4V_6$ double QW, as the STO barrier layer becomes thinner (the transition probability of electrons between the two QW states increases), a faint dispersive feature emerges near E_F . Eventually, a metallic band whose dispersion crosses E_F is clearly visible in the $V_2T_2V_6$ double QW structures, demonstrating the metallization of the top 2-ML SVO layer. It should be noted that the observed metallic states are at the top 2-ML SVO layer, since the mean-free-path of the photoelectrons in the present experimental condition is about 0.4–0.6 nm (corresponding to 1.0–1.5 ML in the present case) (refs 24–26). Thus, signals from the buried 6-ML SVO layer are negligible in the ARPES results on $V_2T_LV_6$.

The emergence of metallic states created by the proximity of two QWs is more clearly seen in the energy distribution curves (EDCs) shown in Figs. 2b, where one observes a systematic evolution of the dispersive metallic states and subsequent reduction in the lower Hubbard band (localized states) in the $V_2T_LV_6$ double QW structures. In the top 2-ML SVO layer of the $V_2T_\infty V_6$ and $V_2T_{10}V_6$ double QW structures, no metallic-band-like features are visible near E_F and only non-dispersive features are observed below a binding energy of 1 eV. The existence of the non-dispersive structure is caused by spectral weight transfer from the coherent bands near E_F to the

lower Hubbard bands^{17,18,27}, indicating the localized nature of V 3d electrons in the top 2-ML SVO layer (see Supplementary Note 4). When the barrier layer thickness decreases, a band-like feature appears near E_F for $V_2T_4V_6$, while a weak non-dispersive structure is still visible around 0.8 eV. Eventually, for the thinnest barrier, the band-like feature evolves to a clear dispersive feature crossing E_F .

The spectral behavior observed in the top QW layer of $V_2T_LV_6$ is similar to that previously observed in thickness-dependent Mott transition in SVO QWs¹⁷, suggesting the existence of a Mott transition from localized states to standard QW subbands in 2-ML SVO with decreasing L . Thus, the next crucial issue is whether the MIT originates from the RT effects or not. The condition for the RT to occur is that there must be an energetic match between quantized states at both the top and bottom QWs¹. As seen in the 2-ML QW shown in Fig. 2, the bottom of the conduction band (subband bottom energy), corresponding to its first quantization energy, is estimated to be 320 meV. This value is consistent with the one extrapolated from the structure plot of SVO QW as a function of SVO layer thickness (see Supplementary Note 5)^{15–17,20,21}. To confirm the existence of energetically-close QW states for SVO layers at opposite sides of the structure, we investigate the “flip” double QW structure of $V_6T_2V_2$ as shown in Fig. 3a, where we only probe the subband structures of the 6-ML QW due to the photoelectron attenuation^{24–26}. As expected from previous works^{15–17}, the ARPES images consist of the quantized d_{zx} bands with quantum numbers $n = 1$ (band bottom at 500 meV) and $n = 2$ (band bottom at 290 meV). The quantization energy of $n = 2$ states for the 6-ML SVO layer is close to that of the metallic band observed for the 2-ML SVO layer (320 meV). The existence of the energetically close QW states in both the top and bottom QW structures suggests the hybridized nature of the envelope wavefunctions of the two subbands^{28,29}, leading to the RT effect between the two QWs.

The occurrence of the RT effects between the two QW states is further supported by density functional theory (DFT) calculation. Figure 3 compares the DFT results of $V_2T_2V_6$ QW structures with the ARPES results. Owing to the hybridization between the top and bottom QW states, the DFT calculation shows the formation of four d_{zx} -derived subbands ($n' = 1 - 4$) from the bottom. As a result of the hybridization of the original $n = 1$ of 2-ML QW and $n = 2$ in 6-ML QW, these two energetically close quantization levels form a bonding ($n' = 2$) and an antibonding ($n' = 3$) state in the double QW. From the DFT calculation, the energy difference between quantization levels $n' = 2$ and $n' = 3$ is estimated to be 40 meV. In contrast, the $n = 1$ and 3 states

in the bottom 6-ML QW are not hybridized to any levels in the top QW and remain unchanged. Judging from the existence probability of electrons belonging to each subband as shown in Fig. 3b, the $n' = 2$ subband, which mainly exists in the 2-ML QW, emerges from the original $n = 1$ subband of 2-ML SVO, whereas the other subbands ($n' = 1, 3, 4$) from the original 6-ML SVO QW states. By considering the escape depth of the present ARPES measurements²⁴⁻²⁶ and the distribution of existence probabilities, only the $n' = 2$ subband is predominately detectable in ARPES for the $V_2T_2V_6$ heterostructure, whereas the $n' = 1, 3, 4$ subbands are detectable for the “flip” $V_6T_2V_2$ heterostructure. These features are well reproduced in the ARPES results of Figs. 3a and 3c, suggesting the occurrence of the RT effects between the top ($n = 1$) and bottom ($n = 2$) QW states.

The DFT calculation provides an important indication regarding the metallization of the top QW states: owing to the close proximity of the two quantization energy levels, only $n' = 2$ and 3 states hybridize with each other. Also, the $n' = 2$ ($n' = 3$) shows weak but finite existence probabilities in the 6-ML SVO layer (2-ML SVO layer) side, and their respective probability maxima spatially overlap. This spread of the existence probability over both sides of the double QW structure results from the hybridization of the corresponding envelope wavefunctions. Actually, the DFT result demonstrates that about 10% of the $n' = 2$ states spread over the 6-ML SVO QW side in the case of $V_2T_2V_6$ double QW structures. As schematically illustrated in Fig. 1, in this situation, strongly correlated electrons in the top “marginal” Mott QW states of 2-ML layer SVO ($U \gtrsim W$) achieve additional spatial freedom, since they can move to the bottom metallic 6-ML QW through the RT effects. The RT effects cause the reduction in effective Coulomb potential ($U < W$) in the 2-ML QW. As a result, the marginal Mott insulator undergoes an insulator-to-metal transition.

The present study demonstrates that the MIT can be controlled by the RT effect in double QW structures of strongly correlated oxides. Our observations offer valuable insight into the quest for novel quantum phenomena using oxide heterostructures^{6-10,30-33}, since the U/W ratio can be controlled by designing the wavefunction of their strongly correlated electrons. In addition, from an applied perspective, the MIT control based on the double QW structure studied here has fundamental advantages over conventional FET control^{4,5,9}: the Mott transition may be operated by aligning two quantization levels through the application of a small voltage, and the entire QW will undergo a MIT irrespective of the limitation imposed by Thomas-Fermi screening. The

present demonstration opens an avenue for creating a Mott-transistor operation based on the quantum RT effects between designed wavefunctions of strongly correlated electrons.

Methods

Laser molecular-beam epitaxy. QW structures were grown on atomically-flat (001) surfaces of TiO₂-terminated Nb-doped STO substrates in a laser molecular-beam epitaxy chamber connected to an ARPES system at BL-2A of Photon Factory (PF)^{14–18}. During the growth, the thickness was precisely and digitally controlled on the atomic scale by monitoring the intensity oscillation of reflection high-energy electron diffraction spots. The details of the growth conditions of SVO and STO layers are described elsewhere^{15–18,34}. Note that all double QW structures were fabricated under the same conditions as those of the previously reported SVO/STO heterostructures^{15–18,34}, wherein atomically-flat surfaces and chemically abrupt interfaces formed. The growth condition details and the characterizations of the QW structures are given in Supplementary Information.

***In situ* angle-resolved photoemission spectroscopy.** After growth, the samples were transferred to the ARPES chamber under an ultrahigh vacuum of 10⁻¹⁰ Torr to avoid the degradation of the sample surfaces on exposure to air. The ARPES experiments were conducted *in situ* at a temperature of 20 K using horizontal linear polarization of the incident light. The incident photon energy was 88 eV. The energy and angular resolutions were respectively set to about 30 meV and 0.3°. The E_F of the samples was calibrated by measuring a gold foil that was electrically connected to the samples. The details of the ARPES measurement setups are given in Supplementary Note 2.

Electronic structure calculations. First-principles calculations based on DFT were carried out in the framework of the Perdew-Burke-Ernzerhof-type generalized-gradient approximation³⁵ using the computational code of QMAS³⁶. The corresponding Brillouin zone was sampled by $8 \times 8 \times 2$ k -mesh for the self-consistent field calculation. To obtain the electronic density of states, calculations with fixed charges were made at additional k points. We have adopted a repeated slab geometry with vacuum layer in between neighboring slabs of the V₂T₂V₆ heterostructure as illustrated in the top panel of Fig. 3b. For the comparison with the ARPES results, the subband dispersion (E_{sub}) was obtained by multiplying the calculated band structures

(E_{DFT}) by the band renormalization factor (Z): $E_{\text{sub}}(k_{\parallel}) = Z \cdot E_{\text{DFT}}(k_{\parallel})$, where $k_{\parallel}$ is the momentum parallel to the surface. The value of Z is inversely proportional to the mass enhancement factor, and the mass enhancement in the subbands is known to be associated with strong interaction among V $3d$ electrons^{12–17,37–39}. The best fit to the ARPES results gives $Z = 0.55$ (mass enhancement factor ~ 1.8) for the heterostructure, in good agreement with previous results measured on SrVO_3 thin films¹⁵.

Acknowledgment

The authors are very grateful to Y. Kuramoto, Y. Matsumoto, and A. Fujimori for their useful discussions and acknowledge T. Kanda and E. Sakai for their support in the experiment at PF. This work was financially supported by a Grant-in-Aid for Scientific Research (Nos. 16H02115, 16KK0107, 19H01830, and 20KK0117) from the Japan Society for the Promotion of Science (JSPS), CREST (JPMJCR18T1) from the Japan Science and Technology Agency (JST), and the MEXT Element Strategy Initiative to Form Core Research Center (JPMXP0112101001). AFSS is supported by public grants from the Centre National de la Recherche Scientifique (CNRS), project PICS FermiAds No. 272651, and the French National Research Agency (ANR), project Fermi-NESt No. ANR-16-CE92-0018. The work performed at KEK-PF was approved by the Program Advisory Committee (proposals 2018S2-004) at the Institute of Materials Structure Science, KEK.

Author contributions

The samples were grown and characterized by R.Y., M. Kobayashi., and M.M. ARPES measurements were performed by R.Y., M. Kobayashi, D.S., M.M., M. Kitamura, and K.H. R.Y. and M. Kobayashi analyzed the ARPES data. R.Y., M. Kobayashi, K.Y., A.F.S-S, and H.K. contributed to the interpretation. S.I. performed the DFT calculation. R.Y., A.F.S-S, and H.K. wrote the paper with input and discussion from all co-authors. H.K. devised the project and were responsible for its overall planning and direction. All authors discussed the results and commented on the manuscript.

Additional information

Supplementary information is available in the online version of the paper. Reprints and permissions information is available online at www.nature.com/reprints. Correspondence and requests for materials should be addressed to H.K. (e-mail: kumigashira@tohoku.ac.jp).

258 **Competing financial interests**

259 The authors declare no competing financial interests.

260

261

262 **References**

263 1. Sze, S. M. & Ng, K. K. *Physics of Semiconductor Devices* 3rd edn (Wiley–Interscience,
264 2006).

265 2. Imada, M., Fujimori, A. & Tokura, Y. Metal-insulator transitions. *Rev. Mod. Phys.* **70**,
266 1039–1263 (1998).

267 3. Georges, A., Kotliar, G., Krauth, W. & Rozenberg, M. J. Dynamical mean-field theory of
268 strongly correlated fermion systems and the limit of infinite dimensions. *Rev. Mod. Phys.*
269 **68**, 13–125 (1996).

270 4. Ahn, C. H., Triscone, J.-M. & Mannhart, J. Electric field effect in correlated oxide systems.
271 *Nature* **424**, 1015–1018 (2003).

272 5. Ahn, C. H. *et al.* Electrostatic modification of novel materials. *Rev. Mod. Phys.* **78**, 1185–
273 1212 (2006).

274 6. Takagi, H. & Hwang, H. Y. An emergent change of phase for electronics. *Science* **327**,
275 1601–1602 (2010).

276 7. Mannhart, J. & Schlom, D. G. Oxide Interfaces--An Opportunity for Electronics. *Science*
277 **327**, 1607–1611 (2010).

278 8. Hwang, H. Y. *et al.* Emergent phenomena at oxide interfaces. *Nat. Mater.* **11**, 103–113
279 (2012).

280 9. Nakano, M. *et al.* Collective bulk carrier delocalization driven by electrostatic surface
281 charge accumulation. *Nature* **487**, 459–462 (2012).

282 10. Tokura, Y., Kawasaki, M. & Nagaosa, N. Emergent functions of quantum materials. *Nat.*
283 *Phys.* **13**, 1056–1068 (2017).

284 11. Hubbard, J. Electron Correlations in Narrow Energy Bands. *Proc. R. Soc. A Math. Phys.*
285 *Eng. Sci.* **276**, 238–257 (1963).

286 12. Inoue, I. *et al.* Systematic Development of the Spectral Function in the $3d^1$ Mott-Hubbard
287 System $\text{Ca}_{1-x}\text{Sr}_x\text{VO}_3$. *Phys. Rev. Lett.* **74**, 2539–2542 (1995).

288 13. Inoue, I. H., Goto, O., Makino, H., Hussey, N. E. & Ishikawa, M. Bandwidth control in a
289 perovskite-type $3d^1$ -correlated metal $\text{Ca}_{1-x}\text{Sr}_x\text{VO}_3$. I. Evolution of the electronic properties
290 and effective mass. *Europhys. Lett.* **58**, 4372–4383 (1998).

291 14. Aizaki, S. *et al.* Self-Energy on the Low- to High-Energy Electronic Structure of

292 Correlated Metal SrVO₃. *Phys. Rev. Lett.* **109**, 056401 (2012).

293 15. Yoshimatsu, K. *et al.* Metallic Quantum Well States in Artificial Structures of Strongly
294 Correlated Oxide. *Science* **333**, 319–322 (2011).

295 16. Kobayashi, M. *et al.* Origin of the Anomalous Mass Renormalization in Metallic Quantum
296 Well States of Strongly Correlated Oxide SrVO₃. *Phys. Rev. Lett.* **115**, 076801 (2015).

297 17. Kobayashi, M. *et al.* Emergence of Quantum Critical Behavior in Metallic Quantum-Well
298 States of Strongly Correlated Oxides. *Sci. Rep.* **7**, 16621 (2017).

299 18. Yoshimatsu, K. *et al.* Dimensional-Crossover-Driven Metal-Insulator Transition in SrVO₃
300 Ultrathin Films. *Phys. Rev. Lett.* **104**, 147601 (2010).

301 19. Zhong, Z. *et al.* Electronics with Correlated Oxides: SrVO₃/SrTiO₃ as a Mott Transistor.
302 *Phys. Rev. Lett.* **114**, 246401 (2015).

303 20. Okamoto, S. Anomalous mass enhancement in strongly correlated quantum wells. *Phys.*
304 *Rev. B* **84**, 201305 (2011).

305 21. Zhong, Z., Zhang, Q. & Held, K. Quantum confinement in perovskite oxide
306 heterostructures: Tight binding instead of a nearly free electron picture. *Phys. Rev. B* **88**,
307 125401 (2013).

308 22. Meevasana, W. *et al.* Creation and control of a two-dimensional electron liquid at the bare
309 SrTiO₃ surface. *Nat. Mater.* **10**, 114–118 (2011).

310 23. Santander-Syro, A. F. *et al.* Two-dimensional electron gas with universal subbands at the
311 surface of SrTiO₃. *Nature* **469**, 189–193 (2011).

312 24. Zangwill, A. *Physics at Surfaces*. (Cambridge University Press, 1988).

313 25. Tanuma, S., Powell, C. J. & Penn, D. R. Calculations of electron inelastic mean free paths.
314 IX. Data for 41 elemental solids over the 50 eV to 30 keV range. *Surf. Interface Anal.* **43**,
315 689–713 (2011).

316 26. Hüfner, S. *Photoelectron Spectroscopy: Principles and Applications* 3rd edn (Springer,
317 2003).

318 27. King, P. D. C. *et al.* Atomic-scale control of competing electronic phases in ultrathin
319 LaNiO₃. *Nat. Nanotechnol.* **9**, 443–447 (2014).

320 28. Kawasaki, J. K. *et al.* Rutile IrO₂/TiO₂ superlattices: A hyperconnected analog to the
321 Ruddelsden-Popper structure. *Phys. Rev. Mater.* **2**, 054206 (2018).

322 29. Choi, W. S., Lee, S. A., You, J. H., Lee, S. & Lee, H. N. Resonant tunnelling in a quantum
323 oxide superlattice. *Nat. Commun.* **6**, 7424 (2015).

324 30. Lee, D. *et al.* Isostructural metal-insulator transition in VO₂. *Science* **362**, 1037–1040
325 (2018).

- 326 31. Domínguez, C. *et al.* Length scales of interfacial coupling between metal and insulator
327 phases in oxides. *Nat. Mater.* **19**, 1182–1187 (2020).
- 328 32. Ramesh, R. & Schlom, D. G. Creating emergent phenomena in oxide superlattices. *Nat.*
329 *Rev. Mater.* **4**, 257–268 (2019).
- 330 33. Matsuno, J. *et al.* Engineering a Spin-Orbital Magnetic Insulator by Tailoring Superlattices.
331 *Phys. Rev. Lett.* **114**, 247209 (2015).
-

332 **References for Methods**

- 333 34. Yoshimatsu, K. *et al.* Determination of the surface and interface phase shifts in metallic
334 quantum well structures of perovskite oxides. *Phys. Rev. B* **88**, 115308 (2013).
- 335 35. Perdew, J. P., Burke, K. & Ernzerhof, M. Generalized Gradient Approximation Made
336 Simple. *Phys. Rev. Lett.* **77**, 3865–3868 (1996).
- 337 36. Ishibashi, S., Tamura, T., Tanaka, S., Kohyama, M. & Terakura, K. *Ab initio* calculations
338 of electric-field-induced stress profiles for diamond/ *c*-BN (110) superlattices. *Phys. Rev. B*
339 **76**, 153310 (2007).
- 340 37. Okamoto, S. & Millis, A. J. Spatial inhomogeneity and strong correlation physics: A
341 dynamical mean-field study of a model Mott-insulator–band-insulator heterostructure.
342 *Phys. Rev. B* **70**, 241104(R) (2004).
- 343 38. Takizawa, M. *et al.* Coherent and incoherent *d* band dispersions in SrVO₃. *Phys. Rev. B* **80**,
344 235104 (2009).
- 345 39. Nekrasov, I. A. *et al.* Momentum-resolved spectral functions of SrVO₃ calculated by LDA
346 + DMFT. *Phys. Rev. B* **73**, 155112 (2006).
- 347

Figure 1 | Schematic illustration of metal-insulator transition induced by resonant tunneling effects. **a**, Before switching on the RT effect. Structure of a double QW composed of a marginal Mott-insulator QW layer/ barrier layer/ metallic QW layer. The marginal Mott-insulator ($U \geq W$), which undergoes the transition to metal by application of a perturbation, is used as top QW layer. Owing to the long distance between the top and bottom QWs, there is no RT effect between the two QWs. The corresponding band diagram and standing waves are illustrated on

the right side. The potential well is represented as a black plate, while the existence-probability amplitudes of the metallic QW states are drawn in red for the top QW and in yellow for the bottom QW. Owing to the marginal Mott insulating nature of top QW states, the strongly correlated electrons in the original top QW states become localized, resulting in a localized state (lower Hubbard band) presented in blue. **b**, After switching on the RT effects. Owing to the hybridization between the top and bottom QW states, bonding (red curve) and antibonding (yellow curve) states are formed. In this situation, electrons in the top QW will be able to move to the bottom QW via RT. By gaining the spatial degree of freedom, the effective Coulomb repulsion of electrons is weakened and the top QW undergoes the transition from the marginal Mott insulator ($U \gtrsim W$) to the metal ($U < W$).

Figure 2 | Visualization of the MIT induced by reduction in the barrier-layer thickness. **a**, Respective ARPES images for $V_2T_LV_6$ double QW structures with L reducing from ∞ to 2. The ARPES data were acquired at a photon energy of $h\nu = 88$ eV along a k_x slice near the Γ point, which includes only the quantized d_{zx} band. Note that the series of ARPES spectra are normalized to the incident photon flux, and the normalized intensity is given by a color scale shown on the right side. **b**, Corresponding EDCs to the respective ARPES images. The red filled triangles are guides to eye for the dispersive features. The broad non-dispersive feature around 1.0 eV is the lower Hubbard band. The inset shows the schematic side views of the corresponding double QW structures.

381

382

383

384 **Figure 3 | Subband structures formed at the $V_2T_2V_6$ heterostructure.** **a, c,** Comparison of
 385 ARPES images taken near the Γ point with the DFT calculations for $V_6T_2V_2$ (**a**) and $V_2T_2V_6$ (**c**)
 386 double QWs. Raw ARPES intensity plots are shown on the right half side and peak-enhanced
 387 plots (see Supplementary Note 3) on the left side, together with the DFT calculation. As shown
 388 in the schematic layout on the top, electrons near the surface (~ 0.4 – 0.6 nm) are detected in the
 389 ARPES measurements. Since only d_{zx} -derived subbands are detected in this experimental
 390 configuration (see Supplementary Note 2), the corresponding subband with predominant d_{zx}
 391 character (filled circles) is presented in the calculation for comparison (the subbands for all t_{2g}
 392 states are shown in Supplementary Fig. S11). The probability of the electron being detected by
 393 ARPES is represented by the size of the filled circles. **b,** Existence probabilities for respective
 394 d_{zx} -derived subbands, which are calculated by Mulliken population analysis, are plotted along the
 395 z direction for the $V_2T_2V_6$ heterostructure. The baselines of the existence probabilities (solid
 396 black lines) correspond to the quantization energies (subband minimum energies). The
 397 existence probability of bonding $n' = 2$ states (red hatched) has central weight at the 2-ML QW,
 398 while that of antibonding $n' = 3$ (yellow hatched) at 6-ML QW, representing their original
 399 character.

400

Figures

a

b

Figure 1

Schematic illustration of metal-insulator transition induced by resonant tunneling effects. a, Before switching on the RT effect. Structure of a double QW composed of a marginal Mott-insulator QW layer/ barrier layer/ metallic QW layer. The marginal Mott-insulator ($U \geq W$), which undergoes the transition to

metal by application of a perturbation, is used as top QW layer. Owing to the long distance between the top and bottom QWs, there is no RT effect between the two QWs. The corresponding band diagram and standing waves are illustrated on the right side. The potential well is represented as a black plate, while the existence-probability amplitudes of the metallic QW states are drawn in red for the top QW and in yellow for the bottom QW. Owing to the marginal Mott insulating nature of top QW states, the strongly correlated electrons in the original top QW states become localized, resulting in a localized state (lower Hubbard band) presented in blue. b, After switching on the RT effects. Owing to the hybridization between the top and bottom QW states, bonding (red curve) and antibonding (yellow curve) states are formed. In this situation, electrons in the top QW will be able to move to the bottom QW via RT. By gaining the spatial degree of freedom, the effective Coulomb repulsion of electrons is weakened and the top QW undergoes the transition from the marginal Mott insulator ($U \approx W$) to the metal ($U < W$).

Figure 2

Visualization of the MIT induced by reduction in the barrier-layer thickness. a, Respective ARPES images for V2TLV6 double QW structures with L reducing from ∞ to 2. The ARPES data were acquired at a photon energy of $h\nu = 88$ eV along a k_x slice near the G point, which includes only the quantized d_{zx} band. Note that the series of ARPES spectra are normalized to the incident photon flux, and the normalized intensity is given by a color scale shown on the right side. b, Corresponding EDCs to the respective ARPES images. The red filled triangles are guides to eye for the dispersive features. The broad non-dispersive feature around 1.0 eV is the lower Hubbard band. The inset shows the schematic side views of the corresponding double QW structures.

Figure 3

Subband structures formed at the V2T2V6 heterostructure. a, c, Comparison of ARPES images taken near the Γ point with the DFT calculations for V6T2V2 (a) and V2T2V6 (c) double QWs. Raw ARPES intensity plots are shown on the right half side and peak-enhanced plots (see Supplementary Note 3) on the left side, together with the DFT calculation. As shown in the schematic layout on the top, electrons near the surface (~ 0.4 – 0.6 nm) are detected in the ARPES measurements. Since only d_{zx} -derived subbands are detected in this experimental configuration (see Supplementary Note 2), the corresponding subband with predominant d_{zx} character (filled circles) is presented in the calculation for comparison (the subbands for all t_{2g} states are shown in Supplementary Fig. S11). The probability of the electron being detected by ARPES is represented by the size of the filled circles. b, Existence probabilities for respective d_{zx} -derived subbands, which are calculated by Mulliken population analysis, are plotted along the z direction for the V2T2V6 heterostructure. The baselines of the existence probabilities (solid black lines) correspond to the quantization energies (subband minimum energies). The existence probability of bonding $n' = 2$ states

(red hatched) has central weight at the 2-ML QW, while that of antibonding $n' = 3$ (yellow hatched) at 6-ML QW, representing their original character.

Supplementary Files

This is a list of supplementary files associated with this preprint. Click to download.

- [210123sSVODQWSI.pdf](#)