Chatter Suppression and Stability Analysis of Rotary Ultrasonic Milling Titanium Alloy Thin-walled Workpiece

Lianjun Sun

School of Mechanical Engineering, Nanjing University of Science and Technology, Nanjing 210094, China

Kan Zheng (✉ zhengkan@mail.njust.edu.cn)

Nanjing University of Science and Technology

Wenhe Liao

School of Mechanical Engineering, Nanjing University of Science and Technology, Nanjing 210094, China

Original Research

Keywords: Titanium alloy, Milling chatter, Rotary ultrasonic milling stability, Thin-walled workpieces

Posted Date: February 4th, 2021

DOI: <https://doi.org/10.21203/rs.3.rs-162478/v1>

License: This work is licensed under a Creative Commons Attribution 4.0 International License.
[Read Full License](#)

Version of Record: A version of this preprint was published at The International Journal of Advanced Manufacturing Technology on September 24th, 2021. See the published version at <https://doi.org/10.1007/s00170-021-07658-3>.

Chatter suppression and stability analysis of rotary ultrasonic milling titanium alloy thin-walled workpiece

Lianjun Sun^a, Kan Zheng^{a,*}, Wenhe Liao^a

^aSchool of Mechanical Engineering, Nanjing University of Science and Technology, Nanjing 210094, China

Corresponding author: Kan Zheng

Tel: 025-84306565, **E-mail:** zhengkan@njust.edu.cn

Abstract

Titanium alloy and its thin-walled structures are widely used in the aerospace field. Aiming at the processing chatter and difficult-to-machine problem of titanium alloy thin-walled workpieces, rotary ultrasonic milling technology (RUM) is employed to restrict machining vibration in this paper. Firstly, the titanium alloy web with low stiffness is equivalent to a mass-spring-damping system with three degrees of freedom for describing its dynamic characteristics. Then, a novel stability analysis method is proposed for RUM thin-walled workpiece (RUM-tww) through defining an ultrasonic function angle. Furthermore, RUM-tww stability lobe diagrams (SLDs) are achieved based on the semi-discrete method (SDM). The simulation results show that the milling stability of titanium alloy webs is improved effectively under the effect of ultrasonic vibration energy. Compared with conventional milling thin-walled workpiece (CM-tww), the stability region of RUM-tww is increased by 80.32% within the spindle speed from 1000r/min to 5000r/min. Finally, milling experiments are carried out to verify the validity and rationality of SLDs via analyzing chatter marks, cutter marks and flatness on the machined surface. The experimental results are in good agreement with the theoretical prediction.

Keywords Titanium alloy · Milling chatter · Rotary ultrasonic milling stability · Thin-walled workpieces

1 Introduction

With the development of overall design concept of aircraft, the demand for high-performance materials such as titanium alloys continues to increase. Especially for some new fighters, titanium alloys are used in large quantities as high as 41% [1]. In

the field of advanced aviation manufacturing, the machining accuracy of titanium alloy thin-walled workpiece affects the service performance of aircrafts directly [2]. However, the processing chatter caused by its weak stiffness property damages the machined surface quality and results in poor geometrical accuracy inevitably [3]. Apart from this, unstable milling environment is easy to bring about the machining deformation [4]. Therefore, the chatter problem of thin-walled parts has always been the focus of scholars. The existing research on vibration control of thin-walled workpiece milling involves two types mainly such as chatter avoidance and stability improvement [5].

In terms of the chatter avoidance, the stability lobe diagrams (SLDs) and online chatter detection are common methods. The former accomplishes offline predication while the later could conduct online dynamic recognition and adjustment. For example, Altintas et al. [6] presented a zero order approximation way (ZOA) which was widely applied to obtain milling SLDs. Nevertheless, this method has difficulty to predict chatter stability boundary with little radial cutting depth accurately. The semi-discrete method (SDM) proposed by Insperger and Stepan [7] and second order full-discretization method (FDM) presented by Ding et al [8] solve this problem successfully. They have the advantage of high simulation precision and serve the important avenues to obtain SLDs of thin-walled workpiece. In addition, Wan et al [9] researched the SLDs construction mechanism of low stiffness machining system from the perspective of multiple modes and delays. Qu et al [10] established a stability analysis model for thin-walled workpieces through assuming the tool as rigid body. According to tool position variation in the milling process, the three-dimensional SLDs were obtained. Yang et al [11] found that the machining dynamic characteristic of thin-walled curved surface workpieces was related to tool length, machining position and material removal which were important factors affecting the milling stability. Gao et al [12] provided an online chatter detection approach based on continuous wavelet transform of acoustic signals in thin-walled component milling process. And the accuracy of this method was proved by the experimental results effectively. However, the above methods avoid milling chatter by reducing machining parameters and sacrificing processing efficiency.

Therefore, the stability improvement viewed as an alternative way is employed to solve milling chatter problem. For instance, Budak et al [13] held view that the machining stability could be enhanced by optimizing system design parameters and operational parameters. Wan et al [14] presented an idea that the dynamic characteristic of thin-walled workpiece could be strengthened by putting additional masses on it. As a result, the milling stability was improved apparently. A new type of vibration controller acted on workpieces was developed by Smis [15]. It could restrict machining vibration through adjusting its own stiffness and damping. Yang et al. [16] improved machining stability region through designing a device. It could generate forces to counteract processing vibration. Bolsunovsky et al [17] presented a tuned mass damper to suppress milling chatter. These approaches mentioned above have achieved very good effect on chatter control of thin-walled workpiece. Nevertheless, most studies have failed to provide accurate SLDs for guiding actual production. And they have difficulty to improve the difficult-to-machine circumstances of titanium alloys thin-walled workpieces induced by its material property and structure feature. Titanium alloys milling is restricted to low spindle speed and little feed rate because of high cutting temperature and large cutting force.

Currently, ultrasonic vibration cutting technology is widely applied for processing difficult-to-machine materials since it has the advantage of reducing milling force [18, 19], improving machined surface quality [20, 21] and strengthening structure stiffness [22]. Therefore, it is used to suppress milling chatter of titanium alloy thin-walled workpieces in this paper. Compared with the conventional milling, it achieves the pulsed intermittent cutting with tool-chip separation by adding an ultrasonic vibration signal to the cutter (or workpiece) [23, 24]. For the case of vibration acted on the tool (VAT), it's difficult to design an ultrasonic device since this equipment is mounted on the spindle rotating in processing [25]. Thereby, the majority of studies about ultrasonic milling are based on the vibration of workpiece (VOW) which is droved by the ultrasonic vibration workbench [26]. Nevertheless, VOW restricts the size and weight of workpieces greatly. Especially for large aerospace parts, the working space of table and transducer load are hard to meet the processing requirements. Thus,

its application is limited in the aviation industry. In this study, to avoid this problem, the ultrasonic vibration acts on the milling cutter called rotary ultrasonic milling (RUM). The published literatures [27-29] about the chatter stability focus on ultrasonic vibration milling with absolute separation of the tool and workpiece mainly. In this condition, the discontinuous feature of dynamic milling force contributes to the improvement of milling stability [30]. However, for the RUM with single axial ultrasonic vibration, it is difficult to make the cutter and workpiece separate completely during milling. As a result, the milling forces are continuous. Previous chatter stability models based on cutting separation effect are no longer suitable for RUM with non-separation characteristic. Therefore, in this paper, a novel stability analysis method is proposed for RUM thin-walled workpiece (RUM-tww). The effectiveness and accuracy of stability boundary obtained by SDM are proved by conducting RUM titanium alloy webs experiments.

2 Motion characteristics of RUM-tww

On the basis of common milling thin-walled workpiece (CM-tww), RUM-tww is added with a micron-level vibration effect along the axial direction of milling cutter. As shown in the Fig.1 (a), the high frequency ultrasonic vibration causes intermittent contact between the bottom of cutter and machined surface of workpiece. It affects the material removal inevitably by changing tool kinematic laws. Thus, motion analysis is the basis and premise of constructing RUM-tww stability model.

2.1 Movement trajectory and velocity analysis

As presented in Fig.1 (a) and (b), the point P is the any point on the cutting edge. H_0 denotes the height of OP from the tool bottom (mm). O_t is coordinate origin. Z -axis represents positive direction of ultrasonic vibration. Y -axis is perpendicular to the X -axis while the X -axis along the feed direction. Without loss of generality, the point P is viewed as research object. The cutting movement is composed of axial ultrasonic vibration (V_v), circumferential rotation (V_c) and horizontal feed (V_f). Its motion trajectory can be expressed as:

$$\begin{cases} \zeta_x(t) = R \cos(\omega t) + V_f t \\ \zeta_y(t) = R \sin(\omega t) \\ \zeta_z(t) = H_0 + (S / 1000) \sin(2\pi f_v t) \end{cases} \quad (1)$$

Where $\zeta_x(t)$, $\zeta_y(t)$ and $\zeta_z(t)$ are the track coordinates; R represents the tool radius (mm); ω is the angular velocity (rad/s); t is the time (s); S represents the ultrasonic amplitude (μm); f_v is ultrasonic vibration frequency (Hz).

By differentiating the expression of $\zeta_z(t)$, the ultrasonic vibration velocity (V_v) can be written as:

$$V_v = 2\pi f_v \cdot (S / 1000) \cdot \cos(2\pi f_v t) \quad (2)$$

Fig.1(c) describes the rate variation of RUM in single ultrasonic vibration period. Meantime, a new coordinate system is established based on the point P . The direction of Z_A -axis is same as the Z -axis. The X_R -axis indicates OP direction while the Y_C -axis represents the direction of cutting speed (V_c). The feed rate (V_f) is decomposed into X_R and Y_C direction. They could be written as:

$$V_{XR} = V_f \cdot \sin(\varphi_j) \quad (3)$$

$$V_{YC} = V_f \cdot \cos(\varphi_j) \quad (4)$$

Among them, the V_{YC} is much smaller than cutting speed (V_c). Thus, it could be ignored. In this study, φ_j denotes the radial immersion angle of tooth j . By considering the tool helix angle (λ), it can be expressed as:

$$\varphi_j = (2\pi n / 60) \cdot t + 2\pi(j-1) / N_z - [a_p / (2R)] \cdot \tan \lambda \quad (5)$$

Where n denotes the spindle speed; N_z is tooth number of milling cutter; a_p is axial cutting depth.

ultrasonic function angle (α) is defined according to above motion analysis. The parameter α denotes the angle between V_{Rv} and negative direction of Z_A -axis. In the plane Z_APX_R , it can be written as:

$$\alpha = \begin{cases} \arctan \left| \frac{V_{XR}}{V_v} \right|, & V_v \leq 0 \\ \pi - \arctan \left| \frac{V_{XR}}{V_v} \right|, & V_v > 0 \end{cases} \quad (6)$$

It's worth noting that the ultrasonic vibration is along the negative direction of Z_A -axis when $V_v < 0$. At this time, α is an acute angle; when $V_v > 0$, the tool vibrates in the positive direction of Z_A -axis. Then, α is an obtuse angle; when $V_v = 0$, α denotes right angle. As a result, the RUM turns into CM. The angle α varies with the time t in single ultrasonic vibration period. Thus, the axial ultrasonic vibration changes the direction of external excitation during RUM. It is very likely to affect the milling stability of thin-walled workpiece with low-stiffness.

3 Dynamic model of RUM-tww

During RUM-tww, the machine tools system could be assumed to be a rigid structure without occurring vibration. The stiffness of thin-walled workpiece is much smaller than machine tools generally. Modal property of the former occupies a dominant position on SLDs. In this study, the milling system of thin-walled workpiece is equivalent to a mass-spring-damping system as shown in Fig.1 (a) and (b). Meantime, as presented in Fig.1 (c), the high-frequency vibration of tool changes external excitation direction of thin-walled workpiece continuously in single ultrasonic vibration period. Thereby, the milling force of Z -direction shouldn't be ignored. For RUM-tww, the dynamic differential equation with three degrees of freedom (3-DOF) can be defined as follows:

$$[M_w] \ddot{\chi} + [C_w] \dot{\chi} + [K_w] \chi = [dF_w] \quad (7)$$

Where M_w , C_w and K_w with dimensions being 3×3 are the physical mass, damping and stiffness matrices of thin-walled workpiece. χ and dF_w are the vectors of displacement and dynamic milling force, respectively.

3.1 Chip thickness model

For milling, the chip includes two parts such as the static thickness (h_s) and dynamic thickness (dh). Among them, the static chip thickness (h_s) can be defined as:

$$h_s = \frac{2\pi R \cdot V_f}{N_z \cdot V_c} \cdot \sin(\varphi_j) \quad (8)$$

In CM, the dynamic thickness ($dh_{c,j}$) of tooth j is usually measured along the tool radial direction (X_R) as shown in Fig.1 (d). It can be written as:

$$dh_{c,j} = \left[x_j(t) - x_j(t - T_{j-1}) \right] \cdot \sin(\varphi_j) + \left[y_j(t) - y_j(t - T_{j-1}) \right] \cdot \cos(\varphi_j) \quad (9)$$

Where $x_j(t) - x_j(t - T_{j-1})$ and $y_j(t) - y_j(t - T_{j-1})$ represent the dynamic displacement vectors. However, this characterization method of dynamic chip thickness cannot be simply used for RUM-tww since ultrasonic vibration effect changes the external excitation direction of thin-walled workpiece system. Thus, the dynamic chip thickness ($dh_{v,j}$) under the effect of ultrasonic vibration should be calculated along the radial velocity direction (V_{Rv}). By considering the Z -direction vibration, it can be defined in three-dimensional space as:

$$dh_{v,j} = dh_c \cdot \sin(\alpha) - \left[z_j(t) - z_j(t - T_{j-1}) \right] \cdot \cos(\alpha) \quad (10)$$

It's worth noting that $dh_{v,j}$ is smaller than $dh_{c,j}$ when the ultrasonic function angle α is an acute angle. While α becomes right angle, the $dh_{v,j}$ is equal to the $dh_{c,j}$. Otherwise, the $dh_{v,j}$ is larger than $dh_{c,j}$ if ultrasonic vibration is along the positive direction of Z_A -axial. In other words, the value of $dh_{v,j}$ varies within one ultrasonic vibration cycle continuously.

For RUM-tww, the total chip thickness ($Th_{v,j}$) can be written as:

$$Th_{v,j} = h_s + dh_{v,j} \quad (11)$$

3.2 Dynamic milling force model

In RUM-tww, the cutting force on the tooth j could be denoted by the radial milling force ($TF_{r,j}$), axial milling force ($TF_{a,j}$) and the tangential milling force ($TF_{t,j}$), which changes with the variety of ultrasonic vibration direction. Based on the exponential force model, they could be defined as:

$$\begin{bmatrix} TF_{r,j} \\ TF_{t,j} \\ TF_{a,j} \end{bmatrix} = \Psi(\varphi_j) \cdot \left\{ \begin{bmatrix} k_r \\ k_t \\ k_a \end{bmatrix} \cdot (Th_{v,j})^\gamma + \begin{bmatrix} k_{re} \\ k_{te} \\ k_{ae} \end{bmatrix} \right\} \cdot [a_p + (S/1000) \cdot s_v] \quad (12)$$

Among them, $s_v = \sin(2\pi f_v t)$; the parameters k_r , k_t and k_a are average shear force coefficients while the k_{re} , k_{te} and k_{ae} represent average plowing force coefficients; γ is exponential constant; $\Psi(\varphi_j)$ is a window function, and its value range is 0 or 1[6].

Based on the literature [31], total milling force with ultrasonic vibration ($TF_{v,j}$) in the Eq. (12) could be linearized at $\chi=0$ as:

$$TF_{v,j} = TF_{v,j}(\chi=0) + dF_{v,j} \quad (13)$$

Among them, $TF_{v,j}(\chi=0)$ represents the static cutting force without chatter occurrence while the $dF_{v,j}$ is the dynamic milling force causing instability phenomenon. In this study, the $dF_{v,j}$ could be calculated by the Eq. (13) as:

$$\begin{bmatrix} dF_{r,j} \\ dF_{t,j} \\ dF_{a,j} \end{bmatrix} = \Psi(\varphi_j) \cdot \left\{ \begin{bmatrix} k_r \\ k_t \\ k_a \end{bmatrix} \cdot [a_p + (S/1000) \cdot s_v] \cdot \gamma \cdot (Th_{v,j})^{\gamma-1} \cdot (dh_{v,j}) \right\} \quad (14)$$

Obviously, the plowing force coefficients (k_{re} , k_{te} and k_{ae}) are eliminated after the formula transformation.

According to the geometric relationship of dynamic milling force presented in Fig. 1(e), the dynamic milling force of tooth j ($dF_{x,j}$, $dF_{y,j}$ and $dF_{z,j}$) could be obtained by projecting the forces ($dF_{r,j}$, $dF_{t,j}$ and $dF_{a,j}$) to X , Y and Z direction, respectively. They satisfy the following matrix transformation as:

$$\begin{bmatrix} dF_{x,j} \\ dF_{y,j} \\ dF_{z,j} \end{bmatrix} = \begin{bmatrix} -\sin(\varphi_j) \cdot \sin \alpha & -\cos(\varphi_j) & -\sin(\varphi_j) \cdot \cos \alpha \\ -\cos(\varphi_j) \cdot \sin \alpha & \sin(\varphi_j) & -\cos(\varphi_j) \cdot \cos \alpha \\ -\cos \alpha & 0 & \sin \alpha \end{bmatrix} \cdot \begin{bmatrix} dF_{r,j} \\ dF_{t,j} \\ dF_{a,j} \end{bmatrix} \quad (15)$$

Then, by taking the Eq. (14) into Eq. (15) and summing the dynamic milling forces of all teeth continuously, the total dynamic milling forces under the X , Y and Z direction could be written as:

$$\begin{bmatrix} dF_x \\ dF_y \\ dF_z \end{bmatrix} = a_p \cdot A_I(t) \cdot \{\chi\} + S \cdot A_2(t) \cdot \{\chi\} \quad (16)$$

Among them, the matrixes $A_I(t)$ and $A_2(t)$ satisfy the relationship as $A_2(t) = S_v \cdot A_I(t)$. And $A_I(t)_{3 \times 3}$ can be expressed as:

$$A_I(t) = \begin{bmatrix} a_{xx} & a_{xy} & a_{xz} \\ a_{yx} & a_{yy} & a_{yz} \\ a_{zx} & a_{zy} & a_{zz} \end{bmatrix} \quad (17)$$

Where

$$\begin{aligned} a_{xx} &= \sum_{j=1}^{N_z} \Psi(\varphi_j) \cdot \gamma \cdot (h_s)^{\gamma-1} \cdot (-s's'') \cdot (k_r \cdot s's'' + K_t \cdot c' + k_a \cdot s'c'') \\ a_{xy} &= \sum_{j=1}^{N_z} \Psi(\varphi_j) \cdot \gamma \cdot (h_s)^{\gamma-1} \cdot (-c's'') \cdot (k_r \cdot s's'' + K_t \cdot c' + k_a \cdot s'c'') \\ a_{xz} &= \sum_{j=1}^{N_z} \Psi(\varphi_j) \cdot \gamma \cdot (h_s)^{\gamma-1} \cdot c'' \cdot (k_r \cdot s's'' + K_t \cdot c' + k_a \cdot s'c'') \\ a_{yx} &= \sum_{j=1}^{N_z} \Psi(\varphi_j) \cdot \gamma \cdot (h_s)^{\gamma-1} \cdot (-s's'') \cdot (k_r \cdot c's'' - k_t \cdot s' + k_a \cdot c'c'') \\ a_{yy} &= \sum_{j=1}^{N_z} \Psi(\varphi_j) \cdot \gamma \cdot (h_s)^{\gamma-1} \cdot (-c's'') \cdot (k_r \cdot c's'' - k_t \cdot s' + k_a \cdot c'c'') \\ a_{yz} &= \sum_{j=1}^{N_z} \Psi(\varphi_j) \cdot \gamma \cdot (h_s)^{\gamma-1} \cdot c'' \cdot (k_r \cdot c's'' - k_t \cdot s' + k_a \cdot c'c'') \\ a_{zx} &= \sum_{j=1}^{N_z} \Psi(\varphi_j) \cdot \gamma \cdot (h_s)^{\gamma-1} \cdot (-s's'') \cdot (k_r \cdot c'' - k_a \cdot s'') \\ a_{zy} &= \sum_{j=1}^{N_z} \Psi(\varphi_j) \cdot \gamma \cdot (h_s)^{\gamma-1} \cdot (-c's'') \cdot (k_r \cdot c'' - k_a \cdot s'') \\ a_{zz} &= \sum_{j=1}^{N_z} \Psi(\varphi_j) \cdot \gamma \cdot (h_s)^{\gamma-1} \cdot c'' \cdot (k_r \cdot c'' - k_a \cdot s'') \end{aligned}$$

4 Stability analysis by SDM

4.1 Dynamic expressions of RUM-tww system

During RUM-tww, cutting chatter is usually caused by the displacement feedback. At present, the SDM [7] viewed as an effective means is widely applied for solving SLDs. Due to the effect of ultrasonic vibration, its dynamic expressions should be sorted into delay differential equations with 3-DOF:

$$\begin{bmatrix} \ddot{x}(t) \\ \ddot{y}(t) \\ \ddot{z}(t) \end{bmatrix} + H_W \begin{bmatrix} \dot{x}(t) \\ \dot{y}(t) \\ \dot{z}(t) \end{bmatrix} + B_W \begin{bmatrix} x(t) \\ y(t) \\ z(t) \end{bmatrix} = E_W \begin{bmatrix} x(t-\tau)_i \\ y(t-\tau)_i \\ z(t-\tau)_i \end{bmatrix} \quad (18)$$

Where i denotes the i th time interval; $x(t-\tau)_i$, $y(t-\tau)_i$ and $z(t-\tau)_i$ represent the delay differential terms of X , Y and Z directions, respectively; H_W , B_W and E_W are all three by three matrixes. By considering the modal property of thin-walled workpiece system such as relative damping (ξ_{nx} , ξ_{ny} and ξ_{nz}), the angular natural frequency (ω_{nx} , ω_{ny} and ω_{nz}) and the modal mass (m_{tx} , m_{ty} and m_{tz}), they could be expressed as:

$$H_W = \begin{bmatrix} 2\xi_{nx}\omega_{nx} & 0 & 0 \\ 0 & 2\xi_{ny}\omega_{ny} & 0 \\ 0 & 0 & 2\xi_{nz}\omega_{nz} \end{bmatrix}$$

$$E_W = (a_p + S \cdot s_v) \cdot \begin{bmatrix} \frac{\alpha_{xx}}{m_{tx}} & \frac{\alpha_{xy}}{m_{tx}} & \frac{\alpha_{xz}}{m_{tx}} \\ \frac{\alpha_{yx}}{m_{ty}} & \frac{\alpha_{yy}}{m_{ty}} & \frac{\alpha_{yz}}{m_{ty}} \\ \frac{\alpha_{zx}}{m_{tz}} & \frac{\alpha_{zy}}{m_{tz}} & \frac{\alpha_{zz}}{m_{tz}} \end{bmatrix}$$

$$B_W = \begin{bmatrix} \omega_{nx}^2 + \frac{(a_p + S \cdot s_v) \cdot \alpha_{xx}}{m_{tx}} & \frac{(a_p + S \cdot s_v) \cdot \alpha_{xy}}{m_{tx}} & \frac{(a_p + S \cdot s_v) \cdot \alpha_{xz}}{m_{tx}} \\ \frac{(a_p + S \cdot s_v) \cdot \alpha_{yx}}{m_{ty}} & \omega_{ny}^2 + \frac{(a_p + S \cdot s_v) \cdot \alpha_{yy}}{m_{ty}} & \frac{(a_p + S \cdot s_v) \cdot \alpha_{yz}}{m_{ty}} \\ \frac{(a_p + S \cdot s_v) \cdot \alpha_{zx}}{m_{tz}} & \frac{(a_p + S \cdot s_v) \cdot \alpha_{zy}}{m_{tz}} & \omega_{nz}^2 + \frac{(a_p + S \cdot s_v) \cdot \alpha_{zz}}{m_{tz}} \end{bmatrix}$$

4.2 SDM and stability limit calculations

Firstly, the Eq. (18) can be further expressed as first-order differential form by Cauchy transformation:

$$\dot{\mathbf{q}}_W(t) = \mathbf{U}_W(t) \cdot \mathbf{q}_W(t) + \mathbf{V}_W(t) \cdot \mathbf{q}_W(t - \tau) \quad (19)$$

Where $\mathbf{q}_W$ denotes the coordinates x , y and z ; $\mathbf{U}_W(t)$ and $\mathbf{V}_W(t)$ are periodic matrices determined by the dynamic milling force. They can be displayed as:

$$\mathbf{U}_W(t) = \begin{bmatrix} 0 & \mathbf{I} \\ -\mathbf{B}_W & -\mathbf{H}_W \end{bmatrix}$$

$$\mathbf{V}_W(t) = \begin{bmatrix} 0 & 0 \\ \mathbf{E}_W & 0 \end{bmatrix}$$

Among them, $\mathbf{I}$ represents the unit matrix.

The delay time τ could be divided into k discrete time intervals Δt , and satisfy $\tau = k\Delta t$. Based on the research of Insperger and Stepanas [7], a coefficient matrix $\mathbf{D}_i$ is written as:

$$\mathbf{D}_i = \begin{bmatrix} P_D & 0 & R_{Da} & R_{Db} \\ G & 0 & 0 & 0 \\ 0 & \mathbf{I} & 0 & 0 \\ 0 & 0 & \mathbf{I} & 0 \end{bmatrix} \quad (20)$$

Among them,

$$P_D = \begin{bmatrix} P_{i,11} & P_{i,12} & P_{i,13} & P_{i,14} & P_{i,15} & P_{i,16} \\ P_{i,21} & P_{i,22} & P_{i,23} & P_{i,24} & P_{i,25} & P_{i,26} \\ P_{31} & P_{i,32} & P_{i,33} & P_{i,34} & P_{i,35} & P_{i,36} \\ P_{i,41} & P_{i,42} & P_{i,43} & P_{i,44} & P_{i,45} & P_{i,46} \\ P_{i,51} & P_{i,52} & P_{i,53} & P_{i,54} & P_{i,55} & P_{i,56} \\ P_{i,61} & P_{i,62} & P_{i,63} & P_{i,64} & P_{i,65} & P_{i,66} \end{bmatrix} \text{ and } G_{(3 \times 6)} = [\mathbf{I} \quad 0]$$

$$R_{Da} = \begin{bmatrix} R_{i,11} & R_{i,12} & R_{i,13} \\ R_{i,21} & R_{i,22} & R_{i,23} \\ R_{i,31} & R_{i,32} & R_{i,33} \\ R_{i,41} & R_{i,42} & R_{i,43} \\ R_{i,51} & R_{i,52} & R_{i,53} \\ R_{i,61} & R_{i,62} & R_{i,63} \end{bmatrix} \text{ and } R_{Db} = \begin{bmatrix} R_{i,11} & R_{i,12} & R_{i,13} \\ R_{i,21} & R_{i,22} & R_{i,23} \\ R_{i,31} & R_{i,32} & R_{i,33} \\ R_{i,41} & R_{i,42} & R_{i,43} \\ R_{i,51} & R_{i,52} & R_{i,53} \\ R_{i,61} & R_{i,62} & R_{i,63} \end{bmatrix}$$

In this study, the $P_i = \exp(U_W \Delta t)$ and $R_i = 0.5 \cdot [\exp(U_W \Delta t) - I] \cdot (U_W)^{-1} V_W$.

By coupling Eq. (20) for $i = 0, 1, \dots, k-1$, the transition matrix Φ which reflects the cutting state characteristic could be expressed as:

$$\Phi = D_{k-1} D_{k-2} \cdots D_1 D_0 \quad (21)$$

RUM-tww system is stable when all the eigenvalues of matrix Φ in modulus are less than one. Otherwise, the machining system will lose stability under this processing condition. Based on this, the changing law of RUM-tww stability limits with spindle speed could be determined by inputting modal parameters and cutting force coefficients.

5 Stability lobes simulation and experimental verification

5.1 Thin-walled workpiece modes and milling force coefficients

In this study, milling experiments are conducted to verify the accurateness of SLDs achieved by the section 4. The thin-walled workpiece used for verification tests is titanium alloy web, which geometric size is 215mm×145mm×3mm as illustrated in Fig. 2. In terms of the difficult-to-machine material like titanium alloys, the processing parameters such as feed rate and cutting depth are usually very small. Meantime, the purpose of this paper is to clarify the inhibition mechanism of ultrasonic vibration energy on the milling chatter of titanium alloy thin-walled parts. Thereby, the influence of material removal and tool position variation on machining stability is ignored during RUM-tww titanium alloy webs. By taking the workpiece clamping method into consideration, the modal parameters of titanium alloy web presented in Fig. 2 could be acquired based on finite element analysis. The simulation results are as shown in Table.1.

Fig. 2 Schematic diagram of titanium alloy web workpiece

Table 1 Modal parameters of titanium alloy web

Modal frequency f_n (Hz)	Relative damping ξ_n (%)	Modal mass m_t (kg)	Workpiece stiffness K_W (N/mm)
338	2.13	0.327	1.47×10^6

The tool applied for RUM-tww is cemented carbide cutter with three teeth. Its parameters are presented in Table 2. Milling forces are measured by the Kistler 9257B 3-component dynamometer. Based on the cutting force data obtained by milling groove experiments of titanium alloy web, the average milling force coefficients with or without ultrasonic vibration could be calculated as shown in Table 3. In addition, Fig. 3 presents the processing site map. The RUM-tww system includes the machine center (MCV-L850), contactless rotary ultrasonic device and titanium alloy web. As shown in Fig. 3, the ultrasonic tool shank is mounted on the spindle of machining tool. Its working principle is that the electric signal generated by ultrasonic generator is transformed into ultrasonic tool shank by the contactless power transmission firstly. Then, regular mechanical vibration occurs under the effect of piezoelectric ceramic transducer. Furthermore, it can be enlarged by the amplitude transformer effectively. Finally, the stable and high-frequency vibration (20000Hz) with sine or cosine form appears at the end of the milling cutter. Meanwhile, the ultrasonic amplitude is controlled by ultrasonic current. The result measured by the Laser Vibrometer (Polytec, CLV2534) along three-coordinate direction shows that when the ultrasonic current is equal to 150 mA, the ultrasonic amplitude (S) reaches $10\mu\text{m}$ at the tool tip. At this time, the ultrasonic device works at its best state with the largest amplitude. In addition, the

RUM-tww is transformed into CM-tww when ultrasonic current is 0 mA.

Fig. 3 Experimental setup for stability verification

Table 2 Cutting tool parameters

Tool material	Number of teeth N_z	Tool diameter D (mm)	Tool helix angle β ($^\circ$)
cemented carbide	3	8	35

Table 3 Values of milling force coefficients

Coefficient	Value (RUM-tww/CM-tww)	Unit
K_t	1993/2143	N/mm ^{1+γ}
K_r	946/1049	N/mm ^{1+γ}
K_a	252/375	N/mm ^{1+γ}
γ	0.863/0.796	/

5.2 Stability lobe simulation results

On the basis of modal parameters and milling force coefficients, the SLDs of RUM-tww ($S=10\mu\text{m}$) and CM-tww ($S=0\mu\text{m}$) could be obtained by the MATLAB software as shown in Fig. 4. The milling type is set as up-milling along the X direction (feed rate 40mm/min and cutting width 4mm). The envelope area of SLDs could be obtained by the area recognition function in Origin8 software. The result demonstrates that the SLDs areas of RUM-tww and CM-tww are 923.44 and 512.12, respectively. It means that compared with CM-tww, the RUM-tww stability is improved by 80.32% within the spindle speed range (1000r/min to 5000r/min). There are two main reasons for this situation. On the one hand, the impact effect of high-frequency vibration (or

ultrasonic energy) makes the difficult-to-machining material around the cutting edge easier to be removed. On the other hand, the existence of ultrasonic function angle α may decrease dynamic milling force greatly by changing the external excitation direction of the workpiece. Therefore, the introduction of ultrasonic energy has good effect on improving stability of weak-stiffness thin-walled structure parts. It's worth noting that the RUM-tww stability lobe is shifted to the left compared with CM-tww in Fig. 4. As a result, the ultrasonic vibration machining occurs chatter while the common milling is at stable state under some processing parameters. The main reason lies in that the separation characteristic between the cutter and workpiece caused by high-frequency ultrasonic vibration changes the time delay presented in Eq. (18) dynamically. Hence, RUM-tww stability is worse than CM-tww in some machining parameters. And this offset phenomenon enables RUM-tww to obtain a greater depth of cut at a smaller spindle speed. This is another advantage for RUM-tww besides improving milling stability.

Fig. 4 Stability region comparison of RUM-tww and CM-tww

From the theoretical modeling of stability analysis, the ultrasonic function angle α reflects the effect of ultrasonic vibration. The smaller value α is, the better RUM-tww stability will be. Meantime, according to Eq. (6), the angle α increases with the rise of ultrasonic vibration amplitude (S) and frequency (f_v). Thus, the RUM-tww stability is positively related to S and f_v . As shown in Fig. 5, however, the SLDs has no obvious

extension when ultrasonic vibration frequency increases from 10000Hz to 30000Hz. This is due to that the increase ratio of f_v is not enough to cause a big change in α . Then, the effect of ultrasonic vibration frequency on RUM-tww stability is difficult to be reflected in Fig.5. For RRUM-tww with one-dimensional axial ultrasonic vibration, the S and f_v determine the improvement extent of processing stability jointly. Only slightly increasing one of the factors has weaker suppression effect for milling chatter of thin-walled workpieces.

Fig. 5 RUM-tww SLDs under different ultrasonic vibration frequencies

5.3 Experimental results for SLDs verification

In order to verify the accuracy and reasonableness of SLDs presented in Fig. 4, five groups of parameters in Table 4 are selected to carry out comparative experiments of RUM-tww and CM-tww. For the purpose of making the experimental plan as reasonable as possible, there are four situations. As shown in Fig. 4, the RUM-tww stability of group 1 and group 3 is better than CM-tww, which is the opposite of group 4. The group 2 denotes that the processing methods with or without ultrasonic vibration are at loss of stability while the group 5 is stable milling. After milling experiments, the surface chatter mark, surface cutter mark and surface flatness of the workpiece were investigated to prove the effectiveness and rationality of chatter stability boundary presented in Fig. 4. The final experimental results are shown in Table 4.

Table 4 Experimental results for stability verification

Point	Spindle speed (r/min)	Cutting depth (mm)	Milling state	
			CM-tww	RUM-tww
1	1500	0.1	Chatter	Stability
2	2000	0.3	Chatter	Chatter
3	3000	0.3	Chatter	Stability
4	3600	0.2	Stability	Chatter
5	4000	0.08	Stability	Stability

5.3.1 Surface chatter mark

In this study, the machined surface morphology of titanium alloy webs is measured by KEYENCE laser microscope (KEYENCE, VK-X 100 series). The experimental results for five group parameters with or without ultrasonic vibration are presented in Fig. 6. Among them, RUM1 represents the RUM-tww of point 1 while the CM1 is CM-tww (point 1), and so on. The areas marked by the yellow line are the obvious chatter mark patterns. It can be observed from the group 1 that CM-tww surface has obvious vibration marks. They can destroy the consistency of surface morphology and affect the quality of machined surface. On the contrast, the surface morphology produced by RUM-tww possesses very good consistency without chatter marks. It means that the high-frequency vibration and impact of tool could suppress milling chatter of titanium alloy thin-walled parts. It is consistent with the prediction results of point 1 in Fig. 4. In group 2, both RUM-tww and CM-tww show the apparent chatter marks under the experimental parameters of spindle speed 2000 r/min and cutting depth 0.3 mm. The experimental results are also same as the prediction results. In addition, the rest groups of verification experiments agree well with SLDs presented in Fig. 4. Therefore, the accuracy of stability boundary could be proved to some extent.

Fig. 6 Surface morphology diagrams of RUM-tww and CM-tww

5.3.2 Surface cutter mark

During milling, the cutter marks which may destroy machined surface consistency are usually formed by adjacent tool paths. Particularly, when machining chatter occurs, they are bound to be further deteriorated and result in the reduction of machined surface quality inevitably. Fig. 7 presents the cutter mark diagrams of RUM-tww and CM-tww. As shown in group 1 and 3, the addition of ultrasonic energy enhances the uniformity of surface morphology by making cutter marks unobvious. In group 2, the machined surfaces exist significant height differences on both sides of cutter mark. For RUM-tww and CM-tww in group 3, the machined surfaces own good quality. It's worth noting that the cutter mark with ultrasonic vibration is more obvious than CM-tww since the RUM-tww occurs chatter. The specific measurement results of cutter mark height are illustrated in Fig. 8. It can be found that all the cutter mark heights are more than $8\mu\text{m}$ on the groups with processing chatter. For the group 1 and group 3, the cutter mark heights formed by RUM-tww with stable machining are reduced by 43% compared with CM-tww. The above analysis about surface cutter mark verifies the effectiveness of stability region (in Fig. 4) further.

Fig. 7 Cutter mark diagrams of milling titanium alloy web

Fig. 8 Cutter mark height of machined surface

5.3.3 Machined surface flatness

Apart from chatter mark and cutter mark, the flatness is also an important index to evaluate milling surface quality. The milling force generated by severe chatter may cause machining deformation of thin-walled workpieces, which could lower the flatness of the machined surface. In this paper, the flatness of workpiece surface was obtained by the three-coordinate measuring instrument (RA-7525 SEI). And the measurement tests were carried out quickly after milling experiments in order to avoid the residual stress release causing deformation of the workpieces. As shown in Fig. 9, the workpiece was fixed on the table with double-sided tape. Two hundred points were uniformly measured on the machined surface and the flatness was calculated by the corresponding supporting software. The measurement results are shown in Fig. 10. The

smaller flatness value is, the better machined surface flatness will be. All the flatness data of experimental parameters with milling chatter are greater than 0.05, and the maximum value reaches 0.076. Meantime, the stable milling flatness is between 0.04 and 0.05. In addition, as presented in group 1 and group 3, the flatness of RUM-tww surface is significantly superior to CM-tww. This is due to that the ultrasonic vibration could reduce the deformation of titanium alloy web by restricting the milling vibration. The accuracy and effectiveness of SLDs presented in Fig. 4 are verified again.

Fig. 9 Flatness measurement of titanium alloy web

Fig. 10 Flatness of titanium alloy web

6 Conclusions

In this paper, the chatter stability of rotary ultrasonic milling titanium alloy web is investigated. Aiming at the weak stiffness characteristic of thin-walled workpiece, a novel stability analysis method is proposed for obtaining RUM-tww stability lobes. Meanwhile, the inhibition mechanism of ultrasonic vibration energy on milling chatter of thin-walled workpiece is clarified. Based on the stability simulation and experimental results, three conclusions can be summarized as follows:

(1) The introduction of ultrasonic vibration energy has the advantage of lowering dynamic milling force by changing the external excitation direction of the workpiece. As a result, RUM-tww stability region is improved by 80.32% than CM-tww within the spindle speed from 1000r/min to 5000r/min.

(2) Compared with CM-tww, RUM-tww can improve the surface morphology consistency of titanium alloy web by making chatter marks and cutter marks unobvious on the machined surface. In addition, the flatness of RUM-tww surface is also strengthened by ultrasonic vibration under stable milling condition.

(3) The rationality and accuracy of SLDs are proved effectively by RUM-tww and CM-tww experiments. They could be employed to guide the selection of suitable cutting parameters for thin-walled parts milling.

Declarations

Acknowledgments The authors would like to acknowledge Kedong Bi from southeast university for providing us with the three-coordinate measuring instrument (RA-7525 SEI).

Funding This work was supported by the Aviation Science Foundation of China (Grant No.20171659001); and the National Natural Science Foundation of China (Grant No. 91860132, No. 51861145405, No. 52075265).

Conflicts of interest/Competing interests The authors have no conflicts of interest to declare that are relevant to the content of this article.

Availability of data and material All data generated or analyzed during this study are included in this published article.

Code availability Not applicable

Authors' contributions Conceptualization: Kan Zheng, Wenhe Liao; theoretical analysis: Lianjun Sun; experiment and data analysis: Lianjun Sun; manuscript writing: Kan Zheng, Lianjun Sun; constructive discussions: Wenhe Liao, Kan Zheng. All authors have read and agreed to the published version of the manuscript.

Ethics approval Not applicable

Consent to participate Not applicable

Consent for publication Not applicable

References

- [1] Dhuria GK, Singh R, Batish A (2011) Ultrasonic machining of titanium and its alloys: A state of art review and future prospective. *Int J MMM* 10(4):326-355. <http://doi.10.1504/IJMMM.2011.043088>
- [2] Ding X, Chen TT, Yang YF, Li L (2016) Process optimization for milling deformation control of titanium alloy thin-walled web. *Materials science forum* 836-837:147-154. <http://doi.10.4028/www.scientific.net/MSF.836-837.147>
- [3] Sun LJ, Zheng K, Liao WH, Liu JS, Feng JD, Dong S (2020) Investigation on chatter stability of robotic rotary ultrasonic milling. *Rob Comput Inter Manuf* 63:101911. <https://doi.org/10.1016/j.rcim.2019.101911>
- [4] Singh KK, Kartik V, Singh R (2018) Stability modeling with dynamic run-out in high speed micromilling of Ti6Al4V. *Int J Mech Sci* 150:677–690. <https://doi.10.1016/j.ijmecsci.2018.11.001>
- [5] Yue CX, Gao HN, Liu XL, Liang SY, Wang LH (2019) A review of chatter vibration research in milling. *Chinese J Aeronaut* 32(2):215–242. <https://doi.10.1016/j.cja.2018.11.007>
- [6] Altintas Y, Budak E (1995) Analytical prediction of stability lobes in milling. *CIRP Ann* 44 (1): 357–362. [https://doi.10.1016/S0007-8506\(07\)62342-7](https://doi.10.1016/S0007-8506(07)62342-7)
- [7] Insperger T, Stepan G (2010) Updated semi-discretization method for periodic delay-differential equations with discrete delay. *Int J Numer Meth Eng* 61(1):117-141. <https://doi.10.1002/nme.1061>
- [8] Ding Y, Zhu LM, Zhang XJ, Ding H (2010) Second-order full-discretization method for milling stability prediction. *Int J Mach Tools Manuf* 50:926–932. <https://doi.10.1016/j.ijmachtools.2010.05.005>
- [9] Wan M, Ma YC, Zhang WH, Yang Y (2015) Study on the construction mechanism of stability lobes in milling process with multiple modes. *Int J Adv Manuf Technol* 79:589–603. <https://doi.10.1007/s00170-015-6829-4>
- [10] Qu S, Zhao JB, Wang TR (2016) Three-dimensional stability predication and chatter analysis in milling of thin-walled plate. *Int J Adv Manuf Technol* 86(5-8):2291-2300. <https://doi.10.1007/s00170-016-8357-2>
- [11] Yang Y, Zhang WH, Ma YC, Wan M (2016) Chatter prediction for the peripheral milling of

- thin-walled workpiece with curved surfaces. *Int J Mach Tools Manuf* 109:36-48. <https://doi.org/10.1016/j.ijmachtools.2016.07.002>
- [12] Gao J, Song QH, Liu ZQ (2018) Chatter detection and stability region acquisition in thin-walled workpiece milling based on CMWT. *Int J Adv Manuf Technol* 98:699–713. <https://doi.org/10.1007/s00170-018-2306-1>
- [13] Budak E, Erturk A, Ozguven HN (2007) Selection of design and operational parameters in spindle-holder-tool assemblies for maximum chatter stability by using a new analytical model. *Int J Mach Tools Manuf* 47:1401–1409. <https://doi.org/10.1016/j.ijmachtools.2006.08.016>
- [14] Wan M, Dang XB, Zhang WH, Yang Y (2018) Optimization and improvement of stable processing condition by attaching additional masses for milling of thin-walled workpiece. *Mech Syst Signal Pr* 103:196–215. <https://doi.org/10.1016/j.ymssp.2017.10.008>
- [15] Smis N (2007) Vibration absorbers for chatter suppression: A new analytical tuning methodology. *J Sound Vib* 301:3-5. <https://doi.org/10.1016/j.jsv.2006.10.020>
- [16] Yang YQ, Xu DD, Liu Q (2015) Vibration suppression of thin-walled workpiece machining based on electromagnetic induction. *Mater Manuf Process* 30(7):829-835. <https://doi.org/10.1080/10426914.2014.962042>
- [17] Bolsunovsky S, Vermel V, Gubanov G, Leontiev A (2013) Reduction of flexible workpiece vibrations with dynamic support realized as tuned mass damper. *Procedia CIRP* 8:230–234. <https://doi.org/10.1016/j.procir.2013.06.094>
- [18] Niu Y, Jiao F, Zhao B, Gao GF (2019) Investigation of cutting force in longitudinal-torsional ultrasonic-assisted milling of Ti-6Al-4V. *materials* 12:1955. <https://doi.org/10.3390/ma12121955>
- [19] Peng ZL, Zhang DY, Zhang XY (2020) Chatter stability and precision during high-speed ultrasonic vibration cutting of a thin-walled titanium cylinder. *Chinese J Aeronaut.* <https://doi.org/10.1016/j.cja.2020.02.011>
- [20] Tong JL, Wei G, Zhao L, Wang XL, Ma JJ (2019) Surface microstructure of titanium alloy thin-walled parts at ultrasonic vibration-assisted milling. *Int J Adv Manuf Technol* 101:1007-1021. <https://doi.org/10.1007/s00170-018-3005-7>
- [21] Chen P, Tong JL, Zhao JS, Zhang ZM, Zhao B (2020) A study of the surface microstructure and tool wear of titanium alloys after ultrasonic longitudinal-torsional milling. *J Manuf Process* 53:1-11. <https://doi.org/10.1016/j.jmapro.2020.01.040>

- [22] Wu CJ, Chen SJ, Cheng K, Xiao CW (2020) Investigation of strengthening effect on the machining rigidity in longitudinal torsional ultrasonic milling of thin-plate structures. *Proc IMechE Part B: J Engineering Manufacture* 234(3):665-670. <https://doi.10.1177/0954405419875346>
- [23] Ko JH, Tan SW (2013) Chatter marks reduction in meso-scale milling through ultrasonic vibration assistance parallel to tooling's axis. *Int J Precis Eng Man* 14(1):17-22. <https://doi.10.1007/s12541-013-0003-4>
- [24] Verma GC, Pandey PM, Dixit US (2018) Modeling of static machining force in axial ultrasonic-vibration assisted milling considering acoustic softening. *Int J Mech Sci* 136:1–16. <https://doi.10.1016/j.ijmecsci.2017.11.048>
- [25] Xu WX, Zhang LC (2015) Ultrasonic vibration-assisted machining: principle, design and application. *Adv Manuf* 3(3):173-192. <https://doi.10.1007/s40436-015-0115-4>
- [26] Ni CB, Zhu LD, Liu CF, Yang ZC (2018) Analytical modeling of tool-workpiece contact rate and experimental study in ultrasonic vibration-assisted milling of Ti-6Al-4V. *Int J Mech Sci* 142: 97–111. <https://doi.10.1016/j.ijmecsci.2018.04.037>
- [27] Zhang YM, Zhao B, Wang YQ, Chen F (2017) Effect of machining parameters on the stability of separated and unseparated ultrasonic vibration of feed direction assisted milling. *J Mech Sci Technol* 31(2):851-858. <https://doi.10.1007/s12206-017-0137-x>
- [28] Wan SK, Jin XL, Maroju NK, Hong J (2019) Effect of vibration assistance on chatter stability in milling. *Int J Mach Tools Manuf* 145:103432. <https://doi.10.1016/j.ijmachtools>
- [29] Gao J, Altintas Y (2020) Chatter stability of synchronized elliptical vibration assisted milling. *CIRP J Manuf Sci Tec* 28:76–86. <https://doi.10.1016/j.cirpj.2019.11.006>
- [30] Tabatabaei SMK, Behbahani S, Mirian SM (2013) Analysis of ultrasonic assisted machining (UAM) on regenerative chatter in turning. *J Mater Process Tech* 213:418-425. <https://doi.10.1016/j.jmatprotec.2012.09.018>
- [31] Faassen RPH, van de Wouw N, Oosterling JAJ, Nijmeijer H (2003) Prediction of regenerative chatter by modelling and analysis of high-speed milling. *Int J Mach Tools Manuf* 43:1437-1446. [https://doi.10.1016/S0890-6955\(03\)00171-8](https://doi.10.1016/S0890-6955(03)00171-8)

Figures

Figure 1

3-DOF stability model of RUM-tww, a Front view of milling process, b Top view of milling process, c Velocity analysis, d dynamic chip thickness, e dynamic milling force

Figure 2

Schematic diagram of titanium alloy web workpiece

Figure 3

Experimental setup for stability verification

Figure 4

Stability region comparison of RUM-tww and CM-tww

Figure 5

RUM-tww SLDs under different ultrasonic vibration frequencies

Figure 6

Surface morphology diagrams of RUM-tww and CM-tww

Figure 7

Cutter mark diagrams of milling titanium alloy web

Figure 8

Cutter mark height of machined surface

Three-coordinate measuring instrument

Table

Titanium alloy web

Figure 9

Flatness measurement of titanium alloy web

Figure 10

Flatness of titanium alloy web