Decoupling between calorimetric and dynamical glass transitions in high-entropy metallic glasses

Jiang Jing

Tohoku University <https://orcid.org/0000-0002-8912-3896>

Zhen Lu

Institute of Physics, Chinese Academy of Sciences <https://orcid.org/0000-0002-6202-8709>

Jie Shen

Institute of Physics

Takeshi Wada

Tohoku University

Hidemi Kato (✉ hikato@imr.tohoku.ac.jp)

IMR, Tohoku University

Mingwei Chen

Johns Hopkins University

Article

Keywords: Solid-state Physics, Structurally Arrested State, Depressed Dynamical Glass Transition, High Configurational Entropy

Posted Date: February 15th, 2021

DOI: <https://doi.org/10.21203/rs.3.rs-164172/v1>

License: © ⓘ This work is licensed under a Creative Commons Attribution 4.0 International License.

[Read Full License](#)

Version of Record: A version of this preprint was published at Nature Communications on June 22nd, 2021. See the published version at <https://doi.org/10.1038/s41467-021-24093-w>.

Decoupling between calorimetric and dynamical glass transitions in high-entropy metallic glasses

Jing Jiang¹, Zhen Lu², Jie Shen^{3,4}, Takeshi Wada¹, Hidemi Kato^{1*} & Mingwei Chen^{2,5*}

¹Institute for Materials Research, Tohoku University, Sendai 980-8577, Japan

²Advanced Institute for Materials Research, Tohoku University, Sendai 980-8577,
Japan.

³Institute of Physics, Chinese Academy of Sciences, Beijing 100190, China

⁴School of Physical Sciences, University of Chinese Academy of Sciences, Beijing
100049, China

⁵Department of Materials Science and Engineering, Johns Hopkins University,
Baltimore, MD 21218, USA

Correspondence and requests for materials should be addressed to Hidemi Kato

(hikato@imr.tohoku.ac.jp) or to Mingwei Chen (mwchen@jhu.edu)

Abstract

Glass transition is one of the unresolved critical issues in solid-state physics and materials science, during which a viscous liquid is frozen into a solid or structurally arrested state. On account of the uniform arrested mechanism, the calorimetric glass transition temperature (T_g) always follows the same trend as the dynamical glass transition (or α -relaxation) temperature (T_α) determined by dynamic mechanical analysis (DMA). Here, we explored the correlations between the calorimetric and dynamical glass transitions of three prototypical high-entropy metallic glasses (HEMGs) systems. We found that the HEMGs present a depressed dynamical glass transition phenomenon, i.e. HEMGs with moderate calorimetric T_g represent the highest T_α and the maximum activation energy. These decoupled glass transitions from thermal and mechanical measurements reveal the effect of high configurational entropy on the structure and dynamics of supercooled liquids and metallic glasses, which are associated with sluggish diffusion and decreased dynamic and spatial heterogeneities from high mixing entropy. The results have important implications in understanding the entropy effect on the structure and properties of metallic glasses for designing new materials with plenteous physical and mechanical performances.

Metallic glass (MG), or, vitrified metal, is formed by rapidly quenching a liquid melt to bypass the crystallization process, and finally yields a configuration frozen state on a laboratory timescale¹⁻⁵. Owing to the disordered atomic structures and out-of-equilibrium states, MGs exhibit unique and divergent thermodynamic and dynamic characteristics, especially when approaching the glass transition temperature (T_g)^{3,6,7}. Conventionally, calorimetric T_g is defined as the temperature at which the specific heat has an abrupt jump and is commonly determined by calorimetric or thermal mechanical approaches^{8,9,10}. From a dynamical relaxation perspective, diverse relaxation responses emerge with increasing temperature, from local reversible β -relaxation to global α -relaxation or a dynamic glass transition accompanied by the activation and subsequent percolation of shear transformation zones (STZs)¹¹⁻¹⁴. Generally, since the coincident fundamental mechanism of glass transitions, the calorimetric T_g follows a trend consistent with that of the dynamic α -relaxation temperature (T_α), in other words, MGs with high T_g always exhibit high T_α ¹⁵⁻¹⁸.

Conventionally, the traditional MGs design strategy is based on a principal element with adding of secondary and more elements around the eutectic points of the phase diagrams, which restrict the discovery of numerous combinations with unique and divergent physical and mechanical properties¹⁹⁻²¹. Recently, an intriguing alloying approach was developed to design new type of near-equiatomic solid solution metallic alloys, defined as multiple-principal-element alloys or high entropy alloys (HEAs), which breaks the conventional metallurgy development strategy, and exhibits great potential for developing advanced structural and functional materials²²⁻³². Owing to the equimolar concentration of each component, HEAs have distinctive physical and mechanical properties²⁶⁻³² arising from the effects of high configurational-entropy, large lattice-distortion and sluggish diffusion as well as the cocktail effect^{27,33}. Inheriting the distinct properties of MGs and HEAs, the new combinative glass-formed systems termed as “high entropy metallic glasses (HEMGs)” present high thermostabilities with depressed crystallization kinetics and superior magnetic properties, which reflect the theme of “more is different”³⁴⁻³⁶. However, the core critical behaviors of HEAs, especially the effect of sluggish diffusion on the

thermodynamic and dynamic properties of HEMGs have not been systematically studied.

In this study, we utilized the strategy of the equivalent substitution elements to design La(Ce)-based, Pd(Pt)-based and Ti(Zr)-based MGs and HEMGs, as the model systems to investigate the high entropy effect on the structure and dynamics of glass-forming alloys.

Results

Decoupling of calorimetric T_g and dynamical T_a . Three types of prototypical MGs, viz. $\text{La}_{55}\text{Ni}_{20}\text{Al}_{25}$ ($\text{Ce}_{55}\text{Ni}_{20}\text{Al}_{25}$), $\text{Pd}_{42.5}\text{Cu}_{30}\text{Ni}_{7.5}\text{P}_{20}$ ($\text{Pt}_{57.5}\text{Cu}_{14.7}\text{Ni}_{5.3}\text{P}_{22.5}$), and $\text{Zr}_{50}\text{Cu}_{20}\text{Ni}_{20}\text{Al}_{10}$ ($\text{Ti}_{50}\text{Cu}_{20}\text{Ni}_{20}\text{Al}_{10}$) with different relaxation behaviors were selected as model systems in this study. Correspondingly, $\text{La}_{27.5}\text{Ce}_{27.5}\text{Ni}_{20}\text{Al}_{25}$, $\text{Pd}_{20}\text{Pt}_{20}\text{Cu}_{20}\text{Ni}_{20}\text{P}_{20}$, and $\text{Ti}_{25}\text{Zr}_{25}\text{Cu}_{20}\text{Ni}_{20}\text{Al}_{10}$ HEMGs were obtained by the partial replacement of the primary elements in the MGs and are hereafter referred to as LaCe-HEMG, PdPt-HEMG, and TiZr-HEMG respectively. [Figure 1a](#) and [Supplementary Fig. 1](#) display the enthalpy of mixing ΔH_{AB}^{mix} (kJ/mol) values of the different atomic pairs in these representative MGs systems³⁷. The value of zero for ΔH_{AB}^{mix} of the La-Ce pair and similar values for La and Ce with Ni and Al suggest that elemental substitution caused negligible changes in terms of chemical effect on the relaxation behaviors³⁸. [Figure 1b](#) presents the entropy of mixing of the three MGs systems, calculated by $\Delta S_{mix} = -R \sum_{i=1}^n x_i \ln x_i$, where R is the gas constant and x_i is the mole fraction of the i^{th} element²⁷. The designed HEMGs yield values of ΔS_{mix} with $1.38R$, $1.67R$, and $1.57R$ for LaCe-HEMG, PdPt-HEMG, and TiZr-HEMG, respectively, are higher than the value generally defined as high entropy ($1.36R$)³³. Differential scanning calorimeter (DSC) traces of $\text{La}_{55}\text{Ni}_{20}\text{Al}_{25}$, $\text{Ce}_{55}\text{Ni}_{20}\text{Al}_{25}$, and LaCe-HEMG obtain at a heating rate of 20 K/min are shown in [Fig. 1c](#). The obvious glass transition and crystallization signals confirm the glassy state of the three samples. Calorimetric T_g is determined from the intersection of the tangent lines of the onset of transformation and is indicated by arrows ([Fig. 1c](#)). LaCe-HEMG with the highest ΔS_{mix} yields an intermediate T_g , with similar tendencies for PdPt-HEMG and

TiZr-HEMGs, which are consistent with the rule of mixture ([Supplementary Fig. 2a](#) and [Supplementary Fig. 3a](#))^{39,40}. The MGs exhibit multi-complex relaxation dynamics. The α -relaxation as the main relaxation mode is directly related to viscous flow and the glass transition^{3,41}. [Figure 1d](#) presents the temperature dependence of the loss modulus (G'') of La₅₅Ni₂₀Al₂₅, Ce₅₅Ni₂₀Al₂₅, and LaCe-HEMG at 1 Hz with a constant heating rate of 3 K/min (normalized by the maximum peak value). Two relaxation modes are clearly exhibited, which are termed the β -relaxation and α -relaxation, from the low to high temperatures, respectively. The β -relaxation peak shifts to high temperatures with Ce replaced by La, which agree with previous reports and suggests that activation of the β -relaxation mode follows a monotonous evolution according to the mean chemical affinity between the constituent elements^{16,38}. However, with half of La replaced by Ce, LaCe-HEMG exhibits the highest α -relaxation temperature (T_α), which is not synchronous with the calorimetric T_g ([Fig. 1c](#)). According to conventional wisdom, a glass with a higher calorimetric T_g always poses higher difficulty in activating α -relaxation and thus has a larger value of T_α ^{15,42}. Besides, T_α presents a monotonous tendency in the case of regular element substitution¹⁵ and follows the rule of mixture, the same as the calorimetric T_g . Nevertheless, LaCe-HEMG, with a modest thermodynamic devitrification behavior, exhibits the uppermost dynamic glass transition process (inset of [Fig. 1d](#)). Identical results were observed in the other two model MGs systems, viz. Pd(Pt)CuNiP and Ti(Zr)CuNiAl ([Supplementary Fig. 2b](#) and [Supplementary Fig. 3b](#)). Therefore, our findings indicate a decoupling between the calorimetric and dynamical glass transitions of HEMGs.

Fragility and viscosity of HEMGs. Fragility and viscosity are the most fundamental properties, reflecting the temperature-dependent relaxation and dynamic heterogeneity of glasses in supercooled liquid regions. Therefore, the divergent calorimetric and dynamical glass transition behaviors of the HEMGs are expected to be disclosed by fully understanding the kinetic behaviors near the glass transition. Fragility can be determined by the variation in T_g as a function of heating rate^{42,43}. [Figure 2a](#) shows the DSC traces with the heating rates ranging from 25 to 600 K/s for LaCe-HEMG. T_g and the crystallization temperature (T_x) shift to higher temperatures with the increase

of heating rate, which arises from the involvement of thermal activation in these kinetic processes. Figure 2b presents the heating rate dependence of T_g for La₅₅Ni₂₀Al₂₅, Ce₅₅Ni₂₀Al₂₅ and LaCe-HEMG. The particular average structural relaxation time, τ , can be obtained by $\tau = \frac{\Delta T_g}{q_H}$, where $\Delta T_g = T_g^{end} - T_g^{onset}$ is the width of the glass transition with a constant value of 30 K, and q_H is the cooling rate. Furthermore, τ can be well described by the Vogel-Fulcher-Tammann (VFT) equation⁴³:

$$\tau = \tau_{\infty} \exp \left(\frac{DT_0}{T - T_0} \right), \quad (1)$$

where τ_{∞} is the relaxation time at infinite temperature with a constant value of 1×10^{-14} s, T_0 is the VFT temperature, D is the fragility parameter and fragility $m = 16 + 590/D$ ⁴⁴. The m values for La₅₅Ni₂₀Al₂₅, Ce₅₅Ni₂₀Al₂₅, and LaCe-HEMG were calculated as 42, 39, and 35, respectively, by fitting the curves in Fig. 2b with Eq. (1). In comparison with other MGs, LaCe-HEMG exhibits a strong glass behavior in term of lowest fragility.

Figure 2c presents the nonequilibrium viscosity of the three MGs as a function of temperature, which was measured by thermomechanical analysis (TMA). As the temperature increases above T_g , the viscosity decreases rapidly. While, the viscosity of LaCe-HEMG is obviously higher than the others, suggesting the higher dynamic stability and more sluggish dynamic behavior upon heating. Therefore, a plausible origin of the retarded α -relaxation for LaCe-HEMG could be sluggish diffusion from the high entropy effect in HEAs.

Atomic structure. The relaxation behaviors of MGs are related to their spatial heterogeneity in the nanoscale domains^{12,45}. Figure 3a, d and g present high-resolution transmission electron microscope (HRTEM) images of LaCe-HEMG, La₅₅Ni₂₀Al₂₅, and Ce₅₅Ni₂₀Al₂₅, respectively. The homogeneous mazelike features and the diffraction halo in the selected area electron diffraction (SAED) patterns (inset in Fig. 3a, d and g) confirm the typical amorphous nature of the sample. Apparently, no clear atomic structural differences and phase separation could be identified in the three MGs down to the sub-nanoscale from the phase-contrast images. However, when

scanning transmission electron microscopy (STEM) analysis with a high-angle annular dark-field (HAADF) detector was performed to image the local atomic arrangements (Fig. 3b, e, and h), the HAADF-STEM images present obvious contrast variations with a domain sizes of several nanometers. It appears that the contrast variation of LaCe-HEMG is slightly ambiguous, together with a concomitant decrease in domain size. The averaged domain sizes, measured by a rotationally averaged fast Fourier transform method⁴⁶, correspond to feature lengths of 2.491 ± 0.297 , 2.380 ± 0.248 , and 1.851 ± 0.206 nm for $\text{La}_{55}\text{Ni}_{20}\text{Al}_{25}$, $\text{Ce}_{55}\text{Ni}_{20}\text{Al}_{25}$, and LaCe-HEMG, respectively (Supplementary Table 1). Accordingly, LaCe-HEMG with the highest value of ΔS_{mix} possesses the least contrast variation and the smallest domain size. Since the HAADF contrast indicates local element or density variations, energy dispersive spectroscopy (EDS) with a spatial resolution of ~ 3 Å was applied to further reveal the elemental distributions. As shown in Fig. 3f and i, $\text{La}_{55}\text{Ni}_{20}\text{Al}_{25}$ and $\text{Ce}_{55}\text{Ni}_{20}\text{Al}_{25}$ present obvious heterogeneous chemical variations with the sizes of ~ 3 nm, coinciding with the domain size. The dark regions in the HAADF images are enriched with Al and Ni while La or Ce separates from Al and Ni and generates the bright regions. However, La and Ce are nearly evenly distributed in LaCe-HEMG with weeny elemental variations, while evident chemical fluctuations of Al and Ni are still visible, as shown in Fig. 3c. Therefore, the contrast in the HAADF images is attributable to the nanoscale chemical fluctuation. HEMGs with higher T_α plausibly originate from these relatively inconspicuous chemical variations with less pronounced spatial contrast heterogeneity and sluggish diffusion, which may depress the dynamical relaxation behaviors near the glass transition.

Crystallization behavior. HEMGs with higher T_α suggest sluggish cooperative atomic movement in the moderately supercooled liquid states, which, in principle, should also influence the crystallization behavior. Figure 4a shows the XRD spectra of crystallized $\text{La}_{55}\text{Ni}_{20}\text{Al}_{25}$, $\text{Ce}_{55}\text{Ni}_{20}\text{Al}_{25}$ and LaCe-HEMG by heating to T_x of each alloy at a constant rate of 20 K/min and immediately cooled to room temperature. Significantly Bragg peaks emerge in the XRD profiles of $\text{La}_{55}\text{Ni}_{20}\text{Al}_{25}$ and

Ce₅₅Ni₂₀Al₂₅, indicating the appearance of obvious crystallization productions. In contrast, LaCe-HEMG still presents a broad amorphous halo superimposed with a few weak crystalline peaks, demonstrating that LaCe-HEMG is still composed of a large portion of amorphous phase and exhibits high resistance to crystallization. Figure 4b and c display the corresponding TEM images of crystallized La₅₅Ni₂₀Al₂₅ and Ce₅₅Ni₂₀Al₂₅, respectively, in which crystalline grains are widely emerged from the amorphous matrix with the size around 100 nm. In contrast, LaCe-HEMG presents few precipitates with a size of hundreds of nanometers in the amorphous matrix (Fig. 4d), which appears to be formed by heterogeneous crystallization. In addition, the SAED patterns of the three specimens still exhibit amorphous diffraction halos, suggesting the insufficient crystallization processes (the inset of Fig. 4b-d). Figure 4e shows the HRTEM image of the crystallization region for LaCe-HEMG, the large precipitate is comprised of nanocrystals with the average grain size of $\sim 8 \pm 1.7$ nm, which are embedded in the amorphous matrix and smaller than the crystallites in the crystallized La₅₅Ni₂₀Al₂₅ and Ce₅₅Ni₂₀Al₂₅ MGs (Supplementary Fig. 4 and Supplementary Table 1). It appears that HEMGs demonstrate a suppressed crystal nucleation and growth and, consequently, enhanced the thermal stability of the supercooled liquids.

Discussion

HEMGs exhibit retarded α -relaxation (dynamical glass transition) and distinct crystallization resistance, which might originate from the sluggish diffusion hypothesis on account of the effect of high mixing entropy. β -relaxation (or Johari-Goldstein relaxation) is considered the dynamical precursor of α -relaxation and plays a promising role in understanding the dynamical glass transition. The frequency dependence of β -relaxation evolution was explored by dynamic mechanical analysis (DMA) with an amplitude of 0.1% and testing frequency (f) ranging from 0.5 to 16 Hz (inset of Fig. 5a and Supplementary Fig. 5). Figure 5a shows the frequency dependence of the β -relaxation peak temperatures (Supplementary Fig. 5 for details) for La₅₅Ni₂₀Al₂₅, Ce₅₅Ni₂₀Al₂₅, and LaCe-HEMG fitted with the Arrhenius relation¹²,

$f = f_{\infty} \exp(-E_{\beta}/RT)$, where f_{∞} is the pre-factor and E_{β} is the activation energy of β -relaxation. E_{β} was calculated to be 93.9, 85.8, and 88.8 kJ/mol for $\text{La}_{55}\text{Ni}_{20}\text{Al}_{25}$, $\text{Ce}_{55}\text{Ni}_{20}\text{Al}_{25}$, and LaCe-HEMG , respectively. LaCe-HEMG exhibits moderate activation energy for β -relaxation which follows the same tendency as calorimetric T_g . Since β -relaxation only involves local atomic motion, the high entropy effect appears not to influence short-range atomic diffusion. Accordingly, the temperature-dependence of α -relaxation is shown in inset of Fig. 5b and Supplementary Fig. 6. The activation energy values of α -relaxation (E_{α}) (Fig. 5b) were determined to be 249.6, 229.8, and 267.6 kJ/mol for $\text{La}_{55}\text{Ni}_{20}\text{Al}_{25}$, $\text{Ce}_{55}\text{Ni}_{20}\text{Al}_{25}$, and LaCe-HEMG from the Arrhenius plot, $f = f_{\infty} \exp(-E_{\alpha}/RT)$. Remarkably, LaCe-HEMG shows the highest α -relaxation activation energy, suggesting that HEMGs have the highest energy barrier for the dynamical glass transition, and thus the highest T_{α} . Figure 5c and d show the Kissinger plots of T_g and T_x at different heating rates from the flash DSC traces (Fig. 2a). The measured activation energies for the calorimetric glass transition and crystallization are listed in Table 1. Again, LaCe-HEMG has an intermediate activation energy for the glass transition and the highest energy for crystallization, which is in line with the calorimetric T_g and crystallization behavior.

These structural characterization and dynamic measurements build up a comprehensive picture of the decoupling between the calorimetric T_g and DMA T_{α} of HEMG as illustrated in Fig. 6. HEMGs with nearly equimolar components and high configuration entropy, could suppress the dynamic heterogeneity in the supercooled liquid on account of the reduced Gibbs free energy, and then inherit to the glassy state with relatively small and homogeneous nanoscale domains (Figs. 3b and 6a)⁴⁷. These nanoscale spatial domains with an average size of ~ 2 nm are analogous to the size of STZs, and therefore might be associated with the structural origin of the β -relaxation process¹⁴ (Fig. 6b). Consequently, HEMGs with small nanoscale domains possess vibrant potential STZs on account of the favorable cooperative transition probability by “Adam-Gibbs” theory⁴⁸, with the minimum activation energy of β -relaxation (Fig.

5a and Table 1).

Furthermore, β -relaxation could be associated with the activation of isolated STZs, which are confined within the elastic matrix and do not involve long-range diffusion¹⁴. Therefore, the β -relaxation behavior of HEMGs is nearly unaffected by the sluggish diffusion effect. When the density and size of STZs reach a critical point with increasing temperature, their percolation of STZs contributes to distinct α -relaxation⁴⁹. Figure 6b and c illustrate the relationship between β -relaxation and α -relaxation based on the structural and energy perspective. In the α -relaxation process, the expansion and percolation correspond to an increased mismatch penalty between STZs, which relates to long-range cooperation rearrangement and elemental diffusion^{50,51} (Fig. 6b). Small STZs in HEMGs might expect to consume excess energy to reach a critical transition size^{50,51}, and subsequent percolation with long-range propagation could plausibly be suppressed by sluggish diffusion of HEMGs. Therefore, HEMGs with relatively homogeneous structures (Fig. 6a) inhibit large-scale atomic migration in the process of α -relaxation, resulting in delayed α -relaxation transition and elevated activation energy (Fig. 1d and Table 1). Analogously, the EDS mappings of crystallized MGs (Fig. 4f and Supplementary Fig. 4) verify a long-range diffusion and migration, suggesting that sluggish diffusion affects the crystallization behaviors of HEMGs and results in a higher activation energy (Figs. 5d, 6c and Table 1).

Besides relaxation, the calorimetric glass transition is accompanied by an increase in heat capacity with the generation of free volumes near T_g , which is not sensitive to the heterogeneous domain size¹⁰. Entropy might induce negligible effects on the thermal glass transition behaviors, which is consistent with the fact that, LaCe-HEMG presents the relatively low activation energy of calorimetric T_g (Fig. 5c and Table 1). Therefore, the calorimetric T_g could be mainly determined by local thermal diffusion and follow the rule of mixture characterized by a monotonous relationship with composition. Base on systematic examinations of calorimetric, the dynamical glass transitions and atomic structures, the high mixing entropy affects the glass transition and crystallization behaviors of HEMGs, as illustrated by the proposed energy

landscape ([Fig. 6c](#)). It is expected that these HEA ‘core effects’ will benefit studies on the fundamental issues, such as the glass transition, relaxations, and aging behaviors of MGs.

Methods

Sample preparation. Master alloys with the nominal atomic percent compositions of $\text{La}_{55}\text{Ni}_{20}\text{Al}_{25}$, $\text{Ce}_{55}\text{Ni}_{20}\text{Al}_{25}$, $\text{La}_{27.5}\text{Ce}_{27.5}\text{Ni}_{20}\text{Al}_{25}$, $\text{Pd}_{42.5}\text{Cu}_{30}\text{Ni}_{7.5}\text{P}_{20}$, $\text{Pt}_{57.5}\text{Cu}_{14.7}\text{Ni}_{5.3}\text{P}_{22.5}$, $\text{Pd}_{20}\text{Pt}_{20}\text{Cu}_{20}\text{Ni}_{20}\text{P}_{20}$, $\text{Zr}_{50}\text{Cu}_{20}\text{Ni}_{20}\text{Al}_{10}$, $\text{Ti}_{50}\text{Cu}_{20}\text{Ni}_{20}\text{Al}_{10}$, $\text{Ti}_{25}\text{Zr}_{25}\text{Cu}_{20}\text{Ni}_{20}\text{Al}_{10}$ were prepared by arc-melting mixtures of raw metals (purity > 99.9 mass %) in an Ar atmosphere purified with a Ti getter. Glassy ribbons (thickness around 50 μm) were produced by melt-spinning on to a single Cu wheel at 3000 r.p.m. using Ar gas overpressure. $\text{La}_{55}\text{Ni}_{20}\text{Al}_{25}$, $\text{Ce}_{55}\text{Ni}_{20}\text{Al}_{25}$ and $\text{La}_{27.5}\text{Ce}_{27.5}\text{Ni}_{20}\text{Al}_{25}$ glass ribbons were carefully polished to 5 μm by 4000# sandpaper for TEM specimens in advance. The final TEM specimens were prepared by ion milling (Gatan, PIPS II 695) with 3 kV and finally polished with low-voltage (0.5 kV) with a liquid-nitrogen-cooled stage.

Differential scanning calorimetry (DSC) measurements. The Perkin Elmer DSC 8500 was used to perform the thermodynamic transition process of the glassy ribbons with 20 mL/min flowing pure argon gas to prevent possible oxidation during heating. The values of glass-transition temperature T_g (Fig. 1) were determined using DSC at a constant heating rate of 0.33 K/s. Flash DSC (Mettler, Flash DSC 1) with wide heating rates was used to measure the glass transition and crystallization behaviors of $\text{La}_{55}\text{Ni}_{20}\text{Al}_{25}$, $\text{Ce}_{55}\text{Ni}_{20}\text{Al}_{25}$ and $\text{La}_{27.5}\text{Ce}_{27.5}\text{Ni}_{20}\text{Al}_{25}$ samples with the heating rates range from 25 K/s to 600 K/s. Tiny samples with dimensions of about 40 $\mu\text{m} \times 50 \mu\text{m} \times 6 \mu\text{m}$ were cut from a melt-spun ribbons. The samples were then loaded on the center of the Flash DSC sensor chip under an optical microscope. The sensor and the sample were protected from oxygen and moisture under a steady Ar flow of 20 mL/min during whole measurement.

Dynamic mechanical analysis (DMA). The RSA-G2 DMA (TA Instruments) was used to measure the loss and storage moduli of the MGs ribbons. The loss modulus show a sharp maximum near the glass transition temperature associated with α -relaxation. The broad maximum at lower temperature represents the β -relaxation. The α -relaxation temperature (T_a , Fig. 1) was determined by heating the glassy

ribbons from room temperature to over crystallization temperature at 1Hz with heating rate of 0.05 K/s. The frequency-dependence of β -relaxation evolution (Fig. 5) was explored by DMA with amplitude of 0.1% and testing frequency f ranging from 0.5 Hz to 16 Hz. The temperature-dependence of α -relaxation evolution (Fig. 5) explored by DMA with amplitude of 0.1% and testing temperature ranging near T_g .

Viscosity measurement. The thermomechanical analyzer Q400 TMA (TA Instruments) was used to measure the length change of glassy ribbon samples during heating in the argon fluxion atmosphere (20 mL/min). The measurement of viscosity in Fig. 2 was done with a heating rate of 0.33 K/min from room temperature to crystallization temperature with a contrast probe load of 0.1 N. The value of viscosity (η) was calculated from the flow stress by the equation $\eta = \frac{\sigma}{3\dot{\epsilon}}$, where σ is the stress and $\dot{\epsilon}$ is the strain rate¹.

X-rays diffraction. The phase transformation after annealing the glassy ribbons was characterized by RIGAKU Ultima IV X-Ray diffractometer with monochromatic Cu K_α radiation. The ribbons were heated to the onset temperature of crystallization followed by cooling down.

Transmission electron microscopy characterization. Microstructures of the specimens were characterized by a Cs-corrected TEM (JEM-2100F, JEOL, 200kV) equipped with double spherical aberration correctors for both the probe-forming and image-forming lenses. The high-resolution TEM images were captured by a television-rate camera (Gatan, UltraScan 1000), and the high-angle annular dark field (HAADF) images were recorded using an annular-type scanning TEM detector. Energy dispersive spectroscopy (EDS) mappings were acquire at STEM mode with a scan step of 3 Å for elemental analysis.

Data Availability. The data that support the findings of this study are available from the corresponding author upon reasonable request.

References

1. Ediger, M. D. & Harrowell, P. Perspective: Supercooled liquids and glasses. *J. Chem. Phys.* **137**, 080901-080915 (2012).
2. Ediger, M. D., Angell, C. A. & Nagel, S. R. Supercooled liquids and glasses. *J. Phys. Chem.* **100**, 13200-13212 (1996).
3. Debenedetti, P. G. & Stillinger, F. H. Supercooled liquids and the glass transition. *Nature* **410**, 259-267 (2001).
4. Chen, M. A brief overview of bulk metallic glasses. *NPG Asia Mater.* **3**, 82-90 (2011).
5. Berthier, L. & Biroli, G. Theoretical perspective on the glass transition and amorphous materials. *Rev. Mod. Phys.* **83**, 587-645 (2011).
6. Yu, H. B., Wang, W. H. & Samwer, K. The β relaxation in metallic glasses: an overview. *Mater. Today* **16**, 183-191 (2013).
7. Schuh, C. A., Hufnagel, T. C. & Ramamurty, U. Mechanical behavior of amorphous alloys. *Acta Mater.* **55**, 4067-4109 (2007).
8. Ito, K., Moynihan, C. T. & Angell, C. A. Thermodynamic determination of fragility in liquids and a fragile-to-strong liquid transition in water. *Nature* **398**, 492-495 (1999).
9. Martinez, L. M. & Angell, C. A. A thermodynamic connection to the fragility of glass-forming liquids. *Nature* **410**, 663-667 (2001).
10. Van den Beukel, A. & Sietsma, J. The glass transition as a free volume related kinetic phenomenon. *Acta Metall. Mater.* **38**, 383-389 (1990).
11. Demetriou, M.D., Harmon, J. S., Tao, M., Duan, G., Samwer, K. & Johnson, W. L. Cooperative shear model for the rheology of glass-forming metallic liquids. *Phys. Rev. Lett.* **97**, 065502 (2006).
12. Yu, H. B., Shen, X., Wang, Z., Gu, L., Wang, W. H. & Bai, H. Y. Tensile plasticity in metallic glasses with pronounced β relaxations. *Phys. Rev. Lett.* **108**, 015504 (2012).
13. Fan, Y., Iwashita, T. & Egami, T. Crossover from localized to cascade relaxations in metallic glasses. *Phys. Rev. Lett.* **115**, 045501 (2015).
14. Harmon, J. S., Demetriou, M. D., Johnson, W. L. & Samwer, K. Anelastic to plastic transition in metallic glass-forming liquids. *Phys. Rev. Lett.* **99**, 135502 (2007).
15. Yu, H. B., Wang, Z., Wang, W. H. & Bai, H. Y. Relation between β relaxation and fragility in LaCe-based metallic glasses. *J. Non-Cryst. Solids* **358**, 869-871 (2012).
16. Zhu, Z. G. *et al.* Compositional origin of unusual β -relaxation properties in La-Ni-Al metallic glasses. *J. Chem. Phys.* **141**, 084506 (2014).
17. Zhu, Z. G., Wang, Z. & Wang, W. H. Binary rare earth element-Ni/Co metallic glasses with distinct β -relaxation behaviors. *J. Appl. Phys.* **118**, 154902 (2015).
18. Yu, H. B., Wang, W. H., Bai, H. Y. & Samwer, K. The β -relaxation in metallic glasses. *Natl. Sci. Rev.* **1**, 429-461 (2014).
19. Wang, W. H., Dong, C. & Shek, C. H. Bulk metallic glasses. *Mater. Sci. Eng., R: Reports* **44**, 45-89 (2004).
20. Inoue, A., Zhang, T. & Masumoto, T. Al-La-Ni amorphous alloys with a wide supercooled liquid region. *Mater. Tran. JIM.* **30**, 965-972 (1989).
21. Inoue, A., Zhang, T. & Masumoto, T. Zr-Al-Ni Amorphous alloys with high glass transition temperature and significant supercooled liquid region. *Mater. Trans. JIM.* **31**, 177-183 (1990).

22. Yeh, J. W. *et al.* Nanostructured high-entropy alloys with multiple principal elements: novel alloy design concepts and outcomes. *Adv. Eng. Mater.* **6**(5), 299-303 (2004).
23. Chang, X., Zeng, M., Liu, K. & Fu, L. Phase engineering of high-entropy alloys. *Adv. Mater.* **32**, 1907226 (2020).
24. Yeh, J. W. Recent progress in high entropy alloys. *Ann. Chim. Sci. Mat.* **31**, 633-648 (2006).
25. Tsai, M. H. & Yeh, J. W. High-Entropy Alloys: A Critical Review. *Mater. Res. Lett.* **2**, 107-123 (2014).
26. Wei, S. *et al.* Natural-mixing guided design of refractory high-entropy alloys with as-cast tensile ductility. *Nat. Mater.* **19**, 1175-1181 (2020).
27. George, E. P., Raabe, D. & Ritchie, R. O. High-entropy alloys. *Nat. Rev. Mater.* **4**, 515-534 (2019).
28. Han, C., Fang, Q., Shi, Y., Tor, S. B., Chua, C. K. & Zhou K. Recent advances on high-entropy alloys for 3D printing. *Adv. Mater.* **32**, 1903855 (2020).
29. Li, W., Liaw, P. K. & Gao, Y. Fracture resistance of high entropy alloys: A review. *Intermetallics* **99**, 69-83 (2018).
30. Lei, Z. *et al.* Enhanced strength and ductility in a high-entropy alloy via ordered oxygen complexes. *Nature* **563**, 546-550 (2018).
31. Zhang, R. *et al.* Short-range order and its impact on the CrCoNi medium-entropy alloy. *Nature* **581**, 283-287 (2020).
32. Miracle, D. B. High entropy alloys as a bold step forward in alloy development. *Nat. Commun.* **10**, 1805 (2019).
33. Miracle, D. B. & Senkov, O. N. A critical review of high entropy alloys and related concepts. *Acta Mater.* **122**, 448-511 (2017).
34. Yang, M., Liu, X. J., Ruan, H. H., Wu, Y., Wang, H. & Lu, Z. P. High thermal stability and sluggish crystallization kinetics of high-entropy bulk metallic glasses. *J. Appl. Phys.* **119**, 245112 (2016).
35. Yang, M., Liu, X. J., Wu, Y., Wang, H., Wang, X. Z. & Lu, Z. P. Unusual relation between glass-forming ability and thermal stability of high-entropy bulk metallic glasses. *Mater. Res. Lett.* **6**, 495-500 (2018).
36. Sheng, W., Wang, J. Q., Wang, G., Huo, J., Wang, X. & Li, R. W. Amorphous microwires of high entropy alloys with large magnetocaloric effect. *Intermetallics* **96**, 79-83 (2018).
37. Takeuchi, A. & Inoue, A. Classification of bulk metallic glasses by atomic size difference, heat of mixing and period of constituent elements and its application to characterization of the main alloying element. *Mater. Trans.* **46**, 2817-2829 (2005).
38. Yu, H. B., Samwer, K., Wang, W. H. & Bai, H. Y. Chemical influence on β -relaxations and the formation of molecule-like metallic glasses. *Nat. Commun.* **4**, 2204 (2013).
39. Wang, W. H. The elastic properties, elastic models and elastic perspectives of metallic glasses. *Prog. Mater. Sci.* **57**, 487-656 (2012).
40. Wang, W. H. Elastic moduli and behaviors of metallic glasses. *J. Non-Cryst. Solids* **351**, 1481-1485 (2005).
41. Lunkenheimer, P., Schneider, U., Brand, R. & Loid, A. Glassy dynamics. *Contemp. Phys.* **41**, 15-36 (2000).
42. Cangialosi, D., Alegria, A. & Colmenero, J. Relationship between dynamics and thermodynamics in glass-forming polymers. *Europhys. Lett.* **70**, 614-620 (2005).

43. Evenson, Z., Gallino, I. & Busch, R. The effect of cooling rates on the apparent fragility of Zr-based bulk metallic glasses. *J. Appl. Phys.* **107**, 123529 (2010).
44. Bohmer, R., Ngai, K. L., Angell, C. A. & Plazek, D. J. Nonexponential relaxations in strong and fragile glass formers. *J. Chem. Phys.* **99**, 4201-4209 (1993).
45. Zhu, F. *et al.* Intrinsic correlation between β -relaxation and spatial heterogeneity in a metallic glass. *Nat. Commun.* **7**, 11516 (2016).
46. Takeshi, F. & Chen, M. W. Characteristic length scale of bicontinuous nanoporous structure by fast fourier transform. *J. Appl. Phys.* **47**, 1161 (2008).
47. Douglas, J. F., Dudowicz, J. & Freed, K. F. Does equilibrium polymerization describe the dynamic heterogeneity of glass-forming liquids? *J. Chem. Phys.* **125**, 144907 (2006)
48. Adam, G. & Gibbs, H. On the temperature dependence of cooperative relaxation properties in glass forming liquids. *J. Chem. Phys.* **43**, 139 (1965).
49. Wang, Z., Sun, B. A., Bai, H. Y. & Wang, W. H. Evolution of hidden localized flow during glass-to-liquid transition in metallic glass. *Nat. Commun.* **5**, 5823 (2014).
50. Kirkpatrick, T. R., Thirumalai, D. & Wolynes, P. G. Scaling concepts for the dynamics of viscous liquids near an ideal glassy state. *Phys. Rev. A* **40**, 1045 (1989).
51. Lubchenko, V. & Wolynes, P. G., Theory of structural glasses and supercooled liquids. *Annu. Rev. Phys. Chem.* **58**, 235-269 (2007).

Acknowledgements

This work was primarily supported by a Grant-in-Aid for Scientific Research on Innovative Areas “Science of New-Class of Materials Based on Elemental Multiplicity and Heterogeneity (Grant No. 18H05452)” from the ministry of education, culture, sports, science and technology (MEXT, Japan). And Grant-in-Aid for Scientific Research from the Japan Society for the Promotion of Science (JSPS) KAKENHI (Grant No. 20K15180). M. C. acknowledges the support of U.S. National Science Foundation under grant DMR-1804320.

Author contributions

J.J and Z.L conceived the research plan and designed experiments with valuable input from M.W.C and H.K. J.S prepared the La(Ce)NiAl system master ingots. J.J and Z.L performed the material synthesis and characterization. J.J, Z.L, T.W, M.W.C and H.K. analyzed data. J.J, Z.L, M.W.C wrote and revised the manuscript. All authors discussed the results and contributed feedback for manuscript. M.W.C and H.K. supervised all aspects of the project.

Additional information

Supplementary Information accompanies this paper at
<http://www.nature.com/Naturecommunications>

Competing interests: The authors declare no competing financial interests.

Reprints and permission information is available online at
<http://npg.nature.com/reprintsandpermissions/>

Figure 1 | The mixing of entropy, calorimetric and dynamical behaviors. (a) ΔH^{mix} (kJ/mol) for the constituting atomic pairs in the La(Ce)NiAl system. **(b)** Calculated mixing entropies for the three MGs systems. **(c)** DSC traces (heating rate of 20 K/min) of the La(Ce)NiAl system, the arrows indicate the calorimetric T_g . **(d)** Temperature dependence of the loss modulus of the LaCe MGs system at 1 Hz with a constant heating rate of 3 K/min, normalized by the maximum peak value. The arrows indicate the α -relaxation temperature (T_α), and the inset shows the evolution of T_g and T_α with the components.

Figure 2 | The fragility and viscosity behavior of the La(Ce)NiAl system. (a) DSC traces of LaCe-HEMG for heating rates ranging from 25 to 600 K/s. The left- and right- side arrows indicate T_g and T_x , respectively. (b) Heating rate dependence of T_g for the La(Ce)NiAl MG system and corresponding VFT fitting trace (dashed lines). (c) Non-equilibrium viscosity near the glass transition region for the La(Ce)NiAl MGs, measured with a constant heating rate of 0.33 K/s.

Figure 3 | The atomic structures and corresponding elemental distributions of the La(Ce)NiAl system. (a), (d), and (g) HRTEM images presenting uniform mazelike patterns for the as-cast LaCe-HEMG, La₅₅Ni₂₀Al₂₅, and Ce₅₅Ni₂₀Al₂₅, respectively, and the corresponding SAED patterns (insets) demonstrating the typical amorphous structures. Scale bars: 2 nm. **(b), (e)** and **(h)** HAADF-STEM images of LaCe-HEMG, La₅₅Ni₂₀Al₂₅ and Ce₅₅Ni₂₀Al₂₅, respectively. Scale bars: 5 nm. **(c), (f), and (i)** Corresponding EDS chemical mappings for LaCe-HEMG, La₅₅Ni₂₀Al₂₅ and Ce₅₅Ni₂₀Al₂₅, respectively. LaCe-HEMG exhibits relatively homogeneous elemental distributions. Scale bars: 5 nm

Figure 4 | The crystallization behavior of the La(Ce)NiAl system. (a) XRD profiles of the La(Ce)NiAl system illustrating the depressed crystallization characterization of LaCe-HEMG. **(b), (c), and (d)** Corresponding TEM images of crystallized $\text{La}_{55}\text{Ni}_{20}\text{Al}_{25}$, $\text{Ce}_{55}\text{Ni}_{20}\text{Al}_{25}$, and LaCe-HEMG, respectively. The insets show the respective SAED patterns. Scale bars: 100 nm. **(e)** HRTEM image of the crystallized region (dashed red frame in (d)) showing nanocrystals with an average size of 10 nm embedded in the amorphous matrix of LaCe-HEMG. Scale bar 5 nm. **(f)** EDS mappings of crystallized LaCe-HEMG. Scale bar: 50 nm.

Figure 5 | The activation energies for β -relaxation, α -relaxation, glass transition and crystallization of the La(Ce)NiAl system. (a) Arrhenius plots of the temperature and frequency dependence of the peak temperature of β -relaxations for the La(Ce)NiAl system. The inset shows the temperature-dependent G'' of LaCe-HEMG with testing frequencies ranging from 0.5 to 16 Hz. (b) Frequency and temperature dependence of the peak temperature of α -relaxations fitted with the Arrhenius relationship. The inset presents the frequency-dependent G'' of LaCe-HEMG at different temperatures. (c) and (d) Kissinger plots of T_g and T_x versus heating rate for the La(Ce)NiAl system, respectively.

Figure 6 | Schematic illustration of structure and energy landscape of MGs. (a) HEMGs present relatively homogeneous elemental distributions based on the EDS results, which might originate from the high mixing entropy. (b) Correlation between the evolution of STZs and relaxation behaviors with increasing temperature. The MGs finally yield crystallization state at T_x . (c) Schematic potential energy landscape for MGs, β -relaxation relates a reversible hopping event in an inherent megabasin, while α -relaxation corresponds to an irreversible hopping event across different landscape megabasins.

Table 1 Activation energies of β-relaxation, α-relaxation, glassy transition, and crystallization in the LaCe alloy system.				
Activation energy (kJ/mol)	E_{β}	E_{α}	E_g	E_x
La ₅₅ Ni ₂₅ Al ₂₀	93.9±4	249.6±5	291.7±5	146.1±2
Ce ₅₅ Ni ₂₅ Al ₂₀	85.8±4	229.8±8	267.1±5	155.6±2
La _{27.5} Ce _{27.5} Ni ₂₅ Al ₂₀	88.8±4	267.6±1	241.4±5	178.5±2

Figures

Figure 1

The mixing of entropy, calorimetric and dynamical behaviors. (a) ΔH_{mix} (kJ/mol) for the constituting atomic pairs in the La(Ce)NiAl system. (b) Calculated mixing entropies for the three MGs systems. (c) DSC traces (heating rate of 20 K/min) of the La(Ce)NiAl system, the arrows indicate the calorimetric T_g . (d) Temperature dependence of the loss modulus of the LaCe MGs system at 1 Hz with a constant heating rate of 3 K/min, normalized by the maximum peak value. The arrows indicate the α -relaxation temperature (T_α), and the inset shows the evolution of T_g and T_α with the components.

Figure 2

The fragility and viscosity behavior of the La(Ce)NiAl system. (a) DSC traces of LaCe-HEMG for heating rates ranging from 25 to 600 K/s. The left- and right- side arrows indicate T_g and T_x , respectively. (b) Heating rate dependence of T_g for the La(Ce)NiAl MG system and corresponding VFT fitting trace (dashed lines). (c) Non-equilibrium viscosity near the glass transition region for the La(Ce)NiAl MGs, measured with a constant heating rate of 0.33 K/s.

Figure 3

The atomic structures and corresponding elemental distributions of the La(Ce)NiAl system. (a), (d), and (g) HRTEM images presenting uniform mazelike patterns for the as-cast LaCe-HEMG, La55Ni20Al25, and Ce55Ni20Al25, respectively, and the corresponding SAED patterns (insets) demonstrating the typical amorphous structures. Scale bars: 2 nm. (b), (e) and (h) HAADF-STEM images of LaCe-HEMG, La55Ni20Al25 and Ce55Ni20Al25, respectively. Scale bars: 5 nm. (c), (f), and (i) Corresponding EDS

chemical mappings for LaCe-HEMG, La₅₅Ni₂₀Al₂₅ and Ce₅₅Ni₂₀Al₂₅, respectively. LaCe-HEMG exhibits relatively homogeneous elemental distributions. Scale bars: 5 nm

Figure 4

The crystallization behavior of the La(Ce)NiAl system. (a) XRD profiles of the La(Ce)NiAl system illustrating the depressed crystallization characterization of LaCe-HEMG. (b), (c), and (d) Corresponding TEM images of crystallized La₅₅Ni₂₀Al₂₅, Ce₅₅Ni₂₀Al₂₅, and LaCe-HEMG, respectively. The insets show the respective SAED patterns. Scale bars: 100 nm. (e) HRTEM image of the crystallized region (dashed red frame in (d)) showing nanocrystals with an average size of 10 nm embedded in the amorphous matrix of LaCe-HEMG. Scale bar 5 nm. (f) EDS mappings of crystallized LaCe-HEMG. Scale bar: 50 nm.

Figure 5

The activation energies for β -relaxation, α -relaxation, glass transition and crystallization of the La(Ce)NiAl system. (a) Arrhenius plots of the temperature and frequency dependence of the peak temperature of β -relaxations for the La(Ce)NiAl system. The inset shows the temperature-dependent G'' of LaCe-HEMG with testing frequencies ranging from 0.5 to 16 Hz. (b) Frequency and temperature dependence of the peak temperature of α -relaxations fitted with the Arrhenius relationship. The inset presents the frequency-dependent G'' of LaCe-HEMG at different temperatures. (c) and (d) Kissinger plots of T_g and T_x versus heating rate for the La(Ce)NiAl system, respectively.

Figure 6

Schematic illustration of structure and energy landscape of MGs. (a) HEMGs present relatively homogeneous elemental distributions based on the EDS results, which might originate from the high mixing entropy. (b) Correlation between the evolution of STZs and relaxation behaviors with increasing temperature. The MGs finally yield crystallization state at T_x . (c) Schematic potential energy landscape for MGs, β -relaxation relates a reversible hopping event in an inherent megabasin, while α -relaxation corresponds to an irreversible hopping event across different landscape megabasins.

Supplementary Files

This is a list of supplementary files associated with this preprint. Click to download.

- [SupplementalmaterialsHEMG6.pdf](#)