Improvement of Water Resistance by Fe₂O₃/TiO₂ Photoelectrocatalysts for Formaldehyde Removal: Experimental and Theoretical Investigation

Jing Dong

Huaqiao University College of Chemical Engineering

Qing Li

Huaqiao University College of Chemical Engineering

Wenjie Xia

Northwestern University Department of Civil and Environmental Engineering

Bihong Lv

Huaqiao University College of Chemical Engineering

Guohua Jing

Huaqiao University College of Chemical Engineering

Huazhen Shen (✉ hzhshen@hqu.edu.cn)

Huaqiao University College of Chemical Engineering

Chung-shin Yuan

National Sun Yat-sen University IEE: National Sun Yat-sen University Institute of Environmental Engineering

Research Article

Keywords: photoelectrocatalytic, formaldehyde, TiO₂, Fe₂O₃, DFT

Posted Date: June 4th, 2021

DOI: <https://doi.org/10.21203/rs.3.rs-164964/v1>

License: © ⓘ This work is licensed under a Creative Commons Attribution 4.0 International License.

[Read Full License](#)

Version of Record: A version of this preprint was published at Environmental Science and Pollution Research on October 1st, 2021. See the published version at <https://doi.org/10.1007/s11356-021-16459-w>.

- 1
- 2
- 3
- 4
- 5
- 6
- 7
- 8
- 9
- 10
- 11
- 12
- 13
- 14
- 15
- 16
- 17

¹ College of Chemical Engineering, Huaqiao University, Xiamen, Fujian, China

² Department of Civil and Environmental Engineering, North Dakota State University, USA

³ Institute of Environmental Engineering, National Sun Yat-sen University, No. 70, Lian-Hai Road, Kaohsiung 804, Taiwan

ABSTRACT

TiO₂-based photocatalysts are a potential technology for removing indoor formaldehyde (CHOH) owing to their strong photooxidation ability. However, their photooxidation performance is generally weakened when suffering from the competitive adsorption of H₂O. In a method inspired by the oxygen evolution reaction (OER) to generate intermediates with hydroxyl radicals on the anode electrode catalysts, an electric field was employed in this research and applied to the photooxidation of CHOH to prevent the competitive adsorption of H₂O. Additionally, 0.5-5% Fe₂O₃ decorated TiO₂ was employed to improve the photoelectrocatalytic activity. The influence of an electric field on hydroxyl-radical production was investigated by both density functional theory (DFT) with direct-imposed dipole momentum and photoelectrocatalytic experimental tests. The surface characterization of the photocatalysts, including transmission electron microscopy (TEM), X-ray photoelectron spectroscopy (XPS), and electron paramagnetic resonance (EPR), was conducted. DFT results show that a positive electric field with a strength of 0.05 Å/V was more favorable to produce hydroxyl on Fe₂O₃/TiO₂(010) than was a negative electric field. Fe₂O₃ decoration can significantly boost hydroxyl formation, resulting from a decrease in the binding energy between the Fe of Fe₂O₃ and the oxygen and hydrogen atoms of H₂O. The dissociated hydrogen atom of the H₂O preferentially remained on the catalysts' surface rather than being released into the gas flow. The experimental results demonstrated that the application of a low-voltage of 150 V could not directly enhance the photooxidation of CHOH by either TiO₂ or Fe₂O₃/TiO₂ but that

40 it could relieve the H₂O inhibitory effect by more than 10% on the Fe₂O₃/TiO₂.

41 **Keywords:** photoelectrocatalytic; formaldehyde; TiO₂; Fe₂O₃; DFT

1. Introduction

Formaldehyde (CHOH) is one of China's most harmful indoor air pollutants and poses a dangerous threat to human health (Kim et al., 2011; Tang et al., 2009). Various removal technologies including adsorption (Yang et al., 2017), solvent absorption (Yang et al., 2017), catalytic conversion (Guo et al., 2019; Li et al., 2020; Miao et al., 2019; Nie et al., 2016), and photooxidation, can effectively address indoor CHOH pollution. Due to their photoinduced holes and electrons, photocatalysts can produce highly oxidative hydroxyl or superoxide radicals, thus being good candidates for the photooxidation of CHOH (Wang et al., 2017; Yu et al., 2013; Zhang et al., 2017). However, because of the competitive adsorption of the oxygen in H₂O and the carbonyl group in CHOH, photocatalysts suffer from H₂O interference with several-order concentrations higher than CHOH under a specific humidity, which would enormously undermine their photocatalytic activity. A key to solving the inhibitory effect of gaseous H₂O is activating the H₂O molecule and producing more surface hydroxyl radicals. However, H₂O splitting for hydroxyl production cannot proceed spontaneously and requires an enormous amount of energy to overcome the energy barrier of hydroxyl formation (Chen et al., 2014; Ding et al., 2018). It is well known that under overpotentials in an electrochemical cell, the oxygen evolution reaction (OER) on anode catalysts produces an intermediate of hydroxyl radicals by abstracting one hydrogen atom of H₂O. Then, the released electrons are transported to the anodes, following Eq. (1) below,

where * represents the coordinatively unsaturated sites of the catalyst (Valdés et al., 2008). Although the OER commonly occurs in an aqueous environment, it is vital to experimentally and theoretically investigate whether it can proceed between a gas-solid interface. Another question was whether photooxidation of gaseous H_2O to produce hydroxyls could be strengthened under an external electric field, thus substantially enhancing the removal of CHO $\cdot$.

Theoretical calculation methods are currently employed to simulate the electrochemical catalysis, including

(a) The computational hydrogen electrode (CHE) method, proposed by Nørskov et al. (Nørskov et al., 2004);

(b) A double reference method with a modification of the electrical double layer (EDL) (Filhol and Neurock, 2006; Lozovoi and Alavi, 2003);

(c) Direct-imposed dipole momentum on a periodic surface slab representing an electric field (Deshlahra et al., 2009; Jörg and Matthias, 1992).

The CHE model can successfully analyze the overpotential of the OER on a none charged catalyst slab, but it is difficult to simulate the dependence of physiochemical adsorption on an applied external field. The EDL model could well reflect the dependence by adding one or more extra charges and identical compensating charges, which is suitable for analyzing a liquid-solid slab system (Duan and Henkelman, 2019; Filhol and Neurock, 2006). The third method is widely used to simulate a charged gas-solid catalytic reaction system by introducing a dipole momentum on a slab + adsorbates to embody an external electrostatic field (Deshlahra et al., 2009; Jörg and

Matthias, 1992). Herein, the third method of introducing a dipole moment as implemented in Vienna Ab-initio Simulation Package (VASP) was employed to investigate the synergetic effect of photoelectrocatalytic oxidation on the formation of $\cdot\text{OH}$. It is worth noting that unlike when a hydrogen atom diffuses into the electrolyte after producing a hydroxyl radical ($\cdot\text{OH}$) on a liquid-solid interface, hydrogen would be attached to catalysts or transported away by carrier gases on a gas-solid interface. Accordingly, the free energy of the formation of the two terminates was calculated in this research, where (a) one remains on the catalyst's surface as $\cdot\text{OH} + \text{H}$ and (b) the other leaves to form $\cdot\text{OH} + \text{H}^+(\text{gas})$.

TiO_2 , due to its strong photoredox ability, excellent chemical stability, low cost, and few secondary derivatives, has been widely investigated for photodegrading formaldehyde. Under UV irradiation, strong oxidative free radicals, $\cdot\text{O}_2^-$ and $\cdot\text{OH}$, are produced at the surface of TiO_2 and can effectively react with CHOH to form formate and the final products of CO_2 and H_2O (Sun et al., 2010; Tasbihi et al., 2015). Thus, it has great potential to be employed as a commercial photocatalyst inside air cleaners to treat indoor CHOH (Cremer et al., 2014; Liang et al., 2012). However, because of the rapid recombination of photoinduced electron-hole pairs for TiO_2 , the photocatalytic activity of TiO_2 is not high enough to degrade CHOH efficiently (Yu et al., 2013). How to slow the recombination of photogenerated electron-hole pairs plays a vital role in enhancing the photocatalytic activity of TiO_2 .

Thus, a material with low resistance or impedance to modify TiO_2 is needed to enhance photodegrading CHOH assisted with an electric field. Fe_2O_3 , a cheap

ferromagnetic material, possesses good electrical properties, such as high capacity, high charging rate, long-life usage, and low resistance, which can effectively decrease the insulating behavior of TiO_2 (Piva et al., 2016; Ding et al., 2017). Additionally, the interface of Fe_2O_3 and TiO_2 can accelerate the transfer of photoinduced electrons from the conduction band of Fe_2O_3 to that of TiO_2 (Moniz et al., 2014; Wang et al., 2014). Thus, decorating Fe_2O_3 on TiO_2 was employed to enhance the photoelectrical activity.

Therefore, the photoelectrical catalytic oxidation of H_2O to produce hydroxyl on TiO_2 and Fe_2O_3 decorated TiO_2 was explored using DFT calculations. The surface characterization of photocatalysts, including transmission electron microscopy (TEM), X-ray photoelectron spectroscopy (XPS), electron paramagnetic resonance (EPR), was conducted. Furthermore, this study experimentally investigated the photoelectrical catalytic oxidation of gaseous CHOH by Fe_2O_3 -decorated TiO_2 under an external electric field with and without humidity.

Experimental Methods

2.1 Preparation for $\text{Fe}_2\text{O}_3/\text{TiO}_2$

$\text{Fe}_2\text{O}_3/\text{TiO}_2$ was prepared by the impregnation method. A weight of 1.00 g commercial TiO_2 (Tianhe Environmental Engineering Co., Ltd., Baoding) was mixed into 70 mL distilled water and then stirred continuously for 30 min at room temperature. Then, 0.5%, 3.0%, and 5% $\text{Fe}_2\text{O}_3/\text{TiO}_2$ samples were prepared by adding 0.025, 0.150, and 0.250 g $\text{FeCl}_3 \cdot 6\text{H}_2\text{O}$ into the TiO_2 solution, respectively. After continuous stirring for 90 min at room temperature, the mixtures were dried at 105°C in a rotary evaporator at a reduced pressure of 0.01 kPa to dry the residue H_2O . Then, the dried samples were

calculated at 500 °C for 12 h in an air atmosphere to form Fe₂O₃/TiO₂. Before each
CHOH degrading test, the prepared Fe₂O₃/TiO₂s catalysts were loaded onto glass fiber
as follows: 1.0 g photocatalysts were dispersed in 1 L of distilled water with ultrasonic
treatment for 10 min. Cylindrical glass fiber was immersed in the Fe₂O₃/TiO₂ solution
for at least 5 h and then dried for 2 h at 105 °C. The filled amount of Fe₂O₃/TiO₂ was
the weight difference of the glass fiber before and after the loading treatment.

2.2 Characterization of Fe₂O₃/TiO₂

A scanning electron microscope (SEM) was used to obtain the morphologies of
the Fe₂O₃/TiO₂s with a beam accelerating voltage and current of 20 kV and 20 μA,
respectively. High-resolution transmission electron microscopy (HR-TEM) was
performed on a Tecnai G2 F20 (FEI, USA) with an accelerating voltage of 200 kV. An
X-ray diffraction (XRD) analyzer was used to analyze the crystal pattern of TiO₂ and
Fe₂O₃/TiO₂(s) with a Shimadzu X-ray beam with Cu-Kα radiation. Raman spectra of
the specimens were obtained using a SenterraII (BRUCK, USA) with a scanning range
of 100-1000 cm⁻¹. The photoluminescence spectra (PL) of the TiO₂ and Fe₂O₃/TiO₂s
catalysts were recorded on a Varian Cary Eclipse spectrometer with an excitation
wavelength of 325 nm. UV-vis spectra of the photocatalysts were recorded in the range
of 200-800 nm by a Shimadzu UV-vis (UV-2550) spectrometer equipped with a diffuse
reflection accessory. BaSO₄ was employed as the reference substance. Electrochemical
impedance spectroscopy (EIS) and linear sweep voltammetry (LSV) were performed
using an electrochemical workstation (CHI604E, C.H. Inc.). The EIS and LSV were
measured at a constant A.C. amplitude of 5.0 mV with a sweep frequency of 10⁵-0.1

Hz. The voltage ranged from -0.3 to 0.2 V for the LSV measurement with 0.1 M Na₂SO₄ solution as the electrolyte. The Mott-Schottky plots were established with the A.C. amplitude of 10 mV at 100 Hz. The sweep voltage ranged from -1.2 to 0.5 V. The EPR measurements were performed using a Bruker ER200D operated in the X-band. Approximately 10-50 mg of photocatalyst was placed into a particular spectroscopically pure quartz cell.

2.3 DFT experimental methods

The commercial TiO₂ exhibits a predominantly exposed (010) facet, which was also illustrated in the following TEM characterization results. Thus, an anatase TiO₂ (010) slab was constructed to simulate the TiO₂ base. Before constructing the slab, we first optimized the unit cell of anatase TiO₂. The crystal lattice spacing was optimized to be $a = b = 3.80$ and $c = 9.50$ Å; this optimization was in agreement with previous research (Shen et al., 2021). The TiO₂(010) slab consisted of four layers and 48 atoms (Ti₁₆O₃₂), and a vacuum height of 20 Å oriented along the c-axis. The Fe₂O₃ decoration was assembled by loading one (Fe₂O₃) cluster consisting of 2 Fe and 3 O atoms on the TiO₂(010), as shown in Figure 9. An external electric field was applied vertically to the slab by an approach proposed by Naugebeaur and Scheffler. Positive and negative electric fields with strengths of 0.05 and -0.05 eV/Å were imposed on the supercell to simulate different electric-field directions. A positive external electric field led to a distribution of positive charges on the upper side of the slab, and the negative external electric field led to opposite results (Deshlahra et al., 2009). The formation of hydroxyl radicals with (or without) the dissociated hydrogen atom of H₂O connected on TiO₂(010)

and Fe₂O₃/TiO₂(010) was constructed as follows: for the case of hydrogen atoms anchored at the surface, the hydroxyl was connected to an unsaturated five-coordinate Ti atom (Ti_{5c}) and an atop four-coordinate Fe atom (Fe_{4c}), for TiO₂(010) and Fe₂O₃/TiO₂(010), respectively. The hydrogen atom was then linked to the adjacent oxygen atom of the Ti_{5c} (Fe_{4c}) on TiO₂(010) (Fe₂O₃/TiO₂(010)). In the absence of hydrogen, which was taken away from slabs, only a hydroxyl was bonded to the Ti_{5c} (Fe_{4c}) for the TiO₂(010) (Fe₂O₃/TiO₂(010)). The free energies of hydroxyl formation with ($\Delta G^{*-OH + *H}$) and without hydrogen (ΔG^{*-OH}) under an external electric field were determined by Eqs. (2)-(3), respectively,

$$\Delta G^{*-OH + *H} = G^{*-OH + *H} - G_{bare*} - G_{H_2O(g)} - eU \quad (2)$$

$$\Delta G^{*-OH} = G^{*-OH} - G_{bare*} - G_{H_2O(g)} + 1/2 G_{H+} - eU \quad (3)$$

where $G^{*-OH + *H}$ and G^{*-OH} are the free energies of hydroxyl (with or without hydrogen atoms) connected to charged TiO₂(010) and Fe₂O₃/TiO₂(010) and calculated within the applied electric field. G_{bare*} is the free energy of the charged catalysts within the electric field without any hydroxyl or hydrogen atom from H₂O. $G_{H_2O(g)}$, and G_{H+} are the free energies of H₂O and hydrogen atoms without any charges, respectively, which were calculated in the absence of an external electric field. U is the overpotential relative to the standard potential of a hydrogen electrode. Additionally, the difference in zero-point energies and the entropy change in $T\Delta S$ were corrected by determining the vibrational frequencies of the adsorbed -OH with and without hydrogen (Valdés et al., 2008). The reaction temperature was set to 298 K.

The correction for $\Delta G^{*-OH + *H}$ or ΔG^{*-OH} at a neutral pH and in an ambient

environment was also carried out based on Nernst's equation by Eq. (4). Herein, the photocatalysts were enveloped under neutral conditions without any acid or alkaline components in the continuous injection of gaseous H₂O. Thus, the pH was set to 7.0 to simulate the neutral environment on the gas-solid interface.

$$\Delta G_{\text{pH}}(\text{pH}) = 2.30 \times k_{\text{B}}T \times \text{pH} \quad (4)$$

The model calculation was determined based on the generalized gradient approximation with the Perdew-Burke-Ernzerhof exchange-correlation function (GGA-PBE). Hubbard U values (U_{eff}) of 4.20 and 5.00 eV were applied for Ti 3d and Fe 3d atomic orbitals, respectively, referring to previous research (Shim et al., 2009). The Brillouin zone was determined automatically with the gamma center in the Monkhorst-Pack scheme. The energy cutoff was set to 400 eV. The convergence criteria for the energy (EDIFF) and force (EDIFFG) were 10^{-4} eV and -0.02 eV/Å, respectively. All atoms in the slabs were relaxed in all the structure optimizations. All the determinations mentioned above were performed with the VASP.

2.4 Photoelectrocatalytic measurements

The photoelectrocatalytic reaction system consisted of a CHO₂H generation system, a photoelectric catalytic reactor, and an online detector, as shown in Figure 1. Gaseous CHO₂H was produced from a permeable tube enclosed in a U-shaped glass tube filled with a few glass beads to keep the influent gas cross-sectionally uniform. The U-shaped tube was placed in a water bath at a constant temperature of 80°C. Pure N₂ (99.99%) was used as the carrier gas. The influent concentration of CHO₂H was set to 1.50 ppm for each test. Additionally, O₂ (99.9%) and H₂O_(g) were also injected into the

218 reactor. Different humidities of the influent gas flow were adjusted by changing the
219 flow rate of N₂ purged into an impinger bottle containing water, which was measured
220 by a humidity detector. The overall influent flow rate was set to 700 mL/min. Before
221 entering the reactor, all the gas components were thoroughly mixed in a chamber, which
222 contained a magnetic stirrer, at a stirring rate of 200 r/min. All pipelines were made of
223 polytetrafluoroethylene to prevent the adhesion of the CHOH. The
224 photoelectrocatalytic reactor had a cylindrical shape with a height of 600 mm and an
225 interior diameter of 150 mm. A quartz cover on the top of the reactor was used to receive
226 UV irradiation. A UV lamp ($\lambda=254$ nm, P = 15 W) was placed directly above the reactor
227 at a distance of 15 cm from the fixed catalysts, and the fluence rate (ψ) was evaluated
228 to be 5.3 mW/cm². Two pieces of round woven mesh made of stainless steel were used
229 not only as a support for catalyst-coated glass fibers but also as the positive and negative
230 electrodes, which were connected with a self-designed direct-current (DC) voltage
231 output device. To avoid the consumption of energy, the supplied power (P) was as low
232 as 5 W. The output voltage between the two electrodes was measured to be
233 approximately 150 V. Correspondingly, the strength of the electric field was determined
234 to be 5000 V/m since the distance between the two pieces of woven mesh was
235 approximately 3.0 cm. For each test, the fiberglass filter coated with Fe₂O₃/TiO₂ was
236 sandwiched between the woven mesh. The superficial velocity for the photoelectric
237 reaction was determined to be 3.96 cm/min. The reaction temperature inside the reactor
238 was approximately 25°C. A working air conditioner was used to cool the reactor. A
239 CHOH detector (4160-19.99 m, Interscan) was used to monitor the effluent

concentration of CHOH online.

The removal efficiency was determined as the ratio of the difference in the influent and effluent concentrations of CHOH over the influent concentration, as shown in Eq. (5) described,

$$\eta = \frac{C_0 - C_i}{C_0} \times 100\% \quad (5)$$

where C_0 (ppm) is the influent concentration of CHOH, and C_i (ppm) is the effluent concentration of CHOH.

The removal rate r was calculated as the mass of CHOH reduced per unit time (min) and unit mass catalyst (g) described below:

$$r = (C_0 - C_i) \times \frac{M_{\text{CHOH}} \times Q}{24.45 \cdot m} \text{ (ng/min/g)} \quad (6)$$

where M_{CHOH} is the molar mass of CHOH (30 g/mol), Q is the overall influent flow rate (700 mL/min), and m is the catalyst mass (g) loading on the glass fibers.

3 Results and discussion

3.1 Surface characterization of TiO₂ and Fe₂O₃/TiO₂

3.1.1 Morphology of TiO₂ and Fe₂O₃/TiO₂

Figure 2 shows the SEM and TEM morphologies of the commercial TiO₂ and 5%Fe₂O₃/TiO₂. The morphologies of TiO₂ and Fe₂O₃/TiO₂ exhibited similar granule shapes according to SEM (Figure 2(a) and (e)). The TEM images of TiO₂ clearly showed that most of these granules displayed elongated tetragonal cuboids with a d-space of 0.37 nm in Figure 2(b), which highly approached that of the exposed facet of the (010) plane (Pan et al., 2011). Thus, we inferred that the (010) plane accounted for a considerably large proportion of the exposed facet of the TiO₂. Additionally, a minor

portion of granules with a d-space of 0.24 nm was attributed to the (103) plane (Ciancio et al., 2012). The average diameter of the TiO₂ granules was statistically estimated to be 12.9±4.9 nm, as shown in Figure 2(d). After the decoration of Fe₂O₃, the 3.0% Fe₂O₃/TiO₂ also presented a primarily cuboid shape similar to that of TiO₂ (Figures 2(f)-(g)). The primary d-space of the 3.0% Fe₂O₃/TiO₂ cuboid granule was measured to be 0.37 nm, corresponding to the (010) plane, and 0.25 nm for the minor interplane space, assigned to the (110) anatase plane. Thus, the morphology of the prepared Fe₂O₃/TiO₂ was not substantially altered compared with that of pristine TiO₂. Nevertheless, the average size of the 3.0% Fe₂O₃/TiO₂ was estimated to be approximately 14.6 ± 4.6 nm, resembling TiO₂.

3.1.2 Crystal structure and Raman spectra

Figure 3(a) shows that the XRD peaks of TiO₂ occurring at 25.3°, 37.8°, and 48.0° corresponded to the (101), (004), and (020) planes of anatase. The decoration of Fe₂O₃ did not give rise to the characteristic peaks at 2θ = 24.1°(012), 33.2°(104), 35.6°(110) for α-Fe₂O₃ (Maslen et al., 1994), or 36.9°(222), 42.9°(400) for γ-Fe₂O₃ (Jørgensen et al., 2007) in 0.5-5%Fe₂O₃/TiO₂, implying that Fe₂O₃ was mainly present in a highly dispersed amorphous phase, or as tiny crystals on the surface of TiO₂ that could not be detected by XRD (Fang et al., 2007). However, the decoration of Fe₂O₃ substantially influenced the diffraction profiles of the TiO₂s. For instance, the (020) peak intensity was much higher for Fe₂O₃/TiO₂s than TiO₂, as shown in Figure 3(a) and Supplementary Table 1. Additionally, the (020) peak of Fe₂O₃/TiO₂s was much sharper than that of TiO₂, which was probably associated with the expansion of TiO₂ crystals

along the [001] direction (Liu et al., 2017), suggesting that Fe₂O₃ loading could break the strain balance between the top and sublayers of TiO₂, thus influencing the epitaxy processes of TiO₂ during calcination. Additionally, the full width at half maximum (FWHM) at the 25.3° peak representing the (101) plane was 0.646°, 0.593°, 0.585°, and 0.520° for TiO₂ and 0.5-5%Fe₂O₃/TiO₂, respectively. The FWHM was determined according to the Debye-Scherrer equation (Eq. (7)),

$$D = K\lambda/\beta\cos\theta \quad (7)$$

where D (nm) is the average particulate size and β (without the value) is the FWHM. The particle size of 0.5-7%Fe₂O₃/TiO₂ increased slightly, since the β for the peak corresponding to the Fe₂O₃/TiO₂'s (101) plane was larger than that of TiO₂, unveiling that decoration of Fe₂O₃ slightly promoted the growth in TiO₂ size, highly concurring with the size distribution as shown in the TEM images.

Figure 3(b) shows the Raman spectra of TiO₂ and 0.5-5% Fe₂O₃/TiO₂. The Raman peaks at 144, 396, 515, and 640 cm⁻¹ corresponded to the E_g, B_{1g}, B_{2g}, and E_g modes of TiO₂. The characteristic peaks of Fe₂O₃ were not present in the Raman patterns of 0.5-5% Fe₂O₃/TiO₂ such as those for α -Fe₂O₃ occurring at 220 (A_{1g}), 243 (E_g), 290 (E_g), 408 (E_g), 611 (E_g), 638 (E_g) and 1318 cm⁻¹(E_g) (Kodan et al., 2019), as well as those for γ -Fe₂O₃ at 350 (E_g), 395 (T_{2g}), 507 (T_{2g}), 670 (A_{1g}), and 708 cm⁻¹ (A_{1g}) (Pawan et al., 2014). The similar Raman patterns between TiO₂ and 0.5-5%Fe₂O₃/TiO₂ agreed with the XRD results, revealing that the decorated Fe₂O₃ on TiO₂ formed an amorphous phase or tiny crystallite cell. Nevertheless, the intensities of the 144 and 130 cm⁻¹ peaks assigned to the symmetric stretching vibration of the O-Ti-O bonds were relatively

lower for Fe₂O₃/TiO₂ than for the TiO₂s, particularly that of 144 cm⁻¹ in 5% Fe₂O₃/TiO₂ spectrum, which dropped notably. The lower intensity of the E_g vibration mode of the Fe₂O₃/TiO₂s probably resulted from the decrease in the O-Ti-O number on the exposed facet of anatase TiO₂ due to the surface cover of amorphous Fe₂O₃.

3.1.3 X-ray photoelectron spectroscopy

Figure 4(a) shows the binding energy of Ti 2p for TiO₂ and 3%Fe₂O₃/TiO₂. The binding energies of 464.4 and 458.5 eV were assigned to Ti⁴⁺ 2p 1/2 and 3/2 of TiO₂, respectively (Tsai et al., 2013). After the surface loading of Fe₂O₃, two small subpeaks emerged at lower binding energies of 463.4 and 457.7 eV, suggesting that the electron density of the Ti⁴⁺ 2p orbital increased with the loading of Fe due to the formation of Fe-O-Ti. The intensity of the Fe 2p peak, as shown on the Y-axis scale in Figure 4(b), was much smaller than that of Ti⁴⁺, indicating that the content of surface Fe atoms was far lower than that of Ti. The main peaks at approximately 710.2 and 724.6 eV were ascribed to the Fe³⁺ 2p_{1/2} and 2p_{3/2} orbitals of Fe₂O₃, respectively, illustrating that Fe³⁺ dominated most surface Fe atoms. Additionally, minor shake-up peaks were present in the range of 713-720 eV, which resulted from an electron transition from a 3d orbital to an empty 4s orbital as the ejection of the Fe 2p electrons (Yin et al., 1974).

3.1.4 UV-Visible spectra

Figure 5 illustrates the UV-vis spectra of TiO₂ and Fe₂O₃/TiO₂s. Their band gaps were determined from the intercept between the extrapolated tangent line at the maximum first-derivative points of the absorption edge and the X-axis. The band gap of TiO₂ was approximately 3.20 eV, which was in agreement with the UV-vis absorption feature of anatase TiO₂. The absorption edge was gradually redshifted with the Fe₂O₃

content loaded on TiO_2 . The corresponding band gaps of the 0.5%, 3%, and 5% $\text{Fe}_2\text{O}_3/\text{TiO}_2$ dropped to 3.14, 2.99, and 2.87 eV, respectively. The UV-vis spectrum of Fe_2O_3 illustrated a noticeable redshift compared with those of TiO_2 and 0.5-5% $\text{Fe}_2\text{O}_3/\text{TiO}_2$. The adsorption edge occurring at 530-650 nm of the pristine Fe_2O_3 is probably related to the ligand field transition of $2(^6\text{A}_1) \rightarrow (^4\text{T}_1)$ (Huang et al., 2017). The band gap was approximately 1.84 eV, approaching 1.88 eV, as reported by Wang et al. (Mansour et al., 2020). Thus, the redshift for 0.5-5.0% $\text{Fe}_2\text{O}_3/\text{TiO}_2$ compared with TiO_2 was principally attributed to the loading of the Fe_2O_3 cluster.

3.1.5 Photoluminescence spectra and electric properties

Figure 6(a) shows the PL spectra of TiO_2 and $\text{Fe}_2\text{O}_3/\text{TiO}_2$ s. The PL emission peaks at 474 nm (2.61 eV) and 500 nm (2.48 eV) were ascribed to the recombination of photoinduced electrons with holes trapped around surface oxygen vacancies (Abdullah et al., 2018). No distinct peak emerged for the $\text{Fe}_2\text{O}_3/\text{TiO}_2$ s, indicating that the decoration of Fe_2O_3 did not result in new interstitial recombination centers. Nevertheless, the PL intensity decreased with the decorated content of Fe_2O_3 , particularly for 5% $\text{Fe}_2\text{O}_3/\text{TiO}_2$, illustrating improvement of the separation of photoinduced holes and electrons for the $\text{Fe}_2\text{O}_3/\text{TiO}_2$ s as compared to TiO_2 .

The simulated EIS patterns of TiO_2 and $\text{Fe}_2\text{O}_3/\text{TiO}_2$ s are presented in Figure 6(b). The simulated EIS radius of TiO_2 was much larger than those of $\text{Fe}_2\text{O}_3/\text{TiO}_2$ s, illustrating that the decoration of Fe_2O_3 greatly reduced the interface charge transfer resistance between the electrode and electrolyte, which was probably attributed to the lower electronic resistivity of Fe_2O_3 (Chang et al., 2014). Moreover, the simulated EIS

decreased with the content of surface Fe_2O_3 , probably owing to an increase in tiny crystals within the Fe_2O_3 , which could significantly reduce the electronic resistivity, although the XRD results did not discern the α - or γ - Fe_2O_3 crystalline phase (Piva et al., 2016).

The LSV spectra of TiO_2 and $\text{Fe}_2\text{O}_3/\text{TiO}_2$ s were measured under UV illumination, as illustrated in Figure 6(c). The photocurrent density of TiO_2 was much lower than that of $\text{Fe}_2\text{O}_3/\text{TiO}_2$ in the applied voltage range of -0.25-0.3 V. Additionally, the photocurrent density of the specimens also increased with the content of Fe_2O_3 . The EIS and LSV results confirmed that the surface decoration of Fe_2O_3 could promote the separation efficiency of photogenerated electron-hole pairs of TiO_2 .

3.1.6 Electronic structure

The Mott-Schottky plots for TiO_2 and 0.5-5% $\text{Fe}_2\text{O}_3/\text{TiO}_2$ were constructed at 100 Hz using an Ag/AgCl electrode at pH=7.0, as shown in Figure 7(a). The results illustrated that the slope of $1/C^2$ versus the applied potential was positive for both TiO_2 and 0.5-5% $\text{Fe}_2\text{O}_3/\text{TiO}_2$, demonstrating that they were attributed to n-type semiconductors. Thus, the edges of the flat band (FB) of TiO_2 and 0.5-5% $\text{Fe}_2\text{O}_3/\text{TiO}_2$ are nearly equal to those of the conduction band (CB), as shown in Eq. (8),

$$\text{CB} \approx \text{FB} \text{ (NHE, pH=7.0)} \quad (8)$$

The CBs of TiO_2 and 0.5-5% $\text{Fe}_2\text{O}_3/\text{TiO}_2$ were -0.86, -0.91, -1.01, and -1.07 eV, respectively. The corresponding edges of the valence band (VB) could be obtained from the band gap (E_g) and CB as described by Eq. (9),

$$\text{VB} = \text{CB} + E_g \quad (9)$$

The band gaps of TiO_2 and $0.5\text{-}5\%\text{Fe}_2\text{O}_3/\text{TiO}_2$ were 3.20, 3.14, 2.99, and 2.87 eV, respectively. Their VBs were determined to be 2.34, 2.23, 1.98, and 1.80 eV, respectively, as shown in Figure 7(b). The CBs of $0.5\text{-}5\%\text{Fe}_2\text{O}_3/\text{TiO}_2$ were higher than that of TiO_2 (-0.86 eV). This result is possibly related to the realignment of the two Fermi levels of Fe_2O_3 and TiO_2 after the Fe_2O_3 and TiO_2 contacted (Liu et al., 2015). As shown in the schematic diagram of the electronic structure of hybrid $\text{Fe}_2\text{O}_3/\text{TiO}_2$ (see Figure 7(c)), the photogenerated electrons transferred from the conduction band of Fe_2O_3 to that of TiO_2 , while the holes moved from the valence band of TiO_2 to Fe_2O_3 . Thus, $\text{Fe}_2\text{O}_3/\text{TiO}_2$ is beneficial for separating the photogenerated electron-hole pairs.

3.1.7 EPR

The typical feature of the $\cdot\text{OH}$ signal displays a quartet pattern with an intensity ratio of 1 ($g \approx 1.990$): 2 ($g \approx 2.003$): 2 ($g \approx 2.012$): 1 ($g \approx 2.021$) for the TiO_2 and $3\%\text{Fe}_2\text{O}_3/\text{TiO}_2$, as depicted in Figure 8. The results indicated that a higher intensity was ascertained on the $3\%\text{Fe}_2\text{O}_3/\text{TiO}_2$ than on TiO_2 , implying that the decoration of Fe_2O_3 was more conducive to increasing $\cdot\text{OH}$, which was attributed to the efficient photoinduced electron-hole pairs on the interface of Fe_2O_3 and TiO_2 (Sun et al., 2012).

3.2 DFT Calculations

Figure 9(a) shows the effect of the electric field on the free energy of formation of hydroxyl and hydrogen on $\text{TiO}_2(010)$ and $\text{Fe}_2\text{O}_3/\text{TiO}_2(010)$. In the absence of an electric field, energies of 1.56 and 0.70 eV were required for the formation of hydroxyl and hydrogen on $\text{TiO}_2(010)$ and $\text{Fe}_2\text{O}_3/\text{TiO}_2(010)$, respectively, indicating that the decomposition of H_2O to produce hydroxyl and hydrogen could not proceed spontaneously on these slabs; this decomposition reaction resembled the first reaction

step of the OER for anatase TiO₂ in aqueous conditions (Malik et al., 2020). Nevertheless, for Fe₂O₃/TiO₂(010), the free energy of *-OH + *-H formation decreased by approximately half compared with TiO₂. The top Ti-O bond length (2.427 Å) was also reduced to 2.123 Å due to the decoration of amorphous Fe₂O₃, meaning that atop Fe₂O₃ on TiO₂(010) was more active for splitting H₂O than TiO₂(010). When a positive external electric field with a strength of 0.05 eV/Å was applied for TiO₂(010), the free energy (1.44 eV) of *-OH + *-H formation decreased slightly. It is worth noting that the free energy of formation on Fe₂O₃/TiO₂(010) decreased dramatically to -1.04 eV with a positive electric field, thus spontaneously driving the splitting of H₂O into hydroxyl radicals.

To better understand the effect of the electric field on the formation of hydroxyl and hydrogen, the variation in dipole moment (μ_0) of hydroxyl and hydrogen as a whole adsorbed on TiO₂(010) and Fe₂O₃/TiO₂(010) was compared. μ_0 is equivalent to the difference between the dipole moment of *-OH + *-H (*-OH) and that of the bare catalyst slab (Deshlahra et al., 2009), which were both obtained from the resulting DFT file. Without an electric field, the dipole moments of *-OH + *-H for TiO₂(010) and Fe₂O₃/TiO₂(010) were 0.019 and 0.171 eÅ, respectively, which suggested the more negative charges were distributed on the oxygen atoms of the hydroxyl and on the hydrogen atoms of the Fe₂O₃/TiO₂(010) than those of the TiO₂(010). The change in free energy (ΔE , eV) of *-OH + *-H formation due to exposure to an electric field can be predicted by the first-order Stark effect as

$$\Delta E = -\mu_0 \times F \quad (10)$$

where μ_0 (eÅ) is the dipole moment of the adsorbate without an electric field and F (V/Å) is the strength of an external electric field. The ΔE was -0.00865 and -0.00097 eV for $\text{Fe}_2\text{O}_3/\text{TiO}_2(010)$ and $\text{TiO}_2(010)$, respectively, according to Eq. (10), when the electric field was set to 0.05 eV/Å. Although both ΔE values obtained by Eq. (10) were much smaller than those calculated based on the structure optimization results, the ΔE of $\text{Fe}_2\text{O}_3/\text{TiO}_2(010)$ was higher than that of $\text{TiO}_2(010)$; this trend demonstrated that the external electric field in the positive direction favors the formation of hydroxyl and hydrogen on the surface of $\text{Fe}_2\text{O}_3/\text{TiO}_2(010)$. Additionally, the Fe-O bond length (2.077) between the Fe atom and hydroxyl and the O-H bond (1.262 Å) of hydroxyl were much shorter than the corresponding lengths without an electric field, which were 2.123 and 1.274 Å, as shown in Figure 9(a), suggesting that the hydroxyl was bonded more closely to the $\text{Fe}_2\text{O}_3/\text{TiO}_2(010)$ under a positive electric field. It is noted that with the positive electric field, the dissociated hydrogen atom from H_2O preferred to interact with one Fe atom at a shorter distance of 2.392 Å, while before the electric field was added, the hydrogen atom was physically connected to one oxygen atom of Fe_2O_3 at a distance of 2.994 Å. In contrast, a more stable structure was assigned to an unbroken H_2O molecule adsorbed on $\text{TiO}_2(010)$ without the formation of hydroxyl and hydrogen moieties under a positive electric field. The distance between the surface oxygen and surface Ti atom was elongated to 3.208 Å, suggesting that H_2O was more difficult to oxidize and split into hydroxyl on $\text{TiO}_2(010)$ than on $\text{Fe}_2\text{O}_3/\text{TiO}_2(010)$ under a positive electric field.

The effect of a negative electric field on the formation of hydroxyl was also investigated. According to Eq. (10), the predicted ΔE for the change in the formation

energy would be 0.00865 and 0.00097 eV for $\text{TiO}_2(010)$ and $\text{Fe}_2\text{O}_3/\text{TiO}_2(010)$ under a field strength of $-0.05 \text{ V/\AA}$, indicating that an electric field in the negative direction was not beneficial for splitting H_2O compared with the positive electric field. The formation free energies of the hydroxyl and hydrogens were also determined based on structure optimization, as shown in Figure 9(a), which were 1.01 eV for $\text{TiO}_2(010)$ and -0.22 eV for $\text{Fe}_2\text{O}_3/\text{TiO}_2(010)$. They were much lower than those under a positive electric field, demonstrating that a positive electric field was more effective than a negative electric field to promote hydroxyl production. Additionally, the atomic distance between the oxygen atom of the hydroxyl and the Fe or Ti atom, and the distance between the dissociated hydrogen atom and the Fe atom became longer under a negative electric field, as shown in Figure 9(a).

When the detached hydrogen atom of H_2O was lost under the gaseous flow, the production of hydroxyl could not still proceed spontaneously regardless of the direction in which the electric field was applied, as illustrated in Figure 9(b). For instance, the free energy of $^*\text{-OH}$ formation for $\text{TiO}_2(010)$ was 1.759 eV, while it was 1.445 eV for $\text{Fe}_2\text{O}_3/\text{TiO}_2(010)$. The free energy of $^*\text{-OH}$ formation alone increased to 2.927 eV and 2.423 eV for $\text{TiO}_2(010)$ and $\text{Fe}_2\text{O}_3/\text{TiO}_2(010)$, respectively, when a positive electric field was added. Likewise, the negative electric field resulted in free energies of 1.445 eV and 0.7817 eV. The results implied that the hydrogen atom that was dissociated from the H_2O molecule was more likely to remain on the $\text{TiO}_2(010)$ and $\text{Fe}_2\text{O}_3/\text{TiO}_2(010)$ than to be taken away by flow gases.

Figure 10 illustrates the electric field's influence on the density of states of

Fe₂O₃/TiO₂ and Fe₂O₃/TiO₂(010) with the adsorbed hydroxyl and hydrogen. The band gap of Fe₂O₃/TiO₂ was approximately 2.30 eV, as shown in the total density state Fe₂O₃/TiO₂ in Figure 10(a). No distinct energy state emerged within the band gap of Fe₂O₃/TiO₂, concurring with the PL profile of Fe₂O₃/TiO₂. Additionally, the projected density state showed that the profile of Fe 3d mainly resided on the edge of the conduction band. Figure 10(b)-(d) shows that the band gaps of Fe₂O₃/TiO₂(010) with adsorbed hydroxyl and hydrogen with and without an electric field were all 2.30 eV, suggesting the external electric field did not change the magnitude of the band gap of Fe₂O₃/TiO₂(010). However, without the electric field, a few energy states were distributed within the band gap for the Fe₂O₃/TiO₂(010) that had adsorbed hydroxyl and hydrogen; these energy states were mainly derived from the interaction between Fe 3d and the sp hybrid orbitals of the surface hydrogen and oxygen atoms, indicating a strong bond formed between the Fe and atom oxygen and hydrogen, as shown in Figure 10(b). However, once the positive electric field was applied to the Fe₂O₃/TiO₂(010) with adsorbed hydroxyl and hydrogen, most of the band gap density states vanished, particularly at the higher energy level. Only two states closer to the valance band margin remained, revealing that the bond energy between the Fe3d and hybrid OH orbitals became more stable under a positive electric field, thus promoting the bond to be much stronger (see Figure 10(c)). In contrast, if a negative electric field was added, the location and number of the energy state remained almost unchanged, suggesting that a negative direction less influenced the bond of the Fe 3d and OH hybrid orbitals, as illustrated in Figure 10(d).

The Fermi level of $\text{Fe}_2\text{O}_3/\text{TiO}_2$, which is defined herein as the top of the valence band, was -0.72 eV, while that of $\text{Fe}_2\text{O}_3/\text{TiO}_2$ + hydroxyl + hydrogen was 1.12 eV, as shown in Figure 10(a) and (b). The remarkable shift of the Fermi level towards the conduction band margin for $\text{Fe}_2\text{O}_3/\text{TiO}_2$ + hydroxyl + hydrogen resulted from the new mid-gap state of the interaction between Fe 3d and atop hydrogen and oxygen atoms. When an external positive electric field was applied to the slab, the Fermi level (0.09 eV) decreased markedly in comparison to that without an electric field, as shown in Figure 10(c). This implied that the positive electric field attracted more positive charges that accumulated on the surface of $\text{Fe}_2\text{O}_3/\text{TiO}_2$, thus decreasing the Fermi level (Tiewcharoen et al., 2017), which was beneficial for splitting H_2O . In contrast, under the negative electric field, the Fermi level shifted towards a much higher energy level, reaching 1.40 eV, suggesting that the negative electric field resulted in more negative electric charges distributed on the surface, thus notably lifting the Fermi level, but decreasing the formation of hydroxyl and hydrogen.

3.3 Photoelectric Activity

The photocatalytic and photoelectric removal efficiencies of CHOH by neat TiO_2 , and 0.5-5.0% $\text{Fe}_2\text{O}_3/\text{TiO}_2$ were determined without the addition of H_2O , as illustrated in Figure 11. Figure 11(a) displays that without UV irradiation, the removal efficiency by neat TiO_2 was approximately 64%, suggesting that even if no UV was exploited, TiO_2 could adsorb CHOH via the interactions between the surface Ti of TiO_2 and the oxygen atom of CHOH, as well as the surface oxygen and carbon atom of CHOH. Then, the two hydrogen atoms of CHOH were further separated (Wu et al., 2018). The isolated

fragments of C-O and H then reacted with O₂ to produce CO₂ and H₂O. The Fe₂O₃/TiO₂s had a much higher removal efficiency than neat TiO₂, reaching more than 80%, particularly for 3%Fe₂O₃/TiO₂, which had the highest removal efficiency of 86% among these catalysts. The enhancement of the removal efficiency by Fe₂O₃/TiO₂ was probably due to the stronger interaction between the surface Fe₂O₃/TiO₂ and CHOH than between TiO₂ and CHOH, whose adsorption energies were determined to be -1.49 and -1.08 eV, respectively, as illustrated in Figure S-1. When an external voltage of 150 V was introduced into the reactor, the removal efficiencies were nearly the same as those without the addition of applied voltage for both TiO₂ and Fe₂O₃/TiO₂s, conveying that an external voltage of 150 V on the catalysts could not directly influence the interaction between CHOH and TiO₂ (Fe₂O₃/TiO₂s).

Figure 11(b) shows that when the UV irradiation was added, the photocatalytic removal efficiencies of CHOH were approximately 68% and 85-97% by TiO₂ and Fe₂O₃/TiO₂s, respectively, an overall increase of 5-10% compared with their removal efficiency without UV irradiation. The increase in the removal efficiencies was attributed to the oxidation of CHOH by hydroxyl radicals derived from the photoinduced holes with surface adsorbed H₂O, as described by Eqs. (11)-(12),

Additionally, the increment contributed by Fe₂O₃/TiO₂s was 7-10%, much higher than 5% by TiO₂, owing to the interfacial transportation of photoinduced electrons and a lower electrical impedance of Fe₂O₃/TiO₂. When the electric field and UV irradiation

were simultaneously applied to the reaction system, the removal efficiencies of CHOH were not further enhanced, suggesting that the interaction between the surface Ti and Fe atoms and CHOH could not be influenced by such a relatively low electric field, even if electrons had moved freely within their conduction band.

When a mixed flue gas with a relative humidity of 50% was supplied into the reactor, the removal efficiencies of CHOH by TiO_2 and 0.5-5% $\text{Fe}_2\text{O}_3/\text{TiO}_2$ under irradiation or not were all depressed compared to those without H_2O interference, as illustrated in Figure 12(a) and (b), indicating that H_2O caused competitive adsorption with CHOH. Nevertheless, either the catalytic (41%) or photocatalytic (51%) removal efficiencies of CHOH by TiO_2 were lower than 54-60% and 70-80% by 0.5-5% $\text{Fe}_2\text{O}_3/\text{TiO}_2$, implying that the decoration of Fe_2O_3 can relieve H_2O inhibition to some degree. When an external voltage of 150 V was introduced, the catalytic removal efficiencies of CHOH by TiO_2 and $\text{Fe}_2\text{O}_3/\text{TiO}_2$ were still not enhanced without irradiation. Noticeably, once UV irradiation was added, their photocatalytic activity was markedly promoted, and the removal efficiencies had increased by approximately 5% and 10% for TiO_2 and $\text{Fe}_2\text{O}_3/\text{TiO}_2$, respectively. Consistent with the DFT results, the combined effect of the applied electric field and UV irradiation on the $\text{Fe}_2\text{O}_3/\text{TiO}_2$ was more beneficial for enhancing the removal efficiency of CHOH than TiO_2 . Additionally, the pH of the effluent gas during the photoelectrical catalytic degradation of CHOH under a relative humidity of 50% was sampled at the outlet and measured to be neutral, experimentally revealing that the protons were not taken away by the carrier gases with the external electric field. Additionally, after the reaction finished, we observed that the

Fe₂O₃/TiO₂ retained the same faint, slightly yellowish as it had when it was fresh, revealing that the electric field-assisted photooxidation of CHOH on Fe₂O₃/TiO₂ does not cause an accumulation of photogenerated electrons or holes on the Fe₂O₃/TiO₂, therefore avoiding drastic changes in its structure. The photogenerated holes were principally distributed on Fe₂O₃, which finally participated in the formation of hydroxyl radicals to oxidize CHOH. The photogenerated electrons trapped by the Ti³⁺ had different reaction pathways, dominantly including a) reacting with O₂ to produce ·O₂⁻ for CHOH oxidation or directly participating in the attachment of the carbonyl of CHOH to Ti³⁺ (Cremer et al., 2014), or (b) moving towards the positive electrode of the input DC device, particularly for those produced by the TiO₂ or Fe₂O₃/TiO₂ nanogranules having physical contact with the mesh plates.

Additionally, the photoelectrical removal efficiencies of CHOH under different relative humidity (20-80%) conditions were much higher than their photooxidation efficiency of CHOH, as illustrated in Figure S-2. Therefore, combining the DFT and EPR results, the resistance to the competitive adsorption of H₂O was attributed to the more hydroxyl radicals were photoelectrical splitting of H₂O molecules.

By adjusting the distance between the two mesh plates to change the electric field's strength, we investigated the relationship between the applied electric field's strength and the incremental change in removal efficiency and rate compared to those of the samples without an applied electric field, as shown in Figure 13(a). The results illustrated that the removal efficiencies of CHOH by 3%Fe₂O₃/TiO₂ were $74.3 \pm 1.83\%$, $76.8 \pm 1.57\%$, $86.8 \pm 1.30\%$, and $89.9 \pm 1.57\%$, under electric field strengths of 0, 2500,

5000, and 7500 V/m, respectively, suggesting an increase in the removal efficiencies with the electric field strength. However, the relationship between the increments of removal rate and the electric field magnitude was not a good linear relationship, as illustrated in Figure 13(b). The results implied that the formation of free energy of hydroxyl depends on the electric field strength, and other reaction parameters such as the energy barrier are possibly influenced

The removal rates of CHOH with various low levels of power input were compared in Figure 14. Without competitive adsorption of H₂O, 15-W lump irradiation could improve the removal rates by 7% and 10%, reaching maximum removal rates of 2954 and 4129 ng/g/min for TiO₂ and 3% Fe₂O₃/TiO₂, respectively, while the 5-W electric field contributed little to the enhancement. Under a relative humidity of 50%, the removal rates of CHOH significantly dropped for both TiO₂ and Fe₂O₃/TiO₂ without any input energy. However, after introducing 15-W irradiation, the removal rates of CHOH increased by 26% and 24% for TiO₂ and 3% Fe₂O₃/TiO₂, respectively. Moreover, the 5-W electric field was further added, the removal rates increased further by 13% and 23%, particularly for 3% Fe₂O₃/TiO₂, which had nearly the same efficacy as the 15-W input power. Additionally, the final photoelectrocatalytic oxidation rate reached 3747 ng/g/min for 3% Fe₂O₃/TiO₂, which approached its highest H₂O-free removal rate of 4130 ng/g/min. Therefore, a total of 20-W low-power input was verified to effectively resist the inhibition of H₂O on the CHOH removal by 3%Fe₂O₃/TiO₂.

Conclusions

The photoelectric removal of CHOH by TiO₂ and 0.5-5.0%Fe₂O₃/TiO₂ in a humid

environment was theoretically and experimentally investigated in this study. The DFT results demonstrated that a positive electric field was beneficial for splitting H₂O into a hydroxyl and a hydrogen atom on TiO₂ and Fe₂O₃/TiO₂ than a negative electric field, and without any electric fields. The Fe₂O₃ decoration can enhance the formation of hydroxyls than TiO₂ under the positive electric field. The DOS result showed that the bond energy of Fe 3d orbital and the sp hybrid orbital of OH decreased to a lower energy state, thus leading to the hydroxyl formation. Additionally, it was favorable for the dissociated hydrogen atom from the H₂O molecule to attach to the surface of catalysts rather than being transported by flow gas. The experimental results demonstrated that the addition of a low-energy external field could not directly improve the removal efficiency of CHOH but could relieve the adsorptive adsorption of the H₂O molecule, concurring with the DFT results. Fe₂O₃/TiO₂ exhibited a higher H₂O resistance than TiO₂, which was attributed to more hydroxyl radicals produced on Fe₂O₃/TiO₂. In the future, we will focus on the influence of a high-voltage electric field on the photooxidation of CHOH by more active modified TiO₂, and investigate the direct influence of dipole moment of CHOH, adsorption of CHOH.

Acknowledgment

This study was performed under the auspices of the Xiamen Science & Technology Plan, under the contract number of 3502Z20183026, the National Key Research and Development Program (2019YFC0214305), and the National Natural Science Foundation of China, China, (Grant No. 51908230). The authors are grateful to their financial supports in order to accomplish this study. **The supplemented materials have**

616 **other 1 table and 2 figures.**

617

Ethics approval and consent to participate: Not applicable

Consent for publication: Not applicable

Competing interests: The authors declare that they have no competing interests

Availability of data and materials: Not applicable

Funding: This study was performed under the auspices of the Xiamen Science & Technology Plan, under the contract number of 3502Z20183026, the National Key Research and Development Program (2019YFC0214305), and the National Natural Science Foundation of China, China, (Grant No. 51908230). W. Xia gratefully acknowledge the support from the Department of Civil & Environmental Engineering at North Dakota State University.

Authors' contributions: Not applicable

Dong Jing: Writing-original draft preparation; Data curation; Methodology.

Li Qing: Data curation; Methodology.

Xia Wenjie: Writing-reviewing and editing; Software; Validation.

Lv Bihong: Writing-reviewing and editing.

Jing Guohua: Writing-reviewing and editing.

Shen Huazhen: Conceptualization; Writing-reviewing and editing.

Yuan Chung-shin: Conceptualization; Writing-reviewing and editing.

References

- Abdullah SA, Sahdan MZ, Nafarizal N, Saim H, Bakri AS, Rohaida CHC, Adriyanto F, Sari Y (2018) Photoluminescence study of trap-state defect on TiO₂ thin films at different substrate temperature via RF magnetron sputtering. *J Phys: Conf Ser* 995: 012067.
- Adawiah MARa, Zaidon A, Izreen FAN, Bakar ES, Hamami SM, Paridah MT (2012) Addition of urea as formaldehyde scavenger for low molecular water phenol formaldehyde-treated compeg wood. *J Tropical Forest Sci* 24: 348-357.
- Chang KC, Ji WF, Lai MC, Hsiao YR, Hsu CH, Chuang TL, Wei Y, Yeh JM, Liu WR (2014) Synergistic effects of hydrophobicity and gas barrier properties on the anticorrosion property of PMMA nanocomposite coatings embedded with graphene nanosheets. *Polym Chem* 5: 1049-1056.
- Chen BB, Zhu XB, Crocker M, Wang Y, Shi C (2014) FeO_x-supported gold catalysts for catalytic removal of formaldehyde at room temperature. *Appl Catal, B* 154-155: 73-81.
- Ciancio R, Carlino E, Rossi G, Aruta C, Uccio USd, Vittadini A, Selloni A (2012) Magn'eli-like phases in epitaxial anatase TiO₂ thin films. *Phys Rev B* 86: 104110.
- Cremer T, Jensen SC, Friend CM (2014) Enhanced photo-oxidation of formaldehyde on highly reduced o-TiO₂(110). *J Phys Chem C* 118: 29242-29251.
- Deshlahra P, Wolf EE, Schneider WF (2009) A periodic density functional theory analysis of CO chemisorption on Pt(111) in the presence of uniform electric fields. *J Phys Chem A* 113: 4125-4133.
- Ding CS, Nohira T, Hagiwara R (2017) TiO₂-Fe₂O₃ nanocomposites as high-capacity negative electrode materials for rechargeable sodium-ion batteries. *Sustainable Energy & Fuels* 1: 371-376.
- Ding JJ, Rui ZB, Lyu PT, Liu YL, Liu XK, Ji HB (2018) Enhanced formaldehyde oxidation performance over Pt/ZSM-5 through a facile nickel cation modification. *Appl Surf Sci* 457: 670-675.
- Duan ZY, Henkelman G (2019) Theoretical resolution of the exceptional oxygen reduction activity of Au(100) in alkaline media. *ACS Catal* 9: 5567-5573.
- Fang J, Bi XZ, Si DJ, Jiang ZQ, Huang WX (2007) Spectroscopic studies of interfacial structures of CeO₂-TiO₂ mixed oxides. *Appl Surf Sci* 253: 8952-8961.
- Filhol JS, Neurock M (2006) Elucidation of the electrochemical activation of water over Pd by first principles. *Angew Chem Int Ed* 45: 402-406.
- Guo JH, Lin CX, Jiang CJ, Zhang PY (2019) Review on noble metal-based catalysts for formaldehyde oxidation at room temperature. *Appl Surf Sci* 475: 237-255.
- Huang RK, Liang RW, Fan HM, Ying SM, Wu L, Wang XX, Yan GY (2017) Enhanced photocatalytic fuel denitrification over TiO₂/α-Fe₂O₃ nanocomposites under visible light irradiation. *Sci Rep* 7: 7858.
- Huang ZW, Du YY, Zhang J, Wu XM, Shen HZ, Jing GH (2019) Exceptional activity over the submonolayer MoO₃ motif on TiO₂ for nitrogen oxide emission abatement. *Environ Sci Technol* 53: 5309-5318.

- Jörg N, Matthias S (1992) Adsorbate-substrate and adsorbate-adsorbate interactions of Na and K adlayers on Al(111). *Phys Rev B* 46: 16067-16080.
- Jørgensen JE, Mosegaard L, Thomsen LE, Jensen JR, Hanson JC (2007) Formation of γ -Fe₂O₃ nanoparticles and vacancy ordering: An in situ X-ray powder diffraction study. *J Solid State Chem* 180: 180-185.
- Kim KH, Jahan SA, Lee JT (2011) Exposure to formaldehyde and its potential human health hazards. *J Environ Sci Health Part C-Environ Carcinog Ecotoxico Rev* 29: 277-299.
- Kodan N, Agarwal K, Mehta BR (2019) All-oxide α -Fe₂O₃/H:TiO₂ heterojunction photoanode: A platform for stable and enhanced photoelectrochemical performance through favorable band edge alignment. *J Phys Chem C* 123: 3326-3335.
- Li R, Huang Y, Zhu DD, Ho WK, Lee SC, Cao JJ (2020) A Review of Co₃O₄-based Catalysts for Formaldehyde Oxidation at Low Temperature: Effect parameters and reaction mechanism. *Aerosol Sci Eng* 4: 147-168.
- Liang WJ, Li J, Jin YQ (2012) Photo-catalytic degradation of gaseous formaldehyde by TiO₂/UV, Ag/TiO₂/UV and Ce/TiO₂/UV. *Build Environ* 51: 345-350.
- Liu J, Yang SL, Wu W, Tian QY, Cui SY, Dai ZG, Ren F, Xiao XH, Jiang CZ (2015) 3D flowerlike α -Fe₂O₃@TiO₂ core-shell nanostructures: general synthesis and enhanced photocatalytic performance. *ACS Sustain Chem Eng* 3:2975-2984.
- Liu J, Olds D, Peng R, Yu L, Foo GS, Qian S, Keum J, Guiton BS, Wu ZL, Page K (2017) Quantitative analysis of the morphology of {101} and {001} faceted anatase TiO₂ nanocrystals and its implication on photocatalytic activity. *Chem Mater* 29: 5591-5604.
- Lozovoi AY, Alavi A (2003) Reconstruction of charged surfaces: General trends and a case study of Pt(110) and Au(110). *Phys Rev B* 68: 245416.
- Malik AS, Liu TF, Dupuis M, Li RG, Li C (2020) Water oxidation on TiO₂: A comparative DFT study of 1e⁻, 2e⁻, and 4e⁻ processes on rutile, anatase, and brookite. *J Phys Chem C* 124: 8094-8100.
- Mansour H, Omri K, Bargougui R, Ammar S (2020) Novel α -Fe₂O₃/TiO₂ nanocomposites with enhanced photocatalytic activity. *Appl Phys A* 126: 151.
- Maslen EN, Streltsov VA, Streltsova NR, N. Ishizawa (1994) Synchrotron X-ray study of the electron density in α -Fe₂O₃. *Acta Crystallographica Section B* 50: 435-441.
- Miao L, Wang JL, Zhang PY (2019) Review on manganese dioxide for catalytic oxidation of airborne formaldehyde. *Appl Surf Sci* 466: 441-453.
- Moniz SJA, Shevlin SA, An X, Guo ZX, Tang Jw (2014) Fe₂O₃-TiO₂ nanocomposites for enhanced charge separation and photocatalytic activity. *Chem-A Europe J* 20: 15571-15579.
- Nie LH, Yu JG, Jaroniec M, Tao FF (2016) Room-temperature catalytic oxidation of formaldehyde on catalysts. *Catal Sci Technol* 6: 3649-3669.
- Nørskov JK, Rossmeisl J, Logadottir A, Lindqvist J, Kitchin JR, Bligaard T, Jónsson H (2004) Origin of the overpotential for oxygen reduction at a fuel-cell cathode. *J Phys Chem B* 108: 17886-17892.
- Pan J, Liu G, Lu GQ, Cheng HM (2011) On the true photoreactivity order of {001},

724 {010}, and {101} facets of anatase TiO₂ crystals. *Angew Chem Int Ed* 50: 2133-
725 2137.

726 Pawan K, Heung NL, Rajesh K (2014) Synthesis of phase pure iron oxide polymorphs
727 thin films and their enhanced magnetic properties. *J Mater Sci: Mater Electron* 25:
728 4553-4561.

729 Piva DH, Piva RH, Venturini J, Ramon J, Caldas V, Morelli MR, Bergmann CP (2016)
730 Effect of Fe₂O₃ content on the electrical resistivity of aluminous porcelain applied
731 to electrical insulators. *Ceram Int* 42: 5045-5052.

732 Shen Hz, Lin MJ, Wang LD, Huang ZW, Wu XM, Jiang XQ, Li Q, Chen CL, Zhao JX,
733 Jing GH, Yuan CS (2021) Experimental and theoretical investigation of the
734 enhancement of the photo-oxidation of Hg⁰ by CeO₂-modified morphology-
735 controlled anatase TiO₂. *J Hazard Mater* 406: 124535.

736 Shim SH, Bengtson A, Morgan D, Sturhahn W, Catalli K, Zhao JY, Lerche M,
737 Prakapenka V (2009) Electronic and magnetic structures of the postperovskite-type
738 Fe₂O₃ and implications for planetary magnetic records and deep interiors. *Proc Nat*
739 *Acad Sci* 106: 5508.

740 Sun Q, Leng WH, Li Z, Xu Y (2012) Effect of surface Fe₂O₃ clusters on the
741 photocatalytic activity of TiO₂ for phenol degradation in water. *J Hazard Mater*
742 229-230: 224-232.

743 Sun S, Ding JJ, Bao J, Gao C, Qi ZM, Li CX (2010) Photocatalytic oxidation of gaseous
744 formaldehyde on TiO₂: An in-situ DRIFTS study. *Catal Lett* 137: 239-246.

745 Tang XJ, Bai Y, Duong A, Smith MT, Li LY, Zhang LP (2009) Formaldehyde in China:
746 Production, consumption, exposure levels, and health effects. *Environ Int* 35:
747 1210-1224.

748 Tasbihi M, Bendyna JK, Notten P, Hintzen H (2015) A short review on photocatalytic
749 degradation of formaldehyde. *J Nanosci Nanotech* 15: 6386-6396.

750 Tiewcharoen S, Warakulwit C, Lapeyre V, Garrigue P, Fourier L, Elissalde C, Buffière
751 S, Legros P, Marion Gayot, Limtrakul J, Kuhn A (2017) Anisotropic metal
752 deposition on TiO₂ particles by electric-field-induced charge separation. *Angew*
753 *Chem Int Ed* 56: 11431-11435.

754 Tsai CY, Hsi HC, Kuo TH, Chang YM, Liou JH (2013) Preparation of Cu-doped TiO₂
755 photocatalyst with thermal plasma torch for low-concentration mercury removal.
756 *Aerosol Air Qual Res* 13: 639-648.

757 Valdés Á, Qu ZW, Kroes GJ, Rossmeisl J, Nørskov JK (2008) Oxidation and photo-
758 oxidation of water on TiO₂ surface. *J Phys Chem C* 112: 9872-9879.

759 Wang J, Wang JT, Wu XY, Zhang GK (2017) Pt-TiO₂ microspheres with exposed {001}
760 facets for degradation of formaldehyde in air: Formation mechanism and enhanced
761 visible light photocatalytic activity. *Mater Res Bull* 96: 262-269.

762 Wang S, Lian JS, Zheng WT, Jiang Q (2012) Photocatalytic property of Fe doped
763 anatase and rutile TiO₂ nanocrystal particles prepared by sol-gel technique. *Appl*
764 *Surf Sci* 263: 260-265.

765 Wang YS, Wang SR, Zhang HX, Gao XL, Yang JD, Wang LW (2014) Brookite TiO₂
766 decorated α -Fe₂O₃ nanoheterostructures with rod morphologies for gas sensor

767 application. J Mater Chem A 2: 7935-7943.
768 Wu GF, Zhao CH, Guo CQ, Chen JH, Zhang YB, Li YQ (2018) DFT study on the
769 interaction of TiO₂ (001) surface with HCHO molecules. Appl Surf Sci 428: 954-
770 963.
771 Yang S, Zhu ZX, Wei F, Yang XD (2017) Enhancement of formaldehyde removal by
772 activated carbon fiber via in situ growth of carbon nanotubes. Build Environ 126:
773 27-33.
774 Yin L, Adler I, Tsang T, Matienzo LJ, Grim SO (1974) Paramagnetism and shake-up
775 satellites in X-ray photoelectron spectra. Chem Phys Lett 24: 81-84.
776 Yu JG, Wang SH, Low JX, Xiao W (2013) Enhanced photocatalytic performance of
777 direct Z-scheme g-C₃N₄-TiO₂ photocatalysts for the decomposition of
778 formaldehyde in air. Phys Chem Chem Phys 15: 16883-16890.
779 Zhang GX, Sun ZM, Wei Y, Ma R, Zheng S (2017) Synthesis of nano-TiO₂/diatomite
780 composite and its photocatalytic degradation of gaseous formaldehyde. Appl Surf
781 Sci 412: 105-112.
782

Figure captions

Figure 1. Diagram of the photoelectrical catalytic reaction system.

Figure 2. Morphology of TiO_2 (a) SEM, (b)-(c) TEM, (d) size distribution, and 3% $\text{Fe}_2\text{O}_3/\text{TiO}_2$ (e) SEM, (f)-(g) TEM, (h) size distribution.

Figure 3. (a) XRD and (b) Raman patterns of TiO_2 and 0.5-5% $\text{Fe}_2\text{O}_3/\text{TiO}_2$.

Figure 4. Binding energies of (a) Ti 2p_{1/2}, Ti 2p_{3/2} for TiO_2 and 3% $\text{Fe}_2\text{O}_3/\text{TiO}_2$, and (b) Fe 2p_{1/2}.

Figure 5. UV-Visible spectra of TiO_2 , 0.5-5% $\text{Fe}_2\text{O}_3/\text{TiO}_2$, and Fe_2O_3 .

Figure 6. (a) PL spectra, (b) simulated EIS, and (c) LSV patterns of TiO_2 and 0.5-5% $\text{Fe}_2\text{O}_3/\text{TiO}_2$.

Figure 7. (a) Mott-Schottky plots of TiO_2 , 0.5-5% $\text{Fe}_2\text{O}_3/\text{TiO}_2$, and Fe_2O_3 at 100 Hz using an Ag/AgCl electrode at pH=7.0, (b) electronic structure of TiO_2 and 0.5-5% $\text{Fe}_2\text{O}_3/\text{TiO}_2$, (c) schematic diagram of photogenerated electron-hole pairs transferring at the interface of $\text{Fe}_2\text{O}_3/\text{TiO}_2$, and Fe_2O_3 .

Figure 8. EPR patterns of TiO_2 and $\text{Fe}_2\text{O}_3/\text{TiO}_2$.

Figure 9. Free energy of formation of (a) slab + hydroxyl + H, and (b) slab + hydroxyl.

Figure 10. Projected density of state for bare $\text{Fe}_2\text{O}_3/\text{TiO}_2$ (a), $\text{Fe}_2\text{O}_3/\text{TiO}_2$ + hydroxyl + hydrogen (b) without an electric field, (c) $\text{Fe}_2\text{O}_3/\text{TiO}_2$ + hydroxyl + hydrogen with a positive electric field, and (d) with a negative electric field, respectively. Dashed lines denote the Fermi level.

Figure 11. Removal efficiency of CHOH by neat TiO_2 and 0.5-5% $\text{Fe}_2\text{O}_3/\text{TiO}_2$ without H_2O , (a) in the absence and (b) presence of UV irradiation.

Figure 12. Removal efficiency of CH_2O by neat TiO_2 and 0.5-5% $\text{Fe}_2\text{O}_3/\text{TiO}_2$ at a relative humidity of 50%, (a) in the absence and (b) presence of UV irradiation.

Figure 13. (a) Removal efficiency of CHOH by 3% $\text{Fe}_2\text{O}_3/\text{TiO}_2$, and (b) increment of the removal rates of CHOH by 3% $\text{Fe}_2\text{O}_3/\text{TiO}_2$ at a relative humidity of 50% under different strengths of electric field.

Figure 14. Removal rate of CHOH with different energy input (a) without H_2O , and (b) with H_2O .

Figure 1. Diagram of the photoelectrical catalytic reaction system.

Figure 2. Morphology of TiO_2 (a) SEM, (b)-(c) TEM, (d) size distribution, and $3\%\text{Fe}_2\text{O}_3/\text{TiO}_2$ (e) SEM, (f)-(g) TEM, (h) size distribution.

Figure 3. (a) XRD and (b) Raman patterns of TiO_2 and 0.5-5% $\text{Fe}_2\text{O}_3/\text{TiO}_2$.

Figure 4. Binding energies of (a) Ti 2p_{1/2}, Ti 2p_{3/2} for TiO₂ and 3%Fe₂O₃/TiO₂, and (b) Fe 2p_{1/2}.

Figure 5. UV-Visible spectra of TiO_2 , 0.5-5% $\text{Fe}_2\text{O}_3/\text{TiO}_2$, and Fe_2O_3 .

Figure 6. (a) PL spectra, (b) simulated EIS, and (c) LSV patterns of TiO₂ and 0.5-5%Fe₂O₃/TiO₂.

(c)

Figure 7. (a) Mott-Schottky plots of TiO₂, 0.5-5%Fe₂O₃/TiO₂, and Fe₂O₃ at 100 Hz using an Ag/AgCl electrode at pH=7.0, (b) electronic structure of TiO₂ and 0.5-5%Fe₂O₃/TiO₂, (c) schematic diagram of photogenerated electron-hole pairs transferring at the interface of Fe₂O₃/TiO₂, and Fe₂O₃.

Figure 8. EPR patterns of TiO₂ and Fe₂O₃/TiO₂.

Figure 9. Free energy of formation of (a) slab + hydroxyl + H, and (b) slab + hydroxyl.

Figure 10. Projected density of state for bare $\text{Fe}_2\text{O}_3/\text{TiO}_2$ (a), $\text{Fe}_2\text{O}_3/\text{TiO}_2$ + hydroxyl + hydrogen (b) without an electric field, (c) $\text{Fe}_2\text{O}_3/\text{TiO}_2$ + hydroxyl + hydrogen with a positive electric field, and (d) with a negative electric field, respectively. Dashed lines denote the Fermi level.

Figure 11. Removal efficiency of CHOH by neat TiO_2 and 0.5-5% $\text{Fe}_2\text{O}_3/\text{TiO}_2$ without H_2O , (a) in the absence and (b) presence of UV irradiation. The overall flow rate of 700 mL/min, influent CHOH concentration of 1.50 ppm, the mass of 0.3 g catalysts, the power of 15 W for UV irradiation, and 5 W for the electric field.

Figure 12. Removal efficiency of CH_2O by neat TiO_2 and 0.5-5% $\text{Fe}_2\text{O}_3/\text{TiO}_2$ at a relative humidity of 50%, (a) in the absence and (b) presence of UV irradiation. The overall flow rate of 700 mL/min, influent CHOH concentration of 1.50 ppm, the mass of 0.3 g catalysts, the power of 15 W for UV irradiation, and 5 W for the electric field.

Figure 13. (a) Removal efficiency of CHOH by 3%Fe₂O₃/TiO₂, and (b) increment of the removal rates of CHOH by 3%Fe₂O₃/TiO₂ at a relative humidity of 50% under different strengths of electric field. The overall flow rate of 700 mL/min, influent CHOH concentration of 1.50 ppm, the mass of 0.3 g catalysts, the power of 15 W for UV irradiation, and 5 W for the electric field.

Figure 14. Removal rate of CHOH with different energy input (a) without H_2O , and (b) with H_2O .

Figures

Figure 1
Diagram of the photoelectrical catalytic reaction system.

Figure 2

Morphology of TiO₂ (a) SEM, (b)-(c) TEM, (d) size distribution, and 3%Fe₂O₃/TiO₂ (e) SEM, (f)-(g) TEM, (h) size distribution.

Figure 3

(a) XRD and (b) Raman patterns of TiO₂ and 0.5-5%Fe₂O₃/TiO₂.

Figure 4

Figure 4. Binding energies of (a) Ti 2p_{1/2}, Ti 2p_{3/2} for TiO₂ and 3%Fe₂O₃/TiO₂, and (b) Fe 2p_{1/2}.

Figure 5

UV-Visible spectra of TiO_2 , 0.5-5% $\text{Fe}_2\text{O}_3/\text{TiO}_2$, and Fe_2O_3 .

Figure 6

(a) PL spectra, (b) simulated EIS, and (c) LSV patterns of TiO_2 and 0.5-5% $\text{Fe}_2\text{O}_3/\text{TiO}_2$.

Figure 7

(a) Mott-Schottky plots of TiO_2 , 0.5-5% $\text{Fe}_2\text{O}_3/\text{TiO}_2$, and Fe_2O_3 at 100 Hz using an Ag/AgCl electrode at pH=7.0, (b) electronic structure of TiO_2 and 0.5-5% $\text{Fe}_2\text{O}_3/\text{TiO}_2$, (c) schematic diagram of photogenerated electron-hole pairs transferring at the interface of $\text{Fe}_2\text{O}_3/\text{TiO}_2$, and Fe_2O_3 .

Figure 8

EPR patterns of TiO₂ and Fe₂O₃/TiO₂.

Figure 9

Free energy of formation of (a) slab + hydroxyl + H, and (b) slab + hydroxyl.

Figure 10

Projected density of state for bare Fe₂O₃/TiO₂ (a), Fe₂O₃/TiO₂ + hydroxyl + hydrogen (b) without an electric field, (c) Fe₂O₃/TiO₂ + hydroxyl + hydrogen with a positive electric field, and (d) with a negative electric field, respectively. Dashed lines denote the Fermi level.

Figure 11

Removal efficiency of CHOH by neat TiO₂ and 0.5-5%Fe₂O₃/TiO₂ without H₂O, (a) in the absence and (b) presence of UV irradiation.

Figure 12

Removal efficiency of CH₂O by neat TiO₂ and 0.5-5%Fe₂O₃/TiO₂ at a relative humidity of 50%, (a) in the absence and (b) presence of UV irradiation.

Figure 13

(a) Removal efficiency of CHOH by 3%Fe₂O₃/TiO₂, and (b) increment of the removal rates of CHOH by 3%Fe₂O₃/TiO₂ at a relative humidity of 50% under different strengths of electric field.

Figure 14

Removal rate of CHOH with different energy input (a) without H₂O, and (b) with H₂O.

Supplementary Files

This is a list of supplementary files associated with this preprint. Click to download.

- [Supplementarymaterials.docx](#)