Effect of Diameter, Length, and Chirality on the Properties of Silicon Nanotubes

Mohsen Motamedi (✉ motamedi@shahreza.ac.ir)

Faculty of Engineering, University of Shahreza, P. O. Box 86149-56841, Isfahan, Iran,
<https://orcid.org/0000-0003-3296-4253>

Erphan Safdari

University of Shahreza

Original paper

Keywords: Silicon nanotube, Chirality, Mechanical properties, Molecular dynamics

Posted Date: February 4th, 2021

DOI: <https://doi.org/10.21203/rs.3.rs-173866/v1>

License: © ⓘ This work is licensed under a Creative Commons Attribution 4.0 International License.

[Read Full License](#)

Effect of diameter, length, and chirality on the properties of Silicon nanotubes

Mohsen Motamedi ¹, Erphan Safdari ²

¹ Faculty of Engineering, University of Shahreza, P. O. Box 86149-56841, Isfahan, Iran,
motamedi@shahreza.ac.ir, Tel.: +98 315 323 8379

² Faculty of Engineering, University of Shahreza, P. O. Box 86149-56841, Isfahan, Iran,
erphansafdari@gmail.com

Abstract

The mechanical properties of nanostructures are a researcher's favorite topics. In the meantime, the mechanical and physical properties of the two dimensional structures and the nanotubes have attracted greater attention due to their wide application. Si (Si) nanotubes are structures consisting of Si atoms that are aligned as honeycombs (hexagonal). This structure has created some special properties in Si nanotubes. In this paper, Young's modulus values and stress strain diagrams of Si nanotubes are investigated using molecular dynamics method and the Tersoff potential. Then, the changes effect of size and dimension was investigated for a closer look. For this purpose, the effect of nanotube diameter, length, and chirality shift from zigzag to armchair were studied. The results showed that the fracture stress of nanotube decreased with increasing the length of Si nanotube. It was also shown that the armchair structure was stronger than the zigzag. The effect of diameter change on the mechanical properties was also investigated and it was observed that no specific order could be found between the diameter changes with the Si nanotube strength. The results were in good agreement with other studies.

Keywords: Silicon nanotube; Chirality; Mechanical properties; Molecular dynamics;

1. Introduction

Much of the changes we can make at the material structure to improve their performance are in the nano dimension, and these properties in the nanostructure are not industry specific and exist in nature, and these nanostructures with useful features are always being produced [1-5] such as self-cleaning lotus leaves [6] and butterfly wings colors [7], photoreceptor in brittlestar [8], and anti-reflection eyes of moth [9]. Nanostructures especially Si nanotubes are used at the production of sensors and biosensors [10-15], anode of cells [16-19], solar cell [20-22], transistors [23-25], fuel batteries and biological materials[26], energy storages [27 and 28], rechargeable lithium batteries [29-31], actuators [32] and generation of power sources[21] .

Furthermore, Fahad et al. [23] have pointed out the usefulness and effectiveness of using Si nanotubes in tunnel field-effect transistor. Kunjie et al. [14] found that Si nanotube had a stronger interaction with carbon monoxide (CO) and nitrogen monoxide (NO) compared to carbon nanotube, which could increase the sensitivity of detection and recognition of Si nanotube to these two CO and

NO. Si nanotube converts to metallic state after absorption of carbon monoxide and, if Si nanotube is combined with nitrogen monoxide (NO), will have magnetism properties. Si nanotube is a good option for use in sensors of detection and recognition a carbon monoxide and nitrogen monoxide. Park et al. [17] studied the importance of Si nanotube as a battery anode due to its high charge capacity as well as 89% columbic efficiency and 10 fold capacity per each 200 cycles. Lan et al. [33] studied the Si nanotube and carbon nanotube and compared the capacity of these nanotubes for hydrogen absorption at room temperature (298 K) and pressure of 1 to 10 MPa. In that study, Si nanotube was introduced as a better option for hydrogen absorption. They had found by studying the structure of Si nanotube that rhombic structure (state) of Si nanotube was more capable of hydrogen absorption. They studied the three armchair nanotubes (5-5), (7-7), and (9-9) at 298 K and pressure of 4 to 10 MPa to predict the behavior of the Si nanotube with the changes of the diameter. They found that diameter alone did not alter the rate of hydrogen absorption.

In this study, tubes with chirality 7–7 have the highest rate of hydrogen uptake. With the advancement of tool science towards material shrinkage, low heat transfer tools are expanding and becoming more widely used [34].

Li [35] studied Si nanowire and Si bulk with the molecular dynamics method, and found that the heat transfer in Si nanowires is about half of a Si bulk. Chen [36] found at his investigation using molecular dynamics method that the Si nanotube had 33% heat transfer of Si nanowire at room temperature. He showed that it was possible to reduce the heat transfer capability by increasing the surface to the volume of nanotube, and they introduced Si nanotube as a suitable option for thermoelectric devices. Szczech et al. [37] have introduced Si as a high capacity anode of battery and they stated increasing the Si volume when lithiating and delithiating has prevented its commercial application. Furthermore, the other problem of using Si at battery is the poor recovery capability. These problems can be solved by using Si nanostructures. Isfahani et al. [38] have studied the effect of pore shape on the behavior of single crystalline Si np structures using molecular dynamics method. In that paper, the pore with shapes of circular, elliptical, square and hexagonal were investigated and the elastic modulus, ultimate strength, fracture stiffness and hardness are measured. They stated that the H ellipse pore has the highest strength (stiffness). Chan [39], Pozot [40] and Kasavajjula [41] have proposed nanostructures with holes as a suitable option to eliminate and improve the problems of stability and performance. Bai et al. [42] investigated the various structures of single dimensional Si and Si nanotube had introduced as a good alternative to wide bandgap semiconductor.

Much of the stress of Nano dimension tools is due to thermal inconsistencies and networking between different materials. The reliability of many devices in these dimensions depends on the response of nanostructures to mechanical loading. Therefore, a deep and comprehensive understanding of the deforming of mechanisms under external mechanical forces is needed for technology future of nanostructures. Fagan et al. [43] have theoretically investigated the similarities and differences between Carbon and Silicon structures using two methods, i.e., DFT and Monte Carlo (which employs the Tersoff potential). They had investigated the electrical and structural properties of the two material by DFT method and found that these properties were dependent on diameters and chirality. They had shown that Si nanotubes can play both metal (armchair) and semiconductor (zigzag) roles. They had also investigated the thermal behavior of these two structures using the Monte Carlo method. Palaria [44] has investigated the structural properties of Si nanotubes including atomic structure and elastic properties using molecular dynamics and first principle–base force field theory and density functional theory. He measured and published the Si Nanotube Young's modulus at various structural scales. He had shown according the structure that this number varies between 50 and 493 MPa. Zhang et al. [45] investigated the electronic and structural properties of Si nanotube using DFT and found that the structure of Si nanotube in small diameters is metallic and armchair

structure of Si nanotube is more stable. San Paulo [46] investigated the mechanical structure of Si nanowires using the AFM method using the vapor solid liquid method, and he found experimentally that the Young's modulus was 186 GPa. Kang et al. [47] studied Si nanowire using the molecular dynamics method and with applying the MEAM potential and investigated the relationship between temperature and fracture mechanism and he found that the failure mechanism is related to both the diameter of the Si nanowire and the temperature.

Therefore at this paper, according the importance of the effect of nanotube diameter on the mechanical properties, the stress and strain behavior and Si nanotube Young's modulus are investigated using molecular dynamics method and the chirality effect and nanotube length are discussed.

2. Simulation

Molecular dynamics is a powerful method that involves solving the classical many-body problem in contexts relevant to the study of matter at the atomistic level [48]. This simulation is carried out based on the Tersoff potential. Tersoff shows that if this function is used for pair terms, it can be a good starting point for prediction because this potential included a large range of structural features of Si. Earlier, Kang [47] had used this potential to investigate the effect of temperature and size changes of nanowires on the fracture mechanism using molecular dynamics method. As well as Verma and Jeong Won Kang have separately studied Si nanotube structure using this potential [50-52]. This potential follows the following equations:

$$\begin{aligned}
 &1) E = \sum_i E_i = \frac{1}{2} \sum_{i \neq j} V_{ij}, \quad 2) V_{ij} = f_C(r_{ij}) [f_R(r_{ij}) + b_{ij} f_A(r_{ij})]; \\
 &3) f_R(r_{ij}) = A_{ij} \exp(-\lambda_{ij} r_{ij}), \quad 4) f_A(r_{ij}) = -B_{ij} \exp(-\mu_{ij} r_{ij}); \\
 &5) f_C(r_{ij}) = \begin{cases} 1, & r_{ij} < R_{ij} \\ \frac{1}{2} + \frac{1}{2} \cos \Sigma \pi (r_{ij} - R) / (s_{ij} - R_{ij}), & R_{ij} < r_{ij} < s_{ij} \\ 0, & r_{ij} > s_{ij} \end{cases} \\
 &6) b_{ij} = \chi_{ij} \left(1 + \beta_i^{n_i} \zeta_{ij}^{n_i}\right)^{-1/2n_i}, \quad 7) \zeta = \sum_{k \neq i, j} f_C(r_{ik}) \omega_{ik} g(\theta_{ijk}), \\
 &8) g(\theta_{ijk}) = 1 + c_i^2 / d_i^2 - c_i^2 / [d_i^2 + (h_{i-\cos} \theta_{ijk})^2] \\
 &9) \lambda_{ij} = (\lambda_i + \lambda_j) / 2, \quad 10) \mu_{ij} = (\mu_i + \mu_j) / 2, \quad 11) A_{ij} = (A_i A_j)^{1/2}, \quad 12) B_{ij} = (B_i B_j)^{1/2}, \\
 &13) A_{ij} = (A_i A_j)^{1/2}, \quad 14) R_{ij} = (R_i R_j)^{1/2}, \quad 15) S_{ij} = (S_i S_j)^{1/2}
 \end{aligned}$$

Labels of system atoms are i, j and k and r_{ij} is the bond length and θ_{ijk} is the angle between the bonds. n_i and λ_i , only depend on the type of atom (carbon, Si, Ge). E is the total energy of the system and E_i is the site energy. V_{ij} is bond energy between atoms i and j. The function f_R states a repulsive pair potential, which includes the orthogonalization energy when atomic wave functions overlap. f_A displays an attractive pair potential associated with bonding. Function of f_A and f_R represents the repulsion and attraction potential between two atoms, respectively. The extra term f_C

is merely a smooth cutoff function to limit the range of the potential. The function b_{ij} is the sole novel feature of the potential. It represents a measure of the bond order, and is for now assumed to be a monotonically decreasing function of the coordination of atoms i and j . Parameter of ω_{ij} (where $\omega_{ii}=1$) are available for possible future use that permit greater flexibility when dealing with more drastically different types of atoms.

The value of 1 is considered for χ and ω in this calculation. Other values are shown at Table 1.

Table1: used parameters at the Tersoff potential

<i>Parameters</i>	<i>C</i>	<i>Si</i>	<i>Ge</i>
<i>A</i> (eV)	1.3936×10^3	1.8308×10^3	1.769×10^3
<i>B</i> (eV)	3.467×10^2	4.7118×10^2	4.1923×10^2
λ ($\text{\AA}^{-1}$)	3.4879	2.4799	2.4451
μ ($\text{\AA}^{-1}$)	2.2119	1.7322	1.7047
β	1.5724×10^{-7}	1.1000×10^{-6}	9.0166×10^{-7}
<i>n</i>	1.5724×10^{-7}	7.8734×10^{-1}	7.5627×10^{-1}
<i>C</i>	3.8049×10^4	1.0039×10^5	1.0643×10^5
<i>d</i>	4.384×10^0	1.6217×10^1	1.5652×10^1
<i>h</i>	-5.7058×10^{-1}	-5.9825×10^{-1}	-4.3884×10^{-1}
<i>R</i> ($\text{\AA}$)	1.8	2.7	2.8
<i>S</i> ($\text{\AA}$)	2.1	3.0	3.1
$\chi_{C-Si}=0.9776$		$\chi_{Si-Ge} = 1.0061$	

3. Results and discussion

In this simulation, we try to predict the behavior of stretched Si nanotubes in different shapes. In this process, the nanotube is first relaxed and then the two its sides are fixed at the appropriate sizes and moves with a rate of $0.012 \text{ \AA/ps}$ in the opposite direction and a fillet stress in the nanotube is created by increasing the tension and the nanotube is divided into two parts when the tension reaches to the critical stress limit. In these nanotubes, the distance between the two Si atoms is considered $2.248 \text{ \AA}$ [28 , 36].

The investigation of changes effect of sizes and shapes is divided to three parts:

3.1.The effect of length change on strength

In the first part, three nanotubes with lengths of 100, 200 and $300 \text{ \AA}$ and with chirality of (9-9) and diameter of $19.32 \text{ \AA}$ were simulated in box with $30 \times 30 \times 110$, $30 \times 30 \times 210$ and $30 \times 30 \times 310 \text{ \AA}$ dimension and number of atoms of 936, 1854 and 2790 to study the effect of nanotube length on their strength. Fig 1 Shows the schematic of length comparison of SI nanotube.

Figure 1. schematic of length comparison of Si nanotube

Previously, Peng et al. [53] had investigated the effect of length change on tension strength of multiwall carbon nanotube. They found that tension strength reduced with increasing the length of the nanotube sample. In this simulation, we also obtained similar results and we observed a reduction of critical stress with increasing length of the nanotube sample (Fig. 2). The values are also presented in Table 2. As expected, the value of the critical stress decreases from 27.6 to 24.7 MPa by increasing the nanotube length from 100 to 300Å,

Table 2. Mechanical properties of nanotubes with different lengths

length	Atomicity	chirality	Diameter(A)	Critical stress	Young's modulus(GPa)
100	936	(9-9)	19.32	27.62	168.13±1.06
200	1854	(9-9)	19.32	25.53	197.52±0.6
300	2790	(9-9)	19.32	24.75	205.37±0.58

Figure 2. Stress strain diagram for lengths 100, 200 and 300Å.

3.2. The effect of diameter change on the strength

In the second part, the purpose is to find the effect of nanotube diameter on its strength. For this purpose, four nanotubes with a length of 150 Å and diameters of 12.3, 14.8, 17.3 and 23.5Å and chirality of (0-10), (12-0), (14-0) and (19-0), respectively are stretched at simulation boxes with dimensions of 20×20×160, 30×30×160, 30×30×160 and 40×40×160, and the number of atoms of 890, 1068, 1246 and 1691 (Fig. 3).

Figure 3. schematic comparison of diameters 12.3, 14.8, 17.3 and 23.5 Å

The stress strain diagram is shown in Fig. 4. As can be seen in Figure. 4, there is no particular order between the change in diameter and the strength. The results are also presented in more detail in Table 3. In this simulation, we notice that the nanotube strength is affected by factors other than the diameter of the nanotube and this is similar to the Young's modulus.

Kang [47] had studied the Si nanowires and found that the diameter changes alone did not change the nanotube strength, and other factors such as temperature also influenced the nanotube strength.

Table 3. Mechanical properties of nanotubes of different lengths

Chirality	Atomicity	Length(A)	Diameter(A)	Critical stress	Young's modulus(GPa)
10-0	890	150	12.3	10.65	182.5456±1
12-0	1068	150	14.8	10.39	175.09±0.01
14-0	1246	150	17.3	10.86	183.481±1.038
19-0	1691	150	23.5	11.66	185.173±0.01

Figure 4. stress strain diagram for Si nanotube with diameters 12.3, 14.8, 17.3 and 23.5 Å

3.3. Effect of Chirality on strength

In this part, four nanotubes will be used that each pair have the same diameter and length, and just have different chirality, one zigzag and the other armchair. The nanotubes have a length of 150 Å, a diameter of 14.8 and 17.3 Å, and with chirality of [(12-0) and (7-7)] and [(14-0) and (8-8)] (Fig. 5). The size of the simulation boxes are (30×30×160), (30×30×155) and (30×30×160) and (30×30×160) and the number of atoms are 1092 and 1068 and 1248 and 1246.

Figure 5. Structure schematic comparison of tubes with same diameters and different chirality.

The stress strain diagram for both states is shown in Figure. 6.

Figure 6. Si nanotube stress strain diagrams with different chirality.

The results of these figures are analyzed and presented in Table 4 completely. As can be seen, under the same geometrical conditions, the critical stress of the zigzag nanotube (0-12) is lower than the critical stress of the armchair nanotube (7-7) and furthermore, it has less Young's modulus. The same results are for the zigzag and armchair of nanotubes (0-14) and (8-8), respectively. Therefore, it can be concluded that Si nanotubes with chirality of armchair have more strength and their Young's modulus is higher than zigzag structure. Furthermore, Zhang et al. [45] showed in their study that nanotubes with armchair structure have more strength.

Table 4. Mechanical properties of nanotubes with chirality of zigzag and armchair

Chirality	Atomicity	Length(A)	Diameter(A)	Critical Stress	Young's Modulus (Gpa)
7-7	1092	150	15	15.05	185.07±1.258
0-12	1068	150	14.8	10.39	175.09±0.01
8-8	1248	150	17.17	14.38	183.98±1.159
0-14	1246	150	17.3	10.86	183.481±1.038

Conclusion

In this paper, the Young's modulus values and stress strain diagrams of Si nanotubes are investigated using molecular dynamics method and the Tersoff potential. Then, for a closer look, the changes effect of size and dimension was examined. For this purpose, the change effect of diameter and length of nanotube and the shift effect of chirality from zigzag to armchair were investigated. The results showed that the fracture stress decreased from 276 to 247 MPa with increasing the length of Si nanotube from 100 to 300 Å.

Furthermore, it was shown that the armchair structure has more strength than the zigzag. For example, the elastic modulus of armchair and zigzag were 185 and 175 GPa, respectively for two Si nanotubes with the same diameter and length. The change effect of diameter on the mechanical properties was also investigated and it was observed that no specific order could be found between the diameter change with the strength of Si nanotube and other parameters such as temperature may be involved which should be investigated in future research. The results were in good agreement with other studies.

Declarations

Funding: This research received no specific grant from any funding agency in the public, commercial, or not-for-profit sectors.

Conflicts of interest/Competing interests: The authors declare that there is no conflict of interest

Availability of data and material: The data that support the findings of this study are available from the corresponding author

Code availability: The LAMMPS package is free and open-source software.

Authors' contributions: Both authors contributed to the design and implementation of the research, to the analysis of the results and to the writing of the manuscript.

References:

- 1)Huang, Y. Chattopadhyay, S. Jen, Y. Peng, Y. Liu, T. Hsu, Y. Pan, C. Lo, H. Hsu, C. Chang, Y. Lee, C. Chen, K. Chen, L. “Improved broadband and quasiomnidirectional anti-reflection properties with biomimetic silicon nanostructures”, *Nature Nanotech.*, **2**, pp. 770–774 (2007).
- 2)Lee, L.P. Szema, R. “Inspirations from biological optics for advanced photonic systems”. *Science.*, **310**, pp. 1148–1150 (2005).
- 3)Vukusic, P. Sambles, J. R. “Photonic structures in biology”, *Nature.*, **424**, pp. 852–855 (2003).
- 4)Parker, A. R. Townley, H. E. “Biomimetics of photonic nanostructures”. *Nature Nanotech.*, **2**, pp. 347–353 (2007).
- 5)Potyrailo, R. Ghiradella, H. Vertiatchikh, A. Dovidenko, K. Cournoyer, J. Olson, E. “Morpho butterfly wing scales demonstrate highly selective vapour response”, *Nature Photon.*, **1**, pp. 123–128 (2007).
- 6)Neinhuis, C. Barthlott, W. “Characterisation and distribution of water-repellent, self-cleaning plant surfaces”, *Ann. Bot.*, **79**, pp. 667–677 (1997).
- 7)Ghiradella, H. Aneshansley, D. Eisner, T. Silberglied, R.E. Hinton, H.E. “Ultraviolet reflection of a male butterfly: Interference color caused by thin-layer elaboration of wing scales”, *Science.*, **178**, pp. 1214–1217 (1972).
- 8)Aizenberg, J. Tkachenko, A. Weiner, S. Addadi, L. Hendler, G. “Calcitic microlenses as part of the photoreceptor system in brittlestars”, *Nature.*, **412**, pp. 819–822 (2001).

- 9)Bernhard, C.G. “Structural and functional adaptation in a visual system”, *Endeavour.*, **26**(98), pp. 79–84 (1967).
- 10)Cui, Y. Wei, Q. Park, H. Lieber, C.M. “Nanowire nanosensors for highly sensitive and selective detection of biological and chemical species”, *Science.*, **293**, pp. 1289–1292 (2001b).
- 11)Hahm, J. Lieber, C.M. “Direct ultrasensitive electrical detection of DNA and DNA sequence variations using nanowire nanosensors”, *Nano Letters.*, **4**(1), pp. 51–54 (2004).
- 12)Patolsky, F. Timko, B.P. Yu, G. Fang, Y. Greytak, A.B. Zheng, G. Lieber, C.M., “Detection, simulation, and inhibition of neuron signals with high-density nanowire transistor arrays”, *Science.*, **313**, pp. 1100–1104 (2006).
- 13)Camilli, L. Passacantando, M. “Advances on Sensors Based on Carbon Nanotubes”, *Chemosensors.*, **6**(4), p. 62 (2018).
- 14)Kunjie, Li. Wang, W. Cao, D. “Novel Chemical Sensor for CO and NO: Silicon Nanotube”, *J. Phys. Chem. C.*, **115**(24), pp. 12015–12022 (2011).
- 15)Ji, X. Wang, H. Song, B. Chu, B. He, Y. “Silicon Nanomaterials for Biosensing and Bioimaging Analysis”, *Frontiers in chemistry.*, **6**, p. 38 (2018).
- 16)Chan, C.K. Peng, H. Lui, G. McIlwrath, K. Zhang, X.F. Huggins, R.A. Cui, Y. “High-performance lithium battery anodes using silicon nanowires”, *Nature Nanotechnology.*, **3**, pp. 31–35 (2007).
- 17)Park, M. Kim, M. Joo , J. Kim, K. Kim, J. Ahn, S. Cui, Y. Cho, J. “Silicon Nanotube Battery Anodes”, *Nano Lett.*, **9**(11), pp. 3844–3847 (2009).
- 18)Chou, Sh. Zhao, Y. Wang, J. Chen, Z. Liu, H. Dou, Sh. “Silicon/Single-Walled Carbon Nanotube Composite Paper as a Flexible Anode Material for Lithium Ion Batteries”, *J. Phys. Chem. C.*, **114**(37), pp. 15862–15867 (2010).
- 19)Wu, H. Chan, G. Choi, J. Ryu, I. Yao, Y. McDowell, M.T. Lee, S. Jackson, A. Yang, Y. Hu, L. Cui, Y. “Stable cycling of double-walled silicon nanotube battery anodes through solid electrolyte interphase control”, *Nature Nanotech.*, **7**, pp. 310–315 (2012).
- 20)Jia, Y. Cao, A. Bai, X. Li, Z. Zhang, L. Guo, N. Wei, J. Wang, K. Zhu, H. Wu, D. Ajayan, P.M. “Achieving High Efficiency Silicon - Carbon Nanotube Heterojunction Solar Cells by Acid Doping”, *Nano Lett.*, **11**(5), pp.1901–1905 (2011).
- 21)Tian, B. Zheng, X. Kempa, T.J. Fang, Y. Yu, N. Yu, G. Huang, J. Lieber, C.M. “Coaxial silicon nanowires as solar cells and nanoelectronic power sources”, *Nature.*, **449**, pp. 885–890 (2007).
- 22)Shu, Q. Wei, J. Wang, K. Zhu, H. Li, Z. Jia, Y. Gui, X. Guo, N. Li, X. Ma, C. Wu, D. “Hybrid Heterojunction and Photoelectrochemistry Solar Cell Based on Silicon Nanowires and Double-Walled Carbon Nanotubes”, *Nano Lett.*, **9**, pp. 4338–4342 (2009).
- 23)Fahad, H.M. Hussain, M.M. “High-Performance Silicon Nanotube Tunneling FET for Ultralow-Power Logic Applications”, *IEEE Transactions on Electron Devices.*, **60**(3), pp. 1034 – 1039 (2013).
- 24)Cui, Y. Zhong, Z. Wang, D. Wang, W.U. Lieber, C.M. “High performance silicon nanowire field effect transistors”, *Nano Letters.*, **3**(2), pp. 149–152 (2003).

- 25)Wang, D. Wang, Q. Javey, A. Tu, R. Dai, H. “Germanium nanowire field-effect transistors with SiO₂ and high- κ HfO₂ gate dielectrics”, *Appl. Phys. Lett.*, **83**(12), pp. 2432–2434 (2003).
- 26)Chen, J.F. Ding, H.M. Wang, J.X. Shao, L. “Preparation and characterization of porous hollow silica nanoparticles for drug delivery application”, *Biomaterials.*, **25**(4), pp. 723-727 (2004).
- 27)Mai, L. Tian, L. Xu, X. Chang, L. Xu, L. “Nanowire Electrodes for Electrochemical Energy Storage Devices”, *Chem. Rev.*, **114**(23), pp. 11828-11862 (2014).
- 28)Yoo, J. Kim, J. Jung, Y.S. Kang, K. “Scalable Fabrication of Silicon Nanotubes and their Application to Energy Storage”, *Advanced Materials.*, **24**(40), pp. 5452-5456 (2012).
- 29)Chen, X. Li, H. Yan, Z. Cheng, F. Chen, J. “Structure design and mechanism analysis of silicon anode for lithium-ion batteries”, *Science China Materials.*, **62**(11), pp. 1515–1536 (2019).
- 30)Sun, Y. Liu, N. Cui. Y. ”Promises and challenges of nanomaterials for lithium-based rechargeable batteries”, *Nat Energy.*, **1**(7), p. 16071 (2016).
- 31)Yang, Y. McDowell, M.T. Jackson, A. Cha, J.J. Hong, S.S. Cui, Y. “New Nanostructured Li₂S/Silicon Rechargeable Battery with High Specific Energy”, *Nano Lett.*, **10**(4), pp. 1486-1491 (2010).
- 32)Chau, M. Englander, O. Lin, L. “Silicon nanowire-based nanoactuator”, 3rd. IEEE. Conf. on Nanotech, 2, San Francisco, CA, pp. 879–880 (2003).
- 33)Lan, J. Cheng, D. Cao, D. Wang, W. “Silicon Nanotube as a Promising Candidate for Hydrogen Storage: From the First Principle Calculations to Grand Canonical Monte Carlo Simulations”, *J. Phys. Chem. C.*, **112**(14), pp. 5598-5604 (2008).
- 34)Pop, E. Sinha, S. Goodson, K.E. “Heat Generation and Transport in Nanometer-Scale Transistors”, in *Proceedings of the IEEE.*, **94**(8), pp. 1587-1601 (2006).
- 35)Li, D. Wu, Y. Kim, P. Shi, L. Young’s, P. “Thermal conductivity of individual silicon nanowires”, *Appl. Phys. Lett.*, **83**(14), pp. 2934-2936 (2003).
- 36)Chen, J. Zhang, G. Li, B. “Remarkable Reduction of Thermal Conductivity in Silicon Nanotubes”, *Nano Lett.*, **10**(10), pp. 3978-3983 (2010).
- 37)Szczech, J.R. Jin, S. “Nanostructured silicon for high capacity lithium battery anodes” *Energy Environ. Sci.*, **4**, pp. 56-72 (2011).
- 38)Esfahani, M. Alaca, B.E. Jabbari, M. “Mechanical Properties of Honeycomb Nanoporous Silicon: A High Strength and Ductile Structure”, *Nanotechnology.*, **30**(45), (2019).
- 39)Chan, C.K. Peng, H.L. Liu, G. McIlwrath, K. Zhang, C.F. Huggins, R.F. Cui, Y. “High-performance lithium battery anodes using silicon nanowires”, *Nat. Nanotechnol.*, **3**(1), pp. 31-35 (2008).

- 40)Poizot, P. Laruelle, S. Grugeon, S. Dupont, L. Tarascon, J.M. "Searching for new anode materials for the Li-ion technology: time to deviate from the usual path", *J. Power Sources.*, **97-8**, pp. 235-239 (2001).
- 41)Kasavajjula, U. Wang, C.S. Appleby, A.J. "Nano- and bulk-silicon-based insertion anodes for lithium-ion secondary cells", *J. Power Sources.*, **163**, pp. 1003-1039 (2007).
- 42)Bai, J. Zeng, X.C. Tanaka, H. Zeng, J.Y. "Metallic single-walled silicon nanotubes", *National Academy of Sciences.*, **101**(9), pp. 2664-2668 (2004).
- 43)Fagan, S.B. Mota, R. Baierle, R.J. Paiva, G. da Silva, A.J.J. Fazzio, J. "Stability investigation and thermal behavior of a hypothetical silicon nanotube", *Journal of Molecular Structure: Theochem.*, **539**, pp. 101-106 (2001).
- 44)Amritanshu Palaria, Gerhard Klimeck, and Alejandro Strachan. "Structures and energetics of silicon nanotubes from molecular dynamics and density functional theory", *Phys. Rev. B.*, **78**(20), p. 205315 (2008).
- 45)M. Zhang, Y.H. Kan, Q. J. Zang, Z.M. Su, R.S. Wang. "Why silicon nanotubes stably exist in armchair structure?", *Chem. Phys. Lett.*, **379**(1-2), pp. 81-86 (2003).
- 46)A. San Paulo, J. Bokor, R. T. Howe, R. He, P. Young's, D. Gao, C. Carraro, R. Maboudian. "Mechanical elasticity of single and double clamped silicon nanobeams fabricated by the vapor-liquid-solid method", *Applied Physics Letters.*, **87**(5) , 053111 (2005).
- 47)Keonwook Kang , Wei Cai. "Size and temperature effects on the fracture mechanisms of silicon nanowires: Molecular dynamics simulations", *International Journal of Plasticity.*, **26**, pp. 1387-1401 (2010).
- 48)Rapaport, D. "The art of molecular dynamics simulation", Cambridge University Press 1995, UK (2004)
- 49)J. Tersoff. "New empirical model for the structural properties of silicon", *Phys. Rev. Lett.*, **56**, p. 632 (1986).
- 50)Veena Verma, Keya Dharamvir, V.K.Jindal. "Structure and Elastic Moduli of Silicon Nanotubes", *Journal of Nano Research.*, **2**, 85-90 (2008).
- 51)Jeong Won Kang, Jae Jeong Seo, Ho Jung Hwang. "Molecular Dynamics Study of Hypothetical Silicon Nanotubes Using the Tersoff Potential", *Journal of Nanoscience and Nanotechnology.*, **2**, 687-691 (2002).
- 52)Jeong Won Kang, Jae Jeong Seo, Ho Jung Hwang. "A Study on Silicon Nanotubes based on the Tersoff potential"(2002).
- 53)Peng Lv, Yi-yu Feng, Peng Zhang, Hui-min Chen, Naiqin Zhao, Wei Feng. "Increasing the interfacial strength in carbon fiber/epoxy composites by controlling the orientation and length of carbon nanotubes grown on the fibers", *Carbon.*, **49**(14), pp. 4665-4673 (2011).

Figures' captions:

Figure 1. Schematic of length comparison of Si nanotube

Figure 2. Stress strain diagram for lengths 100, 200 and 300Å.

Figure 3. Schematic comparison of diameters 12.3, 14.8, 17.3 and 23.5 Å

Figure 4. Stress strain diagram for Si nanotube with diameters 12.3, 14.8, 17.3 and 23.5 Å

Figure 5. Structure schematic comparison of tubes with same diameters and different chirality

Figure 6. Si nanotube stress strain diagrams with different chirality

Tables' caption

Table1: used parameters at the Tersoff potential

Table 2. Mechanical properties of nanotubes with different lengths

Table 3. Mechanical properties of nanotubes of different lengths

Table 4. Mechanical properties of nanotubes with chirality of zigzag and armchair

Figures

Figure 1

Schematic of length comparison of Si nanotube

Figure 2

Stress strain diagram for lengths 100, 200 and 300Å.

Figure 3

Schematic comparison of diameters 12.3, 14.8, 17.3 and 23.5 Å

Figure 4

Stress strain diagram for Si nanotube with diameters 12.3, 14.8, 17.3 and 23.5 Å

Figure 5

Structure schematic comparison of tubes with same diameters and different chirality

Figure 6

Si nanotube stress strain diagrams with different chirality