Investigating the pulse short electric arc milling of Ti6Al4V alloy

Li Zhang

Xinjiang University

Guoyu Hu (✉ xjhuguoyu@xju.edu.cn)

Xinjiang University

Jianping Zhou

Xinjiang University

Zongjie Zhou

Xinjiang University

Kai Liu

Xinjiang University

Shengsheng Zhang

Xinjiang University

Research Article

Keywords: Pulse SEAM, Ti6Al4V alloy, Material removal rate, Relative electrode wear rate, Surface integrity

Posted Date: February 25th, 2021

DOI: <https://doi.org/10.21203/rs.3.rs-187364/v1>

License: © ⓘ This work is licensed under a Creative Commons Attribution 4.0 International License.

[Read Full License](#)

Abstract

In this study, characteristics of Ti6Al4V alloy are studied by pulse short electric arc milling (SEAM). In this regard, the influence of SEAM parameters on the material removal rate (MRR), relative electrode wear rate (REWR) and surface integrity of Ti6Al4V is studied. A wide variety of processing parameters, including different voltages, frequencies, duty cycles, flushing pressures, electrode rotation speeds and electrode feed rates are considered in the investigation. Scanning electron microscope (SEM), energy dispersive spectrograph (EDS) and micro-hardness analysis are applied to analyze results. Moreover, a multi-channel data acquisition system is used to measure gap voltage and gap current. Obtained results cover the variation of MRR, REWR, surface roughness (Ra), average re-solidified layer thickness and average heat-affected zone thickness with different processing parameters. Furthermore, the electrode surface morphology and chemical composition of the negative growth of REWR are studied. Based on the obtained results, the microstructure of the re-solidified layer and heat-affected zone of the workpiece cross-section is confirmed. This study provides a technological basis for the high-quality pulse SEAM technology of difficult-to-machine (DTM) materials to enter the semi-finishing field.

1. Introduction

Studies show that titanium alloys have excellent physical and mechanical properties so that they are widely applied in diverse applications, including aerospace, marine and biomedical fields. However, these alloys have some drawbacks such as significant chemical activity at high temperatures and low thermal conductivity. In conventional mechanical methods for cutting the specimens made of titanium alloy, the cutting tool is prone to contact wear and stick at high temperatures, thereby reducing the tool life [1–3]. Meanwhile, worn tools yield poor surface finish and inaccurate dimensions. Recently, electrical discharge machining (EDM) has been proposed as a non-contact processing technology to remove DTM materials such as titanium alloys [4]. However, conventional EDM has some shortcomings such as low processing efficiency and emitting environmentally harmful pollutions [5, 6]. Therefore, these shortcomings limit the application of EDM in some industries.

In order to resolve some of the abovementioned shortcomings of EDM, extensive investigations have been carried out on processing parameters, working medium and applying auxiliary processing technologies. Haşçalık et al. studied the surface integrity of Ti6Al4V processed by EDM and found that the average white layer thickness increases with the pulse current and pulse duration. Experiments were conducted and the maximum MRR reached $77.181 \text{ mm}^3/\text{min}$ [7]. Kong et al. applied submersed EDM processing with air and argon as working mediums and studied the characteristics of Ti6Al4V. They showed that almost no micropores and microcracks remains after processing in the argon medium [8]. Zhang et al. proposed a magnetic field-assisted EDM method and showed that the proposed method can reduce electrode wear and processing noise compared with conventional EDM [9].

Although the abovementioned methods improved the performance of EDM processing to a certain extent, the improvement of the processing efficiency is still limited. Compared with the plasma in conventional

EDM, the arc plasma in arc discharges ionizes more efficiently and results in a higher temperature and thermal density, and thus erodes the material more efficiently [10]. Meshcheriakov et al. proposed the arc dimensional machining (ADM) method, which can achieve high MRR and low REWR [11]. Zhao et al. proposed blasting erosion arc machining (BEAM) technology based on the hydrodynamic arc breaking mechanism [12]. Chen et al. studied the BEAM processing performance in Ti6Al4V and found that the maximum MRR exceeds 16800 mm³/min [13]. Kou et al. proposed a high-speed electric arc milling method that works with DC power. Experimental results show that this method can increase the MRR of Ti6Al4V and reduce REWR [14]. Furthermore, Zhang et al. studied the effect of flushing on the performance of EDM and electric arc machining (EAM) and found that flushing in EAM can reduce REWR and surface roughness, while it has no obvious impact on the EDM [15].

As a type of EDM, short electric arc machining (SEAM) uses low-voltage (generally less than 60V), wide pulse and high current (from hundreds to thousands of amperes) pulse power. SEAM technology has been used to machine large high-strength, superhard, and high-toughness alloy parts such as aeroengine casing, honeycomb sandwich, cement rolls and coal mill rolls. Consequently, SEAM has been considered as an effective method for efficient processing of DTM materials [16]. However, there are still some problems in SEAM, including high REWR, poor processing quality and high surface roughness. In order to resolve these problems, several investigations have been conducted so far. Zhu et al. studied the performance of SEAM under high-frequency and high-voltage pulses and achieved high MRR and low TWR [17]. Furthermore, Chen et al. studied the performance of GH4169 in SEAM under different polarities, and found that the thickness of heat-affected layer produced after positive polarity machining was thinner than that of negative polarity machining [18]. Moreover, Liu et al. studied the performance of SEAM in machining Ti6Al4V based on the DC power supply. They found that the maximum MRR of Ti6Al4V reaches 15100 mm³/min, and the surface roughness S_z reaches 699.92 μm [19].

Reviewing the literature indicates that almost few investigations have focused on the machining characteristics and surface integrity of pulsed SEAM for Ti6Al4V alloy. Therefore, it is of significant importance to consider the influence of voltage, frequency, duty cycle, flushing pressure, electrode rotation speed and feed rate on the MRR, REWR and surface integrity of pulsed SEAM machining Ti6Al4V. In this regard, some experiments will be carried out. It is expected to lay the foundation for the realization of the pulse SEAM Ti6Al4V process entering the semi-finishing stage.

2. Experimental Details

2.1 Principle

Figure 1 shows the schematic configuration of the SEAM, where high-power pulses are generated in the power supply to provide sufficient energy. The tubular graphite electrode is installed on the spindle by an electrode clamp to achieve a high-speed rotation. When the process starts, a voltage is applied between the electrode and workpiece. Then the electrode starts to feed and narrows the gap between the electrode and the workpiece. Once the gap reaches a critical value, the working medium breaks down and an arc

occurs. Under this circumstance, a high-temperature plasma discharge channel composed of a large number of high-speed moving charged particles forms between electrodes. Figure 2 indicates that the discharge channel acts on the surface of the workpiece and electrode, and forms a gasification zone. Then a melting zone and a heat-affected zone (HAZ) appear. The discharge channel moves on the workpiece surface through the feeding of electrode to melt and vaporize the workpiece material. Due to the rapid flushing of the water-gas mixture between workpiece and high-speed rotating electrode, the molten material and eroded debris discharge from the processing area. When the discharge is over, the inter-electrode returns to an electrically neutral state.

2.2 Experimental conditions

SEAM occurs under a certain proportion of water-gas mixture with flushing pressure. Figure 3 shows the schematic configuration of the SEAM set-up. The experimental conditions are detailed as follows:

1. Experimental equipment: SEAM CNC milling machine, a wire cutting machine, metallographic mosaic machine, a metallographic sample grinder (8×8×6mm³), and a polishing machine.
2. Electrode: The electrode is a tubular graphite electrode with an external diameter of 18 mm and an internal diameter of 8 mm.
3. Workpiece: Dimensions of the Ti6Al4V workpiece are 32×32×8mm³, and chemical composition, physical and mechanical properties are shown in Tables 1 and 2, respectively.
4. Testing equipment: Multi-channel data acquisition system (DEWESoft SIRIUS), High-precision electronic scales (with a precision of 0.1 mg), digital microscope with a super-field lens (VHX-6000), scanning electron microscopy (JSM-7610FPlus) and Vickers micro-hardness tester.

Table 1

Chemical composition of Ti6Al4V (%)

Al	V	Fe	H	N	O	Ti
6.04	4.15	0.18	0.001	0.006	0.12	Balanced

Table 2

Physical and mechanical properties of Ti6Al4V

Micro-hardness	Melting point	Tensile strength	Thermal conductivity	Elongation	Density
320 ~ 350HV	1604–1660℃	862–1200 MPa	7.1-7.3W/m k	15%	4510 kg/m ³

2.3 Experimental process

In order to ensure the accuracy of the SEAM in the experiment, a single-factor experiment was used in this study, and repeat the experiment 3 times for each parameter. Meanwhile, effects of different processing parameters are studied on the MRR, REWR and surface roughness. Table 3 presents the settings of processing parameters. The surface morphology, cross-sectional morphology, chemical composition and

micro-hardness of a part of the workpiece were tested to further reveal the mechanism and performance of the pulsed SEAM Ti6Al4V. Setting of parameters is shown in Table 4. Moreover, MRR and REWR are defined as follows:

Table 3
Parameters of SEAM

Parameter(units)	Value
Polarity of workpiece	Positive (+)
Voltage (V)	15,20,25,30
Frequency (Hz)	600,1000,2300,3400
Duty cycle (%)	30,40,50,60
Flushing pressure (MPa)	0.2,0.3,0.4,0.5
Electrode rotation speed (rpm)	600,1200,1800,2400,3000
Electrode feed rate (mm/min)	2,4,6,10,20,30
Milling depth (mm)	2
Milling width (mm)	10

Table 4
Parameter settings for microscopic analysis of morphology

No.	Voltage (V)	Frequency (Hz)	Duty cycle (%)	Flushing pressure (MPa)	Electrode rotation speed (rpm)	Electrode feed rate (mm/min)
E1	30	1000	40	0.3	1800	2
E2	30	600	40	0.3	1800	2
E3	30	1000	30	0.3	1800	2
E4	30	1000	40	0.5	1800	2

$$MRR = \frac{M_{wi} - M_{wj}}{\rho_w t} \times 10^3 (\text{mm}^3/\text{min}) \quad (1)$$

$$REWR = \frac{M_{ei} - M_{ej}}{M_{wi} - M_{wj}} \times 100\% \quad (2)$$

where M_{wi} and M_{wj} are the quality of the workpiece before and after processing (g); M_{ei} and M_{ej} are the quality of the electrode before and after the processing (g); t and ρ_w denote the processing time (min) and density (g/cm^3) of the workpiece, respectively.

3. Experimental Results And Discussions

3.1 Effect of voltage on the machining performance

Figure 4 shows the influences of voltage on MRR, REWR and Ra. It is observed that as the voltage increases, MRR and Ra increase while REWR first decreases and then increases. For the voltage of 30V, the corresponding maximum MRR and Ra reach 32 mm³/min and 44.98 μm, respectively. This is because when the voltage increases from 15V to 30V, the output energy of pulsed power supply increases, which increases the energy of plasma discharge channel between electrodes, thereby increasing the critical discharge gap between electrodes. Consequently, the molten material can simply discharge by the flushing liquid, thereby increasing the MRR. Due to the increase of the energy between electrodes and the discharge gap, the large volume of molten material simply removes from electrodes. These large volumes of molten material inevitably form larger pits after peeling off the workpiece surface. Moreover, the diameter of these pits increases as the discharge channel energy increases, thereby increasing Ra. On the other hand, when the voltage reduces to 25V, the minimum REWR is 2%. This is because when the voltage is lower than 25V, the inter-electrode gap becomes smaller, which seriously affects the discharge of the inter-electrode erosion material, resulting in a great increase in the short-circuit rate, and thus will increase the REWR of the graphite electrode. Meanwhile, when the voltage exceeds 25V, the discharge gap and the energy of the discharge channel increases. Consequently, the molten inter-electrode randomly hits the workpiece and electrode. This may be one of the reasons for the increase in REWR.

3.2 Effect of the frequency on the machining performance

Figure 5 shows the influences of frequency on MRR, REWR and Ra. It is observed that as the frequency increases from 600 Hz to 3400 Hz, MRR, Ra and REWR decrease. This is because when the frequency increases, the duration of a single pulse decreases, and the energy in the discharge channel gradually tend to be discrete, which will lead to the formation of small and shallow discharge pits on the workpiece surface, thereby reducing the Ra and MRR. Moreover, as the continuous discharge time of each pulse between the electrodes reduces, discharge points between electrodes gradually uniforms, thereby reducing the corner loss of electrode, which may be one of the reasons for the continuous reduction of REWR.

3.3 Effect of the duty cycle on the machining performance

Figure 6 shows the influences of duty cycle on MRR, REWR and Ra. It is observed that as the duty cycle increases, MRR and Ra increase, while REWR first increases and then decreases. This is because when the duty cycle increases from 30–60%, the pulse width in a single arc discharge cycle increases, thereby increasing the arc discharge energy. Consequently, large and deep discharge pits appear on the workpiece surface and the MRR and Ra increase. When the duty cycle is less than 40%, the REWR increases slowly. This may be attributed to the narrow pulse width in a single discharge cycle when the duty cycle is less than 40%. Accordingly, the arc discharge energy decreases, which increases the electrode wearing. When the duty cycle exceeds 40%, the REWR decreases sharply, which may be because the pulse width output

energy in a single arc discharge cycle is sufficient to melt workpiece material. Therefore, the collision probability between the electrode and workpiece material reduces during the pulse interval.

3.4 Effect of the flushing pressure on the machining performance

Figure 7 shows the impact of flushing pressure on processing performance. It indicates that as the flushing pressure increases, MRR first increases and then decreases, while REWR and Ra first decrease and then increase. This is because the heat dissipation in the SEAM is poor, which mainly originates from the small discharge gap and high viscosity of Ti6Al4V. Therefore, when the flushing pressure is less than 0.3 MPa, the inter-electrode melt cannot be discharged in time by the flushing, which will cause short circuits and secondary discharges. Then the incidence greatly increases, which decreases the MRR and increases the REWR. When the flushing pressure exceeds 0.3 MPa, excessive flushing pressure seriously affects the formation of discharge channel. In order to further illustrate the influence of flushing pressure on the discharge state, a section consisting of inter-electrode discharge waveforms at 0.3 MPa and 0.4 MPa is collected. Figure 7(c) shows that there are gap current waveforms in each pulse and the current average value is high. Consequently, the discharge channel energy is high and the discharge process is stable. Moreover, Fig. 7(d) shows that there is no gap current waveform in some pulses for low-average currents. This is because when the flushing pressure is too high, the steady-state discharge channel is destroyed so that the non-steady-state discharge phenomenon increases, resulting in insufficient energy for the inter-electrode arc plasma to melt material. Consequently, MRR decreases, while REWR and Ra increase. However, Fig. 7(b) shows that when the flushing pressure reaches 0.5 MPa, the tubular graphite electrode cracks. It is concluded that in order to ensure stable processing, the flushing pressure should not be too large.

3.5 Effect of the electrode rotation speed on the machining performance

Figure 8 shows the influences of electrode rotation speed on MRR, REWR and Ra. It is observed that as the electrode rotation speed increases, MRR first increases and then decreases, which is consistent with the variation of MRR in previously published results [20]. However, REWR and Ra first decrease and then increase as the electrode rotation speed increases. This is because when the electrode rotation speed is less than 1200 rpm and the input energy between electrodes and flushing pressure are constant, generated centrifugal force by the rotation of electrode cannot promptly throw the melt between electrodes, thereby solidifying the melt and covering workpiece surface, which affects the MRR. Meanwhile, when the electrode rotation speed exceeds 1200 rpm, discharge channels are generated first among the many micro-spikes. These discharge channels, which originate from non-flat surface of the workpiece and electrode, are easily stretched and twisted or even broken. Accordingly, the cross-section of discharge channels reduces so that the MRR and Ra decrease when the rotating speed of electrode is too high. The proper electrode rotation speed leads to uniform electrode wear and long service life of the

electrode [21]. When the electrode rotation speed is set to 1800 rpm and 2400 rpm, REWR and Ra reach the minimum values of 2% and 18.99 μm , respectively. It is worth noting that excessive electrode rotation speed leads to a twisted discharge channel and causes mechanical contact between the workpiece and electrode so that it may be one of the reasons for the increase in REWR and Ra.

3.6 Effect of the electrode feed rate on the machining performance

Figure 9 shows the influences of electrode feed rate on MRR, REWR and Ra. It is observed that as the electrode feed rate increases, MRR and Ra increase, while REWR increases first, then decreases and finally increases. When the electrode feed rate exceeds 30 mm/min, a short circuit occurs during the feed stage, resulting in the process failure. It is found that the critical electrode feed rate is 30 mm/min, and the MRR reaches a maximum value of 556 mm³/min. On the other hand, when the electrode feed rate is less than 30 mm/min, the energy provided by the inter-electrode discharge channel can effectively melt workpiece material and can ensure the synchronization of the energy and feed rate, thereby increasing the MRR and Ra. When the electrode feed speed is too high, the synchronization between discharge energy and electrode feed speed is poor, which will greatly increase the probability of electrode contact with workpiece. Consequently, possibility of short circuit and collision increases, thereby increasing the REWR. When the electrode feed rate is less than 6 mm/min, the movement speed of the inter-electrode discharge channel on the surface of the workpiece is slow. Therefore, cations in the discharge channel obtain greater kinetic energy and impact the electrode, thereby increasing the REWR. It is found that when the electrode feed rate reaches 6 mm/min, REWR approaches -4%. This result will be discussed in detail in Sect. 4.1.

4 Surface Integrity Analysis

In order to study the influence of the frequency, duty cycle and flushing pressure on the surface morphology and cross-sectional re-solidified layer (RSL), heat-affected zone (HAZ), micro-hardness and chemical composition of Ti6Al4V, other parameters are kept constant in the SEAM process. Table 4 shows that six different levels of the three parameters are named E1, E2, E3 and E4, respectively.

4.1 Surface morphology analysis of the electrode

In the experiment, when the electrode feed rate is set to 6 mm/min, the corresponding REWR is -4%. This group of electrodes is selected to observe and detect the micro-morphology and chemical composition of the graphite electrode surface by SEM and EDS, respectively.

Figure 10 shows the SEM image and EDS spectrum of the graphite electrode. Figure 10(a) illustrates the SEM image of the processed surface of the graphite electrode. It is found that a large number of pits are generated on the surface due to the influence of electric discharge, and some eroded particles are attached to the electrode surface. Moreover, Figs. 10(a) and 10(b) show that a large amount of Ti, O, Ca

and Al are distributed on the eroded particles. Figure 10(c) illustrates that characteristic elements of Ti6Al4V workpieces such as Ti, Fe and Al appear on the surface of the graphite electrode, as well as typical elements of tap water such as O, Ca, Na, and Cl. This is because processing under certain pressure of water and gas medium is affected by the multi-field coupling when the electrodes are discharged, and electrochemical reactions will occur to produce titanium, aluminum, oxygen, calcium, chlorine and other ions. The above-mentioned ions will form TiO_2 , Al_2O_3 , CaO and other compounds under the rapid cooling of the water-gas flushing liquid, and these oxides adhere to the surface of the electrode and workpiece to form an oxide layer similar to an oxide film [8]. The melting points of TiO_2 , Al_2O_3 and CaO are 1842°C , 2054°C , and 2572°C , respectively, which are all higher than the melting point of the Ti6Al4V material ($1604\text{--}1660^\circ\text{C}$). Therefore, to a certain extent, it reduces the further wear of the electrode and affects the removal efficiency of workpiece material. When these oxides adhere to the surface of the electrode, the weight of the electrode increases, which reduces REWR and even compensate the electrode wear. This is one of the reasons that the electrode wear is -4%.

4.2 Surface morphology analysis of the Ti6Al4V

Figure 11 shows the SEM image of the surface after pulsed SEAM Ti6Al4V under different processing parameters. Erosion holes, micro-cracks, RSL, pits, droplets and spherical particles are observed on the Ti6Al4V surface processed with different parameters. Erosion holes are formed due to the rapid flushing of water-gas mixed medium and high-speed rotation of electrode. As a result, the erosion debris hits the molten pool on the surface of workpiece at a high speed. Since the molten material is rapidly cooled and solidified under the high-pressure flushing liquid between poles, the internal thermal stress of the material cannot be released in time, thereby forming micro-cracks. The RSL is formed because the molten workpiece material is rapidly solidified and attached to the surface of workpiece under the cooling of the rapid flushing medium. Due to the different processing parameters, different features will appear on the surface of the workpiece after processing.

Comparison of Figs. 11(a) and 11(b) show that the SEM images are significantly different. It is found that when the frequency is reduced from 1000 Hz to 600 Hz, large and deep pits appear on the surface of the workpiece and the bottom is relatively smooth without RSL. Figure 11b shows that the number of micro-cracks on the surface of workpiece is significantly reduced when the frequency is 600 Hz. When the frequency is reduced, the single arc discharge time is prolonged. Therefore, Fig. 11b shows that large and deep pits occur, which is consistent with the analysis results in Sect. 3.2. Comparing Figs. 11(a) and 11(c) shows that when the duty cycle drops from 40–30%, the surface integrity of the workpiece is significantly improved, the microcracks are reduced, and almost no erosion holes are observed. Moreover, laminated droplets are observed. This is because the pulse width in a single discharge cycle is narrowed, resulting in a shorter arc discharge energy duration. Therefore, the newly melted material cannot be sufficiently cooled and the adhesion between the droplets occurs.

Comparing Figs. 11(a) and 11(d) illustrate that when the flushing pressure increases from 0.3 MPa to 0.5 MPa, larger diameter pits, smaller erosion holes, fewer microcracks and irregular edges RSL are

observed on the surface of the workpiece. Figure 11d shows that when the flushing pressure increases to 0.5 MPa, due to the high-speed flushing of inner and outer flushing fluid, the inter-electrode discharge channel is destroyed and a large explosive force is produced [14]. Therefore, the molten workpiece material does not have enough time to cool and adhere to the surface of the workpiece, which leads to larger pits, smaller erosion holes and fewer micro-cracks.

4.3 Cross-section analysis of the Ti6Al4V

1) Cross-sectional topography analysis

Figure 12 shows the SEM images of the cross-sectional morphology of Ti6Al4V after SEAM under different processing parameters, including partial enlarged images of the RSL and HAZ. Moreover, Fig. 13a shows the average resolidified layer thickness (ARSLT) and average heat-affected zone thickness (AHAZT) under different processing parameters. Figure 12 presents that the RSL, HAZ and base material can be observed in all cross-sectional SEM images [22]. Figure 13a shows that when the frequency is reduced from 1000 Hz to 600 Hz, the ARSLT increases from 41.4 μm to 49.6 μm . Moreover, it is found that the AHAZT is reduced from 14.1 μm to 5.1 μm . Figures 12a and b show that the microstructure of the RSL changes from granular to larger snowflake-like shape, and columnar grains appear in the microstructure of the HAZ. This is because when the frequency decreases, the discharge time of a single pulse is prolonged. Therefore, the energy in a single pulse increases and the ARSLT increases. The decrease in the AHAZT may be explained by the poor thermal conductivity of Ti6Al4V. When other parameters are constant, reducing the frequency will increase the energy of a single pulse, resulting in a snowflake-like microstructure with larger particle size. Due to the poor thermal conductivity of Ti6Al4V, the heat in the cross-section is reduced in a very short time. Therefore, grain refinement appears in the HAZ.

Figure 13a shows that when the duty cycle is reduced from 40–30%, the ARSLT decreases from 41.4 μm to 39.6 μm , and the AHAZT is reduced from 14.1 μm to 7.4 μm . Moreover, Figs. 12a and c show that the microstructure of the RSL changes from larger particles to smaller particles. The microstructure of the HAZ changes from refined columnar crystals to coarse $\alpha + \beta$ phases. This is because when the duty cycle decreases, the pulse width becomes narrower. Therefore, the energy in a single pulse decreases, which will lead to a decrease in ARSLT and AHAZT. When other parameters are constant, the energy of a single pulse is reduced after the duty cycle is reduced, which leads to a smaller size of the microstructure particles of RSL when the duty cycle is 30%. When the heat transferred from the Ti6Al4V machining surface to the HAZ reduces, the degree of the grain refinement reduces too.

Figure 13a shows that when the flushing pressure increases from 0.3 MPa to 0.5 MPa, ARSLT decreases from 41.4 μm to 26.0 μm , and AHAZT decreases from 14.1 μm to 9.3 μm . Moreover, Figs. 12a and 12d show that the microstructure of RSL changes from a granular shape to a snowflake-like shape with larger gaps, while the microstructure of HAZ has fewer columnar crystals. This is because when the flushing pressure increases, the cooling effect between the machining electrodes is better, which leads to the reduction of ARSLT and AHAZT. When other parameters are constant, increasing the flushing pressure

will enhance the ability of the inter-electrode to discharge particles, resulting in a larger gap between the snowflake-like particles in the RSL microstructure when the flushing pressure is 0.5 MPa. Due to the enhancement of the cooling capacity, most of the heat is difficult to transfer to the HAZ. Therefore, the microstructure of HAZ does not change significantly.

2) Micro-hardness and EDS analysis

Figures 13b E1 and E2 show the micro-hardness of RSL, HAZ and base material. It is observed that when the frequency is reduced from 1000 Hz to 600 Hz, the micro-hardness of RSL increases from 464HV to 525HV, and the micro-hardness of HAZ increases from 364.5HV to 482HV. This is because reducing the frequency will increase the duration of a single pulse discharge, so it will increase the energy of a single pulse, so the micro-hardness values of RSL and HAZ increase. According to reports, in the HAZ, because some α -Ti transforms into β -Ti under high temperature and rapid cooling, the micro-hardness of HAZ is lower than that of RSL [23]. Figures 13c and d show the EDS spectra of RSL, HAZ and base material. It is observed that when the frequency is reduced to 600 Hz, the content of Al in the RSL is reduced from 2.10 % to 0.28%, the C content in RSL is more than 1.8 times that of 1000 Hz, and the C content in HAZ is more than 2.6 times that of 1000 Hz. This is due to the lower melting point of Al. When the frequency decreases, the duration of discharge energy increases, and Al is easily lost during processing. In addition, the increase in the duration of energy will lead to an increase in the carbon deposit content.

Comparing Figs. 13b E1 and E3 shows that when the duty cycle reduces from 40–30%, the micro-hardness of HAZ is reduced from 364.5HV to 352.5HV, the micro-hardness of RSL increases from 464HV to 525HV. As the pulse width decreases, the discharge energy decreases, and the micro-hardness of the HAZ decreases. It is interesting that the micro-hardness in RSL has increased, which may be due to the rapid cooling effect of the working medium. Figures 13c and e show that the C content in the RSL at a duty cycle of 40% is lower than at a duty cycle of 30%. This is because when the discharge energy decreases, the electrode wear will increase, and therefore the C content will increase.

Comparing Figs. 13b E1 and E4 shows that when the flushing pressure increases from 0.3 MPa to 0.5 MPa, the rapid cooling between the processing electrodes and the ability to discharge ablated particles are greatly enhanced. The process is similar to quenching. Therefore, the RSL micro-hardness increases from 464HV to 583HV, and the HAZ micro-hardness increases from 364.5HV to 491HV. Combined with the changes in the content of C and O elements in RSL and HAZ, it is found that after increasing the flushing pressure, the discharge channel will be destroyed by working medium fluid. As a result, Figs. 13c and f show that a greater explosive force is generated to accelerate the interpolar element infiltration, which will lead to an increase in the content of C and O elements in RSL at 0.5 MPa. In addition, due to the better cooling effect of rapid flushing, the loss of Al content can be significantly reduced.

5 Conclusions

In the present study, the effects of voltage, frequency, duty cycle, flushing pressure, electrode rotation speed and electrode feed rate on pulsed SEAM Ti6Al4V are experimentally studied. Moreover, the changes in the surface and cross-sectional morphology of Ti6Al4V, the ARSLT, the AHAZT, the element composition and the micro-hardness of the processed Ti6Al4V are investigated. The main conclusions are as follows:

1. MRR increases as the voltage, duty cycle and electrode feed rate increase and decrease as the frequency increases. Moreover, MRR initially increases and then decreases as the flushing pressure and electrode rotation speed increase. When the electrode feed rate is 30 mm/min, MRR reaches the maximum value of 556mm³/min. REWR initially decreases and then increases as the voltage, flushing pressure and electrode rotation speed increase, while it decreases as the frequency increases. Moreover, it initially increases and then decreases as the duty cycle increases. The surface roughness Ra increases as the voltage, duty cycle and electrode feed rate increase, while it decreases as the frequency increases. Moreover, Ra initially increases and then decreases as the flushing pressure and electrode rotation speed increase. When the frequency is 3400 Hz, Ra reaches the minimum value of 13.15 μm.
2. The negative growth of the REWR parameter group is detected. Moreover, it is found that O, Ca, Cl in water and gas medium and Ti, Fe, Al in Ti6Al4V penetrate the electrode surface. An electrochemical reaction occurs between the electrodes, and the compound produced by it adheres to the electrode surface to help compensate for the electrode wear.
3. Appropriate reduction of frequency and duty cycle can result in better surface integrity. Moreover, a reasonable reduction in the flushing pressure can effectively reduce the number of erosion holes and microcracks.
4. The ARSLT increases as the duty cycle and flushing pressure increase, while it decreases as the frequency increases. Moreover, AHAZT increases as the frequency, duty cycle and flushing pressure increase. The micro-hardness of the RSL increases as the flushing pressure increase, while it decreases as the frequency and duty cycle increase. The micro-hardness of HAZ increases as the duty cycle and flushing pressure increase, while it decreases as the frequency increases. Moreover, it is found that the micro-hardness of RSL and HAZ increase as the carburizing amount increases, and the microstructures of RSL and HAZ are confirmed.

Declarations

Not applicable

Funding

This research was supported by the Natural Science Foundation of China (Grant No.51765063), the Natural Science Foundation of Autonomous Region (Grant No.2019D01C070), and the open topic research fund (Grant No. sklms2019009).

Conflict of Interest

The authors declare that they have no conflict of interest.

Availability of data and material (data transparency)

Code availability (software application or custom code)

Authors' contributions (optional: please review the submission guidelines from the journal whether statements are mandatory)

References

1. Gariani S, Shyha I, Inam F, Huo D (2017) Experimental analysis of system parameters for minimum cutting fluid consumption when machining Ti-6Al-4V using a novel supply system. *Int J Adv Manuf Technol* 95:2795–2809. <https://doi.org/10.1007/s00170-017-1216-y>
2. Dandekar CR, Shin YC, Barnes J (2010) Machinability improvement of titanium alloy (Ti-6Al-4V) via LAM and hybrid machining. *Int J Mach Tools Manuf* 50:174–182. <https://doi.org/10.1016/j.ijmachtools.2009.10.013>
3. Zhu Z, Sun J, Li J, Huang P (2016) Investigation on the influence of tool wear upon chip morphology in end milling titanium alloy Ti6Al4V. *Int J Adv Manuf Technol* 83:1477–1485. <https://doi.org/10.1007/s00170-015-7690-1>
4. Abu Qudeiri JE, Mourad AHI, Ziout A et al (2018) Electric discharge machining of titanium and its alloys: review. *Int J Adv Manuf Technol* 96:1319–1339. <https://doi.org/10.1007/s00170-018-1574-0>
5. Jagadish RA (2016) Optimization of process parameters of green electrical discharge machining using principal component analysis (PCA). *Int J Adv Manuf Technol* 87:1299–1311. <https://doi.org/10.1007/s00170-014-6372-8>
6. Garg A, Lam JSL (2016) Modeling multiple-response environmental and manufacturing characteristics of EDM process. *J Clean Prod* 137:1588–1601. <https://doi.org/10.1016/j.jclepro.2016.04.070>
7. Haşçalık A, Çaydaş U (2007) Electrical discharge machining of titanium alloy (Ti-6Al-4V). *Appl Surf Sci* 253:9007–9016. <https://doi.org/10.1016/j.apsusc.2007.05.031>
8. Kong L, Liu Z, Qiu M et al (2019) Machining characteristics of submersed gas- fl ushing electrical discharge machining of Ti6Al4V alloy. *J Manuf Process* 41:188–196. <https://doi.org/10.1016/j.jmapro.2019.02.023>
9. Zhang Z, Yu H, Zhang Y et al (2018) Analysis and optimization of process energy consumption and environmental impact in electrical discharge machining of titanium superalloys. *J Clean Prod* 198:833–846. <https://doi.org/10.1016/j.jclepro.2018.07.053>
10. Xu G, Hu J, Tsai HL (2008) Three-dimensional modeling of the plasma arc in arc welding. *J Appl Phys* 104:103301. <https://doi.org/10.1063/1.2998907>

11. Meshcheriakov G, Nosulenko V, Meshcheriakov NBV (1988) Physical and technological control of arc dimensional machining. CIRP Ann 37:209–212
12. Zhao W, Gu L, Xu H et al (2013) A novel high efficiency electrical erosion process – Blasting erosion arc machining. Procedia CIRP 6:621–625. <https://doi.org/10.1016/j.procir.2013.03.057>
13. Chen J, Gu L, Xu H, Zhao W (2016) Study on blasting erosion arc machining of Ti–6Al–4V alloy. Int J Adv Manuf Technol 85:2819–2829. <https://doi.org/10.1007/s00170-015-8126-7>
14. Kou Z, Han F, Wang G (2019) Research on machining Ti6Al4V by high-speed electric arc milling with breaking arcs via mechanical-hydrodynamic coupling forces. J Mater Process Technol 271:499–509. <https://doi.org/10.1016/j.jmatprotec.2019.04.021>
15. Zhang M, Zhang Q, Dou L et al (2016) Effects of flushing on electrical discharge machining and electro-arc machining. Proc Inst Mech Eng Part B J Eng Manuf 230:293–302. <https://doi.org/10.1177/0954405415598463>
16. Zhou J, Liang C, Teng W et al (2008) Study on rules in material removal rate and surface quality of short electric arc machining process. Adv Mater Res 33–37 PART:1313–1318. <https://doi.org/10.4028/www.scientific.net/amr.33-37.1313>
17. Zhu G, Zhang Q, Wang H et al (2017) Machining behaviors of short electrical arc milling with high frequency and high voltage pulses. Int J Adv Manuf Technol 90:1067–1074. <https://doi.org/10.1007/s00170-016-9399-1>
18. Chen X, Zhou J, Wang K, Xu Y (2020) Influence of different tool polarity on short electric arc machining of GH4169. Proc Inst Mech Eng Part B J Eng Manuf 234:108–117. <https://doi.org/10.1177/0954405419851934>
19. Liu K, Zhou J, Zhou Z et al (2020) Milling performance of titanium alloy based on short electric arc machining with direct current power source. Int J Adv Manuf Technol. <https://doi.org/10.1007/s00170-020-05937-z>
20. Singh NK, Pandey PM, Singh KK (2015) EDM with Air Assisted Multi-Hole Rotating Tool. Mater Manuf Process 6914:0–23. <https://doi.org/10.1080/10426914.2015.1127954>
21. Shen Y, Liu Y, Sun W et al (2015) High-speed dry compound machining of Ti6Al4V. J Mater Process Technol 224:200–207. <https://doi.org/10.1016/j.jmatprotec.2015.05.012>
22. Chen X, Zhou J, Wang K et al (2019) A study on machining characteristics of nickel-based alloy with short electric arc milling. Int J Adv Manuf Technol 105:2935–2945. <https://doi.org/10.1007/s00170-019-04501-8>
23. Shen Y, Liu Y, Sun W et al (2016) High-speed near dry electrical discharge machining. J Mater Process Technol 233:9–18. <https://doi.org/10.1016/j.jmatprotec.2016.02.008>

Figures

Figure 1

Schematic of SEAM.

Figure 2

Discharge channel in SEAM.

Figure 3

The basic experimental set-up.

Figure 4

Effect of voltage on machining performance.

Figure 5

Effect of frequency on machining performance.

Figure 6

Effect of duty cycle on machining performance.

Figure 7

Effect of flushing pressure on machining performance. (a) The influence curve of flushing pressure on MRR, REWR and Ra. (b) Photograph of electrode after processing. Inter-electrode processing waveform: (c) 0.3MPa, (d) 0.4MPa.

Figure 8

Effect of electrode rotation speed on machining performance.

Figure 9

Effect of electrode feed rate on machining performance.

Figure 10

SEM image and EDS spectrum of the graphite electrode surface (6mm/min 30V 1000Hz 40% 0.3MPa 1800rpm): a Microscopic morphology. b Element distribution. c Surface scan energy spectrum.

Figure 11

Effects of different processing parameters on the surface morphology of Ti6Al4V. (a) E1. (b) E2. (c) E3. (d) E4.

Figure 12

Cross-sectional SEM images of the machined surface under different processing parameters. (a) E1. (b) E2. (c) E3. (d) E4.

Figure 13

(a) The influence of different processing parameters on the average resolidified layer thickness and the average heat-affected layer thickness. (b) The influence of different processing parameters on the microhardness of the cross section. Cross-sectional EDS spectrum under different processing parameters: (c) E1. (d) E2. (e) E3. (f) E4.