Fine-grained polycrystalline MoTe₂ with enhanced thermoelectric properties through iodine doping

Pan Ren (✉ ustbrp@163.com)

University of Science and Technology Beijing <https://orcid.org/0000-0002-8461-3116>

Trever Bailey

University of Michigan Department of Physics

Alexander Page

University of Michigan Department of Physics

Quanxin Yang

USTB: University of Science and Technology Beijing

Tu Lv

USTB: University of Science and Technology Beijing

Guiying Xu

USTB: University of Science and Technology Beijing

Research Article

Keywords: n-type MoTe₂, Nano-polycrystalline, Thermoelectric Properties, Ball milling, SPS, Iodine doping, Dislocation scattering

Posted Date: February 15th, 2021

DOI: <https://doi.org/10.21203/rs.3.rs-191034/v1>

License: © ⓘ This work is licensed under a Creative Commons Attribution 4.0 International License.

[Read Full License](#)

Version of Record: A version of this preprint was published at Journal of Materials Science: Materials in Electronics on July 21st, 2021. See the published version at <https://doi.org/10.1007/s10854-021-06461-w>.

Fine-grained polycrystalline MoTe₂ with enhanced thermoelectric properties through iodine doping

Pan Ren^{1,2}, Trevor P. Bailey², Alexander A. Page², Quanxin Yang¹, Tu Lv¹, Guiying Xu^{1,*}

1. Beijing Municipal Key Laboratory of Advanced Energy Materials And Technology, School of Materials Science And Engineering, University of Science and Technology Beijing, Beijing 100083, China

2. Department of Physics, University of Michigan, Ann Arbor, MI 48109, USA

*** Corresponding author: Guiying Xu**

E-mail address: guiyingxu@126.com

Keywords: *n*-type MoTe₂, Nano-polycrystalline, Thermoelectric Properties, Ball milling, SPS, Iodine doping, Dislocation scattering

Abstract: Consisting of heavy elements and favorable electronic structure, MoTe₂ has great potential as a good thermoelectric material for heat-to-electricity conversion. While some experimental work has been performed on the *p*-type version, *n*-type MoTe₂ is theoretically predicted to have a great conversion efficiency and is crucial for eventual device functionality, yet has not been explored. Here, the preparation and thermoelectric properties of *n*-type iodine-doped nano-polycrystalline MoTe₂ are currently reported. Nano-polycrystalline MoTe_{2-x}I_x is obtained by ball milling and spark plasma sintering techniques. The composition, morphology and crystal structure of the prepared materials were analyzed by XRD and FESEM, which indicated a homogeneous single phase. The measured transport properties over the temperature range of 298-823K indicate that iodine doping greatly enhances the carrier concentration and corresponding power factor, and drastically reducing the thermal conductivity. The ECR (Electrical conductivity ratios) carrier scattering analysis demonstrates that dislocation scattering is the main

mechanism throughout the experimental temperature range. With the temperature and doping increasing, the thermal conductivity was reduced rapidly, and the minimum value was $1.19 \text{ Wm}^{-1}\text{K}^{-1}$ at 673K. The maximum value of the figure merit $ZT \sim 0.16$ over 673-750K, which is much higher than other reported values. These excellent properties imply that MoTe_2 will be an efficient candidate for thermoelectric applications.

1. Introduction

In the past several decades, the urgent need for more efficient and environmental friendly energy conversion technologies has driven an increasing interest in the field of thermoelectric (TE) materials, which are capable of converting heat into electricity[1-4]. However, the low conversion efficiency of thermoelectric materials has limited their large-scale commercialization. The dimensionless figure of merit, $ZT = S^2\sigma T\kappa^{-1}$, where S , σ , T , and κ are the Seebeck coefficient, electrical conductivity, absolute temperature and thermal conductivity, respectively, represents the TE performance. Improving the efficiency of TE devices is challenging because ZT is often limited by conflicting relations between its parameters, i.e., S , σ , and κ [5]. Nevertheless, a variety of strategies have proven successful in obtaining high ZT in bulk thermoelectrics, such as nanostructuring [6,7], introducing resonant states [8], and engineering the electronic energy band structure [9]. The dichalcogenides of Group 6 elements, 2H-MX_2 ($\text{M} = \text{Mo}, \text{W}$; $\text{X} = \text{S}, \text{Se}, \text{Te}$), mostly crystallize in the space group $P6_3/mmc$ [10], in which the MX_2 layers made up of edge-sharing MX_6 trigonal prisms are stacked along the c -direction. Hereafter, the “2H” hexagonal notation will be suppressed for simplicity. The MX_2 dichalcogenides have attracted much attention because of their anisotropic thermoelectric properties [11], superconductivity [12] and Weyl semimetal properties [13,14]. MX_2 compounds are good candidates for thermoelectric applications because of their high Seebeck coefficients (S) and low thermal conductivities (κ) [15,16]. In addition,

density functional theory calculations have predicted most of the MX_2 materials to be excellent thermoelectrics if properly doped [17]. Recently, two dimensional and single-crystal p -type MoTe_2 doped with transition metal impurities (such as Nb and Ta) have been researched for the possible enhancement of thermoelectric properties of the compound by tuning the electronic energy band structure [18,19]. However, n -type MoTe_2 -based polycrystalline materials are rarely investigated. In particular, the high temperature thermoelectric transport properties have not been systematically evaluated. To this end, we utilized iodine as an n -type dopant for MoTe_2 and studied the phase structure, morphology, and thermoelectric properties of the resulting compounds. The aim of our work is to probe a way of improving the thermoelectric properties of n -type polycrystalline MoTe_2 on the basis of synthesis and impurity doping.

2. Experimental Section

All polycrystalline $\text{MoTe}_{2-x}\text{I}_x$ ($x = 0-0.04$) samples were synthesized by solid-state reaction. The stoichiometric mixtures of the high-purity elements, Mo (purity 99.99%) and Te (purity 99.999%), and compound TeI_4 (purity 99.99%), in powder form were evacuated quartz tubes, heated at 1273K for 3 days, followed by furnace cooling down to room temperature. The obtained samples were ground, pelletized, and then sealed in evacuated quartz tubes again to be annealed at 1073K for 7 days. All samples after annealing were milled in tungsten carbide grinding tank within an argon atmosphere for 12h, then the powders were put into half inch cylindrical dies and sintered in a spark plasma sintering (SPS) furnace at 873K with a pressure of 50MPa for 5min. TeI_4 as a dopant was selected to increase the carrier concentration to optimize thermoelectric performance of the samples over the whole temperature range. The composition, phase structure, and morphology of the samples were analyzed by X-ray diffraction (XRD; Ultima IV; Rigaku; Japan) with Cu K_α radiation ($\lambda=1.54056 \text{ \AA}$). and field emission scanning

electron microscopy (FESEM; JSM-7800F; JEOL, Japan) equipped with an energy dispersive spectrometer (EDS; Oxford Instruments, UK). The grain size was calculated from the refined XRD data via the Debye-Scherrer Formula, $d = k\lambda/\beta\cos\theta$, where d is the grain diameter perpendicular to the crystal plane (hkl), k is the Scherrer constant (usually 0.89), λ is the incident X-ray wavelength (Cu Ka, $\lambda = 0.15406$ nm), θ is the Bragg diffraction angle, and β is the half-peak width (rad) of the diffraction peak, and detected by FESEM. The high temperature Seebeck coefficient and electrical conductivity were measured by the standard four-probes method at the University of Michigan (UM) utilizing a homemade instrument. Thermal diffusivity (D) for each sample was measured using the laser flash method in a Linseis LFA 1000. Heat capacity (C_p) measurements were performed at UM using a NETZSCH Differential Scanning Calorimeter Model 404C with a calibrated Al_2O_3 standard. The density (ρ) was measured via the Archimedes method. The thermal conductivity was calculated with the equation $\kappa = \rho DC_p$. High temperature carrier concentration was determined by Hall coefficient measurements with a 1 Tesla magnetic field, conducted at UM using a 4-probe AC method with the signal measured by a Linear Research AC Bridge Model LR-700. We assumed a single parabolic band model to extract the carrier concentration, $n = 1/(eR_H)$, where R_H is the measured Hall coefficient. The carrier mobility was calculated as $\mu = \sigma R_H$. All measurements were performed under argon atmospheres to avoid sample oxidation. The carrier scattering mechanism was analyzed by electrical conductivity ratios (ECR) method [20].

3. Results and discussion

3.1 Phase structure and micro morphology

The room temperature XRD patterns of $\text{MoTe}_{2-x}\text{I}_x$ ($x = 0, 0.01, 0.02, 0.03, 0.04$) are shown in **Figure 1**. The results indicate the samples possess a close-packed hexagonal crystal structure. All the main diffraction peaks correspond to the 2H- MoTe_2 phase (PDF#72-0117) crystallizing in the $P6_3/mmc$ space

group. No other phase was detected in the XRD. The values of the lattice parameters (a & c), unit cell volume (V), and grain size (d) for all samples are displayed in **Table 1**.

Table 1. The lattice constants, unit cell volumes and grain sizes of $\text{MoTe}_{2-x}\text{I}_x$ ($x = 0 \sim 0.04$)

x	a [$\text{\AA}$]	c [$\text{\AA}$]	c/a	V [$\text{\AA}^3$]	d [nm]	TF
0	3.316	13.975	4.214	199.614	74.23	0.176
0.01	3.314	13.965	4.214	199.230	73.91	0.148
0.02	3.313	13.959	4.213	199.024	73.82	0.139
0.03	3.312	13.962	4.216	198.947	73.67	0.153
0.04	3.311	13.953	4.214	198.699	73.46	0.161

Evidently, the trend is further reflected in the position of the characteristic XRD peaks, (100) and (103), enlarged in **Figure 1(b)**. Overall, compared to pure MoTe_2 , the diffraction peaks of the I-doped samples are all shifted to higher angles, as shown in **Figure 1(b)**. Correspondingly, the lattice parameters (a , c , and V) of the samples decrease with iodine content increasing. The reason is that the ionic radius of I^- (1.33 $\text{\AA}$) is smaller than that of Te^{2-} (1.36 $\text{\AA}$), indicating a likely simple substitution of the two elements in the crystal structure. Besides, the grain size of samples is similar, and the value is around 74nm.

Figure 1. (a) XRD pattern of $\text{MoTe}_{2-x}\text{I}_x$ ($x=0 \sim 0.04$), and (b) Close-up of the pattern ranging from 27.5 to 36.5 showing

the main (100) and (103) peaks moving with I doping content.

Considering the layered structure of dichalcogenides materials, the spark plasma sintered (SPS) samples may be textured in c-axis direction (i.e., with preferred orientation), in which case the anisotropy of electrical and thermal transport properties must be considered to yield correct ZT values. To quantify the texture, the orientation factors (TF) are calculated according to the Lotgering method using the following equations [21]:

$$TF = \frac{P - P_0}{1 - P_0} \quad (1)$$

$$P = \frac{\sum I(00l)}{\sum I(hkl)} \quad (2)$$

$$P_0 = \frac{\sum I_0(00l)}{\sum I_0(hkl)} \quad (3)$$

Where, P and P_0 are the ratios of the integrated intensity of all lattice plane (00 l) peaks to that of all (hkl) peaks, taken from the experimental SPS pelletized sample data or from the standard powder diffraction file (PDF) data (PDF#72-0117), respectively. I and I_0 are the corresponding peak intensities. The values of TF shown in **Table 1** are much lower than the orientation factors of other reported dichalcogenides, indicating a low level of texture (preferred orientation).

Figure 2(a) shows the typical microstructure of the polished surface of $\text{MoTe}_{1.97}\text{I}_{0.03}$, as observed through field emission scanning electron microscopy (FESEM). Porosity and texturing are mainly absent. Importantly, the microstructure is quite finely grained, which can be attributed to the rapid SPS at lower temperature. The average grain size around 74nm observed in **Figure 2(a)** is in agreement with that calculated from the refined XRD data via the Debye-Scherrer Formula (showed in Table1). Furthermore, the back-scattered electron (BSE) image and EDS mapping results shown in **Figure 2(b)-2(e)** confirm the homogeneous microstructure. All three elements of the compounds, including the dopant iodine, are

distributed uniformly in the matrix.

Figure 2. (a) FESEM image of a polished surface of polycrystalline $\text{MoTe}_{1.97}\text{I}_{0.03}$ and (b) BSE image of a representative surface of the sample. EDS mappings of (c) Te, (d) Mo and (e) I of polycrystalline $\text{MoTe}_{1.97}\text{I}_{0.03}$ show a nicely homogenized matrix.

3.2 Thermoelectric transport properties

The thermoelectric properties from room temperature up to 823 K for the SPS sintered $\text{MoTe}_{2-x}\text{I}_x$ samples are shown in **Figure 3**. The electrical conductivity (**Figure 3(a)**) exhibits a thermally activated behavior that is essentially exponential until approximately 650 K, then more linearly dependent at higher temperatures. As increasing the amounts of TeI_4 doped, the electrical conductivity uniformly increases, mainly due to the elevated carrier concentrations (**Figure 3(c)**). The Seebeck coefficients (**Figure 3(b)**) for the I-doped samples are negative over the entire temperature range, indicating that the majority charge carriers in $\text{MoTe}_{2-x}\text{I}_x$ are electrons and the samples are *n*-type semiconductors. The absolute values of the Seebeck coefficients trend up as the temperature is increased initially, then fall down starting from 650K, with the maximum point shifting to lower temperatures as the iodine content is increased. The maximum

in the Seebeck coefficient is a result of minority carriers (holes) activated at higher temperatures contributing to the conduction [22]. Thermally excited holes lead to a positive Seebeck coefficient that decreases the net voltage [23-25]. The quantity of the thermally activated holes is related to the band gap (E_g) estimated by $E_g = 2e|S_{\max}|T_{\max}$, where $|S_{\max}|$ is the maximum of the absolute Seebeck coefficient and $T_{\max}$ is the temperature at which $|S_{\max}|$ is obtained [26]. Assuming the impact of temperature on E_g is negligible, the E_g of $\text{MoTe}_{2-x}\text{I}_x$ ($x=0, 0.01, 0.02, 0.03, 0.04$) can be estimated roughly from the Seebeck coefficient data, and they are approximately 0.71eV, 0.66eV, 0.63eV, 0.59eV and 0.48eV, respectively. Typically, E_g decreases as dopant concentration increases, so the E_g is affected by the impurity energy level caused by the introduction of iodine. Additionally, the magnitudes of the Seebeck coefficients decrease monotonically with iodine dopant concentration. As expected, as every Iodine ion can contribute a single electron, the carrier concentration will increase with the doping of TeI_4 increasing (**Figure 3(c)**). Specifically, the carrier concentration of the undoped sample increases by an order of magnitude when 3 at% I is doped into the matrix, yielding 10^{18} cm^{-3} charge carriers.

Figure 3. Electrical transport properties of $\text{MoTe}_{2-x}\text{I}_x$ ($x = 0.00, 0.01, 0.02, 0.03, 0.04$). (a) Electrical conductivity σ , (b) Seebeck coefficient S , (c) carrier concentration n , and (d) carrier mobility μ .

The above-mentioned discussion of the Seebeck coefficient and electrical conductivity with varied temperature and dopant concentration indicate that the samples are typical nondegenerate semiconductors. It is also found that iodine doping not only increases the conductivity, but also does not substantially reduce Seebeck coefficient. For further insight into the electronic transport, we can assess the charge carrier mobility, $\mu = \sigma/ne$, which are presented in **Figure 3(d)**. It can be observed that μ rises with both the iodine content and temperature. In the whole temperature range, the mobility approximately follows a $T^{3/2}$ dependence that is likely due to the crystal dislocation scattering [27]. The reason is that nanoscale grains grow slightly with increasing temperature, which generate dislocations because of lattice distortions. If the dislocations have an edge component, they can introduce acceptor centers along the dislocation line that capture electrons from the conduction band in an n -type semiconductor [28,29]. The electron mobility due to such scattering by dislocations is given by the expression [27]:

$$\mu_{\text{dislocation}} = \frac{30\sqrt{2\pi} \varepsilon^2 d^2 (kT)^{3/2}}{Ne^3 f^2 \lambda_d \sqrt{m^*}} \quad (4)$$

where ε is the dielectric constant, d is the distance between acceptor centers (dangling bonds) along the dislocation line, k is Boltzmann constant, f is the occupation rate of the acceptor centers, N is the density of dislocations, m^* is the effective mass of the charge carriers and λ_d is the Debye screening length,

$$\lambda_d = \left(\frac{\epsilon k T}{e^2 n} \right)^{1/2} \quad (5)$$

Where, n is the carrier concentration. Thus according to **Equation** (4) and (5), the carrier mobility owing to scattering by dislocations should increase monotonically with the carrier concentration. That also agrees with the trend of n and μ shown in **Figure 3(c)** and **3(d)**. Therefore, it appears that dislocations play a positive role in transport improvement.

Figure 4. Plot of $\ln\sigma$ versus $1/T$ for $\text{MoTe}_{2-x}\text{I}_x$ samples

In order to examine the temperature behavior of the electrical conductivity for $\text{MoTe}_{2-x}\text{I}_x$, logarithm of the electrical conductivity σ as a function of reciprocal of temperature is given in **Figure 4**. The existence of a linear relationship between $\ln\sigma$ and $1/T$ means that their conductivity can be described by a thermally activated expression (Arrhenius plot) in corresponding temperature regimes, written as

$$\sigma = \sigma_0 \exp(-E/kT) \quad (6)$$

Where, σ_0 is the preexponential factor and E is the activation energy for conduction. By best fit of the experimental data to Equation(6), one can obtain activation energies E_H and E_L in the high-temperature regime ($T > \sim 649$ K) and the low-temperature regime ($T < \sim 423$ K), respectively.

Table 2. List of conduction activation energies E_L and E_H , the energy gap E_g^* and E_g of $\text{MoTe}_{2-x}\text{I}_x$ ($x = 0 \sim 0.04$)

x	$E_L(\text{meV})$	$E_H(\text{eV})$	$E_g^*(\text{eV})$	$E_g(\text{eV})$
0	152.5	0.50	1.00	0.71
0.01	94.4	0.36	0.71	0.66
0.02	88.2	0.28	0.56	0.63
0.03	83.1	0.22	0.45	0.59
0.04	65.6	0.19	0.38	0.48

Activation energies (E_L and E_H) were calculated by means of the linear relationship at low and high temperature, respectively. According to the relationship, $E_g^*=2E_H$, in high temperature range, E_g^* was evaluated and compared with $E_g=2e|S_{\text{max}}|T_{\text{max}}$ calculated correspondingly above. As shown in Table 2, the activation energy (E_L and E_H) and band gaps (E_g^* and E_g) decrease, and the carrier concentration increases with the increase of doping content, which is consistent with Figure 3c. The variation and values of band gaps (E_g^* and E_g) calculated by the two methods are generally consistent, and the E_g^* and E_g for pure MoTe_2 are very close to the theoretical calculated result [30].

Based on the transport properties data shown in Figure 3 (a) and (b), the ECR method was adopted to analyze the carrier scattering mechanism (CSM) [20]. The results for 4 samples are presented in Figure 5. Comparing the ratio of the electrical conductivity, σ_T/σ_{298} (σ_{298} is the value of σ at $T=298$ K), between the experimental data and different scattering models, it can be found that the models for 4 samples matching the experimental data most closely are all dislocation scattering. That is dislocation scattering is the dominant mechanism for 4 samples. Therefore, iodine doping does not alter the dominant scattering mechanism during experimental temperature range.

Figure 5. Logarithmic values of the experimental(*Exp.*) ratios, $\ln(\sigma_T/\sigma_{298})$, depending on temperature, shown with the calculated ratios according to acoustic phonon scattering (*APS*), alloy scattering (*AS*), polar optical phonon scattering (*POPS*) and dislocation scattering (*DS*) models when $\eta < 0$. The four subgraphs show the relations for $\text{MoTe}_{2-x}\text{I}_x$ samples ($x=0.00, 0.02, 0.03, 0.04$), respectively.

In the single parabolic band model, the general carrier concentration (n) applicable to both degenerate and non-degenerate semiconductors can be expressed as follows:

$$n = \frac{4\pi(2m^*kT)^{3/2}}{h^3} F_{1/2}(\eta) \quad (7)$$

Where, h is the Planck constant and $F_{1/2}(\eta)$ is the Fermi-Dirac integral of order $r=1/2$, with $\eta = E_F / T$ the reduced Fermi energy in terms of the Fermi energy E_F .

If assuming that the effective mass is independent depend on temperature, the effective mass (m^*) can be estimated according to the transport data (Seebeck coefficient S and charge carrier concentration n). At room temperature, the effective masses of samples $\text{MoTe}_{2-x}\text{I}_x$ ($x = 0, 0.01, 0.02, 0.03$ and 0.04) are $0.67m_e$, $0.71m_e$, $0.74m_e$, $0.75m_e$ and $0.78m_e$ for, respectively, where m_e is the bare electron mass. The results

demonstrate that the effective mass m^* of the sample increases with the increase of doping content. It is consistent with the improvement of carrier concentration. The results also indicate that I ion occupies the position of Te^{2-} and contributes free electron to $\text{MoTe}_{2-x}\text{I}_x$.

Figure 6. Temperature dependence of (a) the total thermal conductivity (κ), (b) the electronic component of the thermal conductivity (κ_e) and (c) the lattice thermal conductivity (κ_l) of $\text{MoTe}_{2-x}\text{I}_x$ ($x = 0, 0.01, 0.02, 0.03, 0.04$).

The thermal conductivities κ for the $\text{MoTe}_{2-x}\text{I}_x$ samples are displayed in **Figure 6(a)**. The values follow a decreasing trend until about 600 K and then increase gradually. For crystalline materials, the enhanced phonon–phonon interactions drag down the thermal conductivity as the temperature increases. When the temperature is above 600 K, κ rises owing to the bipolar effect. As the amount of iodine doping is increased, the thermal conductivity drops down. As shown in **Figure 6(a)**, $\kappa = 2.64 \text{ W}\cdot\text{m}^{-1}\cdot\text{K}^{-1}$ for the pure

sample at 673 K and is basically twice as large as the $1.19 \text{ Wm}^{-1}\text{K}^{-1}$ for the $x = 0.03$ sample at the same temperature. Generally, the thermal conductivity κ is mainly acted by two portions, one is electronic thermal conductivity κ_e and the other is lattice thermal conductivity κ_l . Thus the lattice thermal conductivity $\kappa_l = \kappa - \kappa_e$, and κ_e can be calculated according to the Wiedemann-Franz law: $\kappa_e = LT\sigma$, where L is the Lorenz number. Actually, the Lorentz number is not invariant in the experiment temperature range, which decreases at high temperature. In order to accurately calculate the electron thermal conductivity, the Lorentz number can be expressed as the following equation (8) [31].

$$L = \left(\frac{k}{e}\right)^2 \left(\frac{(r+7/2)F_{r+5/2}(\eta)}{(r+3/2)F_{r+1/2}(\eta)} - \left[\frac{(r+5/2)F_{r+3/2}(\eta)}{(r+3/2)F_{r+1/2}(\eta)} \right]^2 \right) \quad (8)$$

Where, η is reduced Fermi energy ($\eta = E_F / kT$) and r is scattering parameter ($r = 3/2$). The calculated Lorenz numbers range from 2.36 to $2.43 \times 10^{-8} \text{ V}^2\text{K}^{-2}$.

Compared with the value of κ and κ_e from figure 6a and 6b, the electronic thermal conductivity (κ_e) has little effect on the total thermal conductivity. The total thermal conductivity mainly contributed by the lattice thermal conductivity, which lead to low κ at the high temperature range. At 673K, the lowest thermal conductivity was obtained for the sample ($x=0.03$), reaching about $1.19 \text{ Wm}^{-1}\text{K}^{-1}$. It can be seen by comparing **Figure 6(a)** with **Figure 6(c)** that the values and temperature dependences of the lattice thermal conductivities (κ_l) are similar to that of the total thermal conductivity κ . Below 600 K, the lattice thermal conductivities decrease with temperature, basically following a T^{-1} dependence due to the enhancement of phonon scattering by point defects and other phonons. At higher temperatures, it turns to be dominant that carrier scattering induced by bipolar conductivity and dislocation scattering for the variation of κ_l matches a T^2 function [32].

Figure 7. (a) Power factor (PF) and (b) figure of merit (ZT) of $\text{MoTe}_{2-x}\text{I}_x$ ($x=0, 0.01, 0.02, 0.03, 0.04$)

The power factor of the $\text{MoTe}_{2-x}\text{I}_x$ samples, $PF = S^2\sigma$, is plotted as a function of temperature in **Figure 7(a)**. It can be seen that the power factor first increases slowly and then substantially at higher temperatures and doping concentrations, x . The highest power factor near 5 $\mu\text{W}\cdot\text{cm}^{-1}\cdot\text{K}^{-2}$ was obtained at 823 K for the most heavily doped sample of the study. The ZT values for all the $\text{MoTe}_{2-x}\text{I}_x$ samples in this study are shown in **Figure 7(b)**, from which it can be found that ZT values increase rapidly below 650 K, that is, before the onset of bipolar conduction. The ZT values typically increase versus iodine doping, with the maximum shifting to low temperatures. The highest ZT value of 0.16 is obtained at about 723 K for the sample with $x = 0.03$, more than 5 times the value of the pure sample at the same temperature, and great higher than the value, $ZT=0.02$ at 300K, reported by K. Ikeura et al.¹⁹. Besides, the high level of ZT can be kept in the range of 673 to 750K.

4. Conclusion

N -type nano-polycrystalline $\text{MoTe}_{2-x}\text{I}_x$ samples were fabricated for first time by solid-state reaction, ball milling and spark plasma sintering. The crystal structure and thermoelectric property were investigated. The conclusions can be described below:

(1) The XRD patterns of all the samples indicate that the main diffraction peaks correspond to the

hexagonal MoTe₂ phase (PDF#72-0117) with no texture of the c-axis plane. The grain size is around 74nm. Iodine has been homogeneously doped into the unit cell according to the microstructure and transport properties analysis.

(2) The addition of iodine exactly reduces the ionization energy and band gap of samples. The iodine doping in MoTe₂ also improves the electrical conductivity without a serious reduction of the Seebeck coefficient, leading to substantially enhanced power factors. The electrical conductivity and Seebeck coefficient data show the temperature dependence of a typical non-degenerate semiconductor.

(3) Based on ECR method, dislocations in the microstructure could be responsible for the charge carrier scattering in MoTe_{2-x}I_x (x=0, 0.01, 0.02, 0.03, 0.04) from 298 K to 823 K. The dislocation scattering factor is 3/2, which may be one of the reasons for the large Seebeck coefficient of nano-polycrystalline MoTe₂.

(4) The thermal conductivity κ of the doped samples was reduced sharply owing to point defects and dislocation scattering. As a result, the ZT of all the doped samples is enhanced as compared with that of the pure sample. The largest value of $ZT = 0.16$ at 723 K is obtained for MoTe_{1.97}I_{0.03} nano-polycrystalline.

Acknowledgments

The authors would like to acknowledge helpful communications with Dr. Si Wang and Dr. Si Hui, as well as support in the synthesis by Mr. Ruiming Lu from Materials Science and Engineering at the University of Michigan. This work was financially supported by National Key Research and Development Program (Grant No. 2018YFB0904400), and by the Fundamental Research Funds for the Central Universities [Grant No. FRF-MP-18-005, and FRF-MP-19-005]. Finally, P. Ren would like to acknowledge the fellowship from the China Scholarship Council (CSC) (No. 201506460044).

Conflict of Interest

The authors declare that they have no conflict of interest.

Data Availability Statement

The data that support the findings of this study are available from the corresponding author upon reasonable request.

Reference

1. J. He and T. M. Tritt, *Science* 357, 1369 (2017).
2. L. E. Bell, *Science* 321, 1457 (2008).
3. P. Ren, Y. M. Liu, J. He, T. Lv, J. L. Gao, and G. Y. Xu, *Inorg. Chem. Front.* 5, 2380 (2018).
4. K. Biswas, J. Q. He, Q. C. Zhang, G. Y. Wang, C. Uher, V. P. Dravid, and M. G. Kanatzidis, *Nat. Chem.* 3, 160 (2011).
5. G. J. Snyder and E. S. Toberer, *Nat. Mater.* 7, 105 (2008).
6. K. Biswas, J. He, I. D. Blum, C. I. Wu, T. P. Hogan, D. N. Seidman, V. P. Dravid, and M.G. Kanatzidis, *Nature* 489, 414 (2012).
7. J. F. Li, W. S. Liu, L. D. Zhao, and M. Zhou, *NPG Asia Mater.* 2, 152 (2011).
8. J. P. Heremans, B. Wiendlocha, and S.M. Chamoire, *Energy Environ. Sci.* 5, 5510 (2012).
9. Y. Z. Pei, X. Y. Shi, A. D. LaLonde, H. Wang, L. D. Chen, and G.J. Snyder, *Nature* 473, 66 (2011).
10. V. Petkov, S. J. L. Billinge, P. Larson, S. D. Mahanti, T. Vogt, K. K.Rangan, and M. G. Kanatzidis, *Phys. Rev. B* 65, 092105 (2002).
11. J. N. Coleman, M. Lotya, A. O'Neill, S. D. Bergin, P. J. King, U. Khan, K. Young, A. Gaucher, S. De , R. J. Smith, I. V. Shvets, S. K. Arora, G. Stanton, Hye-Y. Kim, K. Lee, G. T. Kim, G. S. Duesberg, T. Hallam, J. J. Boland, J. J. Wang, J. F. Donegan, J. C. Grunlan, G. Moriarty, A.

- Shmeliov, R. J. Nicholls, J. M. Perkins, E. M. Grieverson, K. Theuwissen, D. W. McComb, P. D. Nellist, and V. Nicolosi, *Science* 331, 568 (2011).
12. F. R. Gamble, F. J. DiSalvo, R. A. Klemm, and T. H. Geballe, *Science* 168, 568 (1970).
 13. M. N. Ali, J. Xiong, S. Flynn, J. Tao, Q. D. Gibson, L. M. Schoop, T. Liang, N. Haldolaarachchige, M. Hirschberger, N. P. Ong, and R. J. Cava, *Nature* 514, 205 (2014).
 14. Z. Wang, D. Gresch, A. A. Soluyanov, W. Xie, S. Kushwaha, X. Dai, M. Troyer, R. J. Cava, and B. A. Bernevig, *Phys. Rev. Lett.* 117, 056805 (2016).
 15. X. Huang, Z. Z. Zeng, and H. Zhang, *Chem. Soc. Rev.* 42, 1934 (2013).
 16. S. Hébert, W. Kobayashi, H. Muguerra, Y. Bréard, N. Raghavendra, F. Gascoin, E. Guilmeau, and A. Maignan, *Phys. Status Solidi A* 210, 69 (2013).
 17. P. Gorai, D. Gao, B. Ortiz, S. Miller, S. Barnett, T. Mason, Q. Lv, V. Stevanovic, and E. S. Toberer, *Comp. Mat. Sci.* 112, 368 (2015).
 18. Y. Liu, W. J. Lu, D. F. Shao, L. Zu, X. C. Kan, W. H. Song, and Y. P. Sun, *Europhys. Lett.* 109, 17003 (2015).
 19. K. Ikeura, H. Sakai, M. S. Bahramy, and S. Ishiwata, *APL Materials* 3, 041514 (2015).
 20. G.Y. Xu, P. Ren, T. Lin, X.F. Wu, Y. H. Zhang, S.T. Niu, and T. P. Bailey, *J. Appl. Phys.* 123, 015101 (2018).
 21. F. K. Lotgering, *J. Inorg. Nucl. Chem.* 9, 113 (1959).
 22. A. F. May, J.-P. Fleurial, and G. J. Snyder, *Phys. Rev. B* 78, 125205 (2008).
 23. H. J. Goldsmid, *Applications of Thermoelectricity*, (Butler & Tanner, London, 1960), p.14.
 24. V. I. Fistul, *Heavily Doped Semiconductors*, (Plenum Press, New York, 1969), p.101.
 25. D. K. C. MacDonald, *Thermoelectricity: An Introduction to the Principles*, (Wiley, New York, 1962) p.37.

26. H. J. Goldsmid and J. W. Sharp, *J. Electron. Mater.* 28, 869 (1999).
27. H. M. Ng, D. Doppalapudi, T. D. Moustakas, N. G. Weimann, and L. F. Eastman, *Appl. Phys. Lett.* 73, 821 (1998).
28. W. T. Read Jr., London, Edinburgh, Dublin *Philos. Mag. J. Science*, 45, 1119-1128 (1954).
29. B. Pödör, *Phys. Status Solidi*. 16, K167 (1966).
30. I. G. Lezama¹, A. Ubaldini, M. Longobardi, E. Giannini, C. Renner, A. B. Kuzmenko, A. F. Morpurgo, , *2D Mater.* 1, 021002 (2014).
31. L. D. Zhao, S. H. Lo, J. Q He, H. Li, K. Biswas, J. Androulakis, C. I. Wu, T. P. Hogan, D. Y. Chung, V. P. Dravid, and M. G. Kanatzidis, *J. Am. Chem. Soc.* 133, 20476 (2011).
32. J. Z. Zhang, *Thermoelectric technology*, (Tianjin Science and Technology Press, Tianjin, 2013), p.40.

Figures

Figure 1

(a) XRD pattern of MoTe_{2-x}I_x ($x=0 \sim 0.04$), and (b) Close-up of the pattern ranging from 27.5 to 36.5 showing the main (100) and (103) peaks moving with I doping content.

Figure 2

(a) FESEM image of a polished surface of polycrystalline MoTe_{1.97}I_{0.03} and (b) BSE image of a representative surface of the sample. EDS mappings of (c) Te, (d) Mo and (e) I of polycrystalline MoTe_{1.97}I_{0.03} show a nicely homogenized matrix.

Figure 3

Electrical transport properties of MoTe_{2-x}I_x (x = 0.00, 0.01, 0.02, 0.03, 0.04). (a) Electrical conductivity σ , (b) Seebeck coefficient S, (c) carrier concentration n, and (d) carrier mobility μ .

Figure 4

Plot of $\ln \sigma$ versus $1/T$ for MoTe_{2-x}I_x samples

Figure 5

Logarithmic values of the experimental(Exp.) ratios, $\ln(\sigma_T/\sigma_{298})$, depending on temperature, shown with the calculated ratios according to acoustic phonon scattering (APS), alloy scattering (AS), polar optical phonon scattering (POPS) and dislocation scattering (DS) models when $\eta < 0$. The four subgraphs show the relations for MoTe_{2-x}I_x samples ($x=0.00, 0.02, 0.03, 0.04$), respectively.

Figure 6

Temperature dependence of (a) the total thermal conductivity (κ), (b) the electronic component of the thermal conductivity (κ_e) and (c) the lattice thermal conductivity (κ_l) of $\text{MoTe}_{2-x}\text{Irx}$ ($x = 0, 0.01, 0.02, 0.03, 0.04$).

Figure 7

(a) Power factor (PF) and (b) figure of merit (ZT) of $\text{MoTe}_{2-x}\text{Ir}_x$ ($x=0, 0.01, 0.02, 0.03, 0.04$)