Highly-porous Uniformly-sized Amidoxime-functionalized Cellulose Beads Prepared by Microfluidics with N-methylmorpholine N-oxide

Seung-Yeop Baek

Kyungpook National University

Soo-Young Park (✉ psy@knu.ac.kr)

Kyungpook National University <https://orcid.org/0000-0001-6796-4929>

Research Article

Keywords: cellulose, microfluidics, N-methylmorpholine N-oxide, amidoxime, metal adsorption, filter

Posted Date: February 24th, 2021

DOI: <https://doi.org/10.21203/rs.3.rs-221648/v1>

License: © ⓘ This work is licensed under a Creative Commons Attribution 4.0 International License.

[Read Full License](#)

1 **Highly-porous uniformly-sized amidoxime-** 2 **functionalized cellulose beads prepared by** 3 **microfluidics with N-methylmorpholine N-oxide**

4 Seung-Yeop Baek and Soo-Young Park*

5 *School of Applied Chemical Engineering, Polymeric Nano Materials Laboratory,*
6 *Kyungpook National University, Daegu 41566, Republic of Korea. E-mail:*
7 psy@knu.ac.kr

8 *Corresponding author

9
10 **Abstract:** Uniformly-sized porous cellulose beads functionalized with amidoxime groups were
11 prepared for the first time using a microfluidic method with N-methylmorpholine N-oxide
12 (NMMO) monohydrate as a cellulose solvent. The molten state cellulose dope in NMMO
13 monohydrate (cell/NMMO dope) as a disperse phase and hot mineral oil as a continuous phase
14 were used in a T-junction microfluidic chip to produce uniformly-sized cell/NMMO droplets.
15 Coagulation of the molten state cell/NMMO droplet at high temperature and amidoxime
16 functionalization could prepare the highly-porous spherical amidoxime-functionalized cellulose
17 beads with a uniform fibrous open internal structure. The prepared amidoxime-functionalized
18 cellulose beads showed excellent metal adsorption properties with a maximum adsorption capacity
19 of $\sim 80 \text{ mg g}^{-1}$ in the case of Cu^{2+} /phthalate ions. The newly developed highly-porous cellulose
20 beads can open many new applications with other proper functionalization at the reactive hydroxyl
21 groups of the cellulose.

22
23 **Keywords:** *cellulose, microfluidics, N-methylmorpholine N-oxide, amidoxime,*
24 *metal adsorption, filter*

25 26 **Introduction**

27 Cellulose, a linear polysaccharide, is the most abundant and renewable biopolymer in nature
28 (Klemm et al. 2011) and has been widely studied because of its unique properties, such as
29 biocompatibility, biodegradability, eco-friendliness, cost-effectiveness, and easy modification.
30 This natural polymer cannot be melted (by heating) and solubilized (in common organic solvents)
31 because of its strong intra- and interchain hydrogen bonding. The cellulose can be a processible
32 liquid form by derivatized chemical modification or direct dissolution with specific solvents.
33 Traditional viscose technology uses derivatization in which cellulose xanthogenate is formed as an
34 intermediate derivative. However, this process produces environmentally hazardous byproducts
35 such as carbon disulfide and hydrogen sulfide (Fink et al. 2001). The direct dissolution process is

36 purely physical without any structural changes (Rosenau et al. 2002). Of the many solvents for
37 direct dissolution, N-methylmorpholine N-oxide (NMMO) is a well-known commercialized
38 solvent (Lidhure et al. 2019). Nontoxic NMMO is economically favorable because it is mostly
39 recycled and reusable (Dawson 2012; Rosenau et al. 2001). NMMO is used in hydrated forms to
40 dissolve cellulose. According to the phase diagram of the NMMO/water/cellulose mixture, the
41 NMMO monohydrate can dissolve cellulose up to 13 wt% (Lidhure et al. 2019). The melting
42 temperature of the NMMO monohydrate is $\sim 76^{\circ}\text{C}$; therefore, the NMMO monohydrate should be
43 heated to $\sim 80^{\circ}\text{C}$ to make the cellulose/NMMO (cell/NMMO) dope. Upon cooling, the cell/NMMO
44 dope becomes solid at temperatures between 20°C and 40°C (Biganska et al. 2002).

45 Cellulose and cellulose derivatives have been used as adsorbents in the form of hydrogels,
46 films, beads, microfibers, and microcrystals (Hua et al. 2019). The cellulose beads can be prepared
47 by sequentially forming spherical cell/NMMO dope, solidification via temperature decrease, and
48 coagulation with water (Gericke et al. 2013). The cellulose beads can be used for the stationary
49 phase in chromatography, protein purification, and drug delivery (Alam et al. 2019). The cellulose
50 beads prepared from the cell/NMMO dope have much porosity because a large amount of NMMO
51 is extracted from the cell/NMMO dope during coagulation. Their high porosity enhances the
52 interfacial area available for interactions with the target molecules when using the cellulose beads
53 as adsorbents. However, the cellulose beads prepared from lower cellulose concentrations have
54 weak mechanical properties (although they provide high porosity); therefore, crosslinking is
55 necessary to enhance mechanical properties. The temperature and composition of the coagulation
56 medium also influence the morphology, internal surface area, and pore size distribution. Hence, to
57 take full advantage of cellulose beads, the porosity and surface area should be controlled and
58 optimized with coagulation conditions because they determine the adsorption capacity of the
59 cellulose beads. The size of the cellulose bead depends on the manufacturing method such that
60 conventional dropping and dispersion techniques produce cellulose droplets with a size above and
61 below $\sim 350\text{ }\mu\text{m}$, respectively, with a certain size distribution (Gericke et al. 2013; Rosenberg et al.
62 2007). Recently, the microfluidic method has become common for producing uniformly-sized
63 particles. However, in our limited knowledge, highly controlled manufacturing methods for
64 producing cellulose beads using microfluidics have not yet been developed using NMMO
65 monohydrate as a solvent of cellulose.

66 The pollution of water resources with harmful metals, such as lead, mercury, cadmium,
67 copper, iron, and chromium, is a serious threat to humans (Sharma et al. 2007). Thus, detecting
68 and removing such harmful metals in water has been critical for modern society. Various efficient
69 but expensive methods are proposed to remove heavy metal ions from industrial effluents using
70 ion-exchange, reverse osmosis, and electrodialysis techniques (Bolto and Pawłowski 1987;
71 Geckeler et al. 1988; Pawłowski 2015). Chemical precipitation is promising, but the generation of
72 precipitated bulky hydroxides is often a major disadvantage. Functional cellulose beads were
73 prepared as biocompatible adsorbents for water treatment using chemical functionalization or
74 blending cellulose with organic and inorganic compounds. For example, the cellulose beads
75 carrying carboxylate groups possess high adsorption capacity for calcium, copper, silver, and lead
76 (Hirota et al. 2009), and those prepared by blending using alginate or chitosan were applied for

77 removing cadmium and copper (Twu et al. 2003; Zhang et al. 2005). The cellulose modified using
78 amine-containing functional groups (aminoalkyl and 2, 2'-diaminodiethylamine) or an anionic
79 moiety (phosphate, thiolate, carboxyl, and carboxymethyl) has been reported for applications to
80 metal adsorption (Saliba et al. 2000a). Strong fixation of metal ions, especially multivalent ones, to
81 cellulose beads has been achieved by coupling with specific ligands that possess multiple
82 functional groups for metal complexation (Diviš et al. 2009; Matúš and Kubová 2005). Several
83 chelating ligands such as diamines, iminodiacetic acid, or ethylenediaminetetraacetic acid have
84 been coupled to cellulose beads (Boeden et al. 1991; He et al. 1999; Kahovec et al. 1980;
85 Yeomans-Reina et al. 2001). The cellulose beads functionalized with amidoxime groups were also
86 used as metal adsorbents (Saliba et al. 2000b). Amidoxime groups have hydroxyamino (=N-OH)
87 and amino (-NH₂) groups at the same carbon atom, offering the fused features of amide, oxime,
88 amidine, and hydroxamic acid functionality (Li et al. 2013b). Adsorption occurs through sharing
89 or exchanging electrons between the transition metal ions and amidoxime ligand (Rahman et al.
90 2016; Wang et al. 2015). Amidoxime groups have no affinity for the common metallic cations
91 (Na⁺, K⁺, Ca²⁺, and Mg²⁺) but have a strong tendency to form a chelate complex with various
92 transition and heavy metal ions (Pb²⁺, Cu²⁺, Fe³⁺, and Cd²⁺) in an aqueous solution. The selective
93 chelation of metal cations of the amidoxime group has been widely applied for fabricating
94 functional materials. For example, chelating resins, gels, fibers, microbeads, and membranes
95 functionalized with amidoxime groups were prepared for removing heavy toxic metal ions,
96 enriching and selective recovery of precious metals from natural water and industrial wastewater,
97 and detecting heavy metal ions (Li et al. 2013a). The amidoxime-functionalized materials also
98 have potential applications in CO₂ capture and storage (Zulfiqar et al. 2011).

99 In this study, uniformly-sized, highly-porous, expandable, and amidoxime-functionalized
100 cellulose (O-cellulose) beads were prepared with the cell/NMMO dope using a microfluidic
101 method. Here stable cell/NMMO droplets in mineral oil were produced with T-junction at 80°C,
102 followed by coagulation in THF/water mixture, crosslinking with epichlorohydrin, and amidoxime
103 functionalization. The structures of the produced cellulose depended on the state of the
104 cell/NMMO droplet (solid or molten) and the temperature of the coagulation bath (hot or cold).
105 The relationship between the internal structure and adsorption properties was studied using
106 samples prepared from a critical point drying (CPD) method with liquid CO₂. The prepared O-
107 cellulose beads showed high affinity to multivalent metal ions that were studied by Langmuir
108 isotherm. The relationship between the internal structure and adsorption property was established,
109 with the cellulose beads having various porous structures prepared by different coagulation
110 conditions. The uniformly-sized porous cellulose beads can be easily expanded to other
111 applications because of the easy introduction of different functional groups.

112

113 **Experimental**

114 *Materials*

115 Cellulose powder and NMMO monohydrate were obtained from KOLON (South Korea), and
116 epichlorohydrin (ECH) and acrylonitrile (AN) were purchased from Daejung (South Korea).
117 Sodium hydroxide (NaOH), sodium carbonate (NaCO₃), hydroxylamine hydrochloride
118 (NH₂OH·HCl), tetrahydrofuran (THF), methanol (MeOH), and potassium hydrogen phthalate
119 (KHP) were purchased from Duksan. Tetramethylammonium (TMA) chloride ((CH₃)₄N⁺Cl⁻),
120 copper(II) nitrate hexahydrate (Cu(NO₃)₂·6H₂O), cadmium(II) nitrate (Cd(NO₃)₂), and iron(III)
121 chloride hexahydrate (FeCl₃·6H₂O) were purchased from Junsei (Japan). Lead(II) nitrate
122 (Pb(NO₃)₂), nickel(II) nitrate hexahydrate (Ni(NO₃)₂·6H₂O), calcium(II) nitrate tetrahydrate
123 (Ca(NO₃)₂·4H₂O), zinc(II) nitrate hexahydrate (Zn(NO₃)₂·6H₂O), and chromium(II) chloride
124 hexahydrate (Cr(NO₃)₂·6H₂O) were purchased from Sigma Aldrich (USA). All chemicals were
125 used as-received without further purifications.

127 *Preparation of uniformly-sized cellulose droplets*

128 Scheme 1a summarizes the overall schematics of producing cellulose beads using
129 microfluidics. The following is a detailed description of the preparation procedure. The NMMO
130 monohydrate (100 g) was melted in a round-bottom glass tube (outer diameter = 60 mm, length =
131 180 mm) at 80°C in which the cellulose powders (4 g) were dissolved using a screw-type propeller
132 (diameter = 125 mm, pitch = 35 mm) at 80°C for 2 h. The dissolved cell/NMMO dope was
133 degassed by maintaining it at 90°C for 2 h with a rubber cap on the top to prevent water
134 evaporation in the NMMO monohydrate. The degassed dope was transferred to a plastic syringe
135 (inner diameter = 20.05 mm) to use as a dispersed phase (DP) in microfluidics. Mineral oil with
136 EM90 (3 wt%) in a plastic syringe (inner diameter = 15.90 mm) was used as a continuous phase
137 (CP). The CP and DP were connected to the T-junction microfluidic chip (PEEK, P-713, IDEX,
138 USA), (thru-hole diameter = 1.25 mm) with two separated syringe pumps (LEGATO 100, KD
139 Scientific, USA).

140 A syringe containing the cell/NMMO dope and the T-junction microfluidic chip is in a bath
141 filled with ethylene glycol at 85°C (Scheme 1a). The flowrates of the DP and CP (Q_d and Q_c) were
142 controlled at 2.0 and 23 μL min⁻¹, respectively, unless otherwise mentioned. When the
143 cell/NMMO dope meets at the edge of the T-junction, the cell/NMMO droplet was formed. Four
144 cellulose beads samples were prepared, depending on the cell/NMMO droplet's state during
145 coagulation and coagulation temperature. The cell/NMMO droplet during coagulation can be a
146 solid state (S) or molten state (M). The S cell/NMMO droplets were prepared by cooling the M
147 cell/NMMO droplets in the CP of hot mineral oil by mixing them with a significant amount of
148 cold mineral oil in a beaker that was placed into an ice-water bath before. The cell/NMMO
149 droplets were coagulated at low S and high M coagulation temperatures, representing the S and M
150 of NMMO monohydrate, respectively. The S cell/NMMO droplets were coagulated by removing

151 the mineral oil from the beaker containing the S cell/NMMO droplets, refilling the beaker with
 152 THF to mix with the remaining mineral oil, removing THF, refilling the beaker with water at 30°C
 153 (S) or 60°C (M), and maintaining them for 30 min. The M cell/NMMO droplets were coagulated
 154 using the following method. The CP hot mineral oil (85°C) containing the M cell/NMMO droplets
 155 appearing from the microfluidic chip was directly dropped into the THF/water mixture (50/50, v/v)
 156 at 30°C (S) or 60°C (M). The THF/water mixture was used during coagulation because the CP
 157 mineral oil containing the cell/NMMO droplets could not be removed in the water bath because of
 158 the immiscibility between water and mineral oil. The coagulated cellulose spherical beads were
 159 filtered using filter papers (Advantec, 110 mm) and washed with water several times. The
 160 produced cellulose beads are denoted as cellulose (S-S), (S-M), (M-S), and (M-M) beads, where
 161 the first S and M represent the solid and molten states of the cell/NMMO droplet, respectively, and
 162 the second S and M represent cold and hot coagulation temperatures, respectively.

Scheme 1. (a) The overall schematics of producing cellulose (S-S), cellulose (S-M), cellulose (M-S), and cellulose (M-M) beads using a T-junction microfluidic chip at 85°C. CP and DP are continuous and disperse phases, respectively. (b) Crosslinking (X-cellulose) and functionalization with AN (CN-cellulose) and NH₂OH (O-cellulose) to incorporate amidoxime groups in the cellulose beads.

Preparation of O-cellulose beads

The cellulose beads were crosslinked with ECH (Scheme 1b). The ECH reacting with hydroxyl groups of the cellulose introduces oxirane moieties that can further react with hydroxyl groups of the same or another cellulose chain nearby (Gough 1967). The detailed reaction conditions are as follows. Briefly, the cellulose beads (0.1 g) were dispersed in an aqueous NaOH solution (3 wt%, 20 mL) under magnetic stirring for 30 min. The ECH/MeOH (3.08 g (1.54 g each), 1:3 mole ratio of anhydrous glucose unit (AGU):ECH) was added dropwise, under magnetic stirring at 60°C for 1 h. After the reaction, the reaction medium was washed with water until a pH 7. The crosslinked cellulose (X-cellulose) beads were dried at 25°C for 2 h in a vacuum oven. The amidoxime groups were introduced into the cellulose beads (Scheme 1b). The dried X-cellulose beads were further functionalized with AN to introduce the –CN groups as follows. Briefly, the X-cellulose beads (0.1 g (0.55 mM)) were dispersed in 20 mL AN into which a 0.56 mL MeOH solution containing 5 wt% TMA chloride was added. A 0.75 mL MeOH solution containing 10 wt% sodium hydroxide at 0°C was added dropwise. The reaction was maintained at 25°C for 2 h under magnetic stirring and finally, washed with water until the medium's pH reached 7. The CN-functionalized cellulose (CN-cellulose) beads were further reacted with NH₂OH·HCl to introduce the amidoxime groups as follows. NH₂OH·HCl (8 g), Na₂CO₃ (6 g), and CN-cellulose beads (0.1 g) were added to a 250 mL beaker, to which 100 mL water was added and sealed. The reaction was maintained at 70°C for 12 h. After the reaction, the O-cellulose beads were washed several times with water to remove the remaining salts. Water was replaced with MeOH, and the O-cellulose beads were dried in a vacuum oven at 25°C.

Critical point drying

To prepare cellulose bead samples for scanning electron microscope (SEM) and porosity/inner surface area determination, the CPD method with liquid CO₂ was used (Pinnow et al. 2008; Trygg et al. 2013) because the simple evaporation of water by vacuuming, heating, and air-drying results in the hornification of the bead surface and loss of their significant porosity and surface area (Gericke et al. 2013). Lyophilization (freeze-drying) also causes water volume expansion upon freezing and the growth of ice crystals, resulting in a micro- and mesopore collapse in cellulose beads (Pinnow et al. 2008). For CPD with liquid CO₂, water should be stepwise exchanged by ethanol, acetone, and liquid CO₂, which is removed under supercritical conditions. To investigate

the internal structure of the prepared cellulose beads using the CPD method, the CPD container was home-made (Fig. S1). Detail CPD procedures can be found in Text S1.

Measurements

Attenuated total reflection (ATR)–Fourier transform infrared (FTIR) (ATR–FTIR) spectra were recorded in the range of 500–4000 cm^{-1} at an average of 64 scans using an FTIR spectrometer (Frontier, PerkinElmer, USA). The dried samples were ground into a fine powder using a pestle and mortar. Field-emission (FE)–SEM (FE–SEM; SU8220, Hitachi, Japan) images of the cellulose beads were obtained from the fractured surfaces of the platinum-coated epoxy-molded samples. The samples for SEM were dried using the CPD method with liquid CO_2 . The epoxy molding was performed by positioning the beads in the cap (Cavity Embedding Mold, Ted Pella, USA), filling the cap with an epoxy mixture of EPON (2 mL), DDSA (1.25 mL), NMA (1.25 mL), and DMP (0.075 mL), curing at 60°C for 24 h, and breaking by half with a vise. The cellulose beads were observed using an optical microscope (ANA-006, Leitz, Germany) equipped with a digital camera (STC-TC83USB-AS, SenTech, Japan) with a transmission mode. The Cu^{2+} /phthalate solution concentration was determined using ultraviolet (UV)–visible (vis) (UV-vis) spectroscopy (UV-2401PC, Shimadzu, Japan). The chemical composition of the cellulose beads was studied using an elemental analyzer (EA, Flash 2000, ThermoFisher, USA). The concentrations of the metal ions in water were investigated using an inductively-coupled plasma spectrometer (ICP, Optima 7300DV, PerkinElmer, USA). The surface area of the cellulose beads (S-S, M-M) was determined using a surface area and pore size analyzer (Quadrascorb Evo, Quantachrome, Austria) using the Brunauer–Emmett–Teller (BET) method. The samples for BET analysis were dried using the CPD method with liquid CO_2 and pre-treated at 100°C for 12 h in a vacuum oven.

Adsorption of metal ions

A Cu^{2+} /phthalate complex aqueous solution was used to demonstrate the O-cellulose beads' performance on the Cu^{2+} ion detection using UV-vis spectroscopy. It was prepared by dissolving $\text{Cu}(\text{NO}_3)_2$ (controlled from 50 to 1000 ppm) and KHP (4.08 g, 0.2 M, excess) in water (100 mL). Fig. S2(a) shows the UV-vis spectra of the $\text{Cu}(\text{NO}_3)_2$ (1000 ppm), KHP (0.2 M), and Cu^{2+} /phthalate (1000 ppm/0.2 M) complex aqueous solutions. The $\text{Cu}(\text{NO}_3)_2$ aqueous solution's UV-vis spectrum shows a small peak at 780 nm. However, the Cu^{2+} /phthalate complex aqueous solution's UV-vis spectrum shows a strong absorption peak at 730 nm with a hypochromic shift, consistent with reported results (Saliba et al. 2000b). The Cu^{2+} /phthalate complex aqueous solution's calibration curve (730 nm) was obtained at different concentrations with a linear regression curve ($r^2 = 0.998$) (Fig. S2(b)). Each adsorption experiment was conducted thrice to investigate the adsorption behavior of metal ions onto the cellulose bead adsorbent. The concentrations of the aqueous metal-ion solutions before and after adsorption were measured using

a UV-vis spectrophotometer (UV-1800, Shimadzu Corporation, Japan) at a wavelength range of 400–800 nm. The adsorption capacity (q_t) for the Cu^{2+} /phthalate complex was evaluated using equation (1).

$$q_t = \frac{(C_0 - C_t) \times V}{m} \quad (1)$$

where C_0 (mg L^{-1}) and C_t (mg L^{-1}) are the dye concentrations at the initial time and time t , respectively, V (L) is the volume of the dye solution, and m (g) is the weight of the dried adsorbent.

Desorption of metal ions

For the desorption experiment, the metal-ion-loaded O-cellulose beads were immersed in 8 mL of 2 M HCl for 30 min under magnetic stirring at 25°C, and the O-cellulose beads were regenerated into the initial form after sequentially rinsing with water and pH 6 buffer solution several times. The adsorption test was performed again by magnetic stirring regenerated O-cellulose beads (4 mg) in Cu^{2+} /phthalate solution (4 mL, 1000 ppm) at pH 7 for 2 h. The adsorption/desorption cycle was repeated five times to investigate the recyclability of the O-cellulose bead.

Results and discussion

Production of cellulose beads using microfluidics

To find the optimum Q_d and Q_c in microfluidics, the cellulose (4 wt%)/NMMO dope was evaluated at different Q_d and Q_c in the T-junction microfluidic chip. The production of the cell/NMMO droplet in the T-junction microfluidic chip in the ethylene glycol bath could not be monitored in situ through an optical microscope; therefore, the cellulose (M-M) bead's shape after coagulation was examined as a model study. Fig. 1a shows the matrix diagram of processability at different Q_d and Q_c . The matrix graph can be divided into three regions representing the non-processible condition (Region I) and conditions for producing asymmetric-prolate (Region II) and symmetric-spherical (Region III) cellulose beads. The inset figures show representative optical microscopy images of the cellulose beads. When $Q_c > \sim 10.0 \mu\text{L min}^{-1}$ and $Q_d > \sim 1.0 \mu\text{L min}^{-1}$ (Region III), the symmetric-spherical cellulose beads were produced. In the case of $6.0 \mu\text{L min}^{-1} < Q_c < 10.0 \mu\text{L min}^{-1}$ (Region II), the asymmetric elongated prolate cellulose beads were produced. When $Q_c < 6.0 \mu\text{L min}^{-1}$ (Region I), the droplets could not be produced.

At low capillary numbers (low Q_c) in the T-junction chip, droplets are formed in a squeezing mode, forming a pressure gradient across the droplet as it is formed (Seemann et al. 2011). Droplets generated in the squeezing mode travel through the channel as a plug confined by the channel walls. As the Q_c increases (i.e., the capillary number increases), droplet generation transits from the squeezing to the dripping mode. It is unclear whether Region III (highest Q_c) is in the dripping mode or not (Zhu and Wang 2017). For clarification, the cellulose/NMMO droplets

275 produced at $Q_d = 4 \mu\text{L min}^{-1}$ and $Q_c = 30 \mu\text{L min}^{-1}$ (high Q_c in Region III) were evaluated at
276 different coagulation temperatures. Figs. 1b and c show the optical microscopy images of the
277 cellulose beads coagulated from the M and S cell/NMMO droplets at different temperatures,
278 respectively. Both M and S cell/NMMO droplets are the same at the T-junction in the microfluidic
279 chip. In the case of the M cell/NMMO droplets (Fig. 1b), ellipsoidal cellulose beads were
280 produced at $T_{\text{coa}} = 10^\circ\text{C}$, 20°C , 30°C , and 40°C , although spherical cellulose beads were at $T_{\text{coa}} >$
281 50°C . The cellulose beads prepared at $T_{\text{coa}} > 50^\circ\text{C}$ represent cellulose (M-M) beads. The
282 ellipsoidal shape of the cellulose beads produced at low T_{coa} indicates that the cell/NMMO
283 droplets at the T-junction were produced in the squeezing mode.

284 The shear stress generated at the T-junction of the microfluidic chip during droplet production
285 can be easily released during coagulation in the case of the cellulose (M-M) bead because of high-
286 temperature coagulation of the M cell/NMMO droplet. Thus, spherical cellulose could be observed
287 for cellulose (M-M) beads, although they were formed in the squeezing mode. The squeeze mode
288 is evident from the S cell/NMMO droplets (Fig. 1c). Ellipsoidal cellulose beads were produced at
289 all studied T_{coa} s because the ellipsoidal shape of the cell/NMMO droplets at the T-junction was
290 fixed during cooling the cell/NMMO droplets to make the S cell/NMMO droplets. Thus, the
291 cell/NMMO droplets at the T-junction are in the squeezing mode. We could not increase Q_c to
292 reach the dripping mode because of the limitation of the syringe pump because of the high
293 viscosity of cell/NMMO dope.

Fig. 1. (a) Matrix diagram of the formation of cellulose (M-M) beads prepared at different Q_d and Q_c with three regions representing the non-processable condition (×) and the conditions for producing asymmetric-prolate (Δ) and symmetric-spherical cellulose (●) beads. (b, c) Optical microscopy images of the cellulose beads coagulated from (b) the M cell/NMMO droplets and (c) the S cell/NMMO droplets coagulated at (i) 10°C, (ii) 20°C, (iii) 30°C, (iv) 40°C, (v) 50°C, and (vi) 60°C. The same scale bar (0.5 mm) is applied to all figures in (b) and (c).

The size distribution of cellulose beads produced under different coagulation conditions was examined. Fig. 2 shows the size distribution of cellulose (S-S), (S-M), (M-S), and (M-M) beads. An ellipsoidal shape is observed from cellulose (S-S), (S-M), and (M-S) beads, whereas a spherical shape is observed from cellulose (M-M) beads, as discussed before. The uniformly-sized ellipsoidal cellulose (S-S), (S-M), and (M-S) beads were obtained with a long axis of $1219.3 \pm 78.7 \mu\text{m}$ and a short axis of $779.4 \pm 42.9 \mu\text{m}$ with a narrow size distribution. The spherical cellulose (M-M) beads were obtained with a diameter of $784 \pm 24.8 \mu\text{m}$ with a narrow size distribution. The cellulose beads coagulated at the molten state (cellulose (S-M) and (M-M)) are whitish compared

to those coagulated at the solid state (cellulose (S-S) and (M-S)), indicating that the internal structure coagulated at the molten state is different from that at the solid state. The coagulation occurs through water diffusion into the cell/NMMO droplet; therefore, the coagulation temperature is critical to control the internal porous structure of the cellulose bead because the produced coagulated structure is governed by the rate of water diffusion, which also strongly depends on the coagulation temperature. The internal structure was studied using a dried sample prepared using the CPD method.

Fig. 2. Size distribution graphs of the produced (a) cellulose (S-S), (b) cellulose (S-M), (c) cellulose (M-S), and (d) cellulose (M-M) beads prepared at $Q_d = 4 \mu\text{L min}^{-1}$ and $Q_c = 30 \mu\text{L min}^{-1}$. The size distribution graphs are for long and short axes of the prolate spheroid in the cases of cellulose (S-S), (S-M), and (M-S), and the diameter of the sphere in the case of cellulose (M-M). The inset graphs are photographic images.

325

326 **Fig. 3.** (a) SEM images of the fractured surfaces of the cellulose (i) (S-S), (ii) (S-M), (iii) (M-S),
 327 and (iv) (M-M) beads. The samples were dried using the CPD method. The right upper insets are
 328 enlarged images of core parts (red square box), and the left upper insets are enlarged images of
 329 shell parts (blue square box). (b) The D_c/D_T of cellulose beads prepared from the S (●) and M (○)
 330 cell/NMMO droplets as a function of coagulation temperature (T_{coa}), where D_c and D_T are the core
 331 and total diameters along the short axis, respectively.

332

333 *Structure of the cellulose bead*

334 Morphologies of the prepared cellulose beads were analyzed with samples dried using the
 335 CPD method. Fig. 3 shows the SEM images of the fractured surfaces of cellulose (S-S), (S-M),
 336 (M-S), and (M-M) beads. During coagulation, water dilutes the NMMO content in the cell/NMMO
 337 droplet, and the diluted NMMO has low solvation power of cellulose, leading the phase
 338 separation. For cellulose (S-S) (Fig. 3a(i)) and (M-M) (Fig. 3a(iv)) beads, the internal structures
 339 are homogeneous, although the cellulose (M-M) bead is coarser and more porous than the
 340 cellulose (S-S) bead. The reason could be that the dissolved cellulose chains in the M cell/NMMO
 341 droplet are coagulated (phase-separated) with high mobility to form large phase-separated fibrous
 342 bundles in the case of the cellulose (M-M) bead. The surface areas of cellulose (S-S) and (M-M)
 343 beads measured using a BET method are 196 and 218 m² g⁻¹, respectively, indicating that
 344 cellulose (M-M) beads have a more porous structure, consistent with morphology data from SEM.
 345 Thus, spherical homogeneous cellulose (M-M) beads with open and porous structures were studied
 346 for further tests. For cellulose (M-S) beads (Fig. 3a(iii)), M cell/NMMO droplets were directly
 347 dropped into the THF/water mixture (at 30°C) during coagulation. The outer surface of the
 348 cell/NMMO droplet in the molten state contacts the cold THF/water mixture in the coagulation
 349 beaker; therefore, the outer part of the cell/NMMO droplet becomes solid but the inner part is still
 350 in the molten state because the temperature cannot be cooled enough to become a solid state
 351 during initial coagulation. Thus, the structure in the outer part of the cellulose (M-S) bead is
 352 different from that in the inner part. The outer and inner parts were coagulated in solid and molten
 353 states, respectively, so that the structure of the core is coarser than that of the shell, as discussed
 354 with cellulose (M-M) and (S-S) beads (Fig. 3a(i), (iv)). For cellulose (S-M) beads (Fig. 3a(ii)), the
 355 S cell/NMMO droplet was dropped into hot water (at 60°C) during coagulation; therefore, the S
 356 cell/NMMO droplet was changed to the M cell/NMMO droplet by heating through hot water.
 357 However, the outer part was coagulated (phase-separated) quickly in the solid state before
 358 reaching the melting temperature for the S cell/NMMO droplet, although the thickness of the shell
 359 is small (Fig. 3a(ii)). Thus, similar to the cellulose (M-S) beads, the coagulation between the outer
 360 and inner parts is different to make the core/shell structure; therefore, the outer and inner parts are
 361 coagulated in solid and molten states, respectively.

362 The effect of the coagulation temperature on the thickness of the shell was studied. Fig. 3b
 363 shows the D_c/D_T of cellulose beads (prepared from S and M cell/NMMO droplets) as a function of
 364 the coagulation temperature (T_{coa}), where D_c and D_T are the core and total diameters (along the
 365 short axis), respectively. The D_T and D_c were measured using optical microscopy and SEM images
 366 (Fig. S3), respectively, because the samples in epoxy for SEM image were distorted during sample
 367 preparation. When $D_c/D_T = 0$ or 1, the cellulose beads are homogenous without a core/shell
 368 structure, although they are compact (closed) and coarse (fibrous) in the case of $D_c/D_T = 0$ and 1,
 369 respectively, as discussed in cellulose (S-S) and (M-M) beads. The cellulose beads from the S
 370 cell/NMMO droplets show the homogenous compact structure ($D_c/D_T = 0$) at $T_{coa} \leq 40^\circ\text{C}$
 371 (cellulose (S-S) bead) and the core/shell structure at $T_{coa} > 40^\circ\text{C}$ (cellulose (S-M) bead). The

cellulose beads from the M cell/NMMO droplets show the core/shell structure at $T_{\text{coa}} = 20^{\circ}\text{C}$ –
 50°C (cellulose (M-S) bead), and the homogeneous open structure ($D_0/D_T = 1$) at $T_{\text{coa}} = 60^{\circ}\text{C}$
 (cellulose (M-M) bead). Thus, four types of cellulose beads could be made by controlling the
 cell/NMMO droplet's state and coagulation temperature and the T_{coa} can control the thickness of
 the shell.

Preparation of O-cellulose beads

The coagulated cellulose beads in water before drying had almost the same size as the
 cell/NMMO droplet. Thus, the dried cellulose beads should be shrunk significantly from the
 cellulose bead in the water because the solid content in the dope is only a few percent. When the
 dried cellulose bead is inserted into the water again for adsorption applications, the reswelling of
 the dried cellulose bead is critical to use as an adsorbent with a large surface area inside the
 cellulose bead. Fig. S4a shows the optical microscopy images of cellulose (M-M) beads *without*
 crosslinking before (in water) and after drying and reswelling of the dried cellulose beads. The
 completely dried cellulose did not swell to the original cellulose bead in the water, indicating that
 the hydrogen bonding bonds formed after drying prevent the reswelling of the dried cellulose
 beads. Fig. S4b shows the optical microscopy images of cellulose (M-M) beads *with* crosslinking.
 The completely dried cellulose beads swelled to the original cellulose bead in water, indicating
 that the crosslinking prevents hydrogen bonding formation after drying (Udoetok et al. 2016).
 Thus, crosslinking the cellulose bead promotes both stability and expansion ability. The degree of
 reswelling of the cellulose bead depended on the cellulose concentration in the dope, which will be
 discussed in a later section.

Table 1 shows the diameters of the X-cellulose beads prepared at different cellulose
 concentrations in the dope before (in water) and after drying, and after reswelling of the dried
 cellulose beads. The diameters of the swollen, dried, and reswollen X-cellulose beads are denoted
 as D_1 , D_2 , and D_3 , respectively. The diameter of the dried X-cellulose bead (D_2) increases as ϕ
 increases because the solid content in the cell/NMMO droplet increases as ϕ increases. However,
 the ratio between reswollen and dried cellulose beads (D_3/D_2) decreases as ϕ increases. When
 crosslinking is performed at low ϕ , it effectively blocked the hydrogen bonding; therefore, the
 small collapsed dried X-cellulose beads (because of low ϕ) can be swollen much but less than the
 original size before drying. Accordingly, the D_3/D_2 becomes larger as ϕ decreases. However, the
 X-cellulose beads prepared at $\phi = 2$ and 3 wt% cannot be reswollen to the original size in water,
 but at $\phi = 4$ and 5 wt% reswelled to close to the original size (D_1); $D_3/D_1 = 0.5, 0.7, 0.9$, and 1 at ϕ
 $= 2, 3, 4$, and 5 wt%, respectively. When ϕ increases to 5 wt%, droplet fabrication became
 challenging because of its high viscosity. Thus, the X-cellulose beads prepared at $\phi = 4$ wt% were
 used for further experiments.

Table 1. Diameters of the X-cellulose beads prepared at different ϕ before (in water) and after drying, and after reswelling of the dried cellulose beads. The diameters of the swollen, dried, and reswollen X-cellulose beads are denoted as D_1 , D_2 , and D_3 , respectively. The diameter of the initial cellulose beads before crosslinking is $784 \pm 24.8 \mu\text{m}$ for all ϕ s.

Dope Concentration (ϕ) (wt%)	Swollen X-cellulose (D_1) (μm)	Dried X-cellulose (D_2) (μm)	Reswollen X-cellulose (D_3) (μm)	Diameter Ratio (D_3/D_2) (Volume Ratio)
2	800	100	400	4 (64)
3	750	200	500	2.5 (16)
4	650–750	250	580–700	2.3 (12.2)
5	550–650	300	550–600	1.8 (5.8)

The X-cellulose beads were functionalized with AN to make intermediate CN-cellulose beads that were further functionalized with NH_2OH to make the final O-cellulose beads. FTIR spectroscopy confirmed the functionalization of X-, CN-, and O-cellulose. Fig. 4a shows the FTIR spectra of the cellulose, X-cellulose, CN-cellulose, and O-cellulose beads. The FTIR spectrum of the X-cellulose bead is close to that of cellulose because of the similarity of their functional groups. The FTIR spectrum of the CN-cellulose shows a characteristic–CN stretching band at 2260 cm^{-1} . The FTIR spectrum of the O-cellulose shows additional peaks at ~ 920 , 1610 , and 1670 cm^{-1} because of the stretching vibration bands of $-\text{N}-\text{O}$, $-\text{N}-\text{H}$, and $-\text{C}=\text{N}$ bonds in amidoxime (Saeed et al. 2008). Thus, the amidoxime groups were successfully introduced into the cellulose beads. The porous structures were studied using SEM with cellulose (M-M) beads and their functionalized cellulose beads (X-, CN-, and O-cellulose beads). Figs. 5 b and c show the SEM images of the outer and fractured surfaces, respectively, of cellulose, X-cellulose, CN-cellulose, and O-cellulose beads that were dried using the CPD method. The internal structures (from the fractured surface, Fig. 4c) of all cellulose beads are porous regardless of functionalization, although the outer surfaces exhibit a small, closed structure (Fig. 4b). The cellulose structure can easily collapse during the drying process because of the strong hydrogen bonding. The CPD is one of the best methods to preserve the swollen structure during drying. Thus, the open fibrous structure of cellulose beads can be observed. However, it is uncertain whether the observed closed structure from the outer surface is produced during CPD or initially exists because the even CPD

method can cause some hornification during drying. To figure out the origin of this observation, studies are necessary but out of this study's scope.

Fig. 4. (a) FTIR spectra of the (i) cellulose, (ii) X-cellulose, (iii) CN-cellulose, and (iv) O-cellulose beads. (b, c) SEM images of the (b) outer and (c) fractured surfaces of cellulose (M-M) beads dried using the CPD method; (i) cellulose, (ii) X-cellulose, (iii) CN-cellulose, and (iv) O-cellulose beads. The insets are enlarged images of the red square box.

The degree of conversion from -OH to -CN groups for CN-cellulose beads and from -CN to amidoxime groups for O-cellulose beads were calculated using EA. Table S1 summarizes the EA results of cellulose, CN-cellulose, and O-cellulose beads. The contents of N are 4.31 and 10.05

wt% for CN-cellulose and O-cellulose beads, respectively, although those of C are $\sim 44 \pm 3$ wt% for all cellulose beads. From EA data, the degree of conversion to –CN groups for CN-cellulose beads and to amidoxime groups for O-cellulose beads was calculated. Scheme S1 shows the chemical structure with x , y , and z where x , y , and z represent the number of –CN groups converted among three –OH groups, the number of converted –CN groups to the amidoxime groups, and the number of unconverted –CN groups, respectively, so that $x = z + y$. The molecular weights of one unit of CN- and O-cellulose are $180 + 54x$ and $180 + 54y + 87z$, respectively, where 54 and 87 are molecular weights (per mole) of –CH₂CH₂CN and amidoxime (–CH₂CH₂C(=NOH)NH₂) groups, respectively. The nitrogen contents in weight percentage are $14x/(180 + 54x) \times 100$ and $(28z + 14y)/(180 + 54y + 87z) \times 100$ for CN- and O-cellulose beads, respectively. The measured nitrogen contents are 4.31 and 10.05 wt% for CN- and O-cellulose beads, respectively, so that the calculated x , y , and z values (with $x = y + z$) are 1.5, 1.0, and 0.5, respectively. Thus, the degree of conversion from –OH to –CN groups (x) for CN-cellulose beads is 50% ($1.5/3 \times 100$), and from –CN to amidoxime group for O-cellulose is 33% ($0.5/1.5 \times 100$). The degree of conversion of the amidoxime group is similar to the reported value of 40% from amidoxime-functionalized poly (acrylonitrile) (PAN) nanofibers, although it is produced by different reaction conditions with different concentrations of NH₂OH·HCl (Saeed et al. 2008).

Isotherm of the metal-ion on O-cellulose bead

The O-cellulose beads were used as an adsorbent for the Cu²⁺/phthalate complex in water. The Cu²⁺/phthalate complex enhances the intensity of Cu²⁺ in UV-vis spectroscopy, as discussed before. Fig. 5 shows the q_t of the Cu²⁺/phthalate complex on O-cellulose beads as a function of elapsed time (t_{elaps}) at different concentrations. Curve-fitting was performed using equation (3) of the pseudo-first-order kinetics (Fig. 5a) and equation (5) of the pseudo-second-order kinetics (Fig. 5b). The curve-fitted data of q_e and k are the amount of adsorbed material at equilibrium and adsorption kinetic coefficient, respectively. The parameters of q_{e1} (and k_1) for the first-order kinetics and q_{e2} (and k_2) for second-order kinetics were calculated using modified equations (4) and (6) with plots of $\ln(q_e - q_t)$ vs. t and t/q_t vs. t , respectively (Fig. S5). Table S2 summarizes the curve-fitting results with parameters q_e , k , and r^2 . The observed data are better curve-fitted with the second-order equation (5) than the first-order equation (3). r^2 are 0.9610 and 0.9919 for the first- and second-order equations, respectively. These results indicate that the adsorption mechanism is because of the chelating reaction between the transition metal ions and the amidoxime group (Rahman et al. 2016; Wang et al. 2015).

$$q_t = q_e(1 - e^{-k_1 t}) \quad (3)$$

$$\ln(q_e - q_t) = -k_1 t + \ln q_e \quad (4)$$

$$q_t = \frac{q_{e2}^2 k_2 t}{1 + q_{e2} k_2 t} \quad (5)$$

481

$$\frac{t}{q_t} = \frac{1}{q_{e2}^2 k_2} + \frac{t}{q_{e2}} \quad (6)$$

482

483 **Fig. 5.** q_t of the Cu^{2+} /phthalate adsorption (at different concentrations) on O-cellulose beads
 484 prepared with cellulose (4 wt%)/NMMO droplets as a function of elapsed time (t_{elaps}) with curve-
 485 fitting using (a) equation (3) of the pseudo-first-order kinetics and (b) equation (5) of the pseudo-
 486 second-order kinetics.

487

488 The isotherm was performed using Langmuir (equation (7)) and Freundlich (equation (9))
 489 models, where q_m is the adsorption capacity (related to the number of available binding sites), C_e is
 490 the aqueous phase concentration at equilibrium, K_L and K_F are the affinity constants for adsorption
 491 for the *Langmuir (equation (7)) and Freundlich (equation (9))* models, respectively, and n is the
 492 index of heterogeneity. The parameters in equations (7) and (9) were calculated by performing
 493 linear curve fittings with modified Langmuir and Freundlich isotherm equations (8) and (10) with
 494 the Cu^{2+} /phthalate complex at a concentration range of 25–1000 ppm at 25°C (Fig. 6). Table S3
 495 summarizes the calculated q_m , K , and n . The r^2 values of the Langmuir and Freundlich isotherm
 496 curves are 0.99 and 0.95, respectively, indicating that the Langmuir model is well-fitted with
 497 observed data and a saturated monolayer (not multilayer) of solute molecules on the adsorbent
 498 surface was formed during adsorption. The affinity constant of K_L is $0.013 \text{ L} \cdot \text{mg}^{-1}$, similar to the
 499 reported value ($0.014 \text{ L} \cdot \text{mg}^{-1}$) from poly(amidoxime) cellulose powder (Rahman et al. 2018). The
 500 calculated q_m is $\sim 81.30 \text{ mg g}^{-1}$, which is larger than the reported value (52.70 mg g^{-1}) from
 501 amidoxime-functionalized poly (acrylonitrile) (PAN) nanofibers with an oxime group conversion
 502 of 25% (Saeed et al. 2008). Thus, the prepared O-cellulose beads from cellulose (M-M) beads
 503 have large adsorption capability of metal ions.

504

$$q_e = \frac{K_L q_m C_e}{1 + K_L C_e} \quad (7)$$

505

$$\frac{C_e}{q_e} = \frac{1}{q_m K_L} + \frac{C_e}{q_m} \quad (8)$$

506

$$q_e = K_F C_e^{1/n} \quad (9)$$

507

$$\log q_e = \log K_F + \frac{\log C_e}{n} \quad (10)$$

Fig. 6. (a, c) Isotherm curve and (b, d) its linear curve-fitting using modified equations (8) and (10) for (a, c) Langmuir and (b, d) Freundlich models for adsorption of Cu²⁺/phthalate complex on O-cellulose beads. The solid lines (a, c) represent the calculated graphs of equations (7) and (9), respectively, with parameters obtained from linear regressions of (b, d).

Internal structure and adsorption property relationship

The O-cellulose beads made from cellulose (S-S), (S-M), and (M-S) beads were also evaluated as adsorbents for the Cu²⁺/phthalate complex in water to establish the relationship between the internal porous structure and adsorption property. Fig. 7a shows the q_t of O-cellulose beads made from cellulose (S-S), (S-M), (M-S), and (M-M) beads 40 h after O-cellulose beads (4 mg) were inserted into the vials containing the Cu²⁺/phthalate complex (1000 ppm, 4 mL). The measured q_t s are 61.2, 66.8, 69.9, and 83.0 mg g⁻¹ for O-cellulose beads prepared from cellulose (S-S), (S-M), (M-S), and (M-M) beads, respectively. The O-cellulose beads prepared from cellulose (M-M) beads have the highest adsorption capacity because it has the highest porous structure, as discussed before, and vice versa for O-cellulose beads prepared from cellulose (S-S) beads. The O-cellulose beads prepared from cellulose (S-M) and (M-S) beads have adsorption capacity between them. Thus, we found that the internal structure of O-cellulose beads governs the adsorption capacity.

528 *Application to fillers in the column*

529 The O-cellulose beads were applied to fillers in a column as an application to a metal filter.
530 The uniformly-sized O-cellulose beads could be packed into the column (Fig. S6). Fig. 7b shows
531 the concentration reduction of the Cu²⁺/phthalate complex aqueous solution (initial concentration;
532 500 ppm) as a function of the cycle number by passing the complex solution (4 mL) through the
533 column (diameter 5.6 mm) filled with the O-cellulose beads (70 mg) with a flow rate of 2.5 mL
534 h⁻¹. The Cu²⁺/phthalate complex aqueous solution was circulated for the cycling test using a
535 syringe pump. The initial Cu²⁺/phthalate complex aqueous solution (500 ppm) concentration was
536 reduced by 324, 409, 442, and 470 ppm during the first, second, third, and fourth cycles. The
537 percentages of the reduction are 64.8%, 81.8%, 88.4%, and 94% during the first, second, third, and
538 fourth cycles. The amount of O-cellulose beads in the column is only 0.07 g, and 94% of the
539 metal-ion was filtered after the fourth cycle. The results indicate that O-cellulose beads can be
540 successfully used as fillers in the column for metal adsorption.

541 Other metal-ion adsorptions were studied using ICP. The Pb²⁺, Cu²⁺, Zn²⁺, Ni²⁺, Cd²⁺, Fe³⁺,
542 Ca²⁺, Cr³⁺, and Mg²⁺ aqueous solution was prepared with the same concentration of 1000 ppm.
543 Their concentrations were measured 24 h after O-cellulose beads (4 mg) were inserted into the vial
544 containing the metal-ion solution (4 mL). Fig. S7 shows the adsorption capacity of Pb²⁺, Cu²⁺,
545 Zn²⁺, Ni²⁺, Cd²⁺, Fe³⁺, Ca²⁺, Cr³⁺, and Mg²⁺ ions, which are 125.0, 75.1, 62.5, 51.1, 34.5, 33.4,
546 11.1, and 0 mg g⁻¹, respectively, indicating that O-cellulose beads can remove hazardous metal
547 ions. The order of the adsorption amount is Pb²⁺ > Cu²⁺ > Zn²⁺ > Ni²⁺ > Cd²⁺ > Fe³⁺ > Ca²⁺ > Cr³⁺
548 = Mg²⁺ (not adsorbed). The Pb²⁺ is adsorbed most and Ca²⁺, Cr³⁺, and Mg²⁺ cannot be adsorbed on
549 O-cellulose beads, similar to other reported results (Rahman et al. 2016; Saeed et al. 2008).

550 The desorption and re-adsorption of the Cu²⁺/phthalate on O-cellulose beads were studied.
551 The O-cellulose beads (4 mg) in the vial were evaluated with the Cu²⁺/phthalate aqueous solution.
552 The 1000 ppm Cu²⁺/phthalate aqueous solution was adsorbed on O-cellulose beads for 2 h. The
553 Cu²⁺/phthalate-loaded O-cellulose beads were treated with 2 M HCl (8 mL) under stirring of 250
554 rpm at 25°C for 30 min to desorb the Cu²⁺/phthalate from the O-cellulose beads. The re-adsorption
555 test was performed using the HCl-treated O-cellulose beads after complete washing with water at
556 the same conditions as the first adsorption. The adsorption amount of the Cu²⁺/phthalate was
557 measured again. The same adsorption and desorption tests were repeated for several cycles. Fig. 7c
558 and d show the adsorption capacity and efficiency of O-cellulose as a function of the number of
559 cycles during the adsorption/desorption of Cu²⁺/phthalate, respectively. The efficiency is the
560 relative amount of the adsorption of Cu²⁺/phthalate at the *i*th cycle compared to that at the (*i* - 1)th
561 cycle defined by equation (11). The adsorption capacity continuously decreases as the number of
562 cycles increases, although the efficiency is constant at ~88%, indicating that the recovery of the
563 oxime groups is high enough for reuse. However, efficiency can be improved by optimizing the
564 desorption conditions.

565
$$\text{Efficiency at the } i^{\text{th}} \text{ cycle} = \frac{\text{adsorption capacity at the } i^{\text{th}} \text{ cycle}}{\text{adsorption capacity at the } (i-1)^{\text{th}} \text{ cycle}} \times 100 \quad (11)$$

566

568

569 **Fig. 7.** (a) Adsorption capacity (q_t) of O-cellulose beads made from cellulose (S-S), (S-M), (M-S),
 570 and (M-M) beads 40 h after O-cellulose beads (4 mg) were inserted into the vials containing the
 571 Cu^{2+} /phthalate complex (1000 ppm, 4 mL). (b) Reduction of the Cu^{2+} /phthalate complex aqueous
 572 solution (initial concentration; 500 ppm) concentration as a function of the cycle number by
 573 passing the complex solution (4 mL) through a column (diameter 5.6 mm) filled with O-cellulose
 574 beads (70 mg), with a flow rate of 2.5 mL h^{-1} . The Cu^{2+} /phthalate complex aqueous solution was
 575 circulated for cycling using a syringe pump. (c) Adsorption capacity (q_t) and (d) efficiency of O-
 576 cellulose as a function of the number of cycles during the adsorption/desorption of Cu^{2+} /phthalate.
 577 The efficiency is the relative adsorption of Cu^{2+} /phthalate at the i^{th} cycle compared to that at the $(i$
 578 $- 1)^{\text{th}}$ cycle defined by equation (11).

579

580 Conclusions

581 Uniformly-sized cellulose beads were successfully prepared by coagulating the cell/NMMO
 582 droplets that were produced using a microfluidic method with molten state cell/NMMO as a
 583 cellulose solvent. The state (solid or molten) of the cell/NMMO droplet and coagulation
 584 temperature can control the morphology of the cellulose beads. Coagulation of the molten state
 585 cell/NMMO droplet at high temperature ($\geq 60^\circ\text{C}$) and amidoxime functionalization could prepare
 586 the highly-porous spherical O-cellulose beads with a uniform fibrous open internal structure. The
 587 prepared O-cellulose beads showed excellent metal adsorption properties with a maximum
 588 adsorption capacity of 80 mg g^{-1} in the case of Cu^{2+} /phthalate ions. The novel cellulose beads
 589 could be successfully applied to fillers in the column for removing hazardous metal ions.

590

591 **Acknowledgments:** This work was supported by the National Research Foundation of Korea
592 (2020R1A2B5B02001556).

593

594 **Conflict of interest**

595 The authors declare no conflict of interest.

596 **References**

- 597 Alam MN, Islam MS, Christopher LPJAo (2019) Sustainable production of cellulose-based
598 hydrogels with superb absorbing potential in physiological saline 4:9419-9426
- 599 Biganska O, Navard P, Bédué OJP (2002) Crystallisation of cellulose/N-methylmorpholine-N-
600 oxide hydrate solutions 43:6139-6145
- 601 Boeden H-F et al. (1991) Bead cellulose derivatives as supports for immobilization and
602 chromatographic purification of proteins 552:389-414
- 603 Bolto BA, Pawłowski Ł (1987) Wastewater treatment by ion-exchange. Spon,
604 Dawson TJCT (2012) Progress towards a greener textile industry 128:1-8
- 605 Diviš P, Szkandera R, BRULÍK L, Docekalova H, MATÚŠ P, BUJDOŠ MJAS (2009) Application
606 of new resin gels for measuring mercury by diffusive gradients in a thin-films technique
607 25:575-578
- 608 Fink H-P, Weigel P, Purz H, Ganster JJPiPS (2001) Structure formation of regenerated cellulose
609 materials from NMMO-solutions 26:1473-1524
- 610 Geckeler K, Shkinev V, Spivakov BYJS, methods p (1988) Liquid-phase polymer-based retention
611 (LPR)-a new method for selective ion separation 17:105-140
- 612 Gericke M, Trygg J, Fardim PJCr (2013) Functional cellulose beads: preparation, characterization,
613 and applications 113:4812-4836
- 614 Gough BM (1967) Interaction of Wheat Starch and Epichlorohydrin 19:240-243
615 doi:<https://doi.org/10.1002/star.19670190802>
- 616 He YB, Meng LZ, Wu CT, Qian TJJoaps (1999) Preparation and coordination behavior of
617 cellulose beads derivative modified by 1, 5-diaminoethyl-3-hydroxy-1, 5-
618 diazacycloheptane 74:1278-1285
- 619 Hirota M, Tamura N, Saito T, Isogai AJC (2009) Surface carboxylation of porous regenerated
620 cellulose beads by 4-acetamide-TEMPO/NaClO/NaClO₂ system 16:841-851
- 621 Hua J et al. (2019) Highly porous cellulose microbeads and their adsorption for methylene blue
622 20:794-803
- 623 Kahovec J, Matějka Z, Štamberg JJPB (1980) EDTA ester of bead cellulose a fast-kinetics
624 chelating sorbent 3:13-17
- 625 Klemm D, Kramer F, Moritz S, Lindström T, Ankerfors M, Gray D, Dorris AJACIE (2011)
626 Nanocelluloses: a new family of nature-based materials 50:5438-5466
- 627 Li W, Liu R, Kang H, Sun Y, Dong F, Huang Y (2013a) Synthesis of amidoxime functionalized
628 cellulose derivatives as a reducing agent and stabilizer for preparing gold nanoparticles
629 Polymer Chemistry 4:2556-2563 doi:10.1039/C3PY00052D
- 630 Li W, Liu R, Kang H, Sun Y, Dong F, Huang YJPC (2013b) Synthesis of amidoxime
631 functionalized cellulose derivatives as a reducing agent and stabilizer for preparing gold
632 nanoparticles 4:2556-2563
- 633 Lidhure A, Jadhav S, Ganvir V, Thakre S Modified lyocell process for producing biopolymer
634 fiber. In: AIP Conference Proceedings, 2019. vol 1. AIP Publishing LLC, p 030062
- 635 Matúš P, Kubová JJJoib (2005) Complexation of labile aluminium species by chelating resins
636 Iontosorb—a new method for Al environmental risk assessment 99:1769-1778
- 637 Pawłowski L (2015) Physicochemical Methods for Water and Wastewater Treatment: Proceedings
638 of the Second International Conference, Lublin, June 1979. Elsevier,
- 639 Pinnow M, Fink HP, Fanter C, Kunze J Characterization of highly porous materials from cellulose
640 carbamate. In: Macromolecular symposia, 2008. vol 1. Wiley Online Library, pp 129-139
- 641 Rahman ML, Sarkar SM, Farid EM, Arshad SE, Sarjadi M, Wid NJJoMS, Part B (2018) Synthesis
642 of tapioca cellulose-based poly (amidoxime) ligand for removal of heavy metal ions
643 57:83-99

644 Rahman ML, Sarkar SM, Yusoff MM, Abdullah MHJRa (2016) Efficient removal of transition
 645 metal ions using poly (amidoxime) ligand from polymer grafted kenaf cellulose 6:745-
 646 757
 647 Rosenau T, Potthast A, Adorjan I, Hofinger A, Sixta H, Firgo H, Kosma PJC (2002) Cellulose
 648 solutions in N-methylmorpholine-N-oxide (NMMO)–degradation processes and
 649 stabilizers 9:283-291
 650 Rosenau T, Potthast A, Sixta H, Kosma PJPips (2001) The chemistry of side reactions and
 651 byproduct formation in the system NMMO/cellulose (Lyocell process) 26:1763-1837
 652 Rosenberg P, Suominen I, Rom M, Janicki J, Fardim PJCC, Technology (2007) Tailored cellulose
 653 beads for novel applications 41:243-254
 654 Saeed K, Haider S, Oh T-J, Park S-YJJoMS (2008) Preparation of amidoxime-modified
 655 polyacrylonitrile (PAN-oxime) nanofibers and their applications to metal ions adsorption
 656 322:400-405
 657 Saliba R, Gauthier H, Gauthier R, Petit-Ramel M (2000a) Adsorption of copper(II) and
 658 chromium(III) ions onto amidoximated cellulose 75:1624-1631
 659 doi:[https://doi.org/10.1002/\(SICI\)1097-4628\(20000328\)75:13<1624::AID-APP8>3.0.CO;2-K](https://doi.org/10.1002/(SICI)1097-4628(20000328)75:13<1624::AID-APP8>3.0.CO;2-K)
 660 APP8>3.0.CO;2-K
 661 Saliba R, Gauthier H, Gauthier R, Petit-Ramel MJJoaps (2000b) Adsorption of copper (II) and
 662 chromium (III) ions onto amidoximated cellulose 75:1624-1631
 663 Seemann R, Brinkmann M, Pfohl T, Herminghaus SJRopip (2011) Droplet based microfluidics
 664 75:016601
 665 Sharma RK, Agrawal M, Marshall FJE, safety e (2007) Heavy metal contamination of soil and
 666 vegetables in suburban areas of Varanasi, India 66:258-266
 667 Trygg J, Fardim P, Gericke M, Mäkilä E, Salonen JJCp (2013) Physicochemical design of the
 668 morphology and ultrastructure of cellulose beads 93:291-299
 669 Twu Y-K, Huang H-I, Chang S-Y, Wang S-LJCP (2003) Preparation and sorption activity of
 670 chitosan/cellulose blend beads 54:425-430
 671 Udoetok IA, Dimmick RM, Wilson LD, Headley JVJCp (2016) Adsorption properties of cross-
 672 linked cellulose-epichlorohydrin polymers in aqueous solution 136:329-340
 673 Wang P, Du M, Zhu H, Bao S, Yang T, Zou MJJoHM (2015) Structure regulation of silica
 674 nanotubes and their adsorption behaviors for heavy metal ions: pH effect, kinetics,
 675 isotherms and mechanism 286:533-544
 676 Yeomans-Reina H, Ruiz-Manriquez A, Wong BR, Mansir ATJBp (2001) Selectivity of IMAC
 677 columns in trypsin inhibitor purification 17:729-733
 678 Zhang L, Cai J, Zhou J, Tang YJSs, technology (2005) Adsorption of Cd²⁺ and Cu²⁺ on Ion-
 679 Exchange Beads from Cellulose/Alginic Acid Blend 39:1203-1219
 680 Zhu P, Wang L (2017) Passive and active droplet generation with microfluidics: a review Lab on a
 681 Chip 17:34-75 doi:10.1039/C6LC01018K
 682 Zulfiqar S et al. (2011) Amidoximes: promising candidates for CO₂ capture 4:4528-4531
 683

Figures

Figure 1

(a) Matrix diagram of the formation of cellulose (M-M) beads prepared at different Q_d and Q_c with three regions representing the non-processible condition (x) and the conditions for producing asymmetric-prolate (Δ) and symmetric-spherical cellulose ($\bullet$) beads. (b, c) Optical microscopy images of the cellulose

beads coagulated from (b) the M cell/NMMO droplets and (c) the S cell/NMMO droplets coagulated at (i) 10°C, (ii) 20°C, (iii) 30°C, (iv) 40°C, (v) 50°C, and (vi) 60°C. The same scale bar (0.5 mm) is applied to all figures in (b) and (c).

Figure 2

Size distribution graphs of the produced (a) cellulose (S-S), (b) cellulose (S-M), (c) cellulose (M-S), and (d) cellulose (M-M) beads prepared at $Q_d = 4 \mu\text{L min}^{-1}$ and $Q_c = 30 \mu\text{L min}^{-1}$. The size distribution graphs are for long and short axes of the prolate spheroid in the cases of cellulose (S-S), (S-M), and (M-S), and the diameter of the sphere in the case of cellulose (M-M). The inset graphs are photographic images.

Figure 3

(a) SEM images of the fractured surfaces of the cellulose (i) (S-S), (ii) (S-M), (iii) (M-S), and (iv) (M-M) beads. The samples were dried using the CPD method. The right upper insets are enlarged images of core parts (red square box), and the left upper insets are enlarged images of shell parts (blue square box). (b) The D_c/D_t of cellulose beads prepared from the S (●) and M (○) cell/NMMO droplets as a function of

coagulation temperature (T_{coa}), where D_c and D_T are the core and total diameters along the short axis, respectively.

Figure 4

(a) FTIR spectra of the (i) cellulose, (ii) X-cellulose, (iii) CN-cellulose, and (iv) O-cellulose beads. (b, c) SEM images of the (b) outer and (c) fractured surfaces of cellulose (M-M) beads dried using the CPD method;

(i) cellulose, (ii) X-cellulose, (iii) CN-cellulose, and (iv) O-cellulose beads. The insets are enlarged images of the red square box.

Figure 5

q_t of the Cu^{2+} /phthalate adsorption (at different concentrations) on O-cellulose beads prepared with cellulose (4 wt%)/NMMO droplets as a function of elapsed time (telaps) with curve-fitting using (a) equation (3) of the pseudo-first-order kinetics and (b) equation (5) of the pseudo-second-order kinetics.

Figure 6

(a, c) Isotherm curve and (b, d) its linear curve-fitting using modified equations (8) and (10) for (a, c) Langmuir and (b, d) Freundlich models for adsorption of Cu²⁺/phthalate complex on O-cellulose beads. The solid lines (a, c) represent the calculated graphs of equations (7) and (9), respectively, with parameters obtained from linear regressions of (b, d).

Figure 7

(a) Adsorption capacity (q_t) of O-cellulose beads made from cellulose (S-S), (S-M), (M-S), and (M-M) beads 40 h after O-cellulose beads (4 mg) were inserted into the vials containing the Cu^{2+} /phthalate complex (1000 ppm, 4 mL). (b) Reduction of the Cu^{2+} /phthalate complex aqueous solution (initial concentration; 500 ppm) concentration as a function of the cycle number by passing the complex solution (4 mL) through a column (diameter 5.6 mm) filled with O-cellulose beads (70 mg), with a flow rate of 2.5 mL h^{-1} . The Cu^{2+} /phthalate complex aqueous solution was circulated for cycling using a syringe pump. (c) Adsorption capacity (q_t) and (d) efficiency of O-cellulose as a function of the number of cycles during the adsorption/desorption of Cu^{2+} /phthalate. The efficiency is the relative adsorption of Cu^{2+} /phthalate at the i th cycle compared to that at the $(i - 1)$ th cycle defined by equation (11).

Figure 8

Scheme 1. (a) The overall schematics of producing cellulose (S-S), cellulose (S-M), cellulose (M-S), and cellulose (M-M) beads using a T-junction microfluidic chip at 85°C. CP and DP are continuous and disperse phases, respectively. (b) Crosslinking (X-cellulose) and functionalization with AN (CN-cellulose) and NH_2OH (O-cellulose) to incorporate amidoxime groups in the cellulose beads.

Supplementary Files

This is a list of supplementary files associated with this preprint. Click to download.

- [supportinginformation.docx](#)