Investigation of spray pyrolyzed cubic structured Cu doped SnS films

Emrah SARICA (✉ saricaemrah@gmail.com)

Bursa Teknik Universitesi <https://orcid.org/0000-0002-9339-5114>

Research Article

Keywords: Tin mono sulfide, Copper doping, spray pyrolysis, Structural properties, Optical properties, Surface morphology

Posted Date: February 26th, 2021

DOI: <https://doi.org/10.21203/rs.3.rs-242408/v1>

License: © ⓘ This work is licensed under a Creative Commons Attribution 4.0 International License.

[Read Full License](#)

Abstract

In this work undoped and Cu doped SnS film at 4% and 8% were deposited onto glass substrates by spray pyrolysis technique in order to investigate the effect of Cu doping on their physical properties. Surface investigations showed that Cu doping reduced the surface roughness of SnS films from 36.5 nm to 8.8 nm. XRD studies revealed that all films have recently solved large cubic phase of SnS (p-SnS) with a-lattice of 11.53 Å and Cu doping led to reduction in crystallite size from 229 Å to 198 Å. Additionally, all deposited films were found to be under compressive strain. Optical band gaps of SnS:Cu varied in the range of 1.83 eV-1.90 eV. Hall-effect measurements exhibited that all film have p-type conductivity with low hole concentration ($\sim 10^{11}$ - 10^{12} cm⁻³) and high electrical resistivity ($\sim 10^4$ - 10^5 Ωcm).

1. Introduction

Thin films solar cells (TFSCs) have great importance due to their low cost and competitive conversion efficiency compared to c-Si solar cells. Among these TFSCs, Cu(In,Ga)(S,Se)₂ (CIGS) and CdTe solar cells have high conversion efficiency (η) of over 20% and are commercially available. Highest efficiency for CIGS and CdTe based solar cell have been reported as 23.35% and 21.0%, respectively [1]. However, toxicity of Cd element and scarcity of In, Ga and Te elements force researchers to work on new materials which consist of environmentally friendly and abundantly elements such as Cu₂ZnSn(S,Se)₄ (CZTS) [2,3]. On the other hand, its structural complexity and undesired secondary phases make it difficult to achieve high efficiency in CZTS solar cells [4]. In order to overcome the above mentioned drawbacks, thin film absorbers, which are binary compounds and contain inexpensive earth-abundant elements, emerges as a suitable material for solar cell applications [5].

In this context, tin mono sulfide (SnS) is a good candidate because it meets the above requirements and also its high absorption coefficient ($>10^4$ cm⁻¹) along with suitable direct band gap ranging from ~1.3 eV (for orthorhombic structure) to ~1.7 eV (for cubic structure) [6,7]. Externally doping of thin film semiconductors most frequently referred way to tailor or improve its physical properties for photovoltaic applications. Recently, some studies have shown that doping of SnS with aluminum (Al), iron (Fe), indium (In), copper (Cu) and silver (Ag) can enhance its photovoltaic properties [8–12]. Doped and undoped SnS films can be deposited by several techniques such as RF magnetron sputtering [8], vapor transport deposition (VTD) [13], e-beam evaporation [14], thermal evaporation [15], electrodeposition [10], chemical bath depositions [7], spray pyrolysis [12]. However, very few studies that investigate the effect of Cu doping on the physical properties of large cubic phase of SnS by spray pyrolysis exist in the literature. Therefore, variation in physical properties of spray pyrolyzed SnS:Cu films as a function of Cu doping concentration were investigated.

2. Experimental

2.1. Deposition of SnS:Cu films

Firstly, glass substrates were cleaned by sonicating them into soap water (after rinsing under running deionized water-DI water), acetone, methanol and DI water, respectively. Each step took 15 min and then glass substrates were left to dry. Following the cleaning process, SnS:Cu films were deposited onto preheated glass substrates at 350°C by spraying of solution prepared by mixing aqueous solution of 0.05 M $\text{SnCl}_2 \cdot 2\text{H}_2\text{O}$ and $\text{CH}_4\text{N}_2\text{S}$. To obtain Cu doped SnS films at 4% and 8%, proper amount of 0.05 M $\text{CuCl}_2 \cdot 2\text{H}_2\text{O}$ aqueous solution were added into spray solution. Solution flow rate and spray duration were fixed at 4 ml/min and 25 min, respectively. Compressed dry air at 1.0 bar was used as carrier gas.

2.2. Characterization Techniques

To perform structural investigations, x-ray diffraction (XRD) patterns were obtained in the range of $2\theta = 25^\circ - 80^\circ$ by means of X-ray diffractometer (Bruker AXS, Discovery D8) with CuK_α radiation of $\lambda = 1.54 \text{ \AA}$. Surface images and cross-sectional images of SnS:Cu films were captured scanning electron microscopy (SEM) (Carl Zeiss, Gemini 300) equipped with EDS set up in order to analyze surface properties, determine film thickness and perform elemental analysis. Additionally, Park Systems XE 100 model atomic force microscope was used to get AFM images. Optical properties were studied via transmittance and absorbance spectra taken between wavelength range of 350-1400 nm by using Shimadzu UV-2600 spectrophotometer. Ecopia HMS-3000 Hall Effect measurement system equipped with 0.556 T magnets was used in Van Der Pauw geometry for determining carrier density, mobility and resistivity of the SnS:Cu films.

3. Results And Discussion

3.1. Morphological and Elemental Analysis

The SEM and AFM images were taken in order to investigate both surface morphologies and determine of film thickness. SEM images, AFM images and EDS spectra were given in Fig 1. As clearly seen from SEM images given in Figure 1(a-c), the film surfaces are formed homogeneously without any cracks or voids. Average film thickness for each film was determined through the inset cross-sectional images in Fig. 1(a-c). Variation in the surface morphology observed by AFM images given in Fig. 1(d-f) were consistent with the SEM images. Agglomeration-like morphology led to high surface roughness was noticed for doped SnS films through not only SEM images but also AFM images. This agglomeration-like structures disappeared after Cu doping and surface roughness decreased. Average surface roughness for SnS:Cu films were listed in Table 1. Fig. 1 (g-i) illustrates EDS spectra of SnS:Cu films. All elements, i.e., both Sn, Cu and S were detected in these spectra and atomic percentages of these elements were listed in Table 1. As seen from the Table 1, Cu amount in doped SnS films are higher than expected. This may be due to loss of not only S but also SnS during the pyrolysis process due to their volatile nature of both SnS and S at higher temperatures [16].

3.2. Structural Analysis

XRD patterns utilized for the structural analysis were given in Fig. 2. As seen from Fig. 2(a), a sharp XRD peak detected at $2\theta \sim 44.4^\circ$ along with some weak diffractions peaks at $2\theta \sim 26.8^\circ$, 31.0° , 64.8° and 78.0° . Moreover, it was noticed that other peaks were suppressed due to the high intensity of the peak located at $\sim 44.4^\circ$, and suppressed peaks appeared after vertical axis was enlarged as seen from Fig. 2(b). XRD patterns in Fig. 2(b) were compared with both orthorhombic phase of SnS (o-SnS) given by JCPDS card No: 39-0354 and recently resolved large cubic phase of SnS (π -SnS) consisting 64 atoms in unit cell and lattice parameters of $a = 11.5873 \text{ \AA}$ which is reported in Ref. [17–19]. As seen from Fig. 2(b), XRD patterns of SnS:Cu films deposited in this study fits well with that of large cubic SnS phase. Accordingly, a -lattice parameter calculated for all detected peaks using following equation [20] and mean values listed in Table 2.

$$\frac{1}{d^2} = \frac{h^2 + k^2 + l^2}{a^2} \quad (1)$$

By supposing that the crystallite size and strain contributions to line broadening are independent to each other, crystallite size and micro-strain values of deposited films were evaluated in accordance with Williamson-Hall approach under uniform deformation model [21].

$$\beta_{(hkl)} \cos \theta = \frac{K\lambda}{D} + 4\varepsilon \sin \theta \quad (2)$$

where β is FWHM, θ is Bragg angle, λ is wavelength of x-ray ($1.54056 \text{ \AA}$), D is crystallite size, K is shape factor, and ε is lattice distribution of micro-strain. Hence, D and ε can be extracted easily from the $\beta \cos \theta$ vs. $4 \sin \theta$ plots given in Fig. 2(c). D and ε values were also listed in Table 2.

As seen Table 2, largest average crystallite size was noted as 229 nm for undoped SnS films and it decreased to 198 $\text{\AA}$ and 199 $\text{\AA}$ for Cu doped films SnS film at 4% and 8%, respectively. The reduction in crystallite size may be arisen from difference between ionic radii of Sn^{2+} (0.93 $\text{\AA}$) and Cu^{2+} (0.73 $\text{\AA}$) [22], which leads to deterioration of crystalline level. On the other hand, negative micro-strain were found for all films and it indicates that compressive strain exists for all SnS:Cu films. The fact that the calculated a -lattice parameter is lower than the reference value $a = 11.5873 \text{ \AA}$, compressive strain on these films is expected. Also as seen from Table 2, variation of micro-strain has an inverse relationship with the change in crystal size.

3.3. Optical Analysis

Transmittance and absorbance spectra recorded for investigation of optical properties of SnS:Cu films were given in Fig. 3(a). It can be seen from Fig. 3(a), optical transmittance is $\sim 50\%$, and it increased for Cu doped films at 4% and then decreased again for Cu doped films at 8%. Transmittance of thin films tightly depends on film thickness, crystalline level and surface homogeneity of material, so combination

of these effects determines optical transmittance level [23]. Although SnS:Cu (4%) films have worse crystallization level compared to that of undoped SnS films, the high optical transmittance may be due to their low thickness. In addition, as seen from the absorbance spectra of SnS:Cu films given as inset in Fig. 3(a) fundamental absorption edge shifted towards lower wavelengths, which is the sign of broadening in optical band gaps. Optical band gaps of SnS:Cu films were determined by using $(\alpha h\nu)^2$ vs. $h\nu$ plots drawn according to Tauc's relation given in eq (3) and listed in Table 2.

$$(\alpha h\nu)^2 = A(h\nu - E_g) \quad (3)$$

where E_g is the optical band gap, h is the Planck's constant, A is a constant, ν is frequency and α is the absorption coefficient calculated according Beer-Lamber formula $\left[\alpha = 2.303 \left(\frac{\text{Absorbance}}{d}\right)\right]$ [24,25]. Optical band gap values of deposited films were noted as 1.83 eV, 1.90 eV and 1.84 eV for SnS, SnS:Cu (4%) and SnS:Cu (8%) films, respectively. Some of studies on Cu doped SnS films which exist in the literature reported that Cu doping led to shrinkage in band gap of SnS films until the certain Cu doping concentration and enlarged for further doping concentrations, regardless of the their crystal system [8,22,26,27]. Sebastian et al. and Bommireddy et al. stated that decrease in band gap due to the increase in crystallite/grain size [22,26]. In this work variation in band gap may be related with the variation in crystallite size. Intentionally doping of impurity atoms may generates band tails called as Urbach tails which indicate the width of the localized states within the forbidden gap. Urbach energies (E_u) were determined from the slope of $\ln(\alpha)$ vs. $h\nu$ plots (given in as inset in Fig. 3(b)) according to eq (4) and listed in Table 2.

$$\alpha = \alpha_0 \exp\left(\frac{h\nu}{E_u}\right) \quad (4)$$

where α_0 is a constant [25]. As seen from Table 2, Urbach energy values increased from 134 meV to 237 meV. The increase in Urbach energy implies that tail width of localized states increased due to increase in the degree of electronic disorder by Cu doping [28].

3.4. Electrical Analysis

Hall-Effect measurement were carried out to investigate the electrical transport properties of SnS:Cu films as a function of Cu concentration using at room temperature. Multiple measurements for each film were taken and result were averaged and then listed in Table 2. It was seen that all films have p-type conductivity with low hole concentration and high electrical resistivity. Highest hole concentration and mobility along with the lowest electrical resistivity were noted for SnS:Cu (8%) films. Such high electrical resistivity values for SnS was also reported by others [29]. However, these electrical properties are not adequate for photovoltaic applications. Especially, low hole concentration limits their utilization in solar cells as an absorber layer. Vidal et al stated that Sn vacancies are responsible for intrinsic p-type conductivity and S-rich condition enhance hole concentration [30]. Low hole concentration in deposited SnS:Cu films in this work may be result from Sulphur deficiency in films as seen from EDS spectra. So

loss of Sulphur spray pyrolyzed SnS film may be compensated by using excessive amount of Sulphur source in spray solution as reported in ref [31] or annealing in Sulphur containing atmosphere (i.e., sulphurization) and thereby hole concentration may be enhanced.

4. Conclusion

In summary, undoped and Cu doped SnS films at 4% and 8% were deposited onto glass substrates by using spray pyrolysis technique in order to investigate Cu doping effect. AFM and SEM images showed that the surface homogeneity of SnS films improved after Cu doping and roughness decreased almost by four times. Additionally, EDS spectra revealed that all films were S-deficient. Based on structural analysis, it was reported that deposited SnS thin films have the large cubic phase with α -lattice ~ 11.53 Å and Cu doping led to reduction in crystallite size. Transmittance and absorbance spectra illustrated that absorption edge was located at between 650 nm- 700 nm. Calculated optical band gaps were found to be in the range of 1.83 eV-1.90 eV. Hall-effect measurement showed that all films have p-type conductivity with low hole concentration and high electrical resistivity, which may arise due to S-deficiency and limits the utilization of spray pyrolyzed SnS:Cu films in thin film solar cells as an absorber layer. Therefore it is proposed that excessive Sulphur source may be added in spray solution or as-grown SnS:Cu films may be post-annealed in Sulphur containing atmosphere.

5. References

- [1] M.A. Green, E.D. Dunlop, J. Hohl-Ebinger, M. Yoshita, N. Kopidakis, X. Hao, Prog. Photovoltaics Res. Appl. (2020) <https://doi.org/10.1002/pip.3303>
- [2] K. Pal, P. Singh, A. Bhaduri, K.B. Thapa, Sol. Energy Mater. Sol. Cells. (2019) <https://doi.org/10.1016/j.solmat.2019.03.001>
- [3] H. Katagiri, N. Sasaguchi, S. Hando, S. Hoshino, J. Ohashi, T. Yokota, Sol. Energy Mater. Sol. Cells. (1997) [https://doi.org/10.1016/S0927-0248\(97\)00119-0](https://doi.org/10.1016/S0927-0248(97)00119-0)
- [4] M. Kumar, A. Dubey, N. Adhikari, S. Venkatesan, Q. Qiao, Energy Environ. Sci. (2015) <https://doi.org/10.1039/C5EE02153G>
- [5] D. Lee, J.Y. Cho, H.-S. Yun, D.-K. Lee, T. Kim, K. Bang, Y.S. Lee, H.-Y. Kim, J. Heo, J. Mater. Chem. A. (2019) <https://doi.org/10.1039/C8TA09820D>
- [6] V.E. González-Flores, R.N. Mohan, R. Ballinas-Morales, M.T.S. Nair, P.K. Nair, Thin Solid Films (2019) <https://doi.org/10.1016/j.tsf.2018.12.044>.
- [7] U. Chalapathi, B. Poornaprakash, S.-H. Park, Sol. Energy (2016) <https://doi.org/10.1016/j.solener.2016.09.046>
- [8] B.H. Baby, D. Bharathi Mohan, Sol. Energy. (2019) <https://doi.org/10.1016/j.solener.2019.10.049>

- [9] S. Gedi, V.R. Minnam Reddy, T.R. Reddy Kotte, S.-H. Kim, C.-W. Jeon, *Ceram. Int.* (2016) <https://doi.org/10.1016/j.ceramint.2016.09.059>
- [10] H. Kafashan, R. Ebrahimi-Kahrizsangi, F. Jamali-Sheini, R. Yousefi, *Phys. Status Solidi.* (2016) <https://doi.org/10.1002/pssa.201532920>
- [11] H. Kafashan, Z. Balak, *Spectrochim. Acta Part A Mol. Biomol. Spectrosc.* (2017) <https://doi.org/10.1016/j.saa.2017.04.082>
- [12] S. Sebastian, I. Kulandaisamy, S. Valanarasu, N. Soundaram, K. Paulraj, D. Vikraman, H.-S. Kim, J. Mater. Sci. Mater. Electron. (2019) <https://doi.org/10.1007/s10854-019-01124-3>
- [13] P.S. Pawar, J.Y. Cho, K.E. Neerugatti, S. Sinha, T.R. Rana, S. Ahn, J. Heo, *ACS Appl. Mater. Interfaces.* (2020) <https://doi.org/10.1021/acsami.9b14329>
- [14] J.R. Hajzus, L.M. Porter, *J. Vac. Sci. Technol. A.* (2019) <https://doi.org/10.1116/1.5122785>
- [15] B. Barman, K. V. Bangera, G.K. Shivakumar, *Superlattices Microstruct.* (2019) <https://doi.org/10.1016/j.spmi.2019.106215>
- [16] J. Xu, J. Yang, S. Jiang, S. Shang, *Ceram. Int.* (2020) <https://doi.org/10.1016/j.ceramint.2020.07.079>
- [17] A.R. Garcia-Angelmo, R. Romano-Trujillo, J. Campos-Álvarez, O. Gomez-Daza, M.T.S. Nair, P.K. Nair, *Phys. Status Solidi.* (2015) <https://doi.org/10.1002/pssa.201532405>
- [18] R.E. Abutbul, A.R. Garcia-Angelmo, Z. Burshtein, M.T.S. Nair, P.K. Nair, Y. Golan, *CrystEngComm.* (2016) <https://doi.org/10.1039/C6CE00647G>
- [19] P.K. Nair, A.R. Garcia-Angelmo, M.T.S. Nair, *Phys. Status Solidi.* (2016) <https://doi.org/10.1002/pssa.201532426>
- [20] B.D. Cullity, *Elements of X-ray Diffraction*, Addison-Wesley Publishing Company, Inc, 1956.
- [21] V. Mote, Y. Purushotham, B. Dole, *J. Theor. Appl. Phys.* (2012) <https://doi.org/10.1186/2251-7235-6-6>
- [22] P.R. Bommireddy, C.S. Musalikunta, C. Uppala, S.-H. Park, *Mater. Sci. Semicond. Process.* (2017) <https://doi.org/10.1016/j.mssp.2017.07.020>
- [23] B.P. Kafle, S. Acharya, S. Thapa, S. Poudel, *Ceram. Int.* (2016) <https://doi.org/10.1016/j.ceramint.2015.09.042>
- [24] J. Tauc, R. Grigorovici, A. Vancu, *Phys. Status Solidi.* (1966) <https://doi.org/10.1002/pssb.19660150224>
- [25] J.I. Pankove, *Optical Processes in Semiconductors*, Courier Corporation, 1975.

- [26] S. Sebastian, I. Kulandaisamy, S. Valanarasu, M. Shkir, V. Ganesh, I.S. Yahia, H.-S. Kim, D. Vikraman, Surf. Eng. (2021) <https://doi.org/10.1080/02670844.2020.1754623>
- [27] B.H. Baby, A.M. Thomas, E.G. Amrutha, D. Bharathi Mohan, Sol. Energy. (2020) <https://doi.org/10.1016/j.solener.2020.05.076>
- [28] H.S. So, S. Bin Hwang, D.H. Jung, H. Lee, J. Korean Phys. Soc. (2017) <https://doi.org/10.3938/jkps.70.706>
- [29] T. Garmim, S. Chahib, L. Soussi, R. Mghaiouini, Z. El Jouad, A. Louardi, O. Karzazi, M. El Jouad, E.K. Hlil, B. Hartiti, M. Monkade, J. Mater. Sci. Mater. Electron. (2020) <https://doi.org/10.1007/s10854-020-04586-y>
- [30] J. Vidal, S. Lany, M. D’Avezac, A. Zunger, A. Zakutayev, J. Francis, J. Tate, Appl. Phys. Lett. (2012) <https://doi.org/10.1063/1.3675880>
- [31] K. Jeganath, N.J. Choudhari, G. Shruthi Pai, A. Rao, Y. Raviprakash, Mater. Sci. Semicond. Process. (2020) <https://doi.org/10.1016/j.mssp.2020.105050>

6. Tables

Table 1. Thickness (d), surface roughness (R) and elemental composition of SnS:Cu films.

Material	d (nm)	R (nm)	Elemental Composition at%		
			Sn	Cu	S
SnS	800	36.5	61.93	-	38.07
SnS:Cu (%4)	600	9.3	50.09	15.13	34.78
SnS:Cu (%8)	795	8.8	41.57	26.42	32.01

Table 2. Average crystallite size (D), micro-strain (ϵ), lattice constant (α), optical band gap (E_g), Urbach energy (E_u), hole concentration (p), resistivity (ρ) and mobility (μ) values of SnS:Cu films.

Material	D (Å)	$\epsilon \times 10^{-4}$	α (Å)	E_g (eV)	E_u (meV)	p ($\times 10^{11} \text{ cm}^{-3}$)	ρ ($\times 10^5 \Omega \text{ cm}$)	μ ($\text{cm}^2 \text{ V}^{-1} \text{ s}^{-1}$)
SnS	229	-3.63	11.537	1.83	134	7.01	1.36	93.1
SnS:Cu (%4)	198	-7.59	11.532	1.90	195	4.49	1.61	90.4
SnS:Cu (%8)	199	-6.57	11.537	1.84	237	40.87	0.11	494.4

Figures

Figure 1

Surface and inserted cross-sectional SEM images of (a) undoped SnS, (b) 4%, (c) 8% Cu doped SnS films. AFM images of (d) undoped SnS (e) 4%, (f) 8% Cu doped SnS films. EDS spectra of (g) undoped SnS (h) 4%, (i) 8% Cu doped SnS films.

Figure 2

(a) XRD patterns of SnS:Cd films, (b) comparison of the XRD patterns with extended vertical axis with JCPDS card No: 39-0354 and Ref.[19], (c) W-H plots of SnS:Cd films.

Figure 3

(a) Transmittance and absorbance (inset) spectra of SnS:Cu films, (b) Tauc plots and $\ln \alpha$ vs. $h\nu$ plots (inset) of SnS:Cu films.