Synthesis of Anatase TiO₂ Microspheres and Their Efficient Performance in Dye-sensitized Solar Cell

Gowthambabu V

Sri Sivasubramaniya Nadar College of Engineering, Kalavakkam-603110

Mural Deshpande

Sri Sivasubramaniya Nadar College of Engineering, Kalavakkam-603110

Govindaraj R (✉ isrogovindaraj@gmail.com)

Sri Sivasubramaniya Nadar College of Engineering, Kalavakkam-603110 <https://orcid.org/0000-0002-6770-7495>

Nithesh Krishna V. K

Sri Sivasubramaniya Nadar College of Engineering, Kalavakkam-603110

Leela Charumathi M

Sri Sivasubramaniya Nadar College of Engineering, Kalavakkam-603110

Manish Kumar J

Sri Sivasubramaniya Nadar College of Engineering, Kalavakkam-603110

Dhilip Vignesh M. S

Sri Sivasubramaniya Nadar College of Engineering, Kalavakkam-603110

Isaac Daniel R

Sri Sivasubramaniya Nadar College of Engineering, Kalavakkam-603110

Ramasamy P

Sri Sivasubramaniya Nadar College of Engineering, Kalavakkam-603110

Research Article

Keywords: Titanium dioxide, Microsphere, Dye-sensitized solar cell, Photoanode

Posted Date: March 15th, 2021

DOI: <https://doi.org/10.21203/rs.3.rs-282653/v1>

License: © ⓘ This work is licensed under a Creative Commons Attribution 4.0 International License.

[Read Full License](#)

Synthesis of anatase TiO₂ microspheres and their efficient performance in dye-sensitized solar cell

V. Gowthambabu^a, Murnal Deshpande^b, R. Govindaraj^{a*}, V. K. Nithesh Krishna^b, M. Leela Charumathi^b, J. Manish Kumar^b, M. S. Dhilip Vignesh^b, R. Isacc Daniel^a, P. Ramasamy^a

^a Department of Physics, SSN Research Centre, Sri Sivasubramaniya Nadar College of Engineering, Kalavakkam, Chennai, Tamilnadu 603 110, India

^b Department of Electrical and Electronics Engineering, Sri Sivasubramaniya Nadar College of Engineering, Kalavakkam, Chennai, Tamilnadu 603 110, India

Corresponding author: isrogovindaraj@gmail.com

Abstract

Nanomaterials play important role in performance of dye sensitized solar cells. In this paper, highly phase pure anatase TiO₂ microspheres were synthesized using a low-cost hydrothermal route. Initially, X-ray diffraction studies and Raman spectroscopic analysis were carried out and the formation of tetragonal structure of TiO₂ with the anatase phase was confirmed. The UV-Vis DRS studies showed the excellent reflectance and optical bandgap energy of 3.29 eV. The well-interconnected spherical nanoparticles with different sizes were examined by Field Emission Scanning Electron Microscopic analysis. The fabricated dye-sensitized solar cell (DSSC) composed of prepared TiO₂ microspheres as photoanode exhibited a higher power conversion efficiency (PCE) (η) of 5.4% as compared to commercial P25 with PCE of 3.6%. The higher J_{sc} (12.03 mA/cm²) in the fabricated DSSC due to efficient dye loading capacity and high light-scattering property was also observed.

Keywords Titanium dioxide, Microsphere, Dye-sensitized solar cell, Photoanode

1. Introduction

According to Nobel laureate Richard Smalley, the big challenge for the next 50 years is mainly in energy conservation and developments towards it to overcome environmental problems [1]. As compared to other renewable energy sources, solar energy proves to be most preferred source due to its continuous and abundant energy supply. The ‘Golden Triangle’ issues were considered to be an important thing to develop photovoltaic (PV) technology. The issue contains, decreasing the device cost, enhancing the power conversion efficiency and improving the long-term stability [2]. Among three generations of solar cells, third-generation solar cells

have the ability to rectify the aforementioned issues. Till date, the third-generation solar cells such as perovskite solar cells (PSC) ($\eta = 22\%$) [3], dye-sensitized solar cells (DSSC) ($\eta = 14\%$) [4], organic solar cells (OSC) ($\eta = 18\%$) [5] and quantum dot sensitized solar cells (QDSSC) ($\eta = 16\%$) [6] were employed due to their superior performance and cost efficiency. More recently DSSCs have received great attention due to their lower cost, easy fabrication process, lightweight and high efficiency. Till date, these cells have shown the maximum power conversion efficiency of 14.3% and 14.7% under 100 mW/cm² and 50 mW/cm² respectively [4]. The cutting edge of research mainly focuses on all DSSCs components such as semiconductor photoanode, highly electrocatalytic counter electrodes, sensitizers and electrolytes. To achieve an excellent performance of photoanodes, larger surface area, fast electron transport kinetics and large light scattering effects are required [7]. TiO₂ is a wide bandgap semiconductor metal oxide and is effectively used in versatile applications like photocatalysis [8], Li-ion battery [9], hydrogen production [10], antireflective coatings [11], gas sensors [12], optical filters [13], water splitting [14] and photoelectrochemical solar energy conversion [15]. Due to its unique features such as the high surface area to absorb dye molecules, long-term stability, ease of availability, cost-affordability, non-toxic nature, compatible optical and electronic properties, it is specifically used as photoanode in DSSCs [16]. As compared to other photoanode materials like ZnO [17], SnO₂ [18], WO₃ [19], Nb₂O₅ [20], SrTiO₂ [21], Zn₂SnO₄ [22] and BaSnO₃ [23], the anatase TiO₂ photoanode exhibits highest power conversion efficiency of about 14% [4]. Various nanostructures like nanotubes [24], nanowires [25], nanofibers [26], hollow spheres [27], microspheres of TiO₂ [28-30] were effectively used as photoanode material. Among these aforementioned nanostructures, microspheres were extensively used in DSSC due to their larger surface area, large sphere diameter, superior dye adsorption ability, better light scattering property and efficient interconnection of nanospheres [31]. Several researchers have adopted various techniques to synthesize the microspheres using high temperature hydro/solvothermal treatment [32-33], electrospray preparation [34], low-temperature copolymer synthesis [35], template-free chemically induced self-transformation [36] and electrospun process [37].

In this investigation, the authors have synthesized well-interconnected TiO₂ microspheres (TiO₂ MS) by hydrothermal method and fabricated the DSSC using prepared TiO₂ as photoanode. The detailed structural and morphological properties were studied using powder X-ray diffraction (XRD) analysis, Raman spectroscopic analysis and field emission scanning electron microscopic (FESEM) analysis. UV-Vis spectroscopic analysis was carried out to

study the optical properties and the optical band gap energy was found to be 3.29 eV. The fabricated DSSC performance was evaluated and the PCE (5.4%) from J-V curves, IPCE (56%) and electron lifetime τ (25.24 ms) from EIS were obtained. It was noted that TiO₂ MS based photoanode exhibits superior DSSC performance than P25 based photoanode due to its better light scattering ability and electron transport kinetics.

2. Experimental section

2.1. Materials used

The following reagents or chemicals were used to prepare TiO₂ MS and fabrication of DSSCs without any further purifications. Fluorine doped tin oxide (FTO, 8 Ω /square) substrates, Pluronic 123 (99%), Titanium tetraisopropoxide (99%), Acetylacetone (99%), Polyoxyethylene (10) octyl phenyl ether (Triton X-100) were purchased from Sigma Aldrich. Titanium tetrachloride (99%) was purchased from Spectrochem. Cis - diisothiocyanato-bis(2,2'-bipyridyl-4,4'-dicarboxylato) ruthenium (II) bis (tetrabutylammonium) (known as N-719 dye), Platisol T/SP, Iodolyte HI-30 were purchased from Solaronix SA, Switzerland, Tetrabutanol Ethanol (99%), Hydrochloric acid (32%) and Acetonitrile were purchased from Merck.

2.2. Synthesis of TiO₂ microspheres

In this typical synthesis procedure, the hydrothermal method was adopted for synthesis of TiO₂ MS and it is as shown in Fig. 1. Initially, 3mL of absolute ethanol containing 0.2g of pluronic 123 was stirred for 15 minutes and it is termed as solution A for future reference. On the other hand, 1mL of titanium tetra isopropoxide was added into solution B containing 0.7mL of concentrated HCl and stirred for 15 minutes. Then, solution B was successively added into solution A and stirred for 30 minutes. The resultant solution was kept at ambient temperature without any disturbance for 24 hours. After that, 12mL of ethanol was added into the resultant mixture and transferred into Teflon-lined stainless steel autoclave for hydrothermal reaction in a hot air oven at 150°C for 24 hours. The obtained product was rinsed several times with deionized water and ethanol to remove unwanted impurities. The resulting material was dried at 80°C for 24 hours in a vacuum oven. The dried material was annealed at 500°C for 1 hour in a muffle furnace.

2.3. Assembly of DSSC

Various steps were followed for assembly of DSSC: Initially, 1g of prepared TiO₂ MS was mixed with 0.1 mL of acetylacetone and grounded well with the aid of agate mortar and pestle.

The grounded products were stirred with a solution containing a 1:1 volume ratio of ethanol and water. 0.4 mL of Triton-X was added to the above solution to form a homogenous TiO_2 paste. The FTO glass substrate was cleaned with deionized water and ethanol using an ultrasonication bath for 15 minutes. The cleaned FTO substrate was soaked with 0.2M of aqueous TiCl_4 solution at 70°C for 30 minutes and rinsed with ethanol and heated at 500°C for 30 minutes (Pre- TiCl_4 treatment). After that, the doctor blade technique was adopted to coat TiO_2 paste on FTO substrate and the coated FTO substrate was sintered at 500°C for 1 hour to evaporate the binder materials in the coated films. The thickness of the sample, coated on FTO substrate was found to be $\sim 14\ \mu\text{m}$ using a thickness profilometer. The post TiCl_4 treatment on sintered TiO_2 film was followed like pre TiCl_4 treatment process. A similar process was followed to prepare commercial P25 film on FTO substrate. The resultant films were soaked in 0.5 mM of N719 dye in a 1:1 volume ratio of tertbutanol (10 mL) and acetonitrile (10 mL) solution for 24 hours under dark conditions. The platinum (Pt) counter electrode was coated on another FTO substrate by doctor blade technique with Platisol T/SP as the platinum precursor and thermally decomposed at 400°C for 30 minutes. At last, the dye adsorbed photoanode and Pt counter electrode were sandwiched together. To complete the device fabrication, a small amount of Iodolyte HI-30 as an aqueous electrolyte was injected in-between the two electrodes and the active area of the cell was found to be $0.25\ \text{cm}^2$ [38].

2.4. Characterization techniques

The crystallographic information of prepared TiO_2 MS was analyzed using a powder X-Ray Diffraction (X'PERT PRO PANALYTICAL, NETHERLANDS) instrument having a Cu $K\alpha$ radiation wavelength of $1.5418\ \text{\AA}$. Micro-Raman measurements were carried out using (RENISHAW InVia Confocal Raman microscope, United Kingdom). Field Emission Scanning Electron Microscope (ZEISS, SIGMA, GHBM, GERMANY) was used to analyze the morphological properties of the prepared TiO_2 MS. The optical properties of the prepared material were analyzed using UV-DRS (PerkinElmer, Lambda 35 spectrometer). The current density – voltage characteristics of fabricated DSSC were measured using Keithley digital source meter 2400 under $100\ \text{mW}/\text{cm}^2$ illumination coming from a solar simulator (UHE-16 equipped with a 150W Xenon Arc lamp and an AM 1.5 filter, Sciencetech, Canada). The light intensity was calibrated with a standard crystalline silicon solar cell to carry out the J-V measurements. Incident photon-to-current conversion efficiency (IPCE) data were collected in the wavelength from 350 nm to 800 nm by using QE system (Enlitech, QE-R). The electrochemical impedance measurement of the fabricated DSSC was analyzed using an

electrochemical workstation (FRA/VERSASTAT3, V3-500, Princeton Applied Research, USA) under the illumination at open-circuit voltage.

3. Results and Discussions

3.1. X-Ray Diffraction analysis

Phase identification, crystalline features and average crystallite size of hydrothermally synthesized TiO₂ MS were examined by powder XRD analysis. Fig. 2 demonstrates the powder XRD pattern of synthesized TiO₂ MS which possesses a tetragonal crystal structure of an anatase phase with preferred (101) orientation at $2\theta = 25.32^\circ$. All the diffraction peaks are well-matched with JCPDS No: 21-1272 ($a = b = 3.785$, $c = 9.513$) with a crystallographic space group of $I4_1/amd$. The diffraction peaks located at 25.31° , 37.86° , 48.07° , 53.97° , 55.09° , 62.72° , 68.85° , 70.31° and 75.15° were corresponding to (101), (004), (200), (105), (211), (204), (116), (220) and (215) crystal planes respectively. No other additional diffraction peaks corresponding to metallic Ti and other impurity phases like rutile and brookite were observed. Hence, it is evident that synthesized material has pure phase and crystalline nature [28]. The average crystallite size was found to be 18 nm with the aid of Debye- Scherrer formula, which is as follows

$$D = \frac{k\lambda}{\beta \cos\theta} \quad (1)$$

Where 'D' is the average crystalline size (nm), 'k' is the shape factor which corresponds to 0.9, ' λ ' is the wavelength of X-Ray used ($1.5418\text{\AA}$), ' β ' is the full width at half maximum of prominent diffraction peak (degree) and ' θ ' is the Bragg's diffraction angle (degree) [39].

3.2. Raman analysis

Fig. 3 shows the Raman spectra of synthesized TiO₂ MS. The raman scattering peaks obtained at 144 cm^{-1} , 197 cm^{-1} , 397 cm^{-1} , 516 cm^{-1} , 639 cm^{-1} were ascribed to E_{1g} , E_{1g} , B_{1g} , A_{1g} , E_{1g} active vibrational Raman modes. The peaks at 144 cm^{-1} , 197 cm^{-1} and 639 cm^{-1} corresponds to E_{1g} mode which is attributed to the symmetric stretching mode of the O-Ti-O bond. The B_{1g} and A_{1g} modes of peaks at 397 cm^{-1} and 516 cm^{-1} mainly correspond to symmetric and antisymmetric vibration bending modes of O-Ti-O bond respectively. Here, all the observed characteristics peaks belong to the typical anatase TiO₂ phase and no other additional phases were observed from Raman spectra which is also in good agreement with XRD results [40-42].

3.3. UV-Visible spectroscopic analysis

To study the optical properties of the prepared TiO₂ MS, UV-Vis DRS spectroscopic measurements were carried out. Fig. 4 shows diffused reflectance spectra of prepared TiO₂ microspheres which was recorded in the wavelength range of 300 to 1100 nm. The prepared TiO₂ microspheres exhibit excellent reflectance which will enhance the light scattering property. The optical band gap energy of prepared TiO₂ microspheres was determined using Kubelka-Munk function method. The relation is given below.

$$F(R) = \frac{(1 - R)^2}{2R} = \frac{K}{S} \quad (2)$$

Where F(R) is the Kubelka-Munk function and R is the reflectance. F(R) is directly proportional to absorption coefficient (K) and inversely proportional to scattering coefficient (S) [43]. To estimate the band gap energy, the graph plotted between $h\nu$ and $(\alpha hF(R))^2$ and the band gap energy was found to be 3.29 eV which is in good agreement with bulk TiO₂.

3.4. FESEM analysis

The surface morphological properties of the prepared material were characterized by field emission scanning microscopic analysis and the FESEM micrograph is shown in Fig. 5. From this micrograph, the TiO₂ MS exhibits smoothly well-defined interconnected nanospheres of various sizes. These microspheres will be the better pathway for electron transport.

3.5. Photovoltaic performance of the fabricated dye-sensitized solar cell

Fig. 6 shows the schematic representation of DSSC consisting of semiconductor metal oxide (TiO₂ MS) coated on FTO substrate sensitized with N719 ruthenium complex dye for absorbing visible light, I₃⁻/I⁻ based redox electrolytes for reducing oxidized dye and boosting the redox couple regeneration, a platinum counter electrode for collecting the electrons from the external circuit. According to the principle of DSSC, the voltage generated under the illumination of light radiation corresponds to the difference between the Fermi level of the electron in the binary semiconductor metal oxide and the redox potential of the electrolyte.

Fig. 7 demonstrates the current density – voltage (J-V) characteristics of fabricated DSSC using prepared TiO₂ MS as photoanode sensitized with N719 dye for 24 hours. The obtained solar cell parameters such as open-circuit voltage (V_{oc}), short circuit current density (J_{sc}), fill factor (FF) and power conversion efficiency (η) are tabulated in Table 1. The fill factor (FF) and power conversion efficiency (η) can be expressed as follows:

$$FF = \frac{J_{max} \times V_{max}}{J_{sc} \times V_{oc}} \times 100 \quad (3)$$

$$PCE (\eta) = \frac{J_{sc} \times V_{oc} \times FF}{P_{in}} \quad (4)$$

Where, V_{oc} and J_{sc} are open-circuit voltage (V) and short circuit current density (mA/cm²) of DSSC respectively. V_{max} and J_{max} are the maximum voltage and current respectively. P_{in} is the incident light power (100 mW/cm²) [41].

Table 1 The photovoltaic parameters of the fabricated device

	V_{oc} (V)	J_{sc} (mA/cm²)	FF	PCE (%)
TiO ₂ MS	0.716	12.03	0.63	5.4
P25	0.612	09.64	0.59	3.6

The results obtained for the fabricated device exhibit the short circuit current density (J_{sc}) about 12.03 mA/cm², open-circuit voltage (V_{oc}) about 0.716 V, fill factor (FF) about 0.63 and the power conversion efficiency (η) of 5.4%. At the same time, the device fabricated using P25 exhibits the short circuit current density (J_{sc}) of about 9.64 mA/cm², open-circuit voltage (V_{oc}) of 0.612 V, fill factor about 0.59 and the power conversion efficiency of about (η) 3.6%. Basically, the J_{sc} of the fabricated DSSC was estimated by the initial number of photo-generated electrons injected into the conduction band of TiO₂ photoanode, which are significantly influenced by the light-harvesting performance of the photoanode including the scattering effect of the photoanode structure and the overall dye loading amount [44]. In DSSC, the incident light loss occurs due to the backscattering of incident light in the FTO/TiO₂ interface. The small underlayer consisting of small-sized TiO₂ nanoparticles or TiCl₄ treatments (pre or post) effectively showed the superior photocurrent density and the power conversion efficiency because of greater effect on electronic transport and causes the downward shift in the band edge [44-45].

Incident photon-to-current conversion efficiency (IPCE) measurements were carried out to understand the performance of photoelectrodes which was shown in Fig 8. The IPCE can be expressed as follows [46]

$$IPCE = \left(\frac{hc}{e} \right) \frac{J}{\lambda I_{light}} \quad (5)$$

$$IPCE = 1240 \frac{J}{\lambda I_{light}} \quad (6)$$

Where J is current density (mA/cm^2), λ is the incident light wavelength (nm) and I_{light} is the measured light intensity (mA/cm^2). Here the authors have used wavelength ranging from 350 nm to 800 nm and the highest IPCE of about 56% was obtained at 520 nm. That mainly attributes to superior light scattering deriving from its characteristic photonic reflection effect which results in the higher J_{sc} in the fabricated device [44].

In DSSC, the electrochemical impedance spectroscopic analysis was used to understand the detailed charge transport and recombination kinetics of electrochemical properties. Fig 9 shows the Nyquist plot of a fabricated device which exhibit three semicircles corresponding to the diffusion of I_3^-/I^- electrolyte in lower frequency region, charge transport at Pt/electrolyte interface in higher frequency region and the electron transport kinetics at dye/ TiO_2 /electrolyte interface in middle-frequency region [47]. Fig 10 demonstrates the corresponding bode plot of the fabricated device and the maximum mid-frequency was observed at 6.31 Hz. The electron lifetime can be found to be 25.24 ms with the aid of the following relation and all EIS parameters are tabulated in Table 2.

$$\tau_e = \frac{1}{2\pi f_{\text{max}}} \quad (7)$$

Where f_{max} is the peak frequency obtained from the bode plot [47].

Table 2 EIS parameters of the fabricated device

Sample	$R_s (\Omega)$	$R_{\text{ct1}} (\Omega)$	$R_{\text{ct2}} (\Omega)$	$R_{\text{ct3}} (\Omega)$	$f_{\text{max}} (\text{Hz})$	$\tau_e (\text{ms})$
TiO_2 MS	11.12	01.82	08.05	04.66	6.31	25.24

4. Conclusion

The TiO_2 microspheres were successfully synthesized using a one-step hydrothermal route. The pure anatase phase formation of TiO_2 MS was confirmed with the aid of XRD and Raman analysis. The average crystallite size was found to be 18 nm by adopting the Debye Scherrer formula. The UV-Vis DRS results depict better reflectance and the optical bandgap energy was found to be 3.29 eV using Kubelka-Munk function plot. The DSSC was fabricated with the structure of FTO/ TiO_2 MS – dye/redox couple electrolyte/Pt/FTO and its efficiency was estimated under standard one sun illumination ($100 \text{ mW}/\text{cm}^2$). The photoanode made of TiO_2 MS exhibits excellent power conversion efficiency of 5.4%. The improved PCE and J_{sc} could be due to superior light scattering properties, electron transport properties and pre-and post-treatment of TiCl_4 in Photoanode.

Acknowledgment

The authors gratefully acknowledge Sathyabama Institute of Science and Technology for providing access to their Raman and FESEM facilities.

Funding

SSN Trust (partially)

Conflicts of interest

There are no conflicts to declare

Availability of data and material

Available data is transparent

References

1. M. S. Ahmad, A. K. Pandey, N. A. Rahim, *Renew. Sust* 77, 89 (2019)
2. S. Mozaffaria, M. R. Nateghib, M. B. Zarandi, *Renew. Sust* 71, 675 (2017)
3. W. S. Yang, B. W. Park, E. H. Jung, N.J. Jeon, Y. C. Kim, D. U. Lee, S. S. Shin, J. Seo, E. K. Kim, J. H. Noh, S. I. Seok, *Science* 356, 1376 (2018)
4. K. Kakiage, Y. Aoyama, T. Yano, K. Oya, J. Fujisawab, M. Hanaya, *ChemComm* 88, 15894 (2015).
5. Q. Liu, Y. Jiang, K. Jin, J. Qin, J. Xu, W. Li, J. Xiong, J. Liu, Z. Xiao, K. Sun, S. Yang, X. Zhang, L. Ding, *Sci. Bull.* 65, 272 (2020)
6. M. Hao, Y. Bai, S. Zeiske, L. Ren, J. Liu, Y. Yuan, N. Zarrabi, N. Cheng, M. Ghasemi, P. Chen, M. Lyu, D. He, J. H. Yun, Y. Du, Y. Wang, S. Ding, A. Armin, P. Meredith, G.Liu, H. M. Cheng, L. Wang, *Nat. Energy* 5, 79 (2020)
7. X. Sun, Y. Liu, Q. Tai, B. Chen, T. Peng, N. Huang, S. Xu, T. Peng, X. Z. Zhao, J. *Phys. Chem. C* 116, 11859 (2012)
8. A. Wold, *Chem. Mater* 5, 280 (1993)
9. H. G. Jung, S. W. Oh, J. Ce, N. Jayaprakash, Y. K. Sun, *Electrochem. Commun* 11, 756 (2009)
10. B. Liu, L. M. Liu, X. F. Lang, H. Y. Wang, X. W. (David) Lou, E. S. Aydil, *Energy Environ. Sci.* 7, 2592 (2014)
11. B. S. Richards, *Sol. Energy Mater. Sol. Cells* 79, 369 (2003)

12. B. Karunakaran, P. Uthirakumar, S.J. Chung, S. Velumani, E.-K. Suh, *Mater. Charact.* 58, 680 (2007)
13. M. Kitui, M. M. Mwamburi, F. Gaitho, C. M. Maghanga, *Int. J. Thin Fil. Sci. Tec.* 4, 17 (2015)
14. S. U. M. Khan, M. Al-Shahry, W. B. I. Jr, *science* 297, 2243 (2002)
15. B. O'Regan, M. Gratzel, *nature* 353, 737 (1991)
16. Y-Y. Yu, B-X. Lei, M-L. Xie, G-L. Huang, W. Sun, Z-F. Sun, *Adv Powder Technol* 26, 1072 (2015)
17. S. S. Kanmani, K. Ramachandran, *J Mater Sci* 48, 2076 (2013)
18. E. Ramasamy, Jinwoo Lee, *J. Phys. Chem. C* 114, 22032 (2010)
19. H. Zheng, Y. Tachibana, K. K. zadeh, *Langmuir* 26, 19148 (2010)
20. J. Z. Ou, R. A. Rani, M. H. Ham, M. R. Field, Y. Zhang, H. Zheng, P. Reece, S. Zhuikov, S. Sriram, M. Bhaskaran, R. B. Kaner, K.K. zadeh, *ACS nano* 6, 4045 (2012)
21. P. Jayabal, V. Sasirekha, J. Mayandi, K. Jeganathan, V. Ramakrishnan, *J. Alloys. Compd* 586, 456 (2014)
22. J. Chen, L. Lu, W. Wang, *J. Phys. Chem. C* 116, 10841 (2012)
23. N. Rajamanickam, P. Soundarrajan, S.M. Senthil Kumar, K. Jayakumar, K. Ramachandran, *Electrochim. Acta* 296, 771 (2019)
24. M. R. Venkatraman, N. Muthukumarasamy, P. Balraju, P. Selvakumar, V. Dhayalan, P. Arivalagan, *Int. J. Hydrog. Energy* 45, 15441 (2020)
25. X. Feng, K. Zhu, A. J. Frank, C. A. Grimes, T. E. Mallouk, *Angewandte Chemie* 124, 2781 (2012)
26. M. S. Mahmoud, M. S. Akhtar, I. M. A. Mohamed, R. Hamdan, Y. A. Dakka, N. A.M. Barakat, *Mater. Lett* 225, 77 (2018)
27. X. Y. Ye, Y. H. Gu, H. Chen, Y. F. Cao, Y.Y. Liu, B. X. Lei, W. Sun, Z. F. Sun, *Adv Powder Technol* 30, 2408 (2019)
28. Z. Q. Li, Y. P. Que, L.E Mo, W.C. Chen, Y. Ding, Y. Mei Ma, L. Jiang, L. H. Hu, S. Y. Dai, *Appl. Mater. Interfaces* 7, 10928 (2015)
29. J. D. Peng, C. M. Tseng, R. Vittal, K. C. Ho, *Nano energy* 22, 136 (2016)
30. P. Ilaiyaraja, T. K. Das, P. S. V. Mocherla, C. Sudakar, *Sol. Energy Mater. Sol. Cells* 169, 86 (2017)
31. H. Tao, W. Chen, J. Wang, W. Ke, J. Wan, J. Wu, G. Fang, *Electrochim. Acta* 137 17 (2014)

32. X. Miao, K. Pan, Y. Liao, W. Zhou, Q. Pan, G. Tian, G. Wang, *J. Mater. Chem* 1, 9853 (2013)
33. F. Sauvage, D. Chen, P. Comte, F. Huang, L. P. Heiniger, Y. B. Cheng, R. A. Caruso, M. Graetzel, *Acs Nano* 8, 4420 (2010)
34. D. Hwang, H. Lee, S. Y. Jang, S. M. Jo, D. Kim, Y. Seo, D. Y. Kim, *Appl. Mater. Interfaces* 3, 2719 (2011)
35. Y. Zhou, E. Y. Ding, W. D. Li, *Mater. Lett* 61, 5050 (2007)
36. J. Yu, J. Zhang, *Dalton Trans* 25, 5860 (2010)
37. G. Zhu, L. Pan, J. Yang, X. Liu, H. Sun, Z. Sun, *J. Mater. Chem* 22, 24326 (2012)
38. R. Govindaraj, N. Santhosh, M. S. Pandian, P. Ramasamy, *Appl. Surf. Sci.* 449, 166 (2018)
39. S. S. Kanmani, N. Rajkumar, K. Ramachandran, *Int. J. Nanosci* 10, 227 (2011)
40. M.R. Venkatraman, N. Muthukumarasamy, S. Agilan, V. Asokan, D. Velauthapillai, *Mater. Res. Bull.* 97, 351 (2018)
41. R. Govindaraj, N. Santhosh, M. S. Pandian, P. Ramasamy, M. Sumita, *J. Mater. Sci.: Mater. Electron.* 29, 3736 (2018)
42. X. Tao, P. Ruan, X. Zhang, H. Sun, X. Zhou, *Nanoscale* 8, 3539 (2015)
43. T. Amutha, M. Rameshbabu, S. S. Florence, N. Senthilkumar, I.V. Potheher, K. Prabha, *Res. Chem. Intermed.* 45, 1929 (2019)
44. C. Ma, L. Wang, Z. Guo, Y. Lv, W. Chen, Hui Ming, P. Ma, J. Wang, *Colloids Surf. A* 538, 94 (2018)
45. S. D. Liu, Y. K. Ren, Z. Zhou, W. C. Chen, Z. Q. Li, F. L. Guo, Li. E. Mo, J.H. Wu, L. H. Hu, S. Y. Dai, *Adv Powder Technol* 329, 225 (2019)
46. N. Rajamanickam, K. Ramachandran, *J. Colloid Interface Sci.* 580, 407 (2020)
47. Z. Ge, C. Wang, Z. Chen, T. Wang, T. Chen, R. Shi, S. Yu, J. Liu, *Mater. Res. Bull.* 135, 111148 (2021)

Fig. 1 Schematic representation for the synthesis of TiO_2 MS

Fig. 2 Powder XRD pattern of TiO_2 MS

Fig. 3 Raman spectrum of TiO₂ MS

Fig. 4 UV-Vis DRS spectrum of TiO_2 MS and inset shows the Kubelka-Munk function plot

Fig. 5 FESEM micrograph of TiO₂ MS

Fig. 6 Schematic diagram of DSSC

Fig. 7 Current density – voltage curves of TiO₂ MS and commercial P25 based DSSCs

Fig. 8 Incident photon-to-current conversion efficiency (IPCE) spectra of TiO₂ MS-based DSSC

Fig. 9 Nyquist plot for TiO₂ MS-based DSSC

Fig. 10 Bode plot for TiO₂ MS-based DSSC

Figures

Figure 1

Schematic representation for the synthesis of TiO₂ MS

Figure 2

Powder XRD pattern of TiO₂ MS

Figure 3

Raman spectrum of TiO_2 MS

Figure 4

UV-Vis DRS spectrum of TiO₂ MS and inset shows the Kubelka-Munk function plot

Figure 5

FESEM micrograph of TiO₂ MS

Figure 6

Schematic diagram of DSSC

Figure 7

Current density – voltage curves of TiO₂ MS and commercial P25 based DSSCs

Figure 8

Incident photon-to-current conversion efficiency (IPCE) spectra of TiO₂ MS-based DSSC

Figure 9

Nyquist plot for TiO₂ MS-based DSSC

Figure 10

Bode plot for TiO₂ MS-based DSSC