Construction of NiMoS₃/BC heterostructure photoanodes and optimization of light scattering to improve the photovoltaic performance of dye sensitized solar cells (DSSCs)

T Sumathi (✉ sumaparames@gmail.com)

Padmavani Arts & Science College for Women <https://orcid.org/0000-0001-8476-9172>

Sonia A Fredricka

Padmavani Arts & Science College for Women

G Deepa

Padmavani Arts & Science College for Women

Research Article

Keywords: NiMoS₃/BC, Heterojunction, Hydrothermal, Photo-conversion efficiency, Dye sensitized solar cell

Posted Date: March 16th, 2021

DOI: <https://doi.org/10.21203/rs.3.rs-289198/v1>

License: © ⓘ This work is licensed under a Creative Commons Attribution 4.0 International License.

[Read Full License](#)

Abstract

In the last two decades, dye sensitized solar cells (DSSCs) have gotten a lot of attention from researchers and have progressed quickly. To promote commercialization and large-scale application of DSSCs, their efficiency should be increased. This paper details significant advancements in advanced NiMoS_3/BC nanocomposites for improving photoanodes and DSSC conversion efficiencies. The fabricated electrode samples were characterized by XRD, SEM, TEM, Raman, UV, PL and BET to explore the structural, morphological and optical properties. A significant reduction band gap with enhanced light absorption and rapid prevention of electron hole pair was explored by UV-DRS and PL studies. The photocurrent density-voltage (J-V) and IPCE characteristics were analyzed for assembled solar cell. The NiMoS_3/BC (NMSC5) nanocomposite DSSC showed a PCE of 8.85%, far higher than that of the NiMoS_3 (2.45%) and a PCE value equivalent to Pt CE (4.79 %). The enhanced PCE of the proposed electrodes are also discussed in scientifically.

1. Introduction

Dye-sensitized solar cells have received significant attention in their potential applications although it is a challenge to achieve high power conversion efficiency (PCE). The development of highly active non-noble metal electro catalysts is essential for the successful renewable energy system [1]. In order to achieve a strong current density and to catalyze cyclic regeneration in the electrolytes, the counter electrode should simultaneously have outstanding electrocatalytic activity and good electrical conductivity as a critical component of the DSSCs. The counter electrode in DSSCs was used widely in platinum excellent electrocatalytic performance toward redox electrolytes [2]. However, low reserves and high platinum costs limit DSSCs' large-scale business use and huge opportunity [3]. Therefore, low cost electrode materials are important to improve the electrochemical performance of DSSCs in order to develop effectively [4–6]. For example, different types of carbons [7–10], inorganic compounds [11–13], composites [14] and metals [15], etc. Because of the adequate electrical conductivity, the strong stability and the low cost of carbon material, the efficient counter electrode DSSCs is considered to be a strong competitor [16]. Among many carbon material, BC has the unique one-dimension dendritic structure that could represent as a conducting electron transportation channel has attracted attention [17–19].

Transition metal sulfides (TMSs) are regarded as an excellent alternative to precious metals with great optic, electric, magnetic and catalytic characteristics [20–23]. The TMSs have been attracted much attention as a counter electrode material because of its excellent redox properties and high conductivity [24–27]. It is worth nothing that some TMSs have demonstrated excellent electric properties with large specific surface areas and unique structures, such as nanosphere [28], flower structures [29], nanorods [30] and nanotubes [31]. Metal sulfide has a high performance catalytic but low conductivity and structural instability, as most reported metals-based materials [32]. As a result, in the sense of developing low-cost and high-efficiency hybrid materials photocatalysts, strengthening the support for TMSs on BC by creating an efficient electronic transfer network merits special attention in both the basic and technical fields. However, carbon can increase the electronic conductivity of metal sulfides significantly [33–35].

The covering of a carbon layer on the NiMoS_3 surface with BC as a carbon source has been reported to significantly improve NiMoS_3 electrical conductivity. The carbon-coated nickel molybdenum sulfide NiMoS_3/BC combines the benefits of two materials, namely the high catalytic activity of the TMSs and the good carbon conductivity, simultaneously with the structure of the shell. In the meantime, it can significantly improve its cycle stability by introducing a thin carbon layer in the NiMoS_3 surface [36]. NiMoS_3/BC has been a promising material for solar energy collection devices like thin-film photovoltaics for the past decade. The increased absorption and wide surface area of NiMoS_3/BC contribute to the composite's improved performance. A series of electrochemical experiments have confirmed that the NiMoS_3/BC composite speeds up electron transfer from the counter electrode to the electrolyte as compared to Pt, pure NiMoS_3 , and CNFs. Composites of NiMoS_3/BC have higher I_3^- reduction catalytic activity and relatively better electrochemical stability.

2. Experimental

2.1. Materials

All chemicals were used as received any further purification. The Nickel Chloride ($\text{NiCl}_2 \cdot 6\text{H}_2\text{O}$), N, N-dimethylformamide, Polyacrylonitrile (PAN, Mw = 150,000), Ethanol, Ammonium, Molybdate ($(\text{NH}_4)_6 \cdot \text{Mo}_7\text{O}_{24} \cdot 4\text{H}_2\text{O}$). The purity of the Raw materials is 99.99%.

2.2. Synthesis of NiMoS_3/BC nanocomposites

The bio carbon was synthesized from aloe vera extract and dried at 80 °C for 12 h. The impurities in the aloe peels were washed away with water and ethanol before being dried at 105°C for 24 hours. After that, obtained substance was crushed into a powder with a particle size of 2.5 m. The resultant solution was transferred to an autoclave and kept at 120 °C for 24 hours after 5 g of aloe peel powder was mixed with 50 ml of DI water and vigorously stirred for about 30 minutes. The final product was annealed at 105 °C for 24 hours after the hydrothermal reaction was completed. It was then annealed at 800°C for 5 hours in a nitrogen atmosphere before being used. Hydrothermal method has been used to prepare the NiMoS_3/BC nanocomposites. Initially, PAN (2 g), 1 mmol $(\text{NH}_4)_6 \cdot \text{Mo}_7\text{O}_{24} \cdot 4\text{H}_2\text{O}$, 7 mmol $\text{NiCl}_2 \cdot 6\text{H}_2\text{O}$ and 2 mmol Citric Acid was dissolved in 18 g N, N-dimethylformamide (DMF) solvent then magnetically stirring 48 h to ensure a homogeneous solution. The resultant product is placed to 75 mL capacity autoclave and maintained 180 °C for 24 h. Then finally dried at 80 °C for overnight for further use. Composites for NiMoS_3/BC are denoted as $\text{NiMoS}_3(\text{X})/\text{BC}$, where X represents the weight percentages of NiMoS_3 in the composites, which were 1%, 3%, and 5%. The composite with various ratio of NiMoS_3 (1%, 3%, and 5%) was named as NMSC1, NMSC3 and NMSC5, respectively.

2.3. DSSC fabrication setup

The present solar cell device is sandwich type, which consists of photoanode, cathode and electrolyte solution, respectively. The photoanode and cathode of DSSC is fabricated using NiMoS_3/BC and

commercial platinum (Pt) paste deposition on FTO substrate using doctor blade method [19]. Then the photoanode was immersed in N719 dye solution. 0.6 M iodide/triiodide liquid electrolyte was injected between photoanode and cathode, respectively. AM1.5, 100 mWcm⁻² solar stimulator was used to monitor the photocurrent vs. voltage characteristics. The active surface area of the DSSC was 0.16 cm² (0.4 x 0.4 cm²).

2.4. Characterization techniques

X-ray diffraction (XRD) (Japan, XD-3A) using CuK α radiation and a scintillation counter detector were used to identify the crystalline structure of the samples. The morphological and optical properties of the samples were analyzed by Hitachi SU8010 type SEM instrument, H-600-II, Hitachi type TEM analytical instrument, UV-Vis spectrophotometer (UV-2550, Shimadzu, Japan). The electronic structure and chemical composition of the sample were determined by XPS (AXIS-165 Shimadzu, Japan). Autolab Potentiostat ECO CHEMIE was used to monitor the electrochemical performance.

3. Results And Discussion

3.1. Structural analysis

XRD patterns were analyzed in depth to clarify the crystal structure of NiMoS₃/BC composite samples. Figure 1 shows the powder XRD pattern of pure BC, NiMoS₃ and NiMoS₃/BC samples, respectively. Since the NiMoS₃/BC pattern reveals a prevalent diffraction peak at 26 ° that can be indexed to the (002) carbon plane (see in Fig. 1). The well crystalline cubic structure of NiMoS₃ was confirmed with respective pattern and the findings are well coincide with standard pattern (Joint Committee on Powder Diffraction Standards card no. 73-1508). Further, Raman spectra were taken to identify the crystalline phase and the corresponding spectra is shown in Fig. 2. BC pattern clearly expose the two band like D and G with equivalent wave number of 1356 and 1588 cm⁻¹, respectively. The E_{2g} and A_{1g} Raman mode of NiMoS₃ was positioned at 365 and 410 cm⁻¹ is due to the crystalline phase of cubic structure [37, 38]. Both BC and NiMoS₃ Raman modes are presented in the composite samples is confirming the successful incorporation BC in the NiMoS₃.

3.2. Morphological analysis

Figure 3 shows the SEM and TEM images of the samples which were taken to identify the morphological characteristics of the samples. Both SEM and TEM images clearly expose the sheets like BC and spherical shaped NiMoS₃. In the composite samples the uniform spherical of NiMoS₃ was disported uniformly of the surface of BC nanosheets. In the high-resolution TEM (HRTEM) images, lattice with a spacing of 0.29 nm, which can be assigned to the (002) plane of NiMoS₃.

3.3. Optical properties

UV-Vis absorption spectra and room temperature photoluminescence a spectrum was carried out to know the ability of absorption and recombination of charge carries. Figures 4 and 5 shows the UV and PL spectra of the samples. The absorption clearly falls in the range of 380–440 nm. Using K-M model [39,40] the estimated band gap energies are 3.26–2.81 eV. The broad emissions were found at 440–480 nm in the PL spectra with the excitation wavelength of 350 nm using He-Ne laser source. The effective recombination of electron-hole pair and chare carriers were found in the spectra due to the reduced PL emission intensity in the composite samples.

3.4. Surface area analysis

In order to analyse the porosity of the samples, the N_2 -adsorption/desorption tests were performed as shown in Fig. 6. The curve indicates standard type IV isotherm hysteresis as per the description of the Global Alliance of Pure and Applied Chemistry [41, 42]. Much of the data points come under the 2–50 nm range, suggesting that the composites of the $NiMoS_3/BC$ have a good number of mesoporous.

$NiMoS_3/BC$ electrode shows high surface area ($98.3\text{ m}^2/\text{g}$) and pores (12.9 nm) than compared with bare $NiMoS_3$ ($39.4\text{ m}^2/\text{g}$ and 23.4 nm).

3.5. Solar cell charectertics

As described before, the DSSCs of the sandwich type were manufactured and studies of J-V characteristics were assessed. Figure 7 displays the graphic image of the assembled unit. For DSSCs possessing Pt, $NiMoS_3$ and $NiMoS_3/BC$ nanocomposites, Fig. 8 elucidates the J-V curves. The $NiMoS_3/BC$ (NMSC5) nanocomposite DSSC showed a PCE of 8.85%, far higher than that of the $NiMoS_3$ (2.45%) and a PCE value equivalent to Pt CE (4.79 %). The corresponding incident photoelectron current emission (IPCE) spectra also illustrate that NMSC5 electrode shows high IPCE value than compared with other photoanode materials (Fig. 9). The overall photovoltaic parameter values are estimated for J-V curves and the values are summarized in Table 1. Figure 10 demonstrates the graphic illustration of the electrode photo-conversion mechanism. The improved BC photo anode level makes it much easier to supply the charged particles within the $NiMoS_3$ and lessens recombination as well. According to our analysis, the deterioration of photovoltaic productivity demonstrated significantly greater diffusion rate and higher recombination effect in the electron transport assessment. Good $NiMoS_3/BCNT$ performance compared to the bare $NiMoS_3$ provides better electron conductivity among $NiMoS_3$ and BC, however. The photo-generated electrons efficiencies are also affected by better dispersion of N719 zirconium dye with carbonyl group.

4. Conclusions

In this report, pure $NiMoS_3$ and composite with various amounts of bio carbon hybrid materials were synthesized by facile hydrothermal method. The well crystalline cubic structure of $NiMoS_3$ was confirmed with respective pattern and the findings are well coincide with standard pattern (Joint Committee on Powder Diffraction Standards card no. 73-1508). Both SEM and TEM images clearly expose the sheets

like BC and spherical shaped NiMoS_3 . In the composite samples the uniform spherical of NiMoS_3 was deposited uniformly on the surface of BC nanosheets. NiMoS_3/BC electrode shows high surface area ($98.3 \text{ m}^2/\text{g}$) and pores (12.9 nm) than compared with bare NiMoS_3 ($39.4 \text{ m}^2/\text{g}$ and 23.4 nm). The NiMoS_3/BC (NMSC5) nanocomposite DSSC showed a PCE of 8.85%, far higher than that of the NiMoS_3 (2.45%) and a PCE value equivalent to Pt CE (4.79 %). The improved BC photo anode level makes it much easier to supply the charged particles within the NiMoS_3 and lessens recombination as well.

References

1. W. Wang, L. Yang, F. Qu, Z. Liu, G. Du, A.M. Asiri, Y. Yao, L. Chen, X. Sun, A self-supported NiMoS_4 nanoarray as an efficient 3D cathode for the alkaline hydrogen evolution reaction, *J. Mater. Chem.* 5 (2017) 16585-16589.
2. S.A. Patil, S. Hussain, N.K. Shrestha, N. Mengal, Y.Y. Noh, Facile synthesis of cobalt-nickel sulfide thin film as a promising counter electrode for triiodide reduction in dye-sensitized solar cells, *Energy* 202 (2020) 117730.
3. H. Jing, Y. Shi, W. Qiu, D. Wu, X. Song, Y. An, C. Hao, Onion-like graphitic carbon covering metallic nanocrystals derived from brown coal as a stable and efficient counter electrode for dye-sensitized solar cells, *J. Power Sources* 414 (2019) 495-501.
4. T. Wang, J.B. Wang, W.L. Chen, A Reusable N-Carbon coated Mo_2C , Composite counter electrode for high-efficiency dye-sensitized solar cells, *Chemistry-A European Journal* 23 (2017) 17311-17317.
5. J. Hong, Y. Wang, Y. Wang, W. Zhang, R. Xu, Noble-metal-free $\text{NiS}/\text{C}_3\text{N}_4$ for efficient photocatalytic hydrogen evolution from water, *Chem Sus Chem* 6 (2013) 2263-2268.
6. F. Yu, Y. Shi, W. Yao, Han, S. Han, J. Ma, A new breakthrough for graphene/carbon nanotubes as counter electrodes of dye-sensitized solar cells with up to a 10.69% power conversion efficiency, *J. Power Sources* 412 (2019) 366-373.
7. M. Wu, M. Sun, H. Zhou, J.Y. Ma, T. Ma, Carbon counter electrodes in dye-sensitized and perovskite solar cells, *Adv. Funct. Mater.* 30 (2020) 1906451.
8. M. Batmunkh, M.J. Biggs, J.G. Shapter, Carbon nanotubes for dye-sensitized solar cells, *Small* 11 (2015) 2963-2989.
9. S.H. Seo, E.J. Jeong, J.T. Han, H.C. Kang, S.I. Cha, D.Y. Lee, Efficient low-temperature transparent electrocatalytic layers based on graphene oxide nanosheets for dye-sensitized solar cells, *ACS Appl. Mater. Interfaces* 7 (2015) 10863-10871.
10. S. Sigdel, A. Dubey, H. Elbohy, A. Aboagye, D. Galipeau, L. Zhang, H. Fong, Qiao, Dye-sensitized solar cells based on spray-coated carbon nanofiber/ TiO_2 nanoparticle composite counter electrodes, *J. Mater. Chem.* 2 (2014) 11448-11453.
11. L. Li, X. Zhang, D. Wang, W. Zhang, X. Li, X. Zhao, Q. Zhang, L. Gu, Z. Yu, M. Wu, Electrospinning synthesis of high performance carbon nanofiber coated flower-like MoS_2 nanosheets for dye-sensitized solar cells counter electrode, *Electrochim. Acta* 280 (2018) 94-100.

12. G.R. Li, J. Song, G.L. Pan, X.P. Gao, Highly Pt-like electrocatalytic activity of transition metal nitrides for dye-sensitized solar cells, *Energy Environ. Sci.* 5 (2011) 1680-1683.
13. M. Chen, L.L. Shao, Z.Y. Yuan, Q.S. Jing, K.J. Huang, Z.Y. Huang, X.H. Zhao, G.D. Zou, General strategy for controlled synthesis of $\text{Ni}_x\text{P}_y/\text{Carbon}$ and its evaluation as a counter electrode material in dye-sensitized solar cells, *ACS Appl. Mater. Interfaces* 9 (2017) 17949-17960.
14. P. Sudhagar, S. Nagarajan, Y.G. Lee, D. Song, T. Son, W. Cho, M. Heo, K. Lee, Won, Y.S. Kang, Synergistic catalytic effect of a composite (CoS/PEDOT: PSS) counter electrode on triiodide reduction in dye-sensitized solar cells, *ACS Appl. Mater. Interfaces* 3 (2011) 1838-1843.
15. J. Wu, Z. Lan, J. Lin, M. Huang, Y. Huang, L. Fan, G. Luo, Y. Lin, Y. Xie, Y. Wei, Counter electrodes in dye-sensitized solar cells, *Chem. Soc. Rev.* 46 (2017) 5975-6023.
16. Y. Li, L. Zhao, Z. Du, J. Du, W. Wang, Y. Wang, L. Zhao, X.M. Cao, X. Zhong, Metal-organic framework derived Co, N-doped carbons as superior electrode catalysts for quantum dot sensitized solar cells, *J. Mater. Chem.* 5 (2018) 2129-2138.
17. P. Joshi, L. Zhang, Q. Chen, D. Galipeau, H. Fong, Q. Qiao, Electrospun carbon nanofibers as low-cost counter electrode for dye-sensitized solar cells, *ACS Appl. Mater. Interfaces* 2 (2010) 3572-3577.
18. C.P. Lee, K.Y. Lai, C.A. Lin, C.T. Li, K.C. Ho, C.I. Wu, S.P. Lau, J.H. He, A paper-based electrode using a graphene dot/PEDOT: PSS composite for flexible solar cells, *Nanomater. Energy* 36 (2017) 260-267.
19. R. Jin, Y. Cui, S. Gao, S. Zhang, L. Yang, $\text{CNTs@NC@CuCo}_2\text{S}_4$ nanocomposites: an advanced electrode for high performance lithium-ion batteries and supercapacitors, *Electrochim. Acta* 273 (2018) 43-52.
20. Rui X, Tan H, Yan Nanostructured metal sulfides for energy storage. *Nanoscale* 2014;6:9889–924.
21. Faber MS, Dziedzic R, Lukowski MA, et al High-performance electrocatalysis using metallic cobalt pyrite (CoS_2) micro- and nanostructures. *J Am Chem Soc* 2014;136:10053–61.
22. Gong F, Xu X, Li Z, et al NiSe_2 as an efficient electrocatalyst for a Pt-free counter electrode of dye-sensitized solar cells. *Chem Commun* 2013;49:1437–9.
23. Li L, Zhang Electrospinning synthesis of high performance carbon nanofiber coated flower-like MoS_2 nanosheets for dye-sensitized solar cells counter electrode. *Electrochim Acta* 2018;280:94–100.
24. Zhang Y, Sun One-pot synthesis of tunable crystalline Ni_3S_4 @amorphous MoS_2 core/shell nanospheres for high-performance supercapacitors. *Small* 2015;11:3694–702.
25. Xie X, Ao $\text{MoS}_2/\text{Graphene}$ composite anodes with enhanced performance for sodium-ion batteries: the role of the two-dimensional heterointerface. *Adv Funct Mater* 2015;25:1393–403.
26. Chuang HM, Li CT, Yeh MH, et al A coral-like film of Ni@NiS with core-shell particles for the counter electrode of an efficient dye-sensitized solar cell. *J Mater Chem* 2014;2:5816–24.
27. Meng XT, Yu C, Song XD, et al Rational design and fabrication of sulfur-doped porous graphene with enhanced performance as a counter electrode in dye-sensitized solar cells. *J Mater Chem* 2017;5:2280–7.

28. Han Q, Zheng H, Wu Designing metal-sulfide-sphere counter-electrode catalysts for ZnO-nanorod-array-based quantum-dot-sensitized solar cells. *Eur J Inorg Chem* 2017;3787–93.
29. Qian X, Li H, Shao L, et al. Morphology-tuned synthesis of nickel cobalt selenides as highly efficient Pt-free counter electrode catalysts for dye-sensitized solar ACS Appl Mater Interfaces 2016;8:29486–95.
30. Chen W, Min W, Qian T, et Rational design and fabrication of skeletal Cu₇S₄ nanocages for efficient counter electrode in quantum dot-sensitized solar cells. *Nano Energy* 2015;12:186–96.
31. Li H, Qian X, Zhu Template synthesis of CoSe₂/Co₃Se₄ nanotubes: tuning of their crystal structures for photovoltaics and hydrogen evolution in alkaline medium. *J Mater Chem* 2017;5:4513–26.
32. L. Fei, B.P. Williams, S.H. Yoo, A general approach to fabricate free-standing metal sulfide@carbon nanofiber networks as lithium ion battery anodes, *Chem. Commun.* 52 (2016) 1501e1504.
33. X. Meng, C. Yu, B. Lu, J. Yang, J. Qiu, Dual integration system endowing two-dimensional titanium disulfide with enhanced triiodide reduction performance in dye-sensitized solar cells, *Nanomater. Energy* 22 (2016) 59-69.
34. X. Han, W. Zhang, X. Ma, C. Zhong, N. Zhao, W. Hu, Y. Deng, Identifying the activation of bimetallic sites in NiCo₂S₄@ g-C₃N₄-CNT hybrid electrocatalysts for synergistic oxygen reduction and evolution, *Adv. Mater.* 31 (2019) 1808281.
35. P. Jiang, Q. Liu, Y. Liang, J. Tian, A.M. Asiri, X. Sun, A cost-effective 3D hydrogen evolution cathode with high catalytic activity: FeP nanowire array as the active phase, *Angew. Chem.* 3 (2014) 12855-12859.
36. Z. Ren, V. Botu, S. Wang, Y. Meng, W. Song, Y. Guo, R. Ramprasad, S.L. Suib, P. Gao, Monolithically integrated spinel M_xCo_{3-x}O₄ (MCo, Ni, Zn) nanoarray catalysts: scalable synthesis and cation manipulation for tunable low-temperature CH₄ and CO oxidation, *Angew. Chem.* 53 (2014) 7223-7227.
37. Y.-C. Lin, D. O. Dumcenco, Y.-S. Huang, K. Suenaga, Atomic mechanism of the semiconducting-to-metallic phase transition in single-layered MoS₂. *Nat. Nanotechnol.* 9, 391–396 (2014).
38. B. Radisavljevic, A. Radenovic, J. Brivio, V. Giacometti, A. Kis, Single-layer MoS₂ transistors. *Nat. Nanotechnol.* 6, 147–150 (2011).
39. Z. Yin, H. Li, H. Li, L. Jiang, Y. Shi, Y. Sun, G. Lu, Q. Zhang, X. Chen, H. Zhang, Single-layer MoS₂ phototransistors. *ACS Nano* 6, 74–80 (2012).
40. L.S. Byskov, J. K. Nørskov, B. S. Clausen, H. Topsøe, DFT calculations of unpromoted and promoted MoS₂-based hydrodesulfurization catalysts. *J. Catal.* 187, 109–122 (1999).
41. X. Huang, Z. Zeng, S. Bao, M. Wang, X. Qi, Z. Fan, H. Zhang, Solution-phase epitaxial growth of noble metal nanostructures on dispersible single-layer molybdenum disulfide nanosheets. *Nat. Commun.* 4, 1444 (2013).
42. B. C. Windom, W. Sawyer, D. W. Hahn, A Raman spectroscopic study of MoS₂ and MoO₃: Applications to tribological systems. *Tribol. Lett.* 42, 301–310 (2011).

Table

Table 4.1. Photovoltaic parameters

Parameters	Pt	NiMoS ₃	NMSC1	NMSC2	NMSC5
Jsc (mA/cm ²)	17.01	10.05	15.11	18.35	20.65
Voc (V)	0.54	0.45	0.51	0.59	0.65
Fill Factor	0.57	0.51	0.53	0.58	0.63
Efficiency η (%)	4.79	2.45	3.16	6.22	8.85

Figures

Figure 1

Powder XRD pattern of the samples

Figure 2

Raman spectra of the samples

Figure 3

SEM images of a) BC; b) NiMoS₃; c) NMSC₅; TEM image of d) BC; e) NiMoS₃; f) NMSC₅; g) SAED pattern and h) EDS of NMSC₅ samples

Figure 4

a) UV absorption spectra and b) K-M plot

Figure 5

PL spectra of the samples

Figure 6

a) N₂ adsorption-desorption spectra and b) pore size distribution of the samples

Figure 7

Schematic illustration of the fabricated DSSC

Figure 8

J-V pot

Figure 9

IPCE spectra

Figure 10

Photovoltaic mechanism of NiMoS₃/BC photoanode under solar light