Fluorescein-Bridged Perylene Bisimide Dimer for Use as Liquid Crystal: Studies on Mesomorphic and Fluorescence Properties

Mingguang Zhu (✉ zhumg91_njun@126.com)

Neijiang Normal University <https://orcid.org/0000-0002-5746-3132>

Meihui Chen

Chemistry and Chemical Engineering, Neijiang Normal University

Hongyu Guo

Fujian Normal University

Fafu Yang

Fujian Normal University

Research Article

Keywords: perylene bisimide, liquid crystal, fluorescein, FRET, fluorescence

Posted Date: March 18th, 2021

DOI: <https://doi.org/10.21203/rs.3.rs-297853/v1>

License: This work is licensed under a Creative Commons Attribution 4.0 International License.

[Read Full License](#)

Version of Record: A version of this preprint was published at Journal of Fluorescence on August 2nd, 2021. See the published version at <https://doi.org/10.1007/s10895-021-02793-2>.

Abstract

A novel fluorescein-bridged perylene bisimide (PBI) dimer for liquid crystal (LC) with geometrically symmetric structure was developed. The mesomorphic results indicated that the energetically stable and unstable conformers of fluorescein fragments could lead to the transformation of mesophases from a hexagonal columnar mesophase to an uncertain phase at 136.9 °C in heating, whilst a stable hexagonal columnar mesophase maintained between 175.6 °C and 58.6 °C in cooling. The selectively excited fluorescence characters in THF solution demonstrated that the fluorescence resonance energy transfer (FRET) effect between fluorescein fragments and PBI units could provide a means to effectively impose strong fluorescence of the dimeric PBIs modified with suitable chromophore at the N-imide position, which alternatively serves as a platform for the further study of multi-functional PBI-based LCs.

Introduction

Boasting the natural virtues of fascinating photophysical properties (e.g., longer excitation wavelength, high fluorescence quantum yield, long fluorescence lifetime, and the stability to light and thermal-exposure), perylene bisimide (PBI) is a recurring and overwhelming motif in various fields of solar photovoltaics[1-4], organic electronic devices[5,6], photoelectrocatalysis[7], photoisomerization[8], near-infrared photothermal conversion[9], phosphorescence[10], moisture detection[11], bioimaging[12,13], theranostics[14,15], and biosensing/bioassay[16]. Additionally, the self-assembled π - π interaction of perylene core plays a decisive role in its functional characteristic and renders it possible to develop various supramolecular species involving host-guest recognition[17,18], gelator[19-21], LCs[22], and so on. On account of 1D charge transport pathways in supramolecular columnar mesophase, discotic PBI-based LCs can be used to fabricate thin semiconducting devices over large areas[23-25]. In fact, bringing the discotic PBI-based LCs more closely to practical applications requires excellent mesomorphic and emission properties. Up to now, although a plenty of discotic PBI-based LCs were achieved using various mesomorphic groups such as triphenylene[26-30], cholesterol[31,32], siloxane[33], dendritic peptides[34], cyclotetrasiloxane[35], oligosiloxane[36], polyhedral oligosilsesquioxane (POSS)[37], and gallic acid derivatives[38-42], most of their fluorescence emission were regulated and managed by substituted groups through the intramolecular charge-transfer (ICT) and/or π -extended conjugation system. While hardly affecting the alteration of emission peak, the substituents at the N-imide positions can weaken the fluorescence because of the photoinduced electron transfer (PET)[22], which limit the practical application of the fluorescent PBI-based LCs in photoelectronic and electroluminescent devices. Thus, to realize the modulation of excited fluorescence of PBIs, modification at the N-imide positions is crucial for development of novel functional LCs.

In order to construct discotic PBI-based LCs, it had been reported that the integration of the perylene core into six peripheral alkyl chains could effectively control over molecular alignment for fabricating a stable hexagonal columnar mesophase[43,44]. On the other hand, a large number of researches have focused the attention on the study and development of some polyploid PBIs for new materials[2,4,45-51]. Unfortunately, a previously reported exploration on the dimeric PBI-based LCs focused on

functionalization with two PBI units through different length of poly methylene spacer at the N-imide position, which has a distinctive feature of little changed emission in free solution state according to Kasha's rule[50]. However, how to trigger changes in emission properties of dimeric PBI-based LCs with suitable substitution at the N-imide position still remains difficult.

In this work, in terms of the enhanced fluorescence originating from FRET effect of bis-chromophoric groups[42,44], a novel fluorescein-bridged PBI dimer for LC was firstly synthesized as shown in Scheme 1. The target PBI 3 exhibited different LC behaviors due to the presence of fluorescein unit, while the emission spectrum of PBIs in THF solution could be improved by transferring the energy from fluorescein fragment to PBI core. This study was an innovative approach to demonstrate the methodology on building two different chromophores functionalized LCs.

Experimental

Materials and Equipments

Acetonitrile (MeCN 98%, Alfa Aesar) was dried over P_2O_5 under a nitrogen atmosphere and distilled before use. The anhydrous potassium carbonate (K_2CO_3) was prepared in a muffle furnace at 400 °C for 12 h. All other commercially purchased chemicals were used without further purification. Column chromatographic separation was performed on silica gel (200–300 mesh). Thin-layer chromatography (TLC) was performed on glass plates precoated with silica gel. All proton nuclear magnetic resonance (1H and ^{13}C NMR) spectra were conducted with a Bruker-ARX 400 spectrometer in $CDCl_3$ solvent, and calibrated using tetramethylsilane (TMS, $\delta = 0$ ppm) as internal standard. Chemical shifts were quoted in parts per million (ppm), and coupling constants were made out as J -values in Hz. MALDI-MS spectrum was determined on a Bruker MALDI-Mass spectrometer. Fourier transform infrared (FT-IR) spectra were measured on Perkin Elmer Spectrum 100 FT-IR spectrometer with solid KBr pellets. DSC measurements were determined in a hermetic aluminium pan using a thermal analyzer (Q100) at a scanning rate of 5 °C min^{-1} from -30 °C to 270 °C under a nitrogen atmosphere. The mesomorphic texture of the sample was captured with a polarization optical microscope (Leica DMRX), operated with a temperature-controlled heating setup (Linkam THMSE 600). The mesomorphic structure of the sample was carried out by XRD measurement using an X-ray diffractometer (XRD7, SEIFERT-FPM), equipped with Cu K α radiation ($\lambda = 1.54056$ Å) at 40 kV and 30 mA. UV-visible absorption spectrophotometer (Shimadzu, UV-2550) and fluorescence spectrophotometer (Shimadzu, RF-5301PC) were employed to investigate the photophysical properties of the sample. Experimentally, the emission spectra of the samples were recorded in THF (10 μ M solutions) using 1 cm quartz cuvette, when slit widths were $\Delta\lambda_{ex} = 3$ nm and $\Delta\lambda_{em} = 5$ nm, respectively. The fluorescence absolute quantum yields (ϕ_F) were measured on an Edinburgh Instruments FLS920 fluorescence spectrometer with a calibrated integrating sphere.

Synthesis of fluorescein-bridged perylene bisimide dimer 3

Under a nitrogen atmosphere, PBI intermediate (compound **2**) (1.29 g, 0.8 mmol), and fluorescein (0.14 g, 0.4 mmol) were placed into a suspension of anhydrous K₂CO₃ (0.14 g, 1 mmol) in 35 mL of anhydrous MeCN. The mixture was refluxed in 18 h under magnetically stirring condition. Reaction was monitored by TLC. As completion of the reaction, the mixture was cooled to room temperature, the excess solvent was then evaporated under reduced pressure. After admixing with 30 mL of HCl solution (1 M), the resulting mixture was extracted with 40 mL of DCM. The organic phase was washed with brine (3 × 30 mL), dried over anhydrous MgSO₄, filtered, and concentrated with a rotary evaporator to afford a red residue. The residue was further purified by a silica gel column (DCM/petroleum ether (2:1, v/v)) to give compound **3** as a red solid in yield of 70%. FT-IR (KBr), ν/cm^{-1} : 1698, 1660 (C=O); ¹H NMR (400 MHz, CDCl₃) δ ppm: 8.20 (bs, 8H, Per-H), 7.54 (d, J = 8.0 Hz, 2H, Flu-H), 7.36 (s, 2H, Flu-H), 7.19 (bs, 16H, Ar-H), 7.15-7.12 (m, 4H, Flu-H), 7.00 (s, 2H, Flu-H), 6.84 (bs, 16H, Ar-H), 4.92 (s, 2H, OCH₂CO), 4.31 (m, 2H, FluOCH₂CO), 4.09 (t, J = 8.0 Hz, 8H, NCH₂), 3.61 (t, J = 8.0 Hz, 4H, OCH₂), 1.68-0.86 (m, 214H, CH₂ and CH₃); ¹³C NMR (100 MHz, CDCl₃) δ ppm: 167.12, 165.53, 163.93, 161.59, 160.66, 159.43, 157.44, 155.97, 152.58, 149.61, 147.13, 144.51, 141.33, 137.86, 135.25, 132.73, 128.74, 127.50, 125.93, 122.00, 119.00, 114.00, 110.26, 105.43, 102.44, 100.73, 97.99, 68.20, 65.05, 62.22, 42.61, 31.69, 29.34, 26.19, 24.19, 21.01, 18.76, 14.84; anal. Calcd for C₂₂₈H₂₈₀N₄O₂₅: C, 78.77; H, 8.12; N, 1.61. Found: C, 79.01; H, 8.10; N, 1.68. MALDI-MS (C₂₂₈H₂₈₀N₄O₂₅) [M]⁺: calcd: m/z = 3476.08. found: m/z = 3476.24.

Results And Discussion

Synthesis and characterization

Fluorescein, as a highly preferable fluorescent chromophore, has been widely applied for biological assays as well as biolabeling due to its exceptional fluorescence properties[52-59], whereas little attention was paid to disk-like LCs of fluorescein. In our previous studies, designing and controlling the effect of a rigid chromophore building block into the columnar mesophase architectures could ensure the mesomorphic nature to optimize photophysical properties, which provided an approach for the design of multifunctional LC materials[60, 61]. With a view to the stiff planar quinoid scaffold of fluorescein as well as the extraordinary mesogenic properties of PBI **1**, the dimeric PBI-based LC **3** was constructed by inserting a fluorescein unite between two PBIs **1** at the N-imide position. The straightforward one-step synthetic route for the dimeric PBI-based LC **3** is illustrated in Scheme 1. With the key intermediate PBI **1** in hand,[44] PBI **3** was easily prepared by nucleophilic substitution of PBI **1** with fluorescein. In the presence of K₂CO₃, the red solid of final compound **3** was obtained by refluxing compound **1** and **2** in MeCN with a yield of 70%. To check the solubility of compound **3**, it was dissolved in different organic solvents including chloroform, dichloromethane (DCM), Toluene, THF and DMF. Compound **3** exhibited relatively good solubility in chloroform, dichloromethane and THF.

The chemical structure of target compound **3** was fully characterized by various characterization techniques (NMR, MALDI-MS, FT-IR and elemental analysis), and the results fitted well to the expected structure. ¹H NMR spectrum and the details of other characterization spectra were listed in the Supporting

Information. In Figure S1, one can see the clear splits for aromatic protons of fluorescein units but broad signals for aromatic protons of nonylphenoxy and perylene skeleton. After examining the proton signals of same skeleton of compound **3**, its precursor **1** and reference compounds **4** and **5**, we noticed all of them showed the broad signals for the H_a, H_b and H_c [43, 44]. The phenomena suggested that this kind of broad signals for the H_a, H_b and H_c could be ascribed to internal structural features for these compounds. By analysing this structural feature, it could be observed that the aromatic ring away from perylene skeleton (such as fluorescein unit in compound **3**) can rotate freely around the single bond due to the small steric resistance, resulting in the clear splits for protons. However, due to the big steric resistance and the long alkyl chains on nonylphenoxy units, the rotation of nonylphenoxy units on perylene skeleton was limited and slow, resulting in compound **3** adopted various conformations which possessed different intersection angles between nonylphenoxy units and perylene skeleton. The signals of H_a, H_b and H_c in Figure S1 were the overlapped and mixed signals of H_a, H_b and H_c in different conformation and changing spatial orientation of compound **3**. Thus, the broad signals for H_a, H_b and H_c were observed. On the other hand, the specific protons of OCH₂CO, FluOCH₂CO and OCH₂ function groups established self-governed chemical shifts at 4.92 (g), 4.31 (f), and 3.61 (e) ppm, respectively. The relative integrals of all peaks agree with the number for protons. Therefore, the well-defined target compound **3** was successfully obtained with good purity.

Mesomorphic studies

To evaluate the mesomorphic properties, the basically recognized results of the thermal phase transition temperatures and enthalpies of the target PBI **3** with differential scanning calorimetry (DSC) were presented in Figure 1, quoting the first cooling and second heating runs to erase the thermal history. The relevant data were summarized in Table 1. Subsequently, the mesomorphic birefringence textures from the crossed polarizing optical microscope (POM) of specimen were observed in the heating-cooling cycles as displayed in Figure 2. During second heating process, the mesomorphic properties of PBI **3** exhibited three endothermic peaks for three transitions, which were subjected to the crystal-LC (61.3 °C), LC-LC (136.9 °C), LC-isotropic (182.2 °C) transitions. This was further supported by the observation of LC textures. Upon heating from the melting temperature at a rate of 2.0 °C min⁻¹, intriguing pseudo-focal conical fan-shaped textures with a large area of homeotropic alignment domains for the column stacks were observed in the temperature range from 61 °C to 137 °C. Figure 2(a) was captured at 95 °C and consistent with the images of the monomeric PBI-based LCs with multistrand peripheral alkyl chains [40]. From Figure 1 and Table 1, a comparative study of the involved PBIs revealed that the mesomorphic phase of PBI **3** occurred at 61.3 °C well above its analogues PBI **4** (46.8 °C) and PBI **5** (56.2 °C) in the course of heating. Such thermotropic behavior was attributed to the rigid structure of fluorescein group needing more energy cost to melt. Moreover, In comparison with PBIs **4** and **5**, PBI **3** had a higher clearing temperature at 182.2 °C and a wider mesomorphic temperature range of ~120 °C. Notably, there was an endothermic peak for LC-LC (136.9 °C) transition in heating trace, suggesting the mesophase changed from one phase to another formation. As shown in Figure 2(b), a temperature rise induced dramatic changes, giving the randomly oriented textures from 137 °C to 182 °C. Figure 2b was pictured at 158 °C in

heating. This observation leads to the conclusion that a separation of the metastable mesophase occurred at 136.9 °C ($\Delta H = 4.7 \text{ kJ mol}^{-1}$) because the fluoresceine fragment were dispersed within the mobile aliphatic chains rather than in the perylene stacks. In addition, another transformation peak of LC-isotropic was observed at 182.2 °C, the POM image of PBI **3** changed into a dark field as the temperature exceeding the clear point (182 °C) in the heating process.

Table 1 Transition temperatures (°C) and enthalpies ΔH (kJ mol ⁻¹) of target compound 3 , reference compounds 4 and 5 .	
PBIs.	Phase transitions ^[a] [°C (kJ mol ⁻¹)]
3	Cr 61.3 (9.2) → Col _h 136.9 (4.7) → Col 182.2 (11.5) → Iso Iso 175.6 (9.6) → Col _h 58.6 (10.3) → Cr
4 ^[b]	Cr 46.8 (12.6) → Col _h 155.7 (21.4) → Iso Iso 144.7 (20.5) → Col _h 42.0 (8.3) → Cr
5 ^[c]	Cr 56.2 (16.84) → Col _h 106.5 (10.36) → Iso Iso 157.3 (11.18) → Col _h 49.6 (17.35) → Cr
[a] Cr = crystalline, Col _h = hexagonal columnar mesophase, Col = columnar mesophase, Iso = isotropic. [b] The data are cited from ref. [43]. [c] The data are cited from ref. [44].	

Nevertheless, the mesomorphic properties of PBI **3** exhibited two exothermic peaks for two transitions in DSC cooling cycle, which were subjected to the isotropic-LC (175.6 °C), LC-crystal (58.6 °C) transitions. When the sample was cooled from the isotropic liquid state at a rate of 2.0 °C min⁻¹, the single mesophase was maintained in the whole DSC cooling curve and stable up to the crystallization of PBI **3** (58.6 °C), and there was no significant phase transition below the crystallized peak. PBI **3** cooled from the isotropic melt until a fully developed LC texture was observed under POM at approximately 175 °C. The mass-produced pseudo-focal conical fan-shaped textures as well as optically isotropic homeotropic domains for PBI **3** were observed between 175 °C and 58 °C in cooling process, which well agreed with the observed result in DSC. Figure 2c was captured at 142 °C in the cooling-down stage, and it represented the POM texture within a temperature range from 175 °C to 58 °C in cooling, similar to the one observed at 95 °C in the heating (Figure 2a). PBI **3** exhibited the two double reversible humps of

crystalline-mesophase and mesophase-isotropic transitions appearing at around melting point and clearing point in DSC curves, respectively. The reversible transition temperatures in the cooling-down stage were below the relative temperatures in heating, known as the hysteresis, referring to the formation of LC germs at lower temperature on cooling. As a consequence, the detailed analysis of mesomorphic properties with a combination of DSC and POM confirmed that fluorescein-bridged perylene dimer **3** hold a stable columnar mesophase between 175.6 °C and 58.6 °C in cooling, while it had two kinds of mesophases with a mesomorphic temperature range of ~120 °C in heating. Insufficiently, more information on the stacked structure of PBI **3** in mesophase could not be obtained via DSC and POM means.

With the comprehensive understanding on the mesomorphic properties via DSC and POM means, we further lucubrated the theoretical packing parameters of LC **3** by variable-temperature XRD measurements at a rate of 2 °C /min under the first cooling and second heating runs. The XRD traces were carried out in Figure 3. The relevant data were summarized in Table 2. In Figure 3(a), the sample heated at 68 °C shows two diffraction peaks at $2\theta = 3.84^\circ$ and $2\theta = 25.87^\circ$ owing to the self-assembly by halves. In heating, both of Figure 3(b) and (c) exhibit that there is a sharp scattering peak (75 °C, $2\theta = 3.84^\circ$; 95°, $2\theta = 3.84^\circ$) along with two weak peaks (75 °C, $2\theta = 6.70^\circ$ and 7.44° ; 95 °C, $2\theta = 6.69^\circ$ and 7.45°) in the small-angle region, respectively. The calculated d -spacings of 22.99 Å, 13.18 Å, and 11.87 Å at 75 °C and 22.99 Å, 13.20 Å, and 11.86 Å at 95 °C, confirmed the interplanar d -spacing ratio of $1:1/\sqrt{3}:1/\sqrt{4}$ for the $[d_{100}]$, $[d_{110}]$ and $[d_{200}]$ planes in a columnar hexagonal mesophase. In the wide-angle region, a broad diffuse halo at $2\theta = 15\text{--}30^\circ$ arising from the molten alkyl chains and a subtle reflection peak at approximately $2\theta = 25.80^\circ$ (3.44 Å) corresponding to the π - π stacking distance of the closest PBI cores for $[d_{001}]$ plane were clearly observed at both 75 °C and 95 °C in heating. Based on these reflections, the observed textures (Figure 2(a)) and DSC data, it proves strongly the existence of the columnar hexagonal mesophase with a temperature range from 61 °C to 137 °C on heating.

Table 2 Summary of the structural information and lattice parameters in mesophases for LC 3 (derived from variable-temperature XRD diffraction experiments)					
T [°C].	Cycle state	Phase ^[a]	d_{100} [Å]	a ^[b] [Å]	c ^[c] [Å]
68	heating	Col _h	22.99	26.55	3.44
75	heating	Col _h	22.99	26.55	3.43
95	heating	Col _h	22.99	26.55	3.45
158	heating	U	/	/	/
142	cooling	Col _h	22.87	26.41	3.44
[a] Col _h = hexagonal columnar mesophase, U = uncertain mesophase;					
[b] $a = \sqrt{4/3 \times d_{200}^2}$;					
[c] Intracolumnar layer spacing c [Å].					

However, only one reflection at $2\theta = 2.10^\circ$ (42.04 Å) in the low-angle region was monitored in heating, and it even remained unchanged in the temperature range from 137 °C to 182 °C. Figure 3(d) was recorded at 158 °C in heating. By comparison to the diffraction profiles of samples at 75 °C and 95 °C in heating (Figures 3(b) and (c)), no more scattering information was acquired in Figure 3(d). Thus, the mesophase model for LC **3** was ill-defined with raising the temperature from 137 °C to 182 °C upon second heating, which was consistent with the results of DSC and POM measurements from 137 °C to 182 °C upon second heating. This observation also indicated that the fluorescein fragment dispersed within the mobile aliphatic chains rather than in the perylene stacks. On the other hand, when the sample was annealed from the isotropic liquid state at a rate of 2.0 °C min⁻¹, only one XRD pattern was measured during 175 °C to 58 °C in cooling process and the XRD trace (Figure 3(e)) at 142 °C served as representative. The dominating d -spacing ratio of the [d_{100}] ($2\theta = 3.86^\circ$, 22.87 Å), [d_{110}] ($2\theta = 6.68^\circ$, 13.22 Å) and [d_{200}] ($2\theta = 7.44^\circ$, 11.87 Å) planes were also 1:1/ $\sqrt{3}$:1/ $\sqrt{4}$, similar to the scattering peaks in figures 3(b) and (c). This observation indicated that a columnar hexagonal mesophase could be processed over a broad temperature range from 175 °C and 58 °C on cooling. Moreover, the 2D correlation of a columnar hexagonal mesophase is again present in cooling process. This could be explained that the molecular motion of PBI **3** was reduced and the fluorescein fragment dispersed within the mobile aliphatic chains rather than in the perylene stacks. In addition, the average lattice parameter ($a = 26.48$ Å) of LC **3** nears the space length (~ 29.54 Å) between PBI core and fluorescein fragment (furnished with Chem 3D Pro 17 software from Cambridge Soft). Taking together with the results of DSC, POM and XRD experiments, the integration of PBI-fluorescein-PBI **3** made a hexagonal columnar model from 61 to 137 °C in heating as well as a broad temperature range of 117 °C in cooling, whilst the mesophase model could not be ascertained between 137 °C and 182 °C in heating. Due to the orderless dispersion of fluorescein might influence on the ordered columnar hexagonal mesophase of perylene skeleton and resulted in the

imperfect XRD diffraction model for mesophase of compound **3**, the signals of XRD diffraction became broad than that of normal perylene liquid crystals (as shown in Figure 3).

Photophysical properties

The photophysical properties of PBI **3** were investigated by the UV-vis absorption and fluorescence spectra. The solvent effect for absorption and fluorescence spectra of PBI **3** was demonstrated in Figure S5 and S6, respectively (see the ESI†). The mirror-image symmetry could be observed between the emission and absorption spectra in various organic solvents (10 μ M solutions). On account of the excellent fluorescence of PBI **3** in THF solvent, THF was chosen for exploring efficiently the emission behaviour of PBI **3**. To compare the photophysical properties of PBI **1**, PBI **3**, and fluorescein raw material, their absorption and emission spectra, measured within 5 min of dispersing them in THF solvent (10 μ M), were presented in Figure 4 and 5, respectively. The relevant data was summarized in Table 3. In Figure 4, the absorption spectrum of fluorescein raw material exhibits two distinctive peaks at 456 and 485 nm in the range of 400- 500 nm due to its lactone and quinoid structures. When compared to the spectrum of PBI **1** with three symbolic bands of 0-2, 0-1, and 0-0 transitions positioned at 446, 534, and 575 nm, the absorption spectrum of PBI **3** exhibits the similar signature of perylene core and the unchanged absorption maxima. Whereas the absorption band of PBI **3** at around 446 nm exhibited a considerably improved profile, the absorbance intensity ratios of peak at 575 nm to that at 446 nm in the absorption spectra of PBI **1** was higher than that of PBI **3**. The ratio values were 2.33 and 1.45 for PBI **1** and PBI **3**, respectively. These results indicated that the absorption of PBI **3** overlaps the absorption of fluorescein fragment in the range of 400-500 nm, and that no electronic coupling existed between PBI chromophores and fluorescein fragment in the ground state.

Table 3 Photophysical properties of PBI 3 , PBI 1 , and fluorescein 2 in solution (10 μ M)							
Compd.	λ_{abs} (nm)	λ_{em} (nm)	Stokes shift nm (cm^{-1})	τ_{f} [a] (ns)	τ_{f} [b] (ns)	ϕ_{f} [a]	ϕ_{f} [b]
1	575	616	41 (1158)	2.89	2.90	0.35	0.80
2	456/485	540	55 (2100)	/	/	/	/
3	572	616	44 (1249)	3.27	3.03	0.86	0.74
[a] Excited at 450 nm in THF solution; [b] Excited at 550 nm in THF solution.							

As shown in Figure 5, the emission spectrum of fluorescein raw material displayed a band at 540 nm (λ_{ex} = 450 nm). PBI **1** had an emission peak concentrated at 616 nm (λ_{ex} = 550 nm). The fluorescence spectrum of target PBI **3** also exhibited a peak at 616 nm (λ_{ex} = 550 nm) due to the substitution at N-imide positions of the PBI core. When selectively excited at λ_{ex} = 450 nm for efficient excitations of the PBI chromophores and fluorescein fragment, the emission spectrum of PBI **3** just showed an enhanced band located at 616 nm, where the intensity was 1.5-fold higher than that of the substantial excitation of

PBI **3** at $\lambda_{\text{ex}} = 550$ nm, indicating the intramolecular FRET between the PBI chromophores and fluorescein fragment as excited at 450 nm.

Moreover, the fluorescence quantum yield (ϕ_f) of PBI **3** is 0.86 and 0.74 (in Table 3) when selectively excited at 450 nm and 550 nm in pure THF solution, respectively. It should be noted that, when excited at 550 nm in pure THF solution, the fluorescence quantum yield (ϕ_f) of PBI **3** is 0.74, matching rather closely with those of PBI **1** (0.80). However, when excited at 450 nm in pure THF solution, the fluorescence quantum yield (ϕ_f) of PBI **3** exhibits remarkable value of 0.86 relative to PBI **1** (0.35), which is further supported by the intramolecular FRET between the PBI chromophores and fluorescein segment as excited at 450 nm. Similarly, the principle of FRET also greatly affects the fluorescence lifetime τ_f (ns) of PBI **3**. The τ_f value of PBI **3** (3.27) is greater than PBI **1** (2.89) as excited at 450 nm. The above discussion demonstrated that the PBI **3** showed different fluorescence specificities due to the intramolecular FRET between the PBI chromophores and fluorescein fragment when the fluorescein fragment was excited at 450 nm. On the other hand, probably because PBI **3** was reciprocally intertwined with a complicated aggregation, the very weakened fluorescence intensity of PBI **3** was detected in solid state. The proposed FRET mechanism for PBI **3** was described in Figure 6.

Conclusion

A novel well-defined perylene liquid crystal with two mesogenic PBIs unit and one fluorescein unit linked by soft spacers at the N-imide position, was successfully obtained and well characterized by NMR, FT-IR, elemental analyses, and MALDI-MS. The mesophase model of target LC was determined to form a hexagonal columnar mesophase and an uncertain phase in heating. The hexagonal columnar mesophase existed stably from 175.6 °C to 58.6 °C on cooling. The fluorescence intensity of PBI **3** excited at 450 nm was 1.5-fold higher than that of the substantial excitation of PBI **3** at 550 nm, giving possible strategy to enhance fluorescence via FRET effect for PBI-based LC.

Declarations

Acknowledgements We are grateful for the National Natural Science Foundation of China (No: 21406036), Fujian Science, Technology Project (No. 2019N0010) and the Key Research Program in Neijiang Normal University (2020).

Authors' Contributions M. Z.: experiments and data treatment; M. C.: synthesis of the target compound; H. G.: some measurements of fluorescence and mesomorphic properties; F. Y.: study design and writing of the manuscript.

Funding The study was supported by the National Natural Science Foundation of China (No: 21406036), Fujian Science, Technology Project (No. 2019N0010) and the Key Research Program in Neijiang Normal

University (2020).

Data Availability All the data and materials from this manuscript will be made available on request.

Compliance with Ethical Standards

Competing Interests No potential conflict of interest was reported by the authors.

Ethical Approval Not applicable.

References

1. Zou D, Yang FF, Zhuang QX et al (2019) Perylene diimide-based electron-transporting material for perovskite solar cells with undoped poly(3-hexylthiophene) as hole-transporting material. *ChemSusChem* 12:1155- <https://doi.org/10.1002/cssc.201802421>
2. Duan YW, Xu XP, Yan H et al (2017) Pronounced effects of a triazine core on photovoltaic performance-efficient organic solar cells enabled by a PDI trimer-based small molecular acceptor. *Adv Mater* 29:1605115. <https://doi.org/10.1002/adma.201605115>
3. Dayneko SV, Hendsbee AD, Welch GC (2018) Combining facile synthetic methods with greener processing for efficient polymer-perylene diimide based organic solar cells. *Small Methods* 2:1800081. <https://doi.org/10.1002/smtd.201800081>
4. Duan YW, Xu XP, Li Y et al (2017) Chalcogen-atom-annulated perylene diimide trimers for highly efficient nonfullerene polymer solar cells. *Macromol Rapid Commun* 38:1700405. <https://doi.org/10.1002/marc.201700405>
5. Gupta RK, Dey A, Singh A et al (2019) Heteroatom bay-annulated perylene bisimides: New materials for organic field effect transistors. *ACS Appl Electron Mater* 1:1378- <https://doi.org/10.1021/acsaelm.9b00004>
6. Matussek M, Filapek M, Gancarz P et al (2018) Synthesis and photophysical properties of new perylene bisimide derivatives for application as emitting materials in OLEDs. *Dyes Pigments* 159:590- <https://doi.org/10.1016/j.dyepig.2018.07.006>
7. Miao H, Yang J, Peng GL et al (2019) Enhancement of the degradation ability for organic pollutants via the synergistic effect of photoelectrocatalysis on a self-assembled perylene diimide (SA-PDI) thin film. *Sci Bull* 64:896- <https://doi.org/10.1016/j.scib.2019.05.006>
8. Zhu MG, Guo HY, Cai KC et al (2017) Novel fluorescence-enhancing effect based on light-induced E/Z isomerization of perylene diimides with Schiff-base groups on bay-positions. *Dyes Pigments* 140:179- <https://doi.org/10.1016/j.dyepig.2017.01.048>
9. Lü BZ, Chen YF, Li PY et al (2019) Stable radical anions generated from a porous perylene diimide metal-organic framework for boosting near-infrared photothermal conversion. *Nat Commun* 10:767. <https://doi.org/10.1038/s41467-019-08434-4>

10. Schulze M, Steffen A, Würthner F (2015) Near-IR phosphorescent ruthenium(II) and iridium(III) perylene bisimide metal complexes. *Angew Chem Int Ed* 54:1570-
<https://doi.org/10.1002/anie.201410437>
11. Wang Z, Wang G, Chang X et al (2019) A perylene bisimide-contained molecular dyad with high-efficient charge separation: Switchability, tunability, and applicability in moisture detection. *Adv Funct Mater* 29:1905295. <https://doi.org/10.1002/adfm.201905295>
12. You SS, Cai Q, Zheng Y et al (2014) Perylene-cored star-shaped polycations for fluorescent genevectors and bioimaging. *ACS Appl Mater Interfaces* 6:16327-
<https://doi.org/10.1021/am5045967>
13. Makkad SK, Asha SK (2017) π -Conjugated chromophore incorporated polystyrene nanobeads as single optical agent for three-channel fluorescent probe in bioimaging application. *ACS Biomater Sci Eng* 3:1788- <https://doi.org/10.1021/acsbiomaterials.7b00259>
14. Sun PF, Yuan PC, Wang GN et al (2017) High density glycopolymers functionalized perylene diimidenanoparticles for tumor-targeted photoacoustic imaging and enhanced photothermal therapy. *Biomacromolecules* 18:3375- <https://doi.org/10.1021/acs.biomac.7b01029>
15. Kim YO, Park SJ, Jung BY et al (2018) Solid-phase synthesis of peptide-conjugated perylene diimidebolaamphiphile and its application in photodynamic therapy. *ACS Omega* 3:5896-
<https://doi.org/10.1021/acsomega.8b00040>
16. Song Y, Zhang W, He S et al (2019) Perylene diimide and luminol as potential-resolved electrochemiluminescence nanoprobe for dual target immunoassay at low potential. *ACS Appl Mater Interfaces* 11:33676- <https://doi.org/10.1021/acsami.9b11416>
17. Sethy R, Kumar J, Métivier R et al (2017) Enantioselective light harvesting with perylene diimide guests on self-assembled chiral naphthalene diimide nanofibers. *Angew Chem Int Ed* 56:15053-
<https://doi.org/10.1002/anie.201707160>
18. Spenst P, Würthner F (2015) A perylene bisimide cyclophane as a “turn-on” and “turn-off” fluorescence probe. *Angew Chem Int Ed* 127:10303- <https://doi.org/10.1002/ange.201503542>
19. Würthner F, Bauer C, Stepanenko V et al (2008) A black perylene bisimide super gelator with an unexpected J-type absorption band. *Adv Mater* 20:1695-
<https://doi.org/10.1002/adma.200702935>
20. Han DX, Han JL, Huo SW et al (2018) Proton triggered circularly polarized luminescence in orthogonal- and co-assemblies of chiral gelators with achiral perylene bisimide. *Chem Commun* 54:5630- <https://doi.org/10.1039/C8CC02777C>
21. Görl D, Soberats B, Herbst S et al (2016) Perylene bisimide hydrogels and lyotropic liquid crystals with temperature-responsive color *Chem Sci* 7:6786-6790. <https://doi.org/10.1039/C6SC02249A>
22. Würthner F, Thalacker C, Diele S et al (2001) Fluorescent J-type aggregates and thermotropic columnar mesophases of perylene bisimide dyes. *Chem Eur J* 7:2245- [https://doi.org/10.1002/1521-3765\(20010518\)7:10<2245::AID-CHEM2245>3.0.CO;2-W](https://doi.org/10.1002/1521-3765(20010518)7:10<2245::AID-CHEM2245>3.0.CO;2-W)

23. Eccher J, Zajackowski W, Faria GC et al (2015) Thermal evaporation versus spin-coating: Electrical performance in columnar liquid crystal OLEDs. *ACS Appl Mater Interfaces* 7:16374-
<https://doi.org/10.1021/acsami.5b03496>
24. Gupta RK, Sudhakar AA (2019) Perylene-based liquid crystals as materials for organic electronics applications. *Langmuir* 35:2455- <https://doi.org/10.1021/acs.langmuir.8b01081>
25. Funahashi M (2014) Nanostructured liquid-crystalline semiconductors – a new approach to soft matter electronics. *J Mater Chem C* 2:7451- <https://doi.org/10.1039/C4TC00906A>
26. Kong X, Gong H, Liu P et al (2018) Synthesis and investigation on optoelectronic properties of mesogenic triphenylene–perylene dyads linked by ethynylphenyl bridges. *New J Chem* 42:3211-3221. <https://doi.org/10.1039/C7NJ04328G>
27. Guo HY, Zhu MG, Wang ZS et al (2016) Triphenylene–perylene–triphenylene triads with bay-substituents: synthesis, mesomorphism, and electron transfer properties. *Tetrahedron Lett* 57:4191-
<https://doi.org/10.1016/j.tetlet.2016.08.004>
28. Xiao Y, Su X, Sosa-Vargas L et al (2016) Chemical engineering of donor–acceptor liquid crystalline dyads and triads for the controlled nanostructuring of organic semiconductors. *CrystEngComm* 18:4787-4798. <https://doi.org/10.1039/C6CE00365F>
29. Lee KJ, Woo JH, Xiao YM et al (2016) Structure-charge transfer property relationship in self-assembled discotic liquid-crystalline donor–acceptor dyad and triad thin films. *RSC Adv* 6:57811-
<https://doi.org/10.1039/C6RA08039A>
30. Zhao KQ, An LL, Zhang XB et al (2015) Highly segregated lamellocolumnar mesophase organizations and fast charge carrier mobility in new discotic donor–acceptor *Chem Eur J* 21:10379-10390. <https://doi.org/10.1002/chem.201500889>
31. Zhu MG, Guo HY, Yang FF et al (2016) Novel room-temperature perylene liquid crystals: synthesis of 1,7-dibrominated cholesterol–perylene bisimides with different ester-bridging chains and their mesomorphic properties. *Liq Cryst* 43:1875- <https://doi.org/10.1080/02678292.2016.1218073>
32. Zhu MG, Guo HY, Yang FF et al (2017) Synthesis, mesomorphic and photophysical properties of novel triads and pentads of perylene liquid crystals with cholesterol units at the bay-position. *RSC Adv* 7:4320- <https://doi.org/10.1039/C6RA27003D>
33. Zhang TJ; Sun DM; Ren XK et al (2013) Synthesis and properties of siloxane modified perylene bisimide discotic liquid crystals. *Soft Matter* 9:10739- <https://doi.org/10.1039/C3SM52054D>
34. Gao BX, Xia DF, Zhang LC et al (2011) Helical columnar liquid crystals based on dendritic peptides substituted perylene bisimides. *J Mater Chem* 21:15975- <https://doi.org/10.1039/C1JM13144C>
35. Funahashi M, Yamaoka M, Takenami K et al (2013) Liquid-crystalline perylene tetracarboxylic bisimide derivatives bearing cyclotetrasiloxane moieties. *J Mater Chem C* 1:7872-
<https://doi.org/10.1039/C3TC31567C>
36. Zeng Y, Lu L, Gao T et al (2018) Synthesis, helical columnar liquid crystalline structure, and charge transporting property of perylene diimide derivative bearing oligosiloxane *Dyes Pigments* 152:139-145. <https://doi.org/10.1016/j.dyepig.2018.01.048>

37. Ben HJ, Ren XK, Song B et al (2017) Synthesis, crystal structure, enhanced photoluminescence properties and fluoride detection ability of S-heterocyclic annulated perylene diimide-polyhedral oligosilsesquioxane dye. *J Mater Chem C* 5:2566- <https://doi.org/10.1039/C6TC05171E>
38. Hecht M, Schlossarek T, Stolte M et al (2019) Photoconductive core-shell liquid-crystals of a perylene bisimide J-aggregate donor-acceptor dyad. *Angew Chem Int Ed* 58:12979-
<https://doi.org/10.1002/anie.201904789>
39. Meng L, Wu QM, Yang FF et al (2015) Novel room-temperature thermotropic liquid crystals: Synthesis and mesomorphism of gallic-perylene-gallic trimers. *New J Chem* 39:72-
<https://doi.org/10.1039/C4NJ00993B>
40. Zhu MG, Chen YZ, Guo HY et al (2018) Perylene liquid crystals with multiple alkyl chains: investigation of the influence of peripheral alkyl chain number on mesomorphic and photophysical properties. *New J Chem* 42:8998-<https://doi.org/10.1039/C8NJ00480C>
41. Zhu MG, Guo HY, Yang FF et al (2016) Novel perylene liquid crystals: Investigation of the influence of bay-substituents on mesomorphism and photophysical property. *Dyes Pigments* 133:387-
<https://doi.org/10.1016/j.dyepig.2016.06.021>
42. Zhu MG, Zhuo YZ, Cai KC et al (2017) Novel fluorescent perylene liquid crystal with diphenylacrylonitrile groups: Observation of a large pseudo Stokes shift based on AIE and FRET effects. *Dyes Pigments* 147:343- <https://doi.org/10.1016/j.dyepig.2017.08.027>
43. Zhu MG, Zhuo YZ, Guo HY et al (2018) Enhanced fluorescence in both solution and solid state for perylene liquid crystals with six peripheral alkyl substituents on 1,6,7,12-bay positions and imides positions. *J Lumin* 194:264- <https://doi.org/10.1016/j.jlumin.2017.10.049>
44. Zhu MG, Chen YX, Zhang XY et al (2018) Perylene bisimide with diphenylacrylonitrile on side-chain: strongly fluorescent liquid crystal with large pseudo Stokes shift based on AIE and FRET *Soft Matter* 14:6737-6744. <https://doi.org/10.1039/C8SM01183D>
45. Hippus C, van Stokkum IHM, Zangrando E et al (2008) Ground- and excited-state pinched cone equilibria in calix[4]arenes bearing two perylene bisimide dyes. *J Phys Chem C* 112:14626-
<https://doi.org/10.1021/jp804068b>
46. Qu JF, Mu Z, Lai HJ et al (2018) Effect of the molecular configuration of perylene diimide acceptor on charge transfer and device performance. *ACS Appl Energy Mater* 1:833-
<https://doi.org/10.1021/acsaem.7b00277>
47. Petrella A, Cremer J, Cola LD et al (2005) Charge transfer processes in conjugated triarylamine-oligothiophene-perylene monoimide dendrimers. *J Phys Chem A* 109:11687-
<https://doi.org/10.1021/jp0510995>
48. Sinks LE, Rybtchinski B, Imura M et al (2005) Self-Assembly of photofunctional cylindrical nanostructures based on perylene-3,4,9,10-bis(dicarboximide). *Chem Mater* 17:6295-
<https://doi.org/10.1021/cm051461s>
49. Zhao Z, Gao SM, Zheng XY et al (2018) Rational design of perylene diimide-substituted triphenylethylene to electron transporting aggregation-induced emission luminogens

- (AIEgens) with highmobility and near-infrared emission. *Adv Funct Mater* 28:1705609. <https://doi.org/10.1002/adfm.201705609>
50. Prajitha KP, Asha SK (2016) The synthesis and structural characterization of twin liquid crystalline perylenebisimides. *New J Chem* 40:8471- <https://doi.org/10.1039/C6NJ00524A>
 51. Lin X, Hirono M, Seki T et al (2013) Covalent modular approach for dimension-controlled self-organization of perylene bisimide dyes. *Chem Eur J* 19:6561- <https://doi.org/10.1002/chem.201300039>
 52. Kobayashi T, Urano Y, Kamiya M et al (2007) Highly activatable and rapidly releasable caged fluorescein derivatives. *J Am Chem Soc* 129:6696- <https://doi.org/10.1021/ja070376d>
 53. Zhang RL, Zhao J, Han GM et al (2016) Real-time discrimination and versatile profiling of spontaneous reactive oxygen species in living organisms with a single fluorescent probe. *J Am Chem Soc* 138:3769- <https://doi.org/10.1021/jacs.5b12848>
 54. Hammers MD, Taormina MJ, Cerda MM et al (2015) A bright fluorescent probe for H₂S enables analyte-responsive, 3D imaging in live zebrafish using light sheet fluorescence microscopy. *J Am Chem Soc* 137:10216- <https://doi.org/10.1021/jacs.5b04196>
 55. Lv J, Wang F, Qiang J et al (2017) Enhanced response speed and selectivity of fluorescein-based H₂S probe via the cleavage of nitrobenzene sulfonyl ester assisted by ortho aldehyde groups. *Biosens Bioelectron* 87:96- <https://doi.org/10.1016/j.bios.2016.08.018>
 56. Urano Y, Kamiya M, Kanda K et al (2005) Evolution of fluorescein as a platform for finely tunable fluorescence probes. *J Am Chem Soc* 127:4888- <https://doi.org/10.1021/ja043919h>
 57. Ogasawara H, Grzybowski M, Hosokawa R et al (2018) A far-red fluorescent probe based on a phospho-fluorescein scaffold for cytosolic calcium imaging. *Chem Commun* 54:299- <https://doi.org/10.1039/C7CC07344E>
 58. Fan T, Shi R, Tang H, Guo H et al (2020) First fluorescein liquid crystals: synthesis, mesomorphic and fluorescence properties of fluorescein-triphenylene dimers. *Liq Cryst* 47:1762-1771. <https://doi.org/10.1080/02678292.2020.1725986>
 59. Guang SY, Tian JC, Wei G et al (2017) A modified fluorescein derivative with improved water-solubility for turn-on fluorescent determination of Hg²⁺ in aqueous and living cells. *Talanta* 170:89- <https://doi.org/10.1016/j.talanta.2017.03.108>
 60. Guo HY, Lin LB, Qiu JB et al (2017) Phenylacrylonitrile-bridging triphenylene dimers: The columnar liquid crystals with high fluorescence in both solid state and solution. *RSC Adv* 7:53316- <https://doi.org/10.1039/C7RA10218F>
 61. Fang XT, Guo HY, Yang FF et al (2017) Near-infrared fluorescent and columnar liquid crystal: synthesis, and photophysical and mesomorphic properties of triphenylene-Bodipy-triphenylene triad. *RSC Adv* 7:23657- <https://doi.org/10.1039/C7RA00982H>

Figures

Figure 1

DSC cycle of target compound 3 exhibiting the second heating and first cooling curves at the scan rate of 5 °C min⁻¹ under a nitrogen atmosphere.

Figure 2

POM images of the fluorescein-bridged perylene dimer 3: (a) the typical pseudo-focal conical textures of the LCs were observed at 95 °C during heating ($\times 200$); (b) the patchy textures of the LCs were observed at 158 °C during heating ($\times 200$); (c) the typical pseudo-focal conical textures of the LCs were observed after cooling from the isotropic phase to 142 °C ($\times 400$).

Figure 3

The variable-temperature XRD traces of PBI 3 in mesophases: (a-d) the scattering traces were measured at 68 °C, 75 °C, 95 °C, and 158 °C in second heating, respectively; (e) the scattering trace was recorded at 142 °C in first cooling.

Figure 4

The UV/Vis absorption spectra of PBI 1, PBI 3, and fluorescein raw material in THF (10 μ M solutions)

Figure 5

The emission spectra of PBI 1 (black, $\lambda_{ex} = 550$ nm), PBI 3 (red, $\lambda_{ex} = 550$ nm; pink, $\lambda_{ex} = 450$ nm) and fluorescein raw material (blue, $\lambda_{ex} = 450$ nm) in THF (10 μ M solutions)

Figure 6

Schematic of the mechanism of FRET effect for PBI 3 in the THF solution.