Controlled Release of Acetyl Salicylic Acid in Intelligent Hydrogel Based on Cross-linked O-Carboxymethyl Chitosan

Yiguang Wu

Shenzhen University

Muhammad Shahid Riaz Rajoka

Shenzhen University

Jun Zeng

Shenzhen University

Hafiza Mahreen Mehwish

Shenzhen University

Wenli Liu

Shenzhen University

Liqing Zhao (✉ lqzhao@szu.edu.cn)

Shenzhen University

Research Article

Keywords: O-carboxymethyl chitosan, acetylsalicylic acid, hydrogel, controlled drug release, pH sensitivity

Posted Date: March 18th, 2021

DOI: <https://doi.org/10.21203/rs.3.rs-312464/v1>

License: © ⓘ This work is licensed under a Creative Commons Attribution 4.0 International License.

[Read Full License](#)

Controlled Release of Acetylsalicylic Acid in pH sensitive Hydrogel Prepared by Cross-linking O-Carboxymethyl Chitosan

Yiguang Wu^{1#}, Muhammad Shahid Riaz Rajoka^{1,2#}, Jun Zeng¹, Hafiza Mahreen Mehwish³, Wenli Liu¹, Liqing Zhao^{1*},

¹College of Chemistry and Environmental Engineering, Shenzhen University, Shenzhen, Guangdong 518060, China

² Food and Feed Immunology Group, Graduate School of Agricultural Science, Tohoku University, Sendai 980-8572, Japan.

³School of Pharmaceutical Science, Health Science Center, Shenzhen University, Shenzhen, Guangdong 518060, China

Correspondence author

Professor Liqing Zhao

Tel: +86-755-26550395

Fax: +86-755-26733095

E-mail: lqzhao@szu.edu.cn

These authors contributed equally

Author's Email IDs

Yiguang Wu (yebsd@sina.com)

Muhammad Shahid Riaz Rajoka (shahidrajoka@yahoo.com)

Jun Zeng (2172226008@email.szu.edu.cn)

Hafiza Mahreen Mehwish (mahreen.mehwish@yahoo.com)

Xia Lixin (xialixin@126.com)

Wenli Liu (61950096@qq.com)

Liqing Zhao (lqzhao@szu.edu.cn)

Abstract

Drug-loading hydrogels were prepared from O-carboxymethyl chitosan (O-CMCS) with a high degree of substitution and different deacetylation degree (DD) using acetylsalicylic acid as drug and glutaraldehyde as a cross-linking agent. Also, the DD's effect on the controlled drug release performance of drug-loading particle was explored. The results showed that the hydrogels and particles were prepared from 5 g of O-CMCS solution (4.0 wt.%), 2.5 g of sodium acetylsalicylate solution (8.0 wt.%), and 1.5 mL of glutaraldehyde solution (1.0 wt.%). The interior pore size of the particle (DD=51%) was between 50 and 100 μ m, and its cumulative drug release ratios in the simulated gastric and intestinal juices were of the top values. The drug release of the drug-loading particle was proved to be obviously pH sensitive and it can be applied as a colonic drug.

Keywords: O-carboxymethyl chitosan; acetylsalicylic acid; hydrogel; controlled drug release; pH sensitivity

Introduction

Besides the discovery of the huge number of therapeutic agents, few have shown the therapeutic success after systematic administration because of their low bioavailability[1]. Nowadays, numerous approaches including the in situ gelling system have been developed to improve the bioavailability of therapeutic agents [2]. In these in situ gelling systems, the therapeutic agents such as drugs can be encapsulated into the matrix which reduced the unexpected side effect associated with systematic administration [3]. The early development of these hydrogels system mainly focuses on the use of synthetic materials such as copolymers of *N* isopropylacrylamide and poly(ethylene glycol)/poly(lactic acid) block copolymers [4]. These materials were suitable for local drug delivery, but on the other hand, the non-biodegradability nature of these materials limits their clinical applications [5]. Therefore, recently the focus has been oriented towards naturally polymers having biodegradability and biocompatibility properties that can also form easily hydrogels [5-6]. Among natural polymers, the chitosan obtained from chitin has gained considerable attention in the drug delivery system due to its biodegradability and biocompatibility nature [7].

A recent study showed that the chitosan and its derivative can be used as a carrier of drug delivery system with no reported toxicity along with excellent biocompatibility and biodegradability[8]. When chitosan was modified by carboxymethylation and deacetylation, the corresponding derivatives carboxymethyl chitin/chitosan (CMCH/CMCS) were found to be water soluble and showed excellent biocompatibility of an amphoteric polymer [9]. The CMCH had been used as tablet additives by Huang et

al. (2012), and the CMCS is currently being investigated in this work as a drug carrier. Theoretically, in the acidic conditions, CMCS with a high degree of substitution (DS) shows many carboxyl (-COOH) groups. However, in the neutral or alkaline condition, these -COOH groups can be transformed into -COO⁻. Consequently, CMCS itself shall be pH sensitive. Interestingly, the molecular chain of CMCS contains certain amounts of -NH₂, which can react with glutaraldehyde to form the Schiff Base. Therefore, it's hopeful to prepare the drug-loading hydrogel by cross-linking the drug-containing CMCS solution with glutaraldehyde in order to control the release of interior drug by its contraction and expansion due to the carboxyl's conversion under different pH environments [10]. Hence, hydrogels themselves are promising biomaterials with basic ability to control the transportation of nutrients, O₂, and other water-soluble metabolites through diffusion. They also have the capability of many other desirable physicochemical indications and of being a cell growth substrate.

The acetylsalicylic acid (aspirin) is non-steroidal drugs having anti-inflammatory, analgesic, and antipyretic effects [11]. Furthermore, the oral intake of a high dose of acetylsalicylic acid may have undesirable side effects including tinnitus, gastric bleeding, and ulcers [12]. Therefore, it would be better if the function of control release of acetylsalicylic acid combines on to the acetylsalicylic acid containing drugs so that the acetylsalicylic acid would be gradually released to form a proper drug concentration in the plasma. Therefore, the combination of chitosan as a drug carrier along with the acetylsalicylic acid drug would be an excellent candidate for the polymeric drug for development of controlled release of acetylsalicylic acid.

In this paper, a series of O-carboxymethyl chitosan (O-CMCS) with a high DS and different deacetylation degrees (DD) were prepared from the primary raw material, chitin. The corresponding hydrogels were prepared by cross-linking O-CMCS solution containing acetylsalicylic acid with glutaraldehyde, while the drug-loading particles were prepared by drying the drug-loading hydrogels. Also, the controlled drug release performance of these drug-loading particles was carefully examined.

Experimental

Preparation and structural parameters' determination of series of O-CMCS

A two-step method was used to prepare a series of O-CMCS with a high DS and different DD. In the first step, O-carboxymethyl chitin (O-CMCH) with a high DS and a low DD was developed. This reaction was made under the optimum conditions including the molar ratio (chitin unit to chloroacetic acid to NaOH), the concentration of NaOH, the reaction temperature, and the reaction time as outlined elsewhere[13]. In the second step, the series of O-CMCS with a high DS and different DD were obtained. Here, the concentration of NaOH, the reaction temperature and the reaction time were all controlled.

200 g of chitin powder was added into 1,300 mL of NaOH solution (23 wt.%) with stirring, and the slurry was vacuumized overnight by a water pump to form alkalized chitin. As a dispersant, an

appropriate amount of isopropyl alcohol was added into the alkalized chitin, and the suspension was stirred at 60°C. Then, isopropyl alcohol solution containing 326 g of chloroacetic acid was added; allowed to react for 4 h, and filtered. The filtered residue was dissolved in pure water and neutralized with concentrated HCl solution. Ultrafiltration membrane with a molecular weight retention value of 10,000 was used to ultrafiltrate 5 times where the volume compression ratio was 1/5 each time. Finally, the concentrated solution was dried in an oven at 80°C and then placed in a vacuum oven at 60°C overnight to acquire 20.24 g of O-CMCH, F1.

Furthermore, 2 g of F1 was added to 70 mL of concentrated NaOH solution to dissolve it entirely. After deacetylation reaction at a certain temperature for a definite time, the solution was neutralized with concentrated HCl solution. Subsequently, ultrafiltration membrane with a molecular weight retention value of 10,000 was used again for 5 times' ultrafiltration. As usual, in each of these times, the volume compression ratio was 1/5. Finally, the concentrated solution was dried in an oven at 80°C and placed in a vacuum oven overnight at 60°C to obtain O-CMCS, F2~F5. Respective reaction conditions (NaOH concentration, reaction temperature and time) of F2~F5 were given in Table 1.

Besides, 0.2 g of each O-CMCS sample was added into 50 mL of NaCl solution (0.1 mol/L) in a conical flask and then stirred until completely dissolved. An aliquant amount of HCl solution (0.1 mol/L) was used to adjust the pH value to 3.0, and after that, the solution was titrated with a 0.05 mol/L of standard NaOH solution. Its pH value was verified by a pH meter (Orion 720A, Thermo Scientific, USA) with an interval of 0.04, and the consumption volume (V , mL) of the NaOH solution was recorded. The experimental data were analyzed through a differential titration curve, where: $\Delta\text{pH}/\Delta V$ and V (mL) was earmarked as the ordinate and abscissa, respectively. And the peak pH values for $-\text{COOH}$ and $-\text{NH}_2$ were 5.5 and 9.6, respectively.

The contents of C and N elements in these O-CMCS samples were measured by an Elemental Analyzer (Vario EL III, Elementary, Germany) with high-temperature combustion and complete decomposition methods. For interaction relationships among the DD, the DS, the content ratio of C and N elements, and the titration parameters, Eqs. (1) and (2) were framed.

$$C/N = \frac{[6 + (1 - DD) \times 2 + DS \times 2] \times 12}{1 \times 14} \quad (1)$$

$$DD = c\Delta V \times (203 + DS \times 58 - DD \times 42) / m \quad (2)$$

When Eqs. (1) and (2) were merged, Eqs. (3) and (4) were obtained.

$$DD = \frac{33.83 \times C/N - 29}{m/(c\Delta V) - 16} \quad (3)$$

$$DS = DD + 0.5833 \times C/N - 4 \quad (4)$$

where: C/N is the mass ratio of C and N elements measured from elemental analysis, m (g) is the sample weight used in the titration experiment, c (mol/L) is the concentration of standard NaOH solution, and ΔV (L) is the volumetric difference of standard NaOH solution between the two peaks in differential titration curve.

The calculated DD and DS values of O-CMCS, F2~F5 according to the Eqs. (3) and (4) mentioned above were presented in Table 1.

Preparation and surface morphology observation of the drug-loading particle

Exactly 0.2 g of O-CMCS was completely dissolved in 4.8 g of deionized water. 2.5 g of sodium acetylsalicylate solution (8 wt.%) was added into the O-CMCS solution and stirred continuously. The additional sodium acetylsalicylate solution was prepared by adding 0.8 g of acetylsalicylic acid into 9.2 g of NaHCO₃ solution (5 wt.%) with stirring until it was completely dissolved. The drug-loading hydrogel was then prepared by adding 1.5 mL of glutaraldehyde solution (1 wt.%) into the above-mixed solution with stirring for 10 s, and then it was allowed to stand overnight. The drug-loading particle was prepared by drying the drug-loading hydrogel in a vacuum oven at 60°C for 12 h, and then it was ground to the millimeter scale. The surface morphology of the drug-loading particle was observed by using a field emission scanning electron microscope (JEOL 4000FX, Tokyo, Japan) with ultra-high resolution.

Drug release experimentation

The simulated gastric juice was prepared by mixing 16.4 mL of concentrated HCl and 10 g of pepsin. Deionized water was used to make up to a volume of 1,000 mL which replicated a gastric juice at pH 1.0. On the other hand, the simulated intestinal juice was prepared by mixing potassium dihydrogen phosphate (KH₂PO₄) solution (6.8 g of KH₂PO₄ in 500 mL of deionized water and the pH adjusted to the value of 6.8 by 0.1 mol/L of NaOH solution) and pancreatin solution (10 g of pancreatin) in a same amount of deionized water that was used to fill up to a volume of 1,000 mL in the same way as described above.

The drug release experiments were carried out with the rotating basket method as per the Chinese Pharmacopoeia 2010 Edition [13a, 14]. The 0.05 g of drug-loading particle was loaded in dialysis bag, and then immersed in the 0.5 L of dissolution medium with the stirring speed of 180 ± 1 r/min at $37 \pm 0.5^\circ\text{C}$. The solution samples were taken out at specified time intervals for the respective measurements of acetylsalicylic acid and salicylic acid concentrations using a UV-VIS spectrophotometer (UV-2501PC, Shimadzu, Japan) at 278 and 302 nm for acetylsalicylic acid and salicylic acid, respectively. UV-VIS spectrophotometer also determined the maximum peak wavelengths and the standard working curves for each acid. The following equation (Eq. (5)) was used to express the cumulative release ratio.

$$\text{Cumulative release ratio (\%)} = \frac{cm_2M_rV}{mm_1} \times 100\% \quad (5)$$

where: c (mol/L) is the total concentration of both acetylsalicylic acid and salicylic acid, m (g) is the weight of drug-loading particle used in the experiment, m_1 (0.2 g) is the weight of acetylsalicylic acid loaded in drug-loading particle, m_2 (0.415 g) is the weight of prepared drug-loading particle, V (L) is the volume of the dissolution medium, and M_r is a constant value of 180.16 which represents the molar mass of acetylsalicylic acid.

Statistical analysis

All experiments were performed in triplicate. All data are presented as mean $\pm$ standard deviation (SD). Statistical significance was determined using Student's t-test. The significance level was set at $P < 0.05$.

Results and Discussion

Surface morphology of the drug-loading particle

Figure 1 showed surface morphology observed by SEM of the drug-loading particle prepared from F2 (Table 1). The results reveal that the surface morphologies of the blank and all other drug-loading particles developed from this same organic polymer (O-CMCS) with different DD were similar to each other. It turned out that the drug-loading particles expressed an open pore structure, and the interior pore size of these drug-loading particles was measured and bar-lined between 50 and 100 μm . This structure could raise the contact area between the cross-linked skeleton and dissolution medium, which was beneficial to the formation of a hydrogel.

Drug release performance of the drug-loading particles

As the acetylsalicylic acid released from drug-loading particles, it may be decomposed into the salicylic acid due to the presence of both acidic solution and pepsin in the simulated gastric juice, both acetylsalicylic acid and salicylic acid were detected at pH 1.0, and only acetylsalicylic acid was detected at pH 6.8. The cumulative drug release curves of drug-loading particles based on cross-linked O-CMCS in both simulated gastric and intestinal juices were presented in Fig. 2 and Fig. 3, respectively. As it can be observed, the cumulative drug release ratio of drug-loading particle decreased as the DD of O-CMCS increased, and that of drug-loading particle prepared from O-CMCS with a DD of 51% was the highest. It could be possibly due to the effect of DD on cross-linking density of the carrier. For all drug-loading particles, the weight ratio of O-CMCS to glutaraldehyde was the same, so the cross-linking density of the cross-linked O-CMCS skeleton equally increased as the DD of O-CMCS (amount of $-\text{NH}_2$). Hence, the drug in a corresponding drug-loading particle or hydrogel prepared from O-CMCS with higher DD could not be quickly released.

It is important to emphasize here that the first drug in the drug-loading particle was rapidly released into the simulated gastric juice owe to the liberation of the drug without being encapsulated in the cross-

linking network. After that, its release rate started to slow down, and its cumulative release ratio slowly began to increase as well. For example, the cumulative drug release ratio of drug-loading particle prepared from O-CMCS with a DD of 51% in the simulated gastric juice was only around 25.31% after 720 min. Whereas for all tested drug-loading particles made from the same compound with different DD, both cumulative drug release ratios and release rates in the simulated intestinal juice were all higher than that in the simulated gastric juice. Among them, the highest cumulative drug release ratio of the drug-loading particle prepared from O-CMCS with a DD of 51% in the simulated intestinal juice reached up to the extent of 80% after 720 min (Fig. 3). When the hydrogel was formed by putting a drug-loading particle in an acidic simulated gastric juice, the hydrogen bond density increased owe to the -COOH of the gel network. Soon after that, it appeared that the drug-loading hydrogel contracted and hindered the internal drug release. In addition, the electrostatic attraction between -COOH of acetylsalicylic acid/salicylic acid and few residual -NH₂ of O-CMCS in the acidic simulated gastric juice could possibly bind both acetylsalicylic acid and salicylic acid, and also dedicated to both low cumulative drug release ratio and low release rate of the drug-loading particle in the simulated gastric juice. However, when the same thing was done in neutral simulated intestinal juice, the -COOH of gel network was gradually transformed to -COO⁻. With the repelling action of the negative ions, it was observable that the gel network became loose first, then the drug-loading hydrogel expanded, and finally, the drug was gradually released. Furthermore, the incremental water solubility of acetylsalicylic acid owing to the transformation of -COOH to -COO⁻ in neutral simulated intestinal juice accumulated their diffusion and then elevated both cumulative drug release ratio and release rate of the drug-loading particle. The drug release mechanism of the drug-loading hydrogel in simulated gastric/intestinal juices was shown in Fig. 4.

Besides that, the Zero-order, Higuchi, Logistic, and Weibull drug release kinetics models [14a, 15] were fitted to the drug release kinetics of the drug-loading particle prepared from F2 in the simulated intestinal juice. Those results were shown in Table 2. In another development, the comparison of release kinetics curves tailored by these 4 models with the actual practical experiments was given in Fig. 4. It turned out that both Logistic and Weibull models fitted very well to the experimental results, where their correlation coefficients (R²) were all recorded as 0.99. In addition to that, the release shapes for these 2 models resembled an S-type release as expected.

Conclusion

The drug-controlled release system of a drug-loading hydrogel based on cross-linked O-CMCS was successfully developed. This system proved itself to be reliable and naturally pH sensitive towards the gastric and intestinal conditions in the humans. Consequently, the drug-loading particle can be applied as a colonic drug too.

Author statements

Yiguang Wu: Conceptualization, Methodology, Writing - Original Draft, Formal analysis; **Muhammad Shahid Riaz Rajoka:** Conceptualization, Methodology, Writing - Original Draft, Formal analysis; **Jun Zeng:** Conceptualization, Methodology, Writing - Original Draft, Formal analysis; **Hafiza Mahreen Mehwish:** Software, Validation, Data Curation, Writing - Original Draft; **Xia Lixin:** Funding acquisition, Writing - Review & Editing, Resources; **Wenli Liu:** Validation, Formal analysis, Software, Writing - Original Draft, Writing - Review & Editing; **Liqing Zhao:** Funding acquisition, Project administration, Supervision, Writing - Review & Editing, Investigation.

Conflict of Interest

The authors declare that they have no conflicts of interest.

Acknowledgments

This work was supported by the National Natural Science Foundation of China (21606152 and 31701621), the Natural Science Foundation of Guangdong Province (2016A030313053), the Special Fund for Development of Strategic Emerging Industries in Shenzhen (JCYJ20160520174823939, JCYJ20170817100522830, 20170424181248489), and Fundamental Research Plan (Grant no JCYJ 20170818094217688).

References

- [1] N. Bhattarai, J. Gunn, M. Zhang, *Advanced Drug Delivery Reviews* **2010**, 62, 83-99.
- [2] aD. Ramyadevi, K. S. Rajan, B. N. Vedhahari, K. Ruckmani, N. Subramanian, *Colloids and surfaces. B, Biointerfaces* **2016**, 146, 260-270; bL. Weng, A. Romanov, J. Rooney, W. Chen, *Biomaterials* **2008**, 29, 3905-3913.
- [3] S. B. Makwana, V. A. Patel, S. J. Parmar, *Results in Pharma Sciences* **2016**, 6, 1-6.
- [4] aJ. Zhang, N. A. Peppas, *Macromolecules* **2000**, 33, 102-107; bJ. M. Bezemer, R. Radersma, D. W. Grijpma, P. J. Dijkstra, J. Feijen, C. A. van Blitterswijk, *Journal of Controlled Release* **2000**, 64, 179-192.
- [5] E. Ruel-Gariépy, J.-C. Leroux, *European Journal of Pharmaceutics and Biopharmaceutics* **2004**, 58, 409-426.
- [6] G. Tan, S. Yu, J. Li, W. Pan, *International Journal of Biological Macromolecules* **2017**, 103, 941-947.
- [7] aG. Huang, Y. Liu, L. Chen, *Drug delivery* **2017**, 24, 108-113; bJ. Sarvaiya, Y. K. Agrawal, *Int J Biol Macromol* **2015**, 72, 454-465.
- [8] aP. Geetha, A. J. Sivaram, R. Jayakumar, C. Gopi Mohan, *Carbohydr Polym* **2016**, 142, 240-249; bT. Jain, S. Kumar, P. K. Dutta, *Int J Biol Macromol* **2016**, 82, 1011-1017.

- [9] aA. L. Bukzem, R. Signini, D. M. Dos Santos, L. M. Liao, D. P. Ascheri, *Int J Biol Macromol* **2016**, 85, 615-624; bY. Tan, M. Leonhard, D. Moser, B. Schneider-Stickler, *Carbohydr Polym* **2016**, 149, 77-82.
- [10] aY. F. Liu, K. L. Huang, D. M. Peng, P. Ding, G. Y. Li, *Int J Biol Macromol* **2007**, 41, 87-93; bN. A. Gujarathi, B. R. Rane, J. K. Patel, *Int J Pharm* **2012**, 436, 418-425.
- [11] C. Liu, Y. Wu, L. Zhao, X. Huang, *International Journal of Biological Macromolecules* **2015**, 78, 189-194.
- [12] R. Casado-Arroyo, C. Gargallo, Á. Lanas Arbeloa, *Best Practice & Research Clinical Gastroenterology* **2012**, 26, 173-184.
- [13] aY. J. Wang, E. Assaad, P. Ispas-Szabo, M. A. Mateescu, X. X. Zhu, *Int J Pharm* **2011**, 419, 215-221; bX. Huang, Y. Wu, S. Wei, C. Liao, Q. Chen, *Int J Biol Macromol* **2010**, 47, 223-227.
- [14] aC. Liu, Y. Wu, L. Zhao, X. Huang, *Int J Biol Macromol* **2015**, 78, 189-194; bL. Pachua, B. Mazumder, *International Journal of Biological Macromolecules* **2013**, 61, 333-339.
- [15] aN. Yuksel, A. E. Kanik, T. Baykara, *Int J Pharm* **2000**, 209, 57-67; bF. O. Costa, J. J. Sousa, A. A. Pais, S. J. Formosinho, *Journal of controlled release : official journal of the Controlled Release Society* **2003**, 89, 199-212.

Figures

Figure 1

The surface’s SEM photographs of the drug-loading particle prepared from F2

Figure 2

The cumulative drug release curves of the drug-loading particles in simulated gastric juice

Figure 3

The cumulative drug release curves of the drug-loading particles in simulated intestinal juice

Figure 4

The drug release mechanism of the drug-loading hydrogel in simulated gastric/intestinal juices

Figure 5

The comparison of release kinetics curves fitted by the four models with the experimental

Supplementary Files

This is a list of supplementary files associated with this preprint. Click to download.

- [Table.docx](#)