Bifunctional copper-zinc bimetallic tungstate nanoparticles decorated reduced graphene oxide (CuZnWO₄/rGO) for high-performance photocatalytic and supercapacitor application

Elumalai Dhandapani

J.K.N arts and science

Prabhu S

Periyar university

Navaneethan Duraisamy (✉ naveennanoenergy@gmail.com)

J.K.K Nataraja college of arts and science <https://orcid.org/0000-0001-7285-1742>

Ramesh R

Periyar university

Research Article

Keywords: Bimetallic tungstate, Reduced graphene oxide, Photocatalysis, Supercapacitor

Posted Date: April 22nd, 2021

DOI: <https://doi.org/10.21203/rs.3.rs-350051/v1>

License: © ⓘ This work is licensed under a Creative Commons Attribution 4.0 International License.

[Read Full License](#)

Version of Record: A version of this preprint was published at Journal of Materials Science: Materials in Electronics on June 26th, 2021. See the published version at <https://doi.org/10.1007/s10854-021-06339-x>.

Bifunctional copper-zinc bimetallic tungstate nanoparticles decorated reduced graphene oxide (CuZnWO₄/rGO) for high-performance photocatalytic and supercapacitor application

Elumalai Dhandapani¹, Prabhu S², Navaneethan Duraisamy^{1}, Ramesh R²*

¹Department of Chemistry, J.K.K. Nataraja College of Arts and Science, Komarapalayam, Namakkal, Tamil Nadu, India

²Department of Physics, Periyar University, Salem, Tamil Nadu, India

Corresponding Author Email: naveennanoenergy@gmail.com

Abstract

In the present work, an attempt to synthesis of bimetallic copper zinc tungstate (CuZnWO₄) nanoparticles with reduced graphene oxide (CuZnWO₄/rGO) via one-step hydrothermal technique. The synthesized CuZnWO₄/rGO composite are characterized by Fourier transform infrared spectroscopy (FTIR), Powder X-ray diffraction (XRD), scanning electron microscopy (SEM), UV-Vis diffuse reflectance spectroscopy (UV-DRS) and Photoluminescence (PL). The photocatalytic performance is examined by the degradation of methylene blue (MB) dye under visible-light irradiation. The MB dye is almost 73 % degraded within 80 minutes. Further, the electrochemical performance of hybrid CuZnWO₄-rGO composite showed the specific capacity (SC) of 480 Fg⁻¹ at 4 Ag⁻¹ in 6 M KOH electrolyte with excellent cyclability conserving a capacitance retention of 127% after 5000 cycles due to increase diffusion of electrolyte ions to the electrode materials. These results support that the hybrid CuZnWO₄-rGO composite as an appropriate electrode material for high-performance SCs electrode and an auspicious catalyst for the degradation of dye (organic) contaminants in aqueous media.

Keywords: *Bimetallic tungstate; Reduced graphene oxide; Photocatalysis; Supercapacitor*

1. Introduction

In the 21st century, the mankind met massive challenges in energy crisis and ecological pollution. Owing to the increasing human population and industrialization, fossil fuels and coal are highly utilized and depleted very soon. The environmental problems accompanying with direct release of harmful organic pollutants from the textile industry to water sources are a serious issue[1–3]. Therefore, the investigation of fast and effective ecological protection and energy storage technologies has become a hottest theme for researchers. Generally various kinds of materials are used as a catalyst for photocatalytic activity and electrodes for energy storage device (such as metal oxides, conducting polymers, carbonaceous materials, metal sulfides and etc.,) [4–7]. Regrettably, most of the catalysts and electrodes suffer from low-light energy garnering and quick extermination of electron-hole pairs. Among these materials, the metal tungstate's has a significant consideration owing to their immeasurably wide-range of applications in various fields such as supercapacitors (SCs), photocatalysis, optical devices, structural, electrical/electronics, humidity sensors, metal-ion batteries and electrocatalysis[8,9].

Chemical contaminants such as dyes emitted from the clothing, food, and leather industries pose a major environmental threat. Photocatalytic nanomaterials are the most effective agents for the degradation of toxic organic dyes, such as methylene blue (MB), rhodamine-B (RhB) and methyl orange (MO). Due to the extreme huge release from different factories, it causes significant adverse effects on the environment and critically increases water contamination, thus effectively disrupts the ecosystem[10]. Zinc tungstate (ZnWO_4), a typical traditional catalyst, has been extensively used as photo-catalyst and applied in photocatalytic degradation of dyes (organic contaminants) due to its extraordinary aspects of cost effectiveness, high stability, non-toxicity, high quantum yield, commercial accessibility and outstanding photoelectrical performance. However, the pure ZnWO_4 shows feeble visible-light photocatalytic activity due to the wide range of band gap.

Electrochemical capacitors or supercapacitors (SCs) are a new class of electric energy storage devices, they get more consideration due to its extraordinary properties such as high cyclability, high power/energy density, and they could rapidly deliver greater energy-density than conversional capacitors and simultaneously larger power density than secondary batteries[13]. The performance of SCs is based on the electrodes, so it plays a major role in SCs. Nowadays various kinds of materials are used as a SCs electrode they are carbonaceous materials

(such as: activate carbon, graphene, carbon quantum dots, carbon nano tubes and etc.) metal oxides (MOs) (such as: NiO, V₂O₅, Fe₂O₃, CuO and etc.) and conducting polymers (CPs) (such as: polyaniline, polypyrrole, polyindole, polythiophene and etc.) [14]. The major disadvantage of the SCs is low energy density, where does not meet the future demand of portable electrical/electronic devices and modern electric vehicles [15]. Similarly, the commercializing of SCs is still stuck by the moderately poor-overall performance, like the carbonaceous materials show low specific capacitance (Cs), low conductivity of MOs as well as poor cyclability of conducting polymers (CPs). The current research is fully focused on the synthesis of novel/hybrid nano-structured electrode materials to enhance the energy density of SCs. Among the various electrode materials, the metal tungstate's (MWO₄; M = Ni, Cu, Pb, Mn, Co, Zn and etc.) are recognized as effective resources consuming adaptable chemical properties. The MWO₄ attract more attention in past few decays owing to its astonishing physio-chemical assets which makes them it as a potential and auspicious materials for various applications in the arena of photocatalytic activity, energy storage, electrical/electronics, antimicrobial, magnetic, electrocatalysis, and ceramics [16,17].

In this present work, a copper zinc bimetallic tungstate (CuZnWO₄) nanoparticle decorated reduced graphene oxide (rGO) (CuZnWO₄/rGO) nanocomposites synthesized via hydrothermal technique. As synthesized materials are used as an electrode for SCs and catalyst for photocatalytic applications. CuZnWO₄ and CuZnWO₄-rGO are examined by XRD, FTIR, SEM, and optical study of UV-DRS and photoluminescence. Electrochemical behavior is investigated by cyclic voltammetry (CV), galvanic charge discharge (GCD) and impedance (EIS) in 6 M KOH aqueous electrolyte and the photocatalytic activity are evaluated by methylene blue degradation. The above results are projected that the CuZnWO₄/rGO nanocomposite assist as an effective electrode SCs electrode material for and photocatalytic applications.

2. Experimental

2.1. Chemicals and materials

Copper acetate (Sigma-Aldrich), zinc acetate (Merck), sodium tungstate (SD Fine), Cetyltrimethylammonium bromide (Sigma-Aldrich). All of the above-mentioned chemicals

purchased were analytical grade and used without any further purification. The whole reaction was carried out using water and ethanol as solvents.

2.2 Synthesis of CuZnWO₄ and CuZnWO₄-rGO Composite

Reduced graphene oxide was synthesized by hummers method and followed by reduction using ammonia in hydrothermal method [18]. CuZnWO₄ bimetallic tungstate was synthesized by hydrothermal method using copper acetate and zinc acetate as a precursor. The precursors of copper and zinc (1;1 ratio, 0.2 M each) and 4 M CTAB was dissolved in 15 mL distilled under continuous stirring for 30 minutes. Further, as prepared 0.4 M Na₂WO₄·2H₂O was added drop by drop into the above solution under continuous stirring, a thick light green coloration was developed. Then the resultant solution was transferred into a 50 mL of Teflon-lined stainless-steel autoclave and heated for 180 °C for overnight in hot air oven. The attained product was washed several times and followed by centrifuge, the obtained precipitate was dried overnight in a hot air oven at 60 °C and annealed for 450 °C at 2 h.

A composite of CuZnWO₄/rGO hybrid nanostructures was prepared using the same procedure with addition of reduced graphene oxide (rGO). Fig.1 showed the schematic illustration of CuZnWO₄ and CuZnWO₄/rGO composite.

2.3. Characterization

The crystal nature of the synthesized samples was examined by Powder X-ray diffraction (XRD) from the range of $2\theta \sim 10 - 80$, Ni filtered Cu K α radiation as a source. Fourier transform infrared spectra (FTIR) were investigated using Perkin-Elmer instrument (USA) in the range of 4000-400 cm⁻¹ with KBR as a reference material at room temperature. The surface morphology of CuZnWO₄ and CuZnWO₄-rGO composite were visualized by scanning electron microscope (SEM, Hitachi SU-70, Japan) running at 25 kV an accelerating voltage. UV-visible diffuse reflectance spectra (UV-DRS) were recorded by Lambda-900 spectrometer in the range of 200-800 nm.

2.4. Photocatalytic activity

The photocatalytic performance of the synthesized materials was examined against the photo-degradation of synthetic dye methylene blue (MB) under visible light at ambient temperature. Initially 100 mg of methylene blue (MB) was added into 100 mL of de-ionized water and stirred well for 30 minutes. 1 mL of this aqueous solution was introduced into reactor

with 50 mg of synthesized materials at constant stirring. After that, 5 mL of the solution was collected with the time interval of 10 minutes up to 80 minutes. The degradation efficiency of the synthesized samples was calculated by the following equation[19].

$$D\% = \frac{C_0 - C_t}{C_0} \times 100 \text{————— (1)}$$

Where, C_0 is the major absorption intensity of MB dye at 0 min and C_t is the dye degradation peak intensity under visible-light for the time t (10, 20, 30, 40, 50, 60, 70, and 80 min).

2.5. Electrochemical performance

The electrochemical performance of the synthesized electrode material was examined using a three-electrode cell in 3 M KOH aqueous electrolyte solution within the potential-window of 0 - 0.6 V on a biologic S-50 electrochemical workstation. Cyclic voltammogram (CV) and galvanostatic charge and discharge (GCD) and electrochemical impedance spectra (EIS) were performed. CV was used to know the potential of the electrodes and GCD was used to examine the specific capacitance of the electrode and EIS was used to analyze the resistance of the electrode material.

3. Results and discussion

3.1. X-ray diffraction analysis

Fig. 2(a-b) illustrates the XRD spectrum of CuZnWO_4 and CuZnWO_4 -rGO composite. Fig. 2(a) shows the XRD pattern of CuZnWO_4 , where indexed 2θ value of 15.47° , 18.85° , 23.82° , 24.59° , 25.84° , 28.98° , 30.45° , 36.5° , 38.5° , 41.2° , 44.9° , 48.56° , 51.6° , 53.5° , 61.8° , 62.6° , 65.03° and 68.07° corresponding to (010), (100), (011), (110), (101), (111), (111), (021), (200), (102), (112), (112), (130), (202), (113), (230), (040) and (041) diffraction planes, respectively. However, some of the planes are comparative to both metals Cu and Zn in bimetallic tungstate. The XRD diffraction pattern of CuZnWO_4 accord with the pristine structural phase of CuWO_4 and ZnWO_4 in standard JCPDS card no. 80-1918 and 89-7624 respectively[20,21]. The CuZnWO_4 -rGO nanocomposite XRD pattern is shown in Fig.2(b), where illustrates the similar peaks as like Fig. 2a corresponds to CuZnWO_4 but no other characteristic peaks for rGO is not clearly visible in CuZnWO_4 -rGO XRD pattern, due to the shielding effect by strong diffraction peaks of CuZnWO_4 particles but rGO peaks are merged with CuZnWO_4 peaks in CuZnWO_4 -rGO composite [22,23].

3.2. Fourier transform inferred spectra analysis (FT-IR)

FT-IR spectra are used to investigate the surface state and functional groups of the prepared samples. Fig. 3 shows, FTIR spectra of the CuZnWO_4 and $\text{CuZnWO}_4/\text{rGO}$ nanocomposite. Fig. 3(a) displays the FTIR spectrum of CuZnWO_4 , the peak at $3000\text{--}3400\text{ cm}^{-1}$ corresponds to the hydroxyl group (OH)[24], the absorption peaks at 460 cm^{-1} , 595 cm^{-1} and 625 cm^{-1} are associated with the stretching and bending vibration of M-O (M=Cu and Zn). While the band at 806 cm^{-1} is related to the bending/stretching vibration of W-O cm^{-1} for tetrahedral WO_4 [25,26] and the peak at 890 cm^{-1} is associated with the stretching/bending vibration of M-W-O groups[27]. Fig. 3(b) shows the FTIR spectrum of $\text{CuZnWO}_4/\text{rGO}$ composite. The peaks which were obtained in CuZnWO_4 spectra are also present in $\text{CuZnWO}_4/\text{rGO}$ composite and some other absorption bands are obtained with respect to rGO [27]. The peak at 1716 cm^{-1} is allocated for the C=C skeleton of rGO[28]. Therefore, the results shown in Fig. 3. is an evidence to confirm a synthesized product as $\text{CuZnWO}_4/\text{rGO}$ nanocomposite.

3.3. UV-Vis DRS and Photoluminescence analysis

The light absorption property of the synthesized samples is analyzed using UV-Vis diffuse reflection spectra. The synthesized samples (Fig. 4(a,b)) display a strong absorption in visible region owing to the bandgap transition of CuZnWO_4 semiconductor indicating their probable application as photocatalysts. The CuZnWO_4 shows an absorption edge at 530 nm and the rGO loaded CuZnWO_4 shows the high absorption at 545 nm compared to CuZnWO_4 (530 nm). The calculated band-gap energies of 2.27 and 2.18 eV, corresponding to the CuZnWO_4 and $\text{CuZnWO}_4\text{-rGO}$, respectively. It clearly shows the $\text{CuZnWO}_4\text{-rGO}$ composite parades high catalytic activity than CuZnWO_4 under visible light due to the lowest band-gap of 2.18 eV. The trapping and recombination of electron holes is playing a vital role in photocatalytic activity, where analyzed by photoluminescence spectra in Fig. 4(d). The PL spectra of CuZnWO_4 and $\text{CuZnWO}_4\text{-rGO}$ are shown in Fig. 4(d). it possesses a green-blue spectrum with an extreme intensity at 411 nm and $\text{CuZnWO}_4\text{-rGO}$ shows lower intensity than CuZnWO_4 [29,30]. The results demonstrate the recombination capability rate of electrons as well as holes is inhibited considerably in $\text{CuZnWO}_4\text{-rGO}$ composite.

3.4. Scanning Electron Microscope (SEM)

The SEM images of CuZnWO₄ and CuZnWO₄-rGO are revealed in Fig. 5. CuZnWO₄ shows a composed structure of plates and rod-like/crystal structure (Fig. 5(a and b))[31]. CuZnWO₄-rGO revealed the plate as well as improved rod-like structure(Fig. 5(c and d)).The closely crammed surface structure of the CuZnWO₄-rGO composite particles is beneficial for effectual charge transporter separation[32,33].

3.6. Photocatalytic activity

The photocatalytic efficiency of the synthesized samples is examined by degradation of organic pollutant (methylene blue (MB)) under visible light irradiation. Fig. 6 demonstrate the MB dye degradation using pure CuZnWO₄ and CuZnWO₄/rGO composite. The MB aqueous solution displayed the absorbance band at $\lambda = 661$ nm is shown in Fig. 6(a,b). The initial absorbance peak intensity is gradually decreased with the increment of irradiation time from 0 min – 80 min owing to the disintegration of MB dye on the catalyst surface. The pure CuZnWO₄ shows 51 % degradation of MB dye for 80 min under visible light, but the composite shows 73 % of degradation owing to the existence of rGO. which improve the catalytic performance of CuZnWO₄. The efficiency of the synthesized materials is compared with previous reports given in Table-1.

MB degrade and form H₂O, CO₂ and some other inorganic contaminants after photocatalytic degradation. The probable degradation mechanism of MB dye by CuZnWO₄ and its composite is clearly clarified in following equations. Initially the CuZnWO₄ is irradiated by visible light, it captivates the energy approximately equal/higher than its band-gap to enable the development of electron-hole pairs. The electron from the valance band (VB) moved to the vacant conduction band (CB), results show holes formation in the VB and electrons in CB. The oxygen molecules are reduced by highly excited electrons and form a super oxide radical ($*O_2^-$) and also, water molecules oxidized by fast-responsive electron holes to form hydroxy radicals ($*OH$). $*O_2^-$ and $*OH$ radicals are fully responsible for the photocatalytic degradation of organic pollutants into CO₂, H₂O and some other inorganic contaminants as a product [34,35].

Photocatalytic reaction pathway of MB

Fig. 7 shows MB's chemical structure and the pathway of the photocatalytic reaction. In photocatalytic degradation, n-dealkylation of dyes holding auxo-chromic alkylamine groups play a key role. When part of a methyl groups degrades, the color of MB solutions has become frailer (color less) and hypochromic change takes place. Therefore, Methylene blue demethylation appears at first as defined in the pathway, and finally MB depredated to CO₂, H₂O and some other inorganic components[36,37].

Fig. 8(a) shows the degradation efficiency of the synthesized samples. To understand the quantitative kinetics of the MB dye degradation reaction, the degradation data is fit by first order kinetics model, using eq(8).

$$-\ln\left(\frac{C_t}{C_0}\right) = Kt \text{—————} (8)$$

Where k is min⁻¹rate constant of the reaction and t is min are the seeming first-order rate constants and treatment time, C₀ – initial concentration of dye and C_tis remaining concentration of dye at each period. model fitting-plots and consistent k standards are revealed in Fig. 8(a,b). we calculate the seeming reaction-rate constant from slope of the plot of ln(C₀/C) Vs irradiation time. From these plots, we attain the synthesized samples rate constant, the data are shown in Fig. 8(c), the result confirmed that CuZnWO₄-rGO have higher catalytic degradation efficiency than CuZnWO₄. The attained seeming rate constant (k) values are 0.0151 and 0.0083 for CuZnWO₄-rGO and CuZnWO₄ respectively.

3.7. Electrochemical studies

The electrochemical properties of CuZnWO₄ and CuZnWO₄/rGO composite are examined by cyclic voltametric (CV) technique. In a three-electrode cell system, Ag/AgCl is used as a reference electrode, platinum wire as a counter electrode and the synthesized samples as a working electrode in 3 M KOH aqueous electrolyte solution. Fig. 9(a) and (b) shows the CV

curves of CuZnWO₄ and CuZnWO₄/rGO composite electrodes at various scan rates in between the potential range from 0 to 0.6 V. All CV curves display a pair of strong redox-peaks, revealing the pseudo-capacitive features of the synthesized electrode thus the strong redox peaks are mostly governed by reversible Faradic redox process of M²⁺/M³⁺ [38]. According to the CV curve, current response of electrode material will increase with the increases of scan rates. The perfect quasi-rectangular CV shape of the electrodes remain constant at high scan rate, it proposes perfect capacitive behaviour. The potential of oxidation and reduction peaks are moved towards more positive and move negative respectively, which is mostly associated with the internal resistance of the electrode. The CV curves of CuZnWO₄/rGO composite shows higher current density and specific surface area than CuZnWO₄ due to the synergic effects in between rGO and CuZnWO₄, which enhance the electro chemical performance and specific capacitance [39].

Galvanic charge discharge (GCD) measurements of the synthesized samples are conducted at various current density ranges between 4 and 20 Ag⁻¹ (Fig. 9(c) and (d)). CuZnWO₄/rGO composite offer higher Cs (480 Fg⁻¹) than CuZnWO₄ electrode (15 Fg⁻¹) at the same current-density of 4 Ag⁻¹. The CuZnWO₄/rGO composite shows superior electrochemical performance than pristine CuZnWO₄ electrode due to the synergetic effect of electroactive and porous rGO sheets [40], which boost the number of oxidation states, accessible interaction shells and enables the kinetics of ions and electrons transference from the electrolyte. The specific capacitance (Cs) or charge/discharge time decreases with increasing energy density, due to the fact of that the electrolyte-ions are unable to entirely access the internal surface area of the active-materials for charge-storing owing to the decreased diffusion time at high energy density. The Cs is calculated from GCD using the following equation [41–43]

$$C_s = \frac{I \times \Delta t}{\Delta V \times m} \quad (8)$$

Where, Cs - specific capacitance, I – response current, Δt - discharging time, V - Potential window, and m - mass (g) of active material. The calculated specific capacitance (Cs) of 480, 465, 340, 295, 276, 252, 248, 243, 240 F g⁻¹ at current density of 4, 6, 8, 10, 12, 14, 16, 18, 20 A g⁻¹, respectively.

The comparison of GCD curve (Fig. 10(a)) is revealed that the CuZnWO₄/rGO composite offer higher charging and discharging time than pristine CuZnWO₄, due to the high surface area

of rGO based composite [44]. Fig.10(b) shows the specific capacitance comparison of the synthesized electrode materials. It clearly shows that the composite has higher specific capacitance than CuZnWO_4 . Amazingly, the increasing cyclability of $\text{CuZnWO}_4/\text{rGO}$ composite electrode is shown in Fig.10(c). The $\text{CuZnWO}_4/\text{rGO}$ offers cyclic retention of 127 % at 20 A g^{-1} due to the continuous charging/discharging process raises the wettability of $\text{CuZnWO}_4/\text{rGO}$, where enhanced the diffusion of electrolyte ions to the electrode material. The continuous activation of $\text{CuZnWO}_4/\text{rGO}$ composite during charging/discharging process that increase the interaction between electrode and electrolyte ions, resulting to increase specific capacitance (C_s increases with number of charging /discharging cycles)[45–47]. Electrochemical impedance spectra (EIS) of the synthesized electrode materials is illustrated in Fig.10(d). The internal and external resistance of the synthesized electrode materials and electrode/electrolyte are estimated via open circuit potentials (OCP) from 0.1 to 105 Hz respectively. In Fig. 10(d) shows the Nyquist plot and circuit diagram of CuZnWO_4 and $\text{CuZnWO}_4/\text{rGO}$ composite. Pristine CuZnWO_4 shows more resistance than the $\text{CuZnWO}_4/\text{rGO}$ composite from this EIS spectra we conclude that the composite offers higher electrochemical performance and specific capacitance due to the lower internal resistance.

4. Conclusion

In the present work, we synthesized a nano-structured bimetallic tungstate CuZnWO_4 and its composite with rGO via hydrothermal method. The synthesized materials are used as a catalyst for photocatalytic activity and electrode for SCs. $\text{CuZnWO}_4/\text{rGO}$ shows better photocatalytic activity and electrochemical performance than pristine CuZnWO_4 due to efficient interaction of rGO, the high surface area of rGO is captured more electrons for efficient degradation of organic pollutants with degradation efficiency of 73 % ($\text{CuZnWO}_4/\text{rGO}$). The electrochemical performance of the synthesized composite electrode ($\text{CuZnWO}_4/\text{rGO}$) shows the $C_s 480 \text{ F g}^{-1}$ at 4 A g^{-1} in aqueous 6 M KOH electrolyte respectively, the electrode reveals enhanced cyclability of 127% at 20 A g^{-1} after 5000 cycles due to the increasing of interaction between electrode and electrolyte. The synergetic effect of CuZnWO_4 and rGO lead to high storage capacity and outstanding cyclability. The above results confirmed that the synthesized material is a potential candidate for photocatalytic and supercapacitor application.

Acknowledgement

Dr. Navaneethan Duraisamy acknowledges the DST, New Delhi, India, for the DST Inspire Faculty award (DST/INSPIRE/04/ 2018/001444).

Reference

1. J. Yesuraj and S. A. Suthanthiraraj, *J. Mol. Struct.* **1181**, 131 (2019).
2. K. T. G. Carvalho, O. F. Lopes, D. C. Ferreira, and C. Ribeiro, *J. Alloys Compd.* **797**, 1299 (2019).
3. S. M. Alshehri, J. Ahmed, T. Ahamad, N. Alhokbany, P. Arunachalam, A. M. Al-Mayouf, and T. Ahmad, *J. Sol-Gel Sci. Technol.* **87**, 137 (2018).
4. S. Chen, G. Yang, Y. Jia, and H. Zheng, *ChemElectroChem* **3**, 1490 (2016).
5. K. Adib, M. Rahimi-Nasrabadi, Z. Rezvani, S. M. Pourmortazavi, F. Ahmadi, H. R. Naderi, and M. R. Ganjali, *J. Mater. Sci. Mater. Electron.* **27**, 4541 (2016).
6. V. Faka, S. Tsoumachidou, M. Moschogiannaki, G. Kiriakidis, I. Poullos, and V. Binas, *J. Photochem. Photobiol. A Chem.* **406**, 113002 (2021).
7. U. M. García-Pérez, A. Martínez-De La Cruz, and J. Peral, *Electrochim. Acta* **81**, 227 (2012).
8. J. Ahmed, T. Ahamad, N. Alhokbany, B. M. Almaswari, T. Ahmad, A. Hussain, E. S. S. Al-Farraj, and S. M. Alshehri, *ChemElectroChem* **5**, 3938 (2018).
9. S. Kundu, L. Ma, Y. Chen, and H. Liang, *J. Photochem. Photobiol. A Chem.* **346**, 249 (2017).
10. S. M. Alshehri, J. Ahmed, A. M. Alzahrani, and T. Ahamad, *New J. Chem.* **41**, 8178 (2017).
11. A. A. G. Santiago, R. L. Tranquilin, M. S. Li, E. Longo, F. V. Motta, and M. R. D. Bomio, *Mater. Chem. Phys.* **258**, 123991 (2021).
12. H. He, Z. Luo, Z. Y. Tang, and C. Yu, *Appl. Surf. Sci.* **490**, 460 (2019).
13. M. Liu, L. Gan, W. Xiong, F. Zhao, X. Fan, D. Zhu, Z. Xu, Z. Hao, and L. Chen, *Energy and Fuels* **27**, 1168 (2013).
14. M. N. Rantho, M. J. Madito, and N. Manyala, *J. Alloys Compd.* **819**, 152993 (2020).
15. R. D. Kumar, Y. Andou, and S. Karuppuachamy, *J. Alloys Compd.* **654**, 349 (2016).
16. H. Naderi, H. Sobati, A. Sobhani-Nasab, M. Rahimi-Nasrabadi, M. Eghbali-Arani, M. R. Ganjali, and H. Ehrlich, *ChemistrySelect* **4**, 2862 (2019).
17. R. Dhilip Kumar and S. Karuppuachamy, *J. Alloys Compd.* **674**, 384 (2016).
18. J. Jo, S. Lee, J. Gim, J. Song, S. Kim, V. Mathew, M. H. Alfaruqi, S. Kim, J. Lim, and J.

Kim, R. Soc. Open Sci. **6**, (2019).

19. M. Mosleh and K. Taherinejat, J. Mater. Sci. Mater. Electron. **27**, 10510 (2016).

20. C. Wei, Y. Huang, X. Zhang, X. Chen, and J. Yan, Electrochim. Acta **220**, 156 (2016).

21. L. Xu, X. Wang, M. L. Xu, B. Liu, X. F. Wang, S. H. Wang, and T. Sun, Ultrason. Sonochem. **61**, 104815 (2020).

22. K. Qureshi, M. Z. Ahmad, I. A. Bhatti, M. Zahid, J. Nisar, and M. Iqbal, J. Mol. Liq. **285**, 778 (2019).

23. K. S. Samantaray, S. Sahoo, and C. S. Rout, Am. J. Eng. Appl. Sci. **9**, 584 (2016).

24. S. Muthamizh, R. Suresh, K. Giribabu, R. Manigandan, S. P. Kumar, S. Munusamy, L. Vijayalakshmi, A. Stephen, and V. Narayanan, AIP Conf. Proc. **1591**, 508 (2014).

25. B. Kavitha and R. Karthiga, **11**, 57 (2020).

26. W. Zhang, J. Yin, F. Min, L. Jia, D. Zhang, Q. Zhang, and J. Xie, J. Alloys Compd. **690**, 221 (2017).

27. Z. Amouzegar, R. Naghizadeh, H. R. Rezaie, M. Ghahari, and M. Aminzare, Ceram. Int. **41**, 8352 (2015).

28. N. Hu, Z. Yang, Y. Wang, L. Zhang, Y. Wang, X. Huang, H. Wei, L. Wei, and Y. Zhang, Nanotechnology **25**, (2014).

29. Y. Tang, N. Rong, F. Liu, M. Chu, H. Dong, Y. Zhang, and P. Xiao, Appl. Surf. Sci. **361**, 133 (2016).

30. S. Roddaeng, P. Promvong, and R. Anuwattana, MATEC Web Conf. **192**, 8 (2018).

31. P. V. Adhyapak, A. D. Bang, P. More, and N. R. Munirathnam, RSC Adv. **8**, 34035 (2018).

32. S. Zhong, C. Li, M. Shen, C. Lv, and S. Zhang, J. Mater. Res. Technol. **8**, 1849 (2019).

33. A. K. Adep, S. Goskula, S. Chirra, S. Siliveri, S. R. Gujjula, and V. Narayanan, RSC Adv. **9**, 24368 (2019).

34. M. Thirupathi, K. Leeladevi, C. Ramalingam, K. C. Chen, and E. R. Nagarajan, Mater. Sci. Semicond. Process. **106**, 104766 (2020).

35. C. P. Goyal, D. Goyal, V. Ganesh, N. S. Ramgir, M. Navaneethan, Y. Hayakawa, C. Muthamizhchelvan, H. Ikeda, and S. Ponnusamy, Phys. Solid State **62**, 1796 (2020).

36. X. Q. Wang, S. F. Han, Q. W. Zhang, N. Zhang, and D. D. Zhao, MATEC Web Conf. **238**, (2018).

37. R. S. Dariani, A. Esmaceli, A. Mortezaali, and S. Dehghanpour, Optik (Stuttg). **127**, 7143

(2016).

38. R. Dhilip Kumar, Y. Andou, M. Sathish, and S. Karuppuchamy, *J. Mater. Sci. Mater. Electron.* **27**, 2926 (2016).
39. J. Tang, J. Shen, N. Li, and M. Ye, *Facile Synthesis of Layered MnWO₄/reduced Graphene Oxide for Supercapacitor Application* (2016).
40. M. Mitra, S. T. Ahamed, A. Ghosh, A. Mondal, K. Kargupta, S. Ganguly, and D. Banerjee, *ACS Omega* **4**, 1623 (2019).
41. X. Xing, Y. Gui, G. Zhang, and C. Song, *Electrochim. Acta* **157**, 15 (2015).
42. J. Chu, X. Li, Q. Li, J. Ma, B. Wu, X. Wang, R. Zhang, M. Gong, and S. Xiong, *High Perform. Polym.* **32**, 258 (2020).
43. K. Seevakan, A. Manikandan, P. Devendran, Y. Slimani, A. Baykal, and T. Alagesan, *Ceram. Int.* **44**, 20075 (2018).
44. A. Iakunkov, V. Skrypnichuk, A. Nordenström, E. A. Shilayeva, M. Korobov, M. Prodana, M. Enachescu, S. H. Larsson, and A. Vtalyzin, *Phys. Chem. Chem. Phys.* **21**, 17901 (2019).
45. A. E. Elkholy, A. S. Dhmees, F. E. T. Heakal, and M. A. Deyab, *New J. Chem.* **43**, 1987 (2019).
46. M. Ramadan, A. M. Abdellah, S. G. Mohamed, and N. K. Allam, *Sci. Rep.* **8**, 1 (2018).
47. J. Zhou, J. Lian, L. Hou, J. Zhang, H. Gou, M. Xia, Y. Zhao, T. A. Strobel, L. Tao, and F. Gao, *Nat. Commun.* **6**, (2015).
48. M. Mousavi, A. Habibi-Yangjeh, and M. Abitorabi, *J. Colloid Interface Sci.* **480**, 218 (2016).
49. R. Salimi, A. A. Sabbagh Alvani, N. Naseri, S. F. Du, and D. Poelman, *New J. Chem.* **42**, 11109 (2018).
50. A. M. Raba-Páez, J. O. João, C. A. Parra-Vargas, E. C. Paris, and M. Rincón-Joya, *Mater. Today Commun.* (2020).
51. W. Zou, L. Zhang, L. Liu, X. Wang, J. Sun, S. Wu, Y. Deng, C. Tang, F. Gao, and L. Dong, *Appl. Catal. B Environ.* **181**, 495 (2016).
52. H. Wang, X. Yuan, H. Wang, X. Chen, Z. Wu, L. Jiang, W. Xiong, and G. Zeng, *Appl. Catal. B Environ.* **193**, 36 (2016).
53. M. Rahimi-Nasrabadi, S. M. Pourmortazavi, M. Aghazadeh, M. R. Ganjali, M. S. Karimi, and P. Novrouzi, *J. Mater. Sci. Mater. Electron.* **28**, 3780 (2017).
54. S. Ameen, H. K. Seo, M. Shaheer Akhtar, and H. S. Shin, *Chem. Eng. J.* **210**, 220 (2012).

55. B. G. S. Raj, J. Acharya, M. K. Seo, M. S. Khil, H. Y. Kim, and B. S. Kim, *Int. J. Hydrogen Energy* **44**, 10838 (2019).
56. R. Dhilip Kumar and S. Karuppuchamy, *Ceram. Int.* **40**, 12397 (2014).
57. S. M. Pourmortazavi, M. Rahimi-Nasrabadi, M. S. Karimi, and S. Mirsadeghi, *New J. Chem.* **42**, 19934 (2018).
58. D. P. Ojha, H. P. Karki, J. hee Song, and H. J. Kim, *Chem. Phys. Lett.* **712**, 83 (2018).
59. U. Nithiyanantham, S. R. Ede, S. Anantharaj, and S. Kundu, *Cryst. Growth Des.* **15**, 673 (2015).

Table caption

Table – 1: Comparison of Dye degradation efficiency with previous reported literatures

Table – 1: Comparison of the electrochemical performance with previous reported literatures

Figure caption

Fig. 1. Graphical abstract

Fig. 2. XRD pattern: a) CuZnWO₄ and b) CuZnWO₄/rGO

Fig. 3. FTIR spectra: a) CuZnWO₄ and b) CuZnWO₄/rGO

Fig. 4. (a,b) UV-DRS absorption and transmission spectrum and (c) photoluminescence spectram and d) taucplot

Fig. 5. SEM images:a,b) CuZnWO₄ and c,d) CuZnWO₄-rGO low and high magnificaation respectively

Fig. 6. Photocatalytic dye degradation: a) CuZnWO₄, b) CuZnWO₄/rGO and c) Comparison of methylene blue degradation efficiency of CuZnWO₄ andCuZnWO₄/rGO under visible light

Fig. 7. Ln C/C₀vs. irradiation time for photocatalytic degradation of MB dye

Fig. 8. Mechanism of methylene blue dye degradation

Fig. 9. Cyclic voltammograms at various scan rates from 5 to 100 mV.s⁻¹ a) CuZnWO₄ and b) CuZnWO₄/rGO, GCD at various current densities from 4 to 20 A. g⁻¹c) CuZnWO₄ and d) CuZnWO₄.

Fig.10. a) GCD comparison of CuZnWO₄ and CuZnWO₄/rGO at6 Ag⁻¹, b)Comparison specific capacitance Vs current density c) Cyclability and culumbic efficiency ofCuZnWO₄/rGO d) Nyquest plots

Table 1

Catalyst	Pollutant	Efficiency (%)	Time (Min)	Reference
g-C ₃ N ₄ /Fe ₃ O ₄ /AgCl	RhB	49.5	-	[48]
Ag-CuWO ₄ /WO ₃	MB	51	180	[49]
CuO with CuWO ₄	RhB	20	160	[50]
o-Cu ₂ O-rGO	MB	72	160	[51]
CNQD-utg-C ₃ N ₄	MO	70	160	[52]
TiO ₂	MB	50	60	[53]
polyaniline/graphene	RhB	56	180	[54]
CuZnWO ₄ /rGO	MB		80 min	This Work

Table-2

Electrode material	Electrolyte	Specific capacitance	Reference
CoWO ₄	2 M H ₂ SO ₄	378 F/g at 2 mV/s	[5]
MnWO ₄	1 M Na ₂ SO ₄	324 F/g at 1 mA cm ⁻²	[55]
CuWO ₄	0.1 M KCl with 1mM [Fe(CN) ₆] ^{3-/4-}	77 F/g	[56]
CuWO ₄	2 M KOH	302.40 mAh/g at 1 A/g	[20]
Ni-WO ₃	2 M KOH	171.28 F/g at 0.25 A/g	[15]
CWO-NPs	1 M KOH	230 F/g at 5 mV/s	[8]
NiWO ₄ NPs	3 M H ₂ SO ₄	468 F/g at 2 mV/s	[57]
FWO/gCN	2 M KOH	357 F/g at 5 mV/s	[58]
NiWO ₄	2 M KOH	173 F/g at 5 mV/s	[59]
CuZnWO ₄ /rGO	6 M KOH	480 F/g at 6 A/g	This Work

Fig. 1

Fig. 2

Fig. 3

Fig. 4

Fig. 5

Fig. 6

Fig. 7

Fig. 8

Fig. 9

Fig. 10

Figures

Figure 1

Graphical abstract

Figure 2

XRD pattern: a) CuZnWO4 and b) CuZnWO4/rGO

Figure 3

FTIR spectra: a) CuZnWO4 and b) CuZnWO4/rGO

Figure 4

(a,b) UV-DRS absorption and transmission spectrum and (c) photoluminescence spectrum and d) taucplot

Figure 5

SEM images:a,b) CuZnWO4 and c,d) CuZnWO4-rGO low and high magnification respectively

Figure 6

Photocatalytic dye degradation: a) CuZnWO_4 , b) $\text{CuZnWO}_4/\text{rGO}$ and c) Comparison of methylene blue degradation efficiency of CuZnWO_4 and $\text{CuZnWO}_4/\text{rGO}$ under visible light

Figure 7

Ln C/Covs. irradiation time for photocatalytic degradation of MB dye

Figure 8

Mechanism of methylene blue dye degradation

Figure 9

Cyclic voltammograms at various scan rates from 5 to 100 mV.s⁻¹ a) CuZnWO₄ and b) CuZnWO₄/rGO, GCD at various current densities from 4 to 20 A. g⁻¹ c) CuZnWO₄ and d) CuZnWO₄.

Figure 10

a) GCD comparison of CuZnWO_4 and $\text{CuZnWO}_4\text{-rGO}$ at 6 Ag^{-1} , b) Comparison specific capacitance Vs current density c) Cyclability and coulombic efficiency of $\text{CuZnWO}_4\text{-rGO}$ d) Nyquist plots