Mesoporous activated carbon yielded from pre-leached cassava peels

Ronald Kayiwa (✉ kronald@cedat.mak.ac.ug)

Department of Mechanical Engineering, College of Engineering, Design, Art and Technology, Makerere University, P.O. Box 7062, Kampala, Uganda <https://orcid.org/0000-0002-7181-6520>

Hillary Kasedde

Department of Mechanical Engineering, College of Engineering, Design, Art and Technology, Makerere University, P.O. Box 7062, Kampala, Uganda

Michael Lubwama

Department of Mechanical Engineering, College of Engineering, Design, Art and Technology, Makerere University, P.O. Box 7062, Kampala, Uganda

John Baptist Kirabira

Department of Mechanical Engineering, College of Engineering, Design, Art and Technology, Makerere University, P.O. Box 7062, Kampala, Uganda

Research

Keywords: Activated Carbon, Cassava peel, Pre-leaching, FTIR, Surface area and Pore volume

Posted Date: April 9th, 2021

DOI: <https://doi.org/10.21203/rs.3.rs-403321/v1>

License: © ⓘ This work is licensed under a Creative Commons Attribution 4.0 International License.

[Read Full License](#)

Abstract

The search for alternatives to fossil based commercial activated carbon (AC) continues to reveal new eco-friendly potential precursors, among which is agricultural waste. The key research aspect in all these endeavors is empirical ascertainment of the core properties of the resultant AC to suit a particular purpose. These properties include; yield, surface area, pore volume and the active surface groups. It is therefore pertinent to have process conditions controlled and tailored towards these properties for the required resultant AC. Highly porous AC was prepared from cassava peels by pre-treating and activating them using NaOH and KOH respectively. The carbonization temperatures were between 480 and 780°C in an activation-carbonization stepwise process using KOH as the activator at a KOH: peel ratio of 5:2 (mass basis). A 42% maximum yield of AC was realized along with a total pore volume of $0.756 \text{ cm}^3\text{g}^{-1}$ and BET surface area of $1684 \text{ m}^2\text{g}^{-1}$. The AC was dominantly microporous for carbonization temperatures below 780°C but a remarkable increase in mesopore volume ($0.471 \text{ cm}^3\text{g}^{-1}$) relative to the micropore volume ($0.281 \text{ cm}^3\text{g}^{-1}$) was observed at 780°C. The Fourier transform infra red (FTIR) spectroscopy for the pre-treated cassava peels showed distortion in the C-H bonding depicting possible elaboration of more lignin from cellulose disruption by NaOH. A carboxylate stretch was also observed owing to the reaction of Na^+ ions with the carboxyl group in the raw peels. FTIR showed possible absorption bands for the AC between 1425 and 1712 cm^{-1} wave numbers. Besides the botanical qualities of the cassava peel genotype used, pre-leaching the peels and also increasing holding activation temperature above the melting point of potassium enabled the modified process of producing highly porous AC from cassava peel. The SEM imaging showed well-developed hexagonal pores in the resultant AC.

1. Introduction

Activated carbon (AC) continues to find application in both domestic and industrial processes predominantly in adsorption. However, the activated carbons available on market are very costly. Besides the off-shelf cost, the non-renewable raw materials from which they are produced threaten environment hence limiting their applications. With the global need to mitigate climate change and its eco-destructive effects, there is a need to produce AC from biomass rather than fossil sources (Yahya, Al-Qodah, & Ngah, 2015). Appreciably, research into alternative eco-friendly AC precursors has been immensely undertaken globally. Mainly, the clear-cut determinants for AC precursor choices are; availability, ease of handling, ease and cost of production, bi-products' compositions and intended application of the AC (Bhatnagar, Sillanpää, & Witek-Krowiak, 2015). In recent years, there has been a growing interest to produce ACs from lignocellulosic agricultural residues (Yahya et al., 2015). This is majorly attributed to their availability at a low cost, their high carbon content, and low inorganics. Inextricably, besides the general considerations for an AC precursor, the choice of a particular lignocellulosic residue for AC production depends on its chemical and physical properties (Menya, Olupot, Storz, Lubwama, & Kiros, 2018). These include; moisture content, volatile matter, carbon composition, ash content, and dry matter content. Inherently, the resultant quality of the produced AC from a lignocellulosic precursor depends on the reactions and

interactions of the different components of the precursor, mainly cellulose, hemicellulose, and lignin (Gani & Naruse, 2007)

Cassava peel is one of the prospective precursors for AC production. Leveraging the properties of cassava peels for AC is of economic importance given the few competitive applications like animal feed (Adekunle, Orsat, & Raghavan, 2016; Santos et al., 2015) and, potential energy production (Okudoh, Trois, Workneh, & Schmidt, 2014). Like other lignocellulosic biomass, for cassava peel to be harnessed for AC production, it requires pre-treatment to counteract its recalcitrance nature towards thermochemical processing. Fairly, research into harnessing cassava peel for AC production has been conducted (Parvathi, Shoba, Prakash, & Sivamani, 2018; Salahudeen, Ajinomoh, Omaga, & Akpaka, 2014; Sudaryanto, Hartono, Irawaty, Hindarso, & Ismadji, 2006). However, like with other lignocellulosic precursors, there is a need to enhance the core properties of activated carbons while not compromising the production process efficiency and environmental conservation standards. Moreover, the pore size distribution of the resulting activated carbon depends on the precursor, degree of initial impregnation of the catalyst used (Daud & Ali, 2004; Kwiatkowski & Broniek, 2017; Laine & Yunes, 1992; Li et al., 2008; Liu et al., 2015)

More often in the application of ACs, the pore volume and surface area are considered the key characteristics that define the suitability of activated carbon. Inextricably the active surface groups of the carbon are crucial in its application properties. Therefore, more research endeavors have been put into the surface chemistry of ACs. Hence, any attempts to enhance the porosity and surface area of a prospective AC from a precursor inextricably affect the surface groups too. In our past work, peels of six predominant cassava varieties in Uganda were found viable for AC production with varietal preferences accruing to the end use of the prospective AC (Kayiwa, Kasedde, Lubwama, & Kirabira, 2021). NAROCAS 1 variety was the most suitable AC precursor owing to its highest and lowest lignin and ash contents respectively. Moreover, alkaline pretreatment of the same showed an increment in the lignin content hence an implied high char yield. Besides, NAROCAS 1 has been reported as one of the cassava varieties in Uganda that are resistant to common viral cassava diseases (Mukiibi et al., 2019; Shirima et al., 2020). This gives hope for the sustainability of AC production owing to an assured yield of enough cassava. Prospectively there was a need to study the produced AC from the variety to understand further the effect pre-leaching and a higher holding carbonization temperature have on the resultant AC porosity, surface area, and active surface groups. Besides, in AC processing reactions and activation mechanisms are variable depending not only on the activation parameters but also on the reactivity of various carbon sources.

This study aimed at enhancing the porosity and surface area of activated carbon from cassava peel through pre-leaching and carbonizing at temperatures above that of the melting point of the activating reagent base metal.

2. Materials And Methods

2.1 Preparation of Activated Carbon

Activated Carbon was prepared from dry peels of NAROCAS 1 cassava genotype pre-leached using NaOH solution. This genotype was chosen for the study due to its robust characteristics including char yield, carbon content, bulk density, and high lignin content. The proximate and ultimate characteristics of the cassava peel genotype are reported in our earlier work (Kayiwa et al., 2021). The peels were washed with distilled water to a debris free level by gravitational flow method. They were dried in an oven at 40°C for 12 hours to reduce the moisture content to 10–12 (%wt dry basis) and about 100 g of the dry peels was pulverized to 0.25 mm average particle size. 20 g of the pulverized peels was soaked in 150 ml of 4.0%w/v NaOH. This was followed by mixing and heating at 400 rpm and 50°C, respectively, in a centrifuge shaker-HERMLE Z326K for 3 h, and allowing the samples to stand for 12 h. The NaOH pretreated cassava peel sample was then transferred to a chromatographic column, with a filter at its bottom and rinsed with distilled water until a neutral pH was obtained, followed by oven drying of the sample at 105°C for 12 h. 10 g portions of pre-leached powdered cassava peel (0.25 mm average particle size) were mixed with KOH at KOH: peel ratios of 5:2 (mass basis) and heated at 60°C for 2 h. The resultant slurry was dried at 100°C for 24 hours and then carbonized at temperatures of 480°C, 580°C, 680°C and 780°C in triplicate in a furnace of a thermogravimetric analyzer (TA instruments Q500) under nitrogen flow of 150 cm³/min at a ramping rate of 10°C per minute from room temperature of about 28°C. It was held at the respective carbonization temperatures for 2 hours after which the resultant ACs were washed with hydrochloric acid. These were sequentially put in chromatographic columns and washed with warm distilled water to a pH of 6.9. The samples were then dried in an oven at 100°C for 12 hours and kept in separate aluminum bottles for the subsequent analysis.

2.2 Activated Carbon characterization

2.2.1 Yield and bulk density

The resultant ACs were packed into a pre-weighed cylindrical crucible of mass m_1 and trimmed to the top to flash with the top most rim of the crucible. The filled crucible was weighed and the mass recorded as m_2 . The sample mass, m_3 was obtained from; $m_3 = m_2 - m_1$. This was repeated thrice for every AC produced at a given carbonization temperature.

The inside diameter (d) and the height (h) of the crucible were measured using a vernier caliper and the volume calculated from

$$v = \pi(d/2)^2 h \quad (1)$$

$$\text{Bulk density, (kg/m}^3\text{)} \text{ was calculated from} = \frac{m_3}{v} \times 1000. \quad (2)$$

$$\text{The yield of the resulted activated carbon was expressed in percentage and calculated as; } \frac{\text{Weight of activated carbon}}{\text{Weight of raw peels}} \times 100\% \quad (3)$$

2.2.2 Specific surface area, pore size and volume

The specific surface area and the pore volumes were determined from nitrogen isotherm at 77.3 K using the BET method and the Micrometrics density functional theory (DFT) software for analysis. The specific surface area was determined according to the BET method at the relative pressure of 33.5 atm.

2.2.3 Functional surface group determination

Fourier transform infrared spectroscopy, FTIR, was used to study the surface functional groups of raw cassava peels, pre-leached peels and the AC produced at 780°C so that the chemical structure of the prepared AC could be determined. IR spectra were obtained with FTIR spectrometer (Shimadzu, model FTIR-8300) using the transformation of 20 scans with a spectral resolution of 4 cm^{-1} by attenuated total reflectance method. FTIR spectra were collected in the mid infrared region between 4,500 and 500 cm^{-1} . Spectra were acquired using air background correction.

2.2.4 AC morphology

The morphologies of the raw peels, pre-leached peels and the resultant AC carbonized at 780°C were coated with gold using the sputtering technique and observed at a beam energy of 15 kV on a FEI Quanta 600 Scanning Electron Microscope (SEM). For AC the formed briquette was analyzed both on the outer surface and on the cross-sectional cut-away surface. The surface of the AC briquette was analyzed before and after washing with water. The milled AC was also analyzed to ascertain the pore development.

3. Results And Discussion

3.1 Bulk density

The bulk density for the resultant activated carbon was in the range $0.31\text{--}0.39\text{ gcm}^{-3}$ (as shown in Fig. 1) which corroborates well with that reported by Parvathi et al., (2018) but lower than $0.410\text{--}0.415\text{ gcm}^{-3}$ reported by Omotosho & Sangodoyin., (2013). Bulk density is important when estimating the packing volume and the right grade for a new system design or modification of an existing system. Powdered carbons used for decolorization usually have a bulk density in the range $0.25\text{--}0.75\text{ gcm}^{-3}$ while granular grades used in gas adsorption have a bulk density of around $0.40\text{--}0.50\text{ gcm}^{-3}$ according to the ASTM D2854- 70 standard.

The highest surface area AC produced at 780°C, had the lowest bulk density that could limit its application in some processes like adsorption and gas storage. The reduction in bulk density with increasing temperature could be due to the opening of the interstitial spaces (microspores) in the carbon residue coupled with release of a great quantity of the volatile matter at high carbonization temperature.

A trade off of high porosity, and surface area for lower bulk densities has been reported for chemically activated carbons (Casco, Martínez-Escandell, Kaneko, Silvestre-Albero, & Rodríguez-Reinoso, 2015; Wang & Kaskel, 2012). Bulk density is also important in AC intended for a number of application in capacitors. Lower bulk densities imply reduced volumetric capacitance in super capacitors despite the much required

high surface area and pore volumes such ACs might have (Wang & Kaskel, 2012). The lower bulk density could also have a cost implication in absorption applications since more bed volumes could be needed per unit absorbate.

Table 1
Comparison of the bulk densities of the AC produced with those from other studies

Precursor	AC bulk density (gcm ⁻³)	Intended application	Reference
Cassava peel	0.415	Effluent treatment	(Omotosho & Sangodoyin, 2013)
Cassava peel	0.31–0.39	-	This study
Cassava peel	0.36–0.48	Absorption of textile dyes	(Parvathi et al., 2018)
Cassava peel	0.407–0.413	Water decontamination-	(Omotosho & Amori, 2016)
Hard wood	0.55–0.88	-	(Rodriguez - Reinoso, 2002)

3.2 Yield of activated carbon

Results on the AC yield are presented in Fig. 2. The highest AC yield was 42% at 480°C. This is higher than 35% the maximum value reported by Sudaryanto et al., (2006) at 1:1 impregnation ratio, carbonization temperature of 450°C and carbonization time of 1 hour. The yield reduced with increase in carbonization temperature, which is in agreement with other studies (Ekebafé, Imanah, & Okieimen, 2012). This is attributed to the carbon burn off and the higher reaction rate of carbon and KOH to release more volatile components with inherent improvement in the textural properties (Saka, 2012). Other studies have reported reduction in AC yield due to increase in activation temperatures beyond certain limits (Kalderis, Bethanis, Paraskeva, & Diamadopoulos, 2008; Sudaryanto et al., 2006; Yahya et al., 2015). For example, Sudaryanto et al., (2006) reported that the yield of the activated carbon at carbonization temperatures more than 650°C were less than fixed carbon in the raw cassava peels. The relatively higher yield of AC at 780°C could be attributed to the pre-leaching of the peels in this study. The raw peel ash content is less than 5% db, the typical ash percentage composition for AC precursors (Menya et al., 2018).

However, pre-leaching reduced the ash by 0.51%, which could have contributed to an increase in char yield and subsequently upgraded to AC on activating. The small reduction in ash content yet high increment in AC yield renders the resultant AC diversely usable in a number of applications that require small amounts of ash like fuel cells and super capacitors (Xu et al., 2017) and humic acid adsorption (Daifullah, Girgis, & Gad, 2004). The high AC yield is partially attributed to the remarkably high lignin content in the NAROCAS 1 cassava variety (Kayiwa et al., 2021). High char yields have been reported from lignocellulosic precursors with relatively higher Lignin compositions (Barskov et al., 2019; Sharypov

et al., 2002). This is due to the high carbon content constituted in Lignin (González-García, 2018). The thermal treatment of hemicellulose and cellulose contained in the pre-leached cassava peel at temperatures above 250°C contributed highly to the increase in the AC yield. This is because at such temperatures, there is an onset of elimination reactions along with crosslinking reactions leading to an increase in aromaticity.

3.3 Pore characteristics (*Pore volume and BET surface area*)

The total pore volume V_t was in the range 0.432 to 0.756 cm^3g^{-1} and increased with increase in temperature as shown in Fig. 3. The resultant activated carbon exhibited a higher micropore volume V_{mic} at 0.319–0.392 cm^3g^{-1} compared to mesopore volume V_{mes} for temperatures 480–680°C. However, mesopore volume at 780°C was remarkably higher than the micropore volume at 0.471 cm^3g^{-1} compared to 0.281 cm^3g^{-1} . This could be due to the high lignin composition in the primary precursor. Lignocellulosic raw materials rich in lignin have been reported to yield highly mesoporous and macroporous activated carbon at temperatures higher than 650°C (Gergova, Petrov, & Minkova, 1993; Savova et al., 2001). The peels of NAROCAS 1 cassava variety were found to have relatively higher lignin compared with other predominant cassava varieties grown in Uganda (Kayiwa et al., 2021). The mesopores are important in facilitating access of the molecules to the microporosity, this being especially important in adsorption from solution processes.

Decomposition of the lignin rich-derived char's carbonyl, hydroxyl, and carboxyl functional groups, at high activated temperatures in the ranges 600–800°C, produces volatile compounds (H_2O and CO_2) and non-volatile potassium carbonate (K_2CO_3) (Lozano-Castelló, Calo, Cazorla-Amorós, & Linares-Solano, 2007). The in situ formation of CO_2 and H_2O during KOH activation process plays a role in the growth of pores. Yahya et al., (2015) reported that chemical activation at higher temperatures develops the porosity of lignocellulosic samples by removing the low-molecular-weight volatile compounds from the matrix structure. The in situ physical process equations are detailed in a study by Wang & Kaskel. (Wang & Kaskel, 2012). Ramping the mixture of pre-leached Cassava peel and KOH to 780°C and holding it at the same temperature for 2 hours enabled the release of hydrogen and carbon monoxide gases. Moreover the temperature is above the boiling point of metallic potassium (760°C). The metallic potassium gasified and this contributed to the high porosity of the resultant AC. Besides, the intercalated metallic potassium in the carbon matrix widened the lattice spaces between carbon atomic layers (Gratuito, Panyathanmaporn, Chumnanklang, Sirinuntawittaya, & Dutta, 2008; Sudaryanto et al., 2006). These in situ synergistic occurrences do not only contribute to the ordered porous structure but also increment in surface area due to increased pore volumes. Besides, the reactivity of carbon increases with temperature and this implies more release of free K whose intercalation creates more pores notwithstanding its potential occlusion of the micropores (Huang & Zhao, 2016; Liu et al., 2015). However, on washing with hydrochloric acid the blocked pores are freed enhancing the surface area as shown in Fig. 4.

The surface area was remarkably highest at $1684 \text{ m}^2\text{g}^{-1}$, a value higher than $1352 \text{ m}^2\text{g}^{-1}$ reported by Ismanto, Wang, Soetaredjo, & Ismadji., (2010) and $1567 \text{ m}^2\text{g}^{-1}$ by Moreno-Piraján & Giraldo., (2010). This is due to the pre-leaching that reduced ash forming elements in the peels and leaving relatively higher volatile mass composition. At high carbonization temperatures the volatile content gasifies leaving voids (pores) between carbon atom layers and hence increasing the surface area. In a study by Li et al., (2008) on the effects of carbonization temperature on the porosity development in coconut shell chars and activated carbon derived from coconut shell char, the pore volumes and surface area increased appreciably with increase in temperature from 400 to 1000°C . In the same study, surface area and pore volume for the samples at the same carbonization temperature increased with activation time (0.5 to 2 hours). With such a remarkable surface area, cassava peel AC could be leveraged for high-end applications like super capacitor electrodes. At $1684 \text{ m}^2\text{g}^{-1}$, this surface area surpasses that of $1527\text{--}1634 \text{ m}^2 \text{ g}^{-1}$ for AC made from peanut shell and rice husk for super capacitors by He et al. (He et al., 2013) .

3.4 Active surface group analysis

3.4.1 Raw peels

The active surface groups have the expected main heteroatoms of carbon, hydrogen and oxygen. There are several functional groups on the raw cassava peels' surface, namely hydroxyl, carboxyl, carboxylate and others as shown in Table. 2. Similar groups were identified by other researchers (Mohd-Asharuddin, Othman, Mohd Zin, & Tajarudin, 2017; Simate, Ndlovu, & Seepe, 2015). In the same spectrum (Fig. 5(a)) at 1031 cm^{-1} C-O, C = C, and C-C-O stretching can be attributed to C-O-C asymmetrical stretching of hemicellulose, cellulose, and lignin.

3.4.2 Pre-leached peels

When pre-leached, the active surface groups varied according to the FTIR spectra shown in Fig. 5(b)) A peak at wave number 1633 of the pre-leached cassava peel indicates a carboxylate stretch most likely from the reaction of Na^+ from NaOH with carboxyl groups in the peels. This interaction indicates potential for application as a chemisorption based adsorbent. With modifications such as Nitrogen doping, the same can be harnessed in extreme gas adsorption for example carbon dioxide capture (Liu et al., 2018). At 2913 and 2900 wave numbers, there is a distortion tendency for the C-H bond. This could be due to the disruption of hemicellulose leading to elaboration of more lignin (Sun & Cheng, 2002). The distortion in the C-H bond indicates reduced crystallinity of the cellulose rich peels.

Table 2
Identified surface groups from FTIR spectra compared with other studies

Material under study	Wavelength (cm ⁻¹)	Active surface group
Raw peel [this study]	3419	Intermolecular OH
	2915	C-H bond from aliphatic groups
	2904	C-H bond from aliphatic groups
	1751	Carboxyl group stretching
	1634	Carboxylate groups
	1031	OH stretch (lignocellulosic precursors)
Raw peel (Simate et al., 2015)	500	-COOH stretch
	500–1000	OH stretch
	1500–2000	-C = O stretch
	1000–1500	-C-O stretch
	3000–3500	OH stretch
Raw peel (Idress, Shahril, Zuraidin, & Jasamai, 2019)	3700 – 3584	O-H stretch
	3550 – 3200	O-H stretch
	3500	N-H stretch
Pre-leached cassava peel [this study]	3412	O-H groups of free hydroxyl groups
	2913	C-H distortion
	2900	C-H distortion
	1755	C-O bond of carboxyl groups
	1633	Carboxylate group stretch
	1025	C-O vibration
AC from pre-leached cassava peel [this study]	3500–3600	OH group
	2980	Un saturated alkynes
	1712	Carbonyl group
	1620	Aromatic ring
	1445	Stretching C-C bond

Material under study	Wavelength (cm ⁻¹)	Active surface group
AC from cassava peel (Belcaid, Beakou, El Hassani, Bouhsina, & Anouar, 2020)	1147	Aromatic C-H of lignin
	1575	C = C vibration of the aromatic nucleus
AC from cassava peel (Astuti, Hidayah, Fitriana, Mahardhika, & Irchamsyah, 2020)	3841.83	OH group
	1250 – 1170	O-C stretching
Cassava rind carbon (Beakou et al., 2017)	1732	C = O stretch typical of aldehydes from hemicellulose
	1156	C-O-C stretch typical of hemicellulose, cellulose, and lignin
Cassava peel (Mohd-Asharuddin et al., 2017)	3500 – 3200	O-H group in polymeric compounds such as alcohols, phenols and carboxylic acids presented in pectin, cellulose and lignin on the cassava peels
	1750 – 1680	Stretching vibration of C = O bond of carboxyl groups
	1300 – 1000	C-O stretching of COOH
Cassava peel (Rachman et al., 2017)	3412	OH functional group
	1109	C-O vibration from secondary OH
	3000 – 2750	Absorption band which is C-H sp ³

3.4.3 Resultant AC

The FTIR spectrum for the AC produced from pre-leached peels shows some band distortions as observed in Fig. 5(c)). Bands around 3500–3600 cm⁻¹ are assigned to the stretching modes that are related to OH groups. The weak peak around 2980 cm⁻¹ indicates the presence of the unsaturated alkynes C = C stretching modes. This is further coupled with a vibration of C-H bending mode around 625 to 875 cm⁻¹. The band around 1620 cm⁻¹ is related to the stretching vibrations of bonds of aromatic rings, those coupled with conjugated carbonyl groups on the surface (Belcaid et al., 2020). The 1712 cm⁻¹ band corresponds to the stretching C = O bond where as the band at around 1445 cm⁻¹ indicates vibratory stretching of the C-C bond. The possible absorption bands for the AC were observed between 1425 and 1712 cm⁻¹.

3.5 Morphology

SEM investigated the morphology of the raw and pre-leached cassava peels and the resultant AC. Raw peels exhibited heterogeneity in their structure but no porosity with starch granules numerous on the surface (Fig. 6(a)).

It is evident in Fig that KOH played a key role in pore formation by releasing free K from its reactions with Carbon. The quasi chemical bonding of carbon, Oxygen and K (C-O-K) are therefore likely to have created new surface functionalities at temperatures above 700°C hence the evidence of K species on the unwashed AC in Fig. 6(c). The washed AC briquette in Fig. 6(d) shows that most of the free K surface species had been washed whereas the cross sectional view of the AC briquette in Fig. 6(b) showed that K species had been intercalated into the carbon matrix. This further shows that the free K that could have crystallized with in the matrix sublimed due to the temperatures above its melting point leaving free pores as seen in Fig. 6(e). The species intercalated in the AC matrix are hence due to the quasi chemical bonds most likely the -O-K bond (Liu et al., 2015; Mopoung, Moonsri, Palas, & Khumpai, 2015). The SEM image in Fig. 6(e) for the powdered AC showed a highly porous honeycomb structure. This is indicative of an improved surface area (Omotosho & Amori, 2016).

Conclusions

Pre-leaching cassava peels renders them more robust for preparation of high surface area activated carbon. This is enabled by the reduction in ash forming agents leaving more volatile content that contributes to pore formation during carbonization. Pre-leaching also disrupts the hemicellulose hence liberating more lignin.

Cassava peel varieties with relatively higher lignin content are more likely to produce relatively more mesoporous AC at temperatures above 650 °C notwithstanding lower yields and bulk densities of the resultant AC.

Carbonizing KOH activated cassava peels at temperatures above the melting point of potassium improves the surface area and pore volumes. Temperatures above 760 °C enable gasification of the intercalated metallic potassium contributing to formation of more pores. However, mesopores dominate such activated carbon relative to micropores due to the already widened interstitials by the intercalated potassium. This renders the resultant activated carbon applicable in adsorption of large molecules like pharmaceuticals.

Abbreviations

AC: Activated carbon

FTIR: Fourier transform Infrared

SEM: Scanning electron microscope

Declarations

Ethics approval and consent to participate

Not applicable

Consent for publication

Not applicable

Availability of data and materials

The data and the materials are all available in this article as well as the supporting information.

Competing interests

The authors report no declarations of interest.

Funding

African Centre of Excellence in Materials, Product Development & Nanotechnology (MAPRONANO ACE)

Government of Uganda through the Research and Innovation Fund - Makerere University. Grant No. RIF1/CEDAT/007

Authors' contributions

- Ronald Kayiwa - Conceptualization, Data collection, investigation and Writing original draft.
- Hillary Kasedde - Supervision, Writing-review and editing
- Michael Lubwama - Validation, resources and software
- John Baptist Kirabira - Funding acquisition, Methodology and project administration

Acknowledgements

The authors acknowledge the financial support provided by the African Centre of Excellence in Materials, Product Development & Nanotechnology (MAPRONANO) and the Government of Uganda through the Research and Innovation Fund - Makerere University.

Authors' information (optional)

References

Adekunle, A., Orsat, V., & Raghavan, V. (2016). Lignocellulosic bioethanol: A review and design conceptualization study of production from cassava peels. *Renewable and Sustainable Energy Reviews*, 64, 518–530. <https://doi.org/10.1016/j.rser.2016.06.064>

- Astuti, W., Hidayah, M., Fitriana, L., Mahardhika, M. A., & Irchamsyah, E. F. (2020). Preparation of activated carbon from cassava peel by microwave-induced H₃PO₄ activation for naphthol blue-black removal. *AIP Conference Proceedings*, 2243(June). <https://doi.org/10.1063/5.0001464>
- Barskov, S., Zappi, M., Buchireddy, P., Dufreche, S., Guillory, J., Gang, D., ... Sharp, R. (2019). Torrefaction of biomass: A review of production methods for biocoal from cultured and waste lignocellulosic feedstocks. *Renewable Energy*, 142, 624–642. <https://doi.org/10.1016/j.renene.2019.04.068>
- Beakou, B. H., El Hassani, K., Houssaini, M. A., Belbahloul, M., Oukani, E., & Anouar, A. (2017). Novel activated carbon from Manihot esculenta Crantz for removal of Methylene Blue. *Sustainable Environment Research*, 27(5), 215–222. <https://doi.org/10.1016/J.SERJ.2017.06.003>
- Belcaid, A., Beakou, B. H., El Hassani, K., Bouhsina, S., & Anouar, A. (2020). Efficient removal of Cr (VI) and Co (II) from aqueous solution by activated carbon from Manihot esculenta Crantz agricultural bio-waste . *Water Science and Technology*, 556–566. <https://doi.org/10.2166/wst.2020.585>
- Bhatnagar, A., Sillanpää, M., & Witek-Krowiak, A. (2015). Agricultural waste peels as versatile biomass for water purification - A review. *Chemical Engineering Journal*, 270, 244–271. <https://doi.org/10.1016/j.cej.2015.01.135>
- Casco, M. E., Martínez-Escandell, M., Kaneko, K., Silvestre-Albero, J., & Rodríguez-Reinoso, F. (2015). Very high methane uptake on activated carbons prepared from mesophase pitch: A compromise between microporosity and bulk density. *Carbon*, 93, 11–21. <https://doi.org/10.1016/j.carbon.2015.05.029>
- Daifullah, A. A. M., Girgis, B. S., & Gad, H. M. H. (2004). A study of the factors affecting the removal of humic acid by activated carbon prepared from biomass material. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*, 235(1–3), 1–10. <https://doi.org/10.1016/j.colsurfa.2003.12.020>
- Daud, W. M. A. W., & Ali, W. S. W. (2004). Comparison on pore development of activated carbon produced from palm shell and coconut shell. *Bioresource Technology*, 93(1), 63–69. <https://doi.org/10.1016/j.biortech.2003.09.015>
- Ekebafé, L. O., Imanah, J. E., & Okieimen, F. E. (2012). Effect of carbonization on the processing characteristics of rubber seed shell. *Arabian Journal of Chemistry*, 10, S174–S178. <https://doi.org/10.1016/j.arabjc.2012.07.018>
- Gani, A., & Naruse, I. (2007). Effect of cellulose and lignin content on pyrolysis and combustion characteristics for several types of biomass. *Renewable Energy*, 32(4), 649–661. <https://doi.org/10.1016/j.renene.2006.02.017>
- Gergova, K., Petrov, N., & Minkova, V. (1993). A comparison of adsorption characteristics of various activated carbons. *Journal of Chemical Technology & Biotechnology*, 56(1), 77–82.

<https://doi.org/10.1002/jctb.280560114>

González-García, P. (2018). Activated carbon from lignocellulosics precursors: A review of the synthesis methods, characterization techniques and applications. *Renewable and Sustainable Energy Reviews*, 82(August 2017), 1393–1414. <https://doi.org/10.1016/j.rser.2017.04.117>

Gratuito, M. K. B., Panyathanmaporn, T., Chumnanklang, R. A., Sirinuntawittaya, N., & Dutta, A. (2008). Production of activated carbon from coconut shell: Optimization using response surface methodology. *Bioresource Technology*, 99(11), 4887–4895. <https://doi.org/10.1016/j.biortech.2007.09.042>

He, X., Ling, P., Qiu, J., Yu, M., Zhang, X., Yu, C., & Zheng, M. (2013). Efficient preparation of biomass-based mesoporous carbons for supercapacitors with both high energy density and high power density. *Journal of Power Sources*, 240, 109–113. <https://doi.org/10.1016/j.jpowsour.2013.03.174>

Huang, Y., & Zhao, G. (2016). Preparation and characterization of activated carbon fibers from liquefied wood by KOH activation. *Holzforschung*, 70(3), 195–202. <https://doi.org/10.1515/hf-2015-0051>

Idress, M., Shahril, M. A., Zuraidin, A. S., & Jasamai, M. (2019). Experimental investigation of methane hydrate induction time in the presence of cassava peel as a hydrate inhibitor. *Energies*, 12(12), 1–11. <https://doi.org/10.3390/en12122314>

Ismanto, A. E., Wang, S., Soetaredjo, F. E., & Ismadji, S. (2010). Preparation of capacitor's electrode from cassava peel waste. *Bioresource Technology*, 101(10), 3534–3540. <https://doi.org/10.1016/j.biortech.2009.12.123>

Kalderis, D., Bethanis, S., Paraskeva, P., & Diamadopoulos, E. (2008). Production of activated carbon from bagasse and rice husk by a single-stage chemical activation method at low retention times. *Bioresource Technology*, 99(15), 6809–6816. <https://doi.org/10.1016/j.biortech.2008.01.041>

Kayiwa, R., Kasedde, H., Lubwama, M., & Kirabira, J. B. (2021). Characterization and pre-leaching effect on the peels of predominant cassava varieties in Uganda for production of Activated Carbon. *Current Research in Green and Sustainable Chemistry*. <https://doi.org/10.1016/j.crgsc.2021.100083>

Kwiatkowski, M., & Broniek, E. (2017). An analysis of the porous structure of activated carbons obtained from hazelnut shells by various physical and chemical methods of activation. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*, 529(June), 443–453. <https://doi.org/10.1016/j.colsurfa.2017.06.028>

Laine, J., & Yunes, S. (1992). Effect of the preparation method on the pore size distribution of activated carbon from coconut shell. *Carbon*, 30(4), 601–604. [https://doi.org/10.1016/0008-6223\(92\)90178-Y](https://doi.org/10.1016/0008-6223(92)90178-Y)

Li, W., Yang, K., Peng, J., Zhang, L., Guo, S., & Xia, H. (2008). Effects of carbonization temperatures on characteristics of porosity in coconut shell chars and activated carbons derived from carbonized coconut

shell chars. *Industrial Crops and Products*, 28(2), 190–198.

<https://doi.org/10.1016/j.indcrop.2008.02.012>

Liu, J., Liu, X., Sun, Y., Sun, C., Liu, H., Stevens, L. A., ... Snape, C. E. (2018). High Density and Super Ultra-Microporous-Activated Carbon Macrospheres with High Volumetric Capacity for CO₂ Capture. *Advanced Sustainable Systems*, 2(2), 1700115. <https://doi.org/10.1002/adsu.201700115>

Liu, J., Sun, N., Sun, C., Liu, H., Snape, C., Li, K., ... Sun, Y. (2015). Spherical potassium intercalated activated carbon beads for pulverised fuel CO₂ post-combustion capture. *Carbon*, 94, 243–255. <https://doi.org/10.1016/j.carbon.2015.06.036>

Lozano-Castelló, D., Calo, J. M., Cazorla-Amorós, D., & Linares-Solano, A. (2007). Carbon activation with KOH as explored by temperature programmed techniques, and the effects of hydrogen. *Carbon*, 45(13), 2529–2536. <https://doi.org/10.1016/j.carbon.2007.08.021>

Menya, E., Olupot, P. W., Storz, H., Lubwama, M., & Kiros, Y. (2018). Characterization and alkaline pretreatment of rice husk varieties in Uganda for potential utilization as precursors in the production of activated carbon and other value-added products. *Waste Management*, 81, 104–116. <https://doi.org/10.1016/j.wasman.2018.09.050>

Mohd-Asharuddin, S., Othman, N., Mohd Zin, N. S., & Tajarudin, H. A. (2017). A Chemical and Morphological Study of Cassava Peel: A Potential Waste as Coagulant Aid. *MATEC Web of Conferences*, 103(January). <https://doi.org/10.1051/mateconf/201710306012>

Mopoung, S., Moonsri, P., Palas, W., & Khumpai, S. (2015). Characterization and Properties of Activated Carbon Prepared from Tamarind Seeds by KOH Activation for Fe(III) Adsorption from Aqueous Solution. *Scientific World Journal*, 2015. <https://doi.org/10.1155/2015/415961>

Moreno-Piraján, J. C., & Giraldo, L. (2010). Study of activated carbons by pyrolysis of cassava peel in the presence of chloride zinc. *Journal of Analytical and Applied Pyrolysis*, 87(2), 288–290. <https://doi.org/10.1016/j.jaap.2009.12.003>

Mukiibi, D. R., Alicai, T., Kawuki, R., Okao-Okuja, G., Tairo, F., Sseruwagi, P., ... Ateka, E. M. (2019). Resistance of advanced cassava breeding clones to infection by major viruses in Uganda. *Crop Protection*, 115(October 2018), 104–112. <https://doi.org/10.1016/j.cropro.2018.09.015>

Okudoh, V., Trois, C., Workneh, T., & Schmidt, S. (2014). The potential of cassava biomass and applicable technologies for sustainable biogas production in South Africa: A review. *Renewable and Sustainable Energy Reviews*, 39, 1035–1052. <https://doi.org/10.1016/j.rser.2014.07.142>

Omotosho, & Amori, A. (2016). Effect of Zinc Chloride Activation on Physicochemical Characteristics of Cassava Peel and Waste Bamboo Activated Carbon. *International Journal of Chemical and Molecular Engineering*, 2016(6), 815–820. Retrieved from <https://waset.org/publications/10005655/effect-of-zinc>

chloride-activation-on-physicochemical-characteristics-of-cassava-peel-and-waste-bamboo-activated-carbon

Omotosho, O. A., & Sangodoyin, A. Y. (2013). Production and utilization of cassava peel activated carbon in treatment of effluent from cassava processing industry. *Water Practice and Technology*, 8(2), 215–224. <https://doi.org/10.2166/wpt.2013.023>

Parvathi, C., Shoba, U. S., Prakash, C., & Sivamani, S. (2018). Manihot esculenta Peel Powder: Effective Adsorbent for Removal of Various Textile Dyes from Aqueous Solutions. *Journal of Testing and Evaluation*, 46(6), 20170160. <https://doi.org/10.1520/jte20170160>

Rachman, R. A., Tri, U., Martia, I., Pambudi, A. B., Jovita, S., & Kurniawan, F. (2017). Cassava Peel Biosorbent (Manihot Utilissima) for Removal Chromium (Vi) With Microbial Fuel Cell System of Combination Techniques. *Proceeding of International Conference on Green Technology*, 8(1), 235–239.

Rodriguez - Reinoso, F. (2002). Carbons. In F. Schuth, K. S. . Sing, & J. Weitkamp (Eds.), *Handbbok of Porous Solids* (Vol. 3, pp. 1766–1827). WILEY-VCH Verlag GmbH, 69469 Weinheim.

Saka, C. (2012). BET, TG-DTG, FT-IR, SEM, iodine number analysis and preparation of activated carbon from acorn shell by chemical activation with ZnCl₂. *Journal of Analytical and Applied Pyrolysis*, 95, 21–24. <https://doi.org/10.1016/j.jaap.2011.12.020>

Salahudeen, N., Ajinomoh, C. ., Omega, S. ., & Akpaka, C. . (2014). Production of Activated Carbon from Cassava. *Journal of Applied Phytotechnology in Environmental Sanitation*, 3(2), 75–80.

Santos, V. L. F., Ferreira, M. A., Siqueira, M. C. B., Melo, T. T. B., Silva, J. L., Andrade, I. B., ... Costa, C. T. F. (2015). Rumen parameters of sheep fed cassava peel as a replacement for corn. *Small Ruminant Research*, 133, 88–92. <https://doi.org/10.1016/j.smallrumres.2015.09.010>

Savova, D., Apak, E., Ekinici, E., Yardim, F., Petrov, N., Budinova, T., ... Minkova, V. (2001). Biomass conversion to carbon adsorbents and gas. *Biomass and Bioenergy*, 21(2), 133–142. [https://doi.org/10.1016/S0961-9534\(01\)00027-7](https://doi.org/10.1016/S0961-9534(01)00027-7)

Sharypov, V. I., Marin, N., Beregovtsova, N. G., Baryshnikov, S. V., Kuznetsov, B. N., Cebolla, V. L., & Weber, J. V. (2002). Co-pyrolysis of wood biomass and synthetic polymer mixtures. Part I: Influence of experimental conditions on the evolution of solids, liquids and gases. *Journal of Analytical and Applied Pyrolysis*, 64(1), 15–28. [https://doi.org/10.1016/S0165-2370\(01\)00167-X](https://doi.org/10.1016/S0165-2370(01)00167-X)

Shirima, R. R., Legg, J. P., Maeda, D. G., Tumwegamire, S., Mkamilo, G., Mtunda, K., ... Kanju, E. (2020). Genotype by environment cultivar evaluation for cassava brown streak disease resistance in Tanzania. *Virus Research*, 286(January), 198017. <https://doi.org/10.1016/j.virusres.2020.198017>

Simate, G. S., Ndlovu, S., & Seepe, L. (2015). Removal of heavy metals using cassava peel waste biomass in a multi-stage countercurrent batch operation. *Journal of the Southern African Institute of Mining and*

Metallurgy, 115(12), 1137–1141. <https://doi.org/10.17159/2411-9717/2015/v115n12a1>

Sudaryanto, Y., Hartono, S. B., Irawaty, W., Hindarso, H., & Ismadji, S. (2006). High surface area activated carbon prepared from cassava peel by chemical activation. *Bioresource Technology*, 97(5), 734–739. <https://doi.org/10.1016/j.biortech.2005.04.029>

Sun, Y., & Cheng, J. (2002). Hydrolysis of lignocellulosic materials for ethanol production: A review. *Bioresource Technology*, 83(1), 1–11. [https://doi.org/10.1016/S0960-8524\(01\)00212-7](https://doi.org/10.1016/S0960-8524(01)00212-7)

Wang, J., & Kaskel, S. (2012). KOH activation of carbon-based materials for energy storage. *Journal of Materials Chemistry*, 22(45), 23710–23725. <https://doi.org/10.1039/c2jm34066f>

Xu, X., Zhao, Y., Sima, J., Zhao, L., Mašek, O., & Cao, X. (2017). Indispensable role of biochar-inherent mineral constituents in its environmental applications: A review. *Bioresource Technology*, 241, 887–899. <https://doi.org/10.1016/j.biortech.2017.06.023>

Yahya, M. A., Al-Qodah, Z., & Ngah, C. W. Z. (2015). Agricultural bio-waste materials as potential sustainable precursors used for activated carbon production: A review. *Renewable and Sustainable Energy Reviews*, 46, 218–235. <https://doi.org/10.1016/j.rser.2015.02.051>

Figures

Figure 1

AC bulk density variation with carbonization temperature

Figure 2

Variation of AC yield with carbonizing temperature.

Figure 3

Effect of carbonization temperature on the AC pore volume.

Figure 4

Effect of carbonizing temperature on the AC surface area.

Figure 5

FTIR spectra for: (a) raw cassava peel, (b) pre-treated peels and (c) the resultant AC.

Figure 6

SEM micrographs at ×600 resolution; (a) Raw cassava peel, (b) cut away surface for the washed AC briquette, (c) outer surface of the unwashed AC briquette, (d) outer surface of the washed AC briquette, (e) Powdered AC.

Supplementary Files

This is a list of supplementary files associated with this preprint. Click to download.

- [Graphicalabstract.jpg](#)