Efficacy of Titanium Brush, 915 nm Diode Laser, Citric Acid for Eradication of Staphylococcus Aureus from Implant Surfaces

Mohammad Reza Karimi

Islamic Azad University, Tehran

Behshad Farkhondemehr

Islamic Azad University, Tehran

Motahare Ghaeni Najafi

Islamic Azad University, Tehran

Ardavan Etemadi

Islamic Azad University, Tehran

Nasim Chiniforush (✉ n-chiniforush@sina.tums.ac.ir)

Tehran University of Medical Sciences

Research Article

Keywords: Peri-implantitis, Titanium brush, Diode laser, Citric acid

Posted Date: April 15th, 2021

DOI: <https://doi.org/10.21203/rs.3.rs-408196/v1>

License: © ⓘ This work is licensed under a Creative Commons Attribution 4.0 International License.

[Read Full License](#)

Version of Record: A version of this preprint was published at BMC Oral Health on December 1st, 2021.

See the published version at <https://doi.org/10.1186/s12903-021-01997-z>.

Abstract

Background: This study aimed to assess the efficacy of titanium brush, 915 nm diode laser, citric acid and the combination of latter two with titanium brush for decontamination of SLA surface mini-implants.

Materials and Methods: Seventy-five mini-implants contaminated with *Staphylococcus aureus* (*S. aureus*) were randomly divided into five experimental groups (n=12) of titanium brush (TiB), laser, citric acid (CA), brush-laser, and brush-acid, positive [n=12; chlorhexidine mouthwash (CHX)] and negative [n=2; phosphate buffered saline (PBS)] control groups and one no-treatment group (n=1). After counting the colony forming units (CFUs), data were analyzed using the Kruskal-Wallis and Dunn post-hoc tests.

Results: Regardless of the no-treatment and negative control groups, maximum and minimum CFUs were noted in the titanium brush and positive control groups. After CHX, minimum CFUs were noted in brush-acid group followed by brush-laser, laser, and acid groups. Generally, the Kruskal-Walli test revealed a significant difference between the groups regarding the colony count ($P < 0.001$). Dunn post-hoc test showed that the difference between the titanium brush and acid-brush group was significant ($P < 0.001$) while the differences between the brush and laser groups with the brush-laser group were not significant ($P > 0.077$).

Conclusions: Maximum reduction in colony count was noted in the positive control group. Combination of titanium brush and laser was also effective for decreasing the colony count; however, combined use of titanium brush and citric acid yielded superior results compared to other groups.

Introduction

With the increasing use of dental implants in dental rehabilitation of edentulous patients, the rate of related complications is also rising [1,2]. Peri-implantitis is the most common complication that refers to inflammation of the implant surrounding structures, causing their destruction. Peri-implantitis occurs in 10% of implants and 20% of patients within 5 to 10 years after implant placement [3,4]. If continues, the inflammatory mediators invade the junctional epithelium and bone marrow space and eventually cause bone destruction and compromise the implant stability and function. The pathogenesis of peri-implantitis involves colonization of oral flora microorganisms and periodontal pathogens on the implant surface [5-7]. Thus, its treatment should include infection control, decontamination of implant surface, regeneration of the lost tissue, and plaque control programs [4]. The conventional treatment methods for peri-implantitis include the use of curettes and sonic and ultrasonic scaling instruments [8]. Nonetheless, complete elimination of bacterial biofilm from the rough implant surface is not predictably feasible [9-11]. Moreover, these instruments can damage the implant surface and impair osteoblasts' adhesion and reosseointegration to implant [12].

Titanium brush is a mechanical instrument, which can be used for mechanical debridement of implant surfaces as an alternative to other mechanical instruments. Many studies have reported the optimal plaque removal efficacy of titanium brush with minimal surface modifications [13,14]. However, more

favorable results can be obtained by the combination use of titanium brush and chemical agents [14]. Evidence shows that citric acid has maximum decontamination efficacy among other chemical agents [15]. However, some studies have mentioned its irritability and toxicity for periodontal tissues when used in high concentrations [15,16].

Laser application is a relatively novel modality that can be effectively used as an adjunct to the mechanical methods for treatment of peri-implantitis [4]. The efficacy of decontamination by different laser types such as diode and Nd:YAG lasers depends on their thermal effect and subsequent denaturation of proteins and cell lysis [17]. Diode lasers are able to decontaminate implants with no surface damage [18-20]. Thus, this study aimed to compare the efficacy of titanium brush, 915 nm diode laser, citric acid and the combination of latter two with titanium brush for decontamination of mini-implant surfaces contaminated with *Staphylococcus aureus*.

Materials And Methods

Seventy-five ball type titanium mini-implants with SLA (sandblasted and acid-etched) surface (Dentium, Seoul, South Korea) measuring 2 x 6 mm were bought from company distributor for this in-vitro study. They were randomly divided into five experimental, two control and one no-treatment groups. The experimental and positive control groups included 12 mini-implants each. The negative control group included two mini-implants and the no-treatment group included one mini-implant [21]. A culture medium containing *S. aureus* (IBRC-M 10690) was obtained. For the purpose of contamination, each sterile mini-implant was immersed in 1 mL of *S. aureus* solution [mean concentration of 1×10^8 colony forming units (CFUs) per milliliter] [22]. The plates were then incubated at 37°C and 5% CO₂ for 72 h. Eventually, prior to decontamination, the mini-implants were dipped into sterile phosphate buffered saline (PBS; Gibco, Darmstadt, Germany) three times to eliminate unattached (planktonic) bacteria. Then, the two mini-implants in the negative control group were immersed in sterile PBS for 60 s. In the positive control group, 12 mini-implants were immersed in 0.2% v/w chlorhexidine (CHX) mouthwash for 60 s and then immersed in sterile PBS three times to eliminate excess CHX [13]. In the titanium brush group, a titanium brush (with bristles of 3 mm in length and 1 mm in diameter) was attached to a low-speed (20:1) contra-angle hand-piece (NSK, Tokyo, Japan) operating at 150 rpm with clockwise/counter-clockwise rotation, while the hand-piece was connected to a surgical micro-motor (220 V; NSK, Tokyo, Japan). 12 mini-implants in this group were debrided with the titanium brush for 120 s which was positioned perpendicular to the implant surface and was used in one single direction for each mini-implant. The applied pressure to the hand-piece remained constant at 50 N/cm² [13]. Each mini-implant was held by means of forceps from its crown. The debridement process was performed by the same operator.

For decontamination of each mini-implant in the citric acid group, an autoclave-sterilized swab was dipped in 40% citric acid (pH of 1) and gently rubbed on the surface for 2 minutes uniformly from the crown to the apex. To eliminate excess citric acid, each mini-implant was dipped into PBS with a forward-backward movement for three rounds, each round for 10 times [16]. The same operator applied citric acid on 12 mini-implants in this group. In the titanium brush- citric acid group, each of the 12 mini-implants

was first brushed for 120 s and then citric acid was applied for 2 min as explained earlier. In the laser group, each of the 12 mini-implants underwent diode laser irradiation with 910 nm wavelength (88Dent, Milan, Italy) and 1 W power in continuous-wave mode with a 300 μ non-initiated fiber tip for 60 s at 3 mm distance [23]. To ensure complete laser irradiation of all surfaces, each mini-implant was attached to a low-speed hand-piece operating at 20 rpm and during rotation, the laser hand-piece also moved along the longitudinal axis of the mini-implant [22]. The same operator irradiated all mini-implants. In the titanium brush-diode laser group, titanium brush was first used for 12 mini-implants for 120 s and then laser was irradiated for 60 s with methods as explained earlier. After decontamination, each mini-implant was immersed in 1 mL of brain heart infusion (BHI) broth (Merck, Darmstadt, Germany) and then vortexed by maximum intensity (up and down) for 1 min to detach the bacteria from the mini-implant surface. The obtained solution was serially diluted by sterile saline using the drop plate method. For colony counting, 50 μ L of each dilution was cultured on BHI broth agar and incubated under microaerophilic conditions for 48 h. The CFUs were counted by a single blind examiner and reported separately for each sample [24].

Results

The mean and standard deviation of experimental groups were presented in Table 1. As shown, maximum and minimum CFUs (regardless of the negative control and no-treatment groups) were found in the titanium brush and CHX groups. After CHX, minimum CFUs were noted in brush-acid, brush-laser, laser, and acid groups, in an ascending order.

The Kruskal-Wallis test showed a significant difference between the study groups ($P<0.001$). The Dunn post-hoc test was applied for pairwise comparisons of the groups, which revealed significant differences between the CHX group and each of the titanium brush, citric acid, laser, and brush-laser groups ($P\leq0.007$). Also, a significant difference was noted between the titanium brush and brush-acid groups ($P<0.001$). Pairwise comparisons of other groups (Table 2) revealed no significant difference ($P\geq0.077$) for instance the brush-acid and brush-laser ($P=0.405$), and brush-acid and laser ($P=0.077$) groups. Table 2 shows pairwise comparisons precisely.

Table 1

Comparison of the mean and standard deviation of *S. aureus* CFUs in the six groups (all groups except for the negative control and no-treatment groups; n=12)

Groups	Minimum	Maximum	Mean	Std. deviation
TiB+ CA	200	1300	608.3333	352.80263
CA	100	12500	4041.6667	4789.84880
TiB+ laser	600	4500	1908.3333	1151.64573
Laser	500	9000	2825.0000	2253.93595
TiB	2500	8000	4566.6667	1953.70666
CHX (positive control)	0	1500	241.6667	439.95523
PBS (negative control)	500000	1000000	647500	204618.547
TiB: Titanium brush, CT: Citric acid, CHX: Chlorhexidine				

Table 2

P values for pairwise comparisons of the six groups regarding *S. aureus* CFUs

	TiB	CA	Laser	TiB + Laser	TiB + CA	CHX
TiB	-	>0.999	>0.999	0.536	<0.001	<0.001
CA		-	>0.999	>0.999	0.326	0.005
Laser			-	>0.999	0.077	0.001
TiB + Laser				-	0.405	0.007
TiB + CA					-	>0.999
CHX						-
TiB: Titanium brush, CA: Citric acid, CHX: Chlorhexidine						

Discussion

The current results showed that PBS had the lowest efficacy for the decontamination of mini-implant surfaces and showed the highest colony count. No significant difference was noted in colony count between the CHX positive control group and brush-acid group ($P>0.999$), which means that these two groups had almost similar efficacy for the reduction of *S. aureus* colonies. No significant difference was noted between each of the brush and laser groups, and the brush-laser group; this finding indicated that combined use of laser and titanium brush adds no advantage, and the use of each modality alone can

yield the same result as their combined use. However, a significant difference existed between the brush-acid group and the titanium brush group, which indicated that the combined use of titanium brush and acid yielded significantly superior results ($P < 0.001$). In 2016, Saffarpour et al, compared the antimicrobial effects of photodynamic therapy, Er:YAG laser and 2% CHX in the elimination of *Aggregatibacter actinomycetemcomitans* biofilm from SLA implant surfaces CHX group showed the lowest and the control group showed the highest colony count. Their results were in agreement with ours, which may be due to the adoption of similar methodology in saline and CHX groups [21].

In 2016, Carral et al. evaluated dogs with peri-implantitis and found that the use of titanium brush can be an acceptable modality for the treatment of peri-implantitis [25]. Also in 2018, Vigano et al, evaluated six dogs with peri-implantitis and found that the application of titanium brush can effectively help in marginal bone regain. After five months, the dogs were reevaluated for marginal bone level radiographically, and the results revealed 0.6 mm bone gain in both groups with no significant difference between the saline and titanium brush groups. In other words, both methods effectively managed peri-implantitis in short-term [26]. In contrast, our results and those of some other studies [13,21] indicated that saline had minimum efficacy for decontamination of implant surfaces, and its efficacy was much lower than that of titanium brush. This controversy in the results may be due to different application methods of saline (application of a gauze soaked in saline and then rinsing with saline and repeating this procedure for ten times). Also, duration, speed, torque and direction of titanium brush usage and duration of the saline application were not mentioned in their study. In 2019, Toma et al. compared the efficacy of three mechanical modalities for the treatment of peri-implantitis in a randomized clinical trial on 47 patients. These modalities included the use of plastic curettes, air-abrasion and titanium brush. The patients were evaluated regarding plaque index, gingival index, bone loss and periodontal pocket depth at three time points namely initiation of treatment, three months after surgery, and six months after surgery. They reported that these mechanical methods improved the periodontal parameters in a short time. The reduction of periodontal pocket depth and gingival index in the titanium brush group was greater than that in other groups. They reported that titanium brush and glycine air-polishing were more effective than the other modality; however, the percentage of treatment success was still low; thus, they should be used in combination with antibacterial agents or antibiotics to yield more favorable results [27]. Despite the reportedly optimal efficacy of titanium brush in some studies, some others stated that it yields more favorable results when used in combination with other modalities. In this regard, in 2015, Widodo et al. assessed the efficacy of different methods for decontamination of titanium surfaces contaminated with *S. aureus* and showed that the use of titanium brush along with a non-mechanical modality is the most efficient method for reduction of *S. aureus* colony count on the polished and SLA implant surfaces, yielding superior results compared with the application of titanium brush or photodynamic therapy alone [13]. In 2019, De Tapia et al. assessed the efficacy of combined use of titanium brush, ultrasonic scaler and 3% hydrogen peroxide during regenerative surgery in a clinical trial on 30 patients. After one year of follow-up, clinical and radiographic examinations revealed that using titanium brush in regenerative surgery for treatment of peri-implantitis was highly effective and significantly decreased bone loss and pocket depth [28]. In line with our findings, in 2016 Htet et al. performed a clinical study on dogs with peri-

implantitis and concluded that the combined use of titanium burs and citric acid, compared with the use of titanium burs alone, resulted in better bone-implant contact and yielded superior results compared with Er: YAG laser in vertical bone height regeneration. This study was the first to use round titanium burs operating at 800 rpm under copious saline irrigation for 2 minutes; whereas, in previous studies, diamond burs were used to smoothen the implant surface and threads (implantoplasty). However, the 1-mm diameter of titanium burs prevented their complete access to the space between the threads. Thus, for complete debridement, use of a chemical agent along with the mechanical factor was imperative. Radiographic and histologic analyses yielded two important findings: (I) The combined use of citric acid and titanium bur yielded the best results, (II) Citric acid was able to eliminate the smear layer. They used cotton pellets dipped in 40% citric acid and gently rubbed them on the implant surfaces for 2 minutes, which was similar to our methodology [29]. Dalago et al. in their clinical trial in 2019, highlighted the significance of using citric acid as the most efficient chemical agent following mechanical debridement on 27 patients. They used 50% citric acid gel (pH of 1) for 3 minutes [30]. Concentration, form and duration of citric acid application in their study were different from ours; however, the results showed that citric acid, either alone or in combination with other modalities such as subepithelial connective tissue grafts or implantoplasty, could be effective in the treatment of peri-implantitis and increase the survival rate of implants.

In 2018, Rosen et al. stated that citric acid can eliminate the smear layer and residual organic debris. Also, its efficacy in combination with an air powder abrasive system would be high enough to enable the attachment and proliferation of human osteoprogenitor cells on the implant surface and allow performing regenerative treatments [31]. However, it should be noted that their study was pilot, and larger sample size is required in order to generalize the results. One of the crucial factors to consider in peri-implantitis treatment is that an ideal chemical agent should have selective toxicity, and a balance between its decontamination efficacy and resultant changes on titanium surfaces. In other words, evaluation of decontamination efficacy alone would not be enough when comparing chemical agents. It should be noted that a chemical agent residue on the titanium surfaces can change its physical properties and consequently, the response of osteoblasts. In this respect, in 2016 Kotsakis et al, evaluated several chemical agents for decontamination of implant surfaces. They compared four methods for decontamination of titanium discs namely (I) cotton pellets dipped in 0.12% CHX, (II) cotton pellets dipped in 20% citric acid, (III) cotton pellets dipped in 24% EDTA and 1.5% sodium hypochlorite (NaOCl-EDTA group) and (IV) cotton pellets dipped in 9% sterile saline. The duration of decontamination was 20 seconds in all groups. After colony counting, they found that the citric acid group had maximum decontamination efficacy followed by: NaOCl-EDTA, CHX and sterile saline groups. The concentrations of CHX and citric acid used in our study were different from theirs, which seems to be responsible for the difference in the results. Their results revealed that CHX can compromise the biocompatibility of titanium surfaces. Thus, it is not recommended for treatment of peri-implantitis; whereas, citric acid, NaOCl-EDTA and sterile saline enhanced the biocompatibility of titanium surfaces and thus, they can be safely used for treatment of peri-implantitis [32]. The abovementioned study explains why other methods are preferred to CHX for treatment of peri-implantitis despite its availability and ease of application.

Regarding the diode laser, in 2017, Valente et al. assessed 130 implants placed in bone blocks with standardized vertical defects and contaminated with *Streptococcus sanguinis*. Next, they decontaminated the implants using 810 and 980 nm diode lasers. They showed that the application of diode laser at these wavelengths significantly decreased the contamination. Similar to our study, they used 1 W laser for 60 s at a 3 mm distance. A noteworthy issue is that this specific wattage was selected after the results of pilot studies indicated that 0.6 and 0.8 wattages were not sufficient and powers higher than 1 W caused histological changes in bone [23]. In 2010 Goncalvez et al. contaminated the machined, titanium oxide sandblasted, and SLA implant surfaces with *Porphyromonas gingivalis* and *Enterococcus faecalis* and then decontaminated them using 980 nm diode and Nd: YAG lasers with two different powers. Reduction in colony count (in variable percentages) was noted in all groups. The reduction in colony count was 100% on SLA implant surfaces contaminated with *Porphyromonas gingivalis* and decontaminated with diode laser at both powers. However, the reduction in colony count was 50% on SLA implant surfaces contaminated with *Enterococcus faecalis* and decontaminated with 2.5 W diode laser, and 100% in the same group when 3 W laser was used. Differences between their results and ours may be due to the use of different bacterial species, also different wavelengths and powers of diode laser. Also, lasers were used for 5 min in their study [23]. In contrast, a review study in 2016 by Lin et al. on 11 articles, regarding the application of laser for treatment of peri-implantitis and peri-implant mucositis showed that using laser in combination with surgical or non-surgical treatment modalities had low efficacy for decreasing the probing depth and clinical attachment loss. However, application of laser combined with non-surgical treatment modalities decreased bleeding on probing in short-term [33]. This can be due to the fact that this review article evaluated clinical studies and did not include in vitro studies. Also, the diode lasers used in these studies had different wavelengths than ours.

In conclusion, our findings and those of previous studies indicated that the application of titanium brush alone was not highly effective in the treatment of peri-implantitis, but it should be used in combination with some other modalities. Its combination with citric acid yielded better results than its combined use with 915 nm diode laser in this study. Moreover, the application of citric acid has a lower cost and enhances the biocompatibility of titanium surfaces, and is therefore effective and safe for the treatment of peri-implantitis. In this study, PBS and CHX showed minimum and maximum decontamination efficacy, respectively. However, despite the ease of use and availability of CHX, we tried to find alternative methods since previous studies revealed that CHX compromises the biocompatibility of titanium surfaces and is therefore not recommended for treatment of peri-implantitis [32].

It should be noted that this study had an in vitro design, and clinical studies are required to confirm its results prior to their generalization to the clinical setting.

Declarations

Ethics approval and consent to participate:

Not applicable. This study was in-vitro.

Consent for publication:

All authors agree for publish this work.

Availability of data and materials:

The datasets used and/or analyzed during the current study are available from the corresponding author on reasonable request.

Competing interests:

The authors declare that they have no competing interest

Funding:

No funding was received for this research.

Authors' Contributions:

All of the authors contributed to the investigation, supervision, writing, review, and editing of the study. The study was conceptualized by AE, MRK and NCH. Data curation, data visualization, and formal analysis were carried out by MGN and BF.

Acknowledgements:

we thank Tehran Medical Sciences, Islamic Azad University, Tehran, Iran.

References

1. Kim JH, Herr Y, Chung JH, Shin SI, Kwon YH (2011) The effect of erbium-doped: yttrium, aluminium and garnet laser irradiation on the surface microstructure and roughness of double acid-etched implants. J Periodontal Implant Sci.;41(5):234-41.
2. Lee JH ,Kwon YH, Herr Y, Shin SI, Chung JH (2011) Effect of erbium-doped: yttrium, aluminium and garnet laser irradiation on the surface microstructure and roughness of sand- blasted, large grit, acid-etched implants. J Periodontal Implant Sci.;41(3):135-42.
3. Albrektsson TO, Johansson CB, Sennerby L(1994) Biological aspects of implant dentistry:osseointegration. Periodontol 2000;4:58-73.

4. Alshehri FA(2016) The role of lasers in the treatment of peri-implant diseases: A review.Saudi Dent J;28(3):103-8.
5. Alcoforado GA, Rams TE, Feik D, Slots J(1991) Microbial aspects of failing osseointegrated dental implants in humans. J Parodontol;10(1):11-8.
6. Becker W, Becker BE, Newman MG, Nyman S(1990) Clinical and microbiologic findings that may contribute to dental implant failure. Int J Oral Maxillofac Implants ;5(1):31-8.
7. Mombelli A, Buser D, Lang NP(1988)Colonization of osseointegrated titanium implants in edentulous patients. Early results. Oral Microbiol Immunol ;3(3):113-20.
8. Augthun M, Tinschert J, Huber A(1998) In vitro studies on the effect of cleaning methods on different implant surfaces. J Periodontol;69(8):857-64.
9. Schwarz F, Papanicolaou P, Rothamel D, Beck B, Herten M, Becker J(2006) Influence of plaque biofilm removal on reestablishment of the biocompatibility of contaminated titanium surfaces. J Biomed Mater Res A;77(3):437-44.
10. Schwarz F, Sculean A, Romanos G, Herten M, Horn N, Scherbaum W, et al(2005) Influence of different treatment approaches on the removal of early plaque biofilms and the viability of SAOS2 osteoblasts grown on titanium implants. Clin Oral Investig;9(2):111-7.
11. Kreisler M, Kohnen W, Christoffers AB, Gotz H, Jansen B, Duschner H, et al(2005)Invitro evaluation of the biocompatibility of contaminated implant surfaces treated with an Er : YAG laser and an air powder system. Clin Oral Implants Res;16(1):36-43.
12. Takasaki AA, Aoki A, Mizutani K, Kikuchi S, Oda S, Ishikawa I(2007) Er:YAG laser therapy for peri-implant infection: a histological study. Lasers Med Sci.57-143(:)3(22;
13. Widodo A, Spratt D, Sousa V, Petrie A, Donos N(2007)An in vitro study on disinfection of titanium surfaces. Clin Oral Implants Res;27(10):1227-32.
14. Louropoulou A, Slot DE, Van der Weijden F(2014) The effects of mechanical instruments on contaminated titanium dental implant surfaces: a systematic review. Clin Oral Implants Res;25(10):1149-60.
15. Ntrouka V, Hoogenkamp M, Zaura E, van der Weijden F(2011)The effect of chemotherapeutic agents on titanium-adherent biofilms. Clin Oral Implants Res;22(11):1227-34.
16. Valderrama P, Blansett JA, Gonzalez MG, Cantu MG, Wilson TG (2014) Detoxification of Implant Surfaces Affected by Peri-Implant Disease: An Overview of Non-surgical Methods. Open Dent J;8:77-84.
17. Mellado-Valero A, Buitrago-Vera P, Sola-Ruiz MF, Ferrer-Garcia JC (2013) Decontamination of dental implant surface in peri-implantitis treatment: a literature review. Med Oral Patol Oral Cir Bucal;18(6):e869-76.
18. Castro GL, Gallas M, Nunez IR, Borrajo JL, Alvarez JC, Varela LG(2007) Scanning electron microscopic analysis of diode laser-treated titanium implant surfaces. Photomed Laser Surg;25(2):124-8.

19. Goncalves F, Zanetti AL, Zanetti RV, Martelli FS, Avila-Campos MJ, Tomazinho LF, et al(2010)Effectiveness of 980-nm diode and 1064-nm extra-long-pulse neodymium-doped yttrium aluminum garnet lasers in implant disinfection. *Photomed Laser Surg*;28(2):273-80.
20. Kushima SS, Nagasawa M, Shibli JA, Brugnera A, Jr., Rodrigues JA, Cassoni A (2016)Evaluation of Temperature and Roughness Alteration of Diode Laser Irradiation of Zirconia and Titanium for Peri-Implantitis Treatment. *Photomed Laser Surg*;34(5):194-9.
21. Saffarpour A, Fekrazad R, Heibati MN, Bahador A, Rokn AR, et al(2016) Bactericidal Effect of Erbium-Doped Yttrium Aluminum Garnet Laser and Photodynamic Therapy on Aggregatibacter Actinomycetemcomitans Biofilm on Implant Surface. *Int J Oral Maxillofac Implants*;31(3):e71-8.
22. Goncalves F, Zanetti AL, Zanetti RV, Martelli FS, Avila-Campos MJ, Tomazinho LF, et al (2011) Effectiveness of 981-nm diode and 1164-nm extra-long-pulse neodymium-doped yttrium aluminum garnet lasers in implant disinfection. *Photomed Laser Surg* ;28(2):273-81.
23. Valente NA, Mang T, Hatton M, Mikulski L, Andreana S(2017) Effects of Two Diode Lasers With and Without Photosensitization on Contaminated Implant Surfaces: An Ex Vivo Study. *Photomed Laser Surg* ;35(7):347-56.
24. Sousa V, Mardas N, Spratt D, Boniface D, Dard M, Donos N (2016) Experimental models for contamination of titanium surfaces and disinfection protocols. *Clin Oral Implants Res* ;27(10):1233-42."
25. Carral C, Muñoz F, Permuy M, Linares A, Dard M, Blanco J (2016) Mechanical and chemical implant decontamination in surgical peri-implantitis treatment: preclinical "in vivo" study. *J Clin Periodontol*; 43(8):694-701.
26. Vigano P, Apaza KA, Sakuma S, Amari Y, et al (2018) Use of TiBrush for surface decontamination at peri-implantitis sites in dogs: Radiographic and histological outcomes. *J Invest Clin Dent.*; 10(1)
27. Toma, S.; Brex, M.C.; Lasserre, J.F (2019) Clinical Evaluation of Three Surgical Modalities in the Treatment of Peri-Implantitis: A Randomized Controlled Clinical Trial. *J. Clin. Med.*8, 966.
28. De Tapia B, Valles C, Ribeiro-Amaral T, Mor C, et al (2019)The adjunctive effect of a titanium brush in implant surface decontamination at peri-implantitis surgical regenerative interventions: A randomized controlled clinical trial. *J Clin Periodontol*;46:586-596
29. Htet M , Madi M , Zakaria OS, Miyahara T, Xin W, Lin Z, Kasugai SH(2016) Decontamination of Anodized Implant Surface With Different Modalities for Peri-Implantitis Treatment: Lasers and Mechanical Debridement With Citric Acid . *J Clin Periodontol*; 87(8):953-961
30. Dalago HR , Perrotti V , Torres de Freitas SF , Ferreira CF , Piattelli A , Iaculli F(2019) Prospective longitudinal comparison study of surgical therapies for peri-implantitis: 3-year follow-up. *Aus dent J*; 64(3):237-245
31. Rosen, Paul S.; Qari, Maha; Froum, Stuart J.; Dibart, Serge; Chou, L. Le(2018) A Pilot Study on the Efficacy of a Treatment Algorithm to Detoxify Dental Implant Surfaces Affected by Peri-implantitis. *Int J of Periodontics & Restorative Dent* ; 38(2):261-267

32. Kotsakis A, Lan C ,Barbosa J, Lill K, Chen R, Rudney J, Aparicio C (2016)Antimicrobial Agents Used in the Treatment of Peri-Implantitis Alter the Physicochemistry and Cytocompatibility of Titanium Surfaces. J Clin Periodontol; 87(7):809-819
33. Lin GH, Suarez F, Wang HL (2018) Laser therapy for treatment of peri-implant mucositis and peri-implantitis: An American Academy of Periodontology best evidence review. J Periodontol; 89:766-782

Supplementary Files

This is a list of supplementary files associated with this preprint. Click to download.

- [supplementary.docx](#)