Preparation of Cotton Fibers Modified With Aromatic Heterocyclic Compounds and Study of Cr(VI) Adsorption Performance

Zhiyu Huang

Wuhan Textile University

Peng Wu

Third Institute of Oceanography Ministry of Natural Resources

Yankun Yin

Wuhan Textile University

Xiang Zhou

Wuhan Textile University

Lu Fu

Wuhan Textile University

Luoxin Wang

Wuhan Textile University

shaohua chen (✉ shaohuachen@foxmail.com)

Wuhan Textile University <https://orcid.org/0000-0002-0274-2089>

Xu Tang

Third Institute of Oceanography Ministry of Natural Resources

Research Article

Keywords: Degreasing cotton, Chromium, Adsorption, Aminopyridine, Aminopyrazine, Surface modification

Posted Date: May 25th, 2021

DOI: <https://doi.org/10.21203/rs.3.rs-510086/v1>

License: © ⓘ This work is licensed under a Creative Commons Attribution 4.0 International License.

[Read Full License](#)

Preparation of cotton fibers modified with aromatic heterocyclic compounds and study of Cr(VI) adsorption performance

Zhiyu Huang^{a,1}, Peng Wu^{b,1}, Yankun Yin^a, Xiang Zhou^a, Lu Fu^a, Luoxin Wang^a,

Shaohua Chen^{a,*}, Xu Tang^{b,**}

^aKey Laboratory of Textile Fibers and Products, Ministry of Education, P. R. C, College of Materials Science and Engineering, Wuhan Textile University, Wuhan 430200, China

^bThird Institute of Oceanography Ministry of Natural Resources, P. R. C, Xiamen 361005, China

* Corresponding author.

** Corresponding author.

¹ Zhiyu Huang and Peng Wu as co-first author contributed equally to this work

Corresponding author: Shaohua Chen^{a,*} and Xu Tang^{b,**}

Email: shaohuachen@foxmail.com (S.H.C), tangxu@tio.org.cn (X. T)

ABSTRACT:

In order to prepare low-cost and environmentally friendly adsorbent materials for adsorption of heavy metal ion, two kinds of novel modified cottons (C-4-APD and C-2-APZ) were obtained by introducing 4-aminopyridin and 2-aminopyrazine into the surface of degreasing cotton, respectively, and used for the removal of Cr(VI) ions from aqueous solution. The two modified cottons were characterized by Scanning Electron Microscopy (SEM), Fourier Transform Infrared Spectroscopy (FTIR) and X-ray

1 photoelectron spectroscopy (XPS), which confirmed the amino groups, pyridine groups
2 and pyrazine groups grafted onto the surface of modified cottons. The maximum
3 adsorption capacities of C-4-APD and C-2-APZ were 73.78 mg/g and 61.34 mg/g,
4 respectively, at the optimum pH of 6 and an initial concentration of 200 mg/g. Kinetic
5 and isotherm studies were carried out to investigate the adsorption behavior of the
6 modified cottons on Cr(VI) ions. The results showed that the adsorption of Cr(VI) ions
7 by modified cottons followed a pseudo-second-order kinetic model, the equilibrium
8 data were in good agreement with the Langmuir isotherm model, and electrostatic and
9 chemisorption may be the main adsorption mechanisms. The recovery and reuse of
10 modified cotton were achieved by washing with 2 wt% thiourea-hydrochloric acid
11 solution (0.5 mol/L concentration of HCl), and the adsorption capacities of C-4-APD
12 and C-2-APZ were maintained above 90% and 80%, respectively, after six cycles.

13 **Keywords:** Degreasing cotton; Chromium; Adsorption; Aminopyridine;
14 Aminopyrazine; Surface modification

15 **1. Introduction**

16 The presence of chromium in the environment is generally Cr(III) and Cr(VI).
17 Trace amounts of Cr(III) can reduce the blood glucose concentration in the human body
18 to a certain extent, accelerate the metabolic process of sugar and substances required
19 by the body, and the human insulin activity and stress response capacity can also be
20 regulated by Cr(III)(Kooshki et al. 2021 , Moradi et al. 2019). Cr(VI) has higher
21 mobility, bioavailability and carcinogenic effect, and is 100 times more toxic than
22 Cr(III), which can cause more serious harm to various organisms(Kimbrough et al.

1999 , Singh and Chowdhuri 2017). At present, the main methods for treating chromium-containing wastewater are adsorption(Sun et al. 2021), chemical(Bao et al. 2020), ion exchange(Li et al. 2017), electrochemical(Yao et al. 2020) and biological methods(Long et al. 2020), etc. The most industrial application is adsorption method, which is suitable for the deep purification of low concentration chromium-containing wastewater because of its simplicity and convenience(Zhao et al. 2015). However, most of the adsorbents reported in the literature for the removal of hexavalent chromium are prepared under complicated process conditions, raw materials are not easily available, costs are high, and they are also difficult to degrade in the natural environment, which may cause secondary pollution to the environment in practical applications.

Biomass materials are widely available, relatively low-priced, with large specific surface area, good stability and biodegradable, etc. At the same time, the surface of biomass materials is rich in hydroxyl groups and other reactive groups, which can be regulated and functionalized by chemical or physical methods, and are ideal choices for carrier materials(Xu et al. 2016), such as cellulose(Park et al. 2020 , Sharma et al. 2018), lignin(Wu et al. 2008), hemicellulose(Wei et al. 2021), chitosan(Vakili et al. 2018 , Eliodorio et al. 2017), etc. Highly efficient adsorbents were prepared by grafting the cellulose with functional groups(Zhang et al. 2019 , Xie et al. 2017 , Li et al. 2018), Liang et al. (2020) reported the maximum Cr(VI) uptake was 490.3 mg/g for quaternized cellulose grafted with polyethyleneimine in the presence of epichlorohydrin. The imidazole groups were successfully grafted onto the macroporous cellulose by a homogeneous method to fabricate 3D macroporous materials with

1 synergistic advantages of cellulose and polyvinylimidazole, and the optimized
2 adsorbent exhibited a fast adsorption rate (0.12 g / (mg/min)) and high adsorption
3 capacity (134 mg/g)(Peng et al. 2020). However, for crude processed biomass materials
4 such as cotton, hemp, and agricultural wastes, the corresponding reports are less
5 available and have a low Cr(VI) adsorption capacity. For example, Rojas et al. (2018)
6 reported the removal of Cr(VI) from water using cotton fibers coated with deacetylated
7 chitosan, and the adsorption capacity for Cr(VI) was 7.5 mg/g at pH 2.0. The crude
8 processed biomass material is more widely available and if it is utilized to improve and
9 increase its adsorption capacity for Cr(VI), the processing steps for preparing biomass-
10 based adsorbents can be more simplified and less costly.

11 Pyridines and pyrazines are important intermediate compounds that are widely
12 used in the synthesis of medical (agricultural) drugs and in the preparation of dyes, and
13 they can also be used as drugs and analytical reagents themselves. However, there are
14 few reports on the use of pyridines and pyrazines for contaminant treatment. By
15 electron-donating nitrogen, as well as electron-rich π -conjugated structures, and the
16 nitrogen atoms in pyridine group and pyrazine group form hydrogen bonds, so the
17 polymer containing pyridine group or pyrazine group has the ability of coordination
18 chelation, which can be used for the removal of metal ions in solution and
19 environmental pollution control. Geng et al. (2020) reported that two kinds of
20 fluorescent conjugated microporous polymers containing pyrazine moieties were
21 prepared by the polymerization reaction of 2,5-di-triphenylamine-yl-pyrazine(DTPAPz)
22 and N,N,N',N'-tetrapheny-2,5-(diazyl) pyrazine (TDPz), for adsorbing and fluorescent

sensing of iodine. Bayramoglu et al. (2016) reported that aminopyridine modified *Spirulina platensis* biomass for Cr(VI) adsorption in aqueous solution. chemical modification of *Spirulina platensis* biomass was realized by sequential treatment of algal surface with epichlorohydrin and aminopyridine. The adsorption capacity at pH 3.0 was found to be 79.6 and 158.7 mg/g, for native and modified algal biomasses, respectively. It is clear from these studies that pyridines and pyrazines have good potential for the treatment of heavy metal ions and other contaminants.

Therefore, in order to further reduce costs and prepare environmentally friendly adsorbent materials, 4-aminopyridine and 2-aminopyrazine were introduced to the surface of degeasing cotton using one-pot method in this study. The cotton-4-aminopyridine(C-4-APD) and the cotton-2-aminopyrazine(C-2-APZ) were obtained and used for the removal of Cr(VI) ions from aqueous medium. The morphology and structure property of the prepared samples were characterized by the SEM, FTIR and XPS. Additionally, the adsorption behavior of Cr(VI) on C-4-APD and C-2-APZ was investigated by Langmuir and Freundlich models, and the experimental data were fitted by two kinetic models, pseudo-first-order and pseudo-second-order(Simonin 2016), to analyze the mechanism of Cr(VI) adsorption, and its reusability was evaluated by repeated adsorption-elution, and the modification effect of the two groups on cotton fibers was also compared.

2. Experiment

2.1 Materials

Potassium chromate(99.9% metals basis), 4-aminopyridin(98%) and 2-

aminopyrazine(99%) were purchased from Shanghai Macklin Biochemical Co., Ltd(Shanghai, China). Epichlorohydrin, N,N-dimethylformamide (DMF), hydrochloric acid(30%) and thiourea(AR 99%) were purchased from Sinopharm Chemical Reagent Corp (Shanghai, China). Degreasing cotton was supplied from Xuzhou Weicai Hygiene of Material Factory Co. LTD (Xuzhou, China).

2.2 Preparation of cotton-4-aminopyridin and cotton-2-aminopyrazine

1 g of degreasing cotton was soaked in the solvent of 50 mL of N,N-dimethylformamide and 50 mL of epichlorohydrin to soak. In the first stage, the reaction temperature was controlled at 80 °C, and the chloromethylated skimmer was stirred slowly for 2 h with a magnetic stirrer to obtain chloromethylated degreasing cotton; In the second stage, 10 mmol of 4-aminopyridin or 2-aminopyrazine was accurately added to the above solution. The mixture continued to be stirred for 5 h at 90 °C. The procedure for preparation of C-4-APD/C-2-APZ is illustrated in Fig. 1.

Fig.1 Schematic illustration of the C-4-APD and C-2-APZ preparation process.

2.3 Characterization

Surface morphological characteristics of degreasing cotton, C-4-APD and C-2-APZ were examined by scanning electron microscopy (SEM) using a JSM-IT300A scanning electron microscope (JEOL Ltd., Tokyo, Japan). Bonding structure and surface functionalization of samples were conducted on a VERTEX 70 FT-IR spectrometer by using potassium bromide pressed-disk technique, respectively. The scan range was 400 to 4000 cm^{-1} . The elemental composition of the samples was measured by XPS using Thermo Scientific K-Alpha (Thermo Fisher).

2.4 Adsorption experiments

The effect of pH of the reaction system on the Cr(VI) adsorption capacity brought by C-4-APD and C-2APZ in Cr(VI) adsorption experiments, as well as their adsorption thermodynamics, adsorption kinetics, and recyclability were investigated by a series of adsorption experiments. All Cr(VI) adsorption experiments were performed in 150 mL beakers at room temperature and shaken at 120 rpm in a mechanical shaker. To explore the effect of pH on the Cr(VI) adsorption capacity, 0.16 g of C-4-APD/C-2-APZ was placed into 100 ml of 100 mg/L Cr(VI) solution with different pH values. The pH was adjusted by concentrations of 0.5 M and 1 M hydrochloric acid. Cr(VI) concentrations were determined by ICP 2060T inductively coupled plasma emission spectrometer (Jiangsu Tianrui Instruments Co., Ltd., Kunshan, China), and the adsorption capacity of modified cotton for Cr(VI) was calculated as follows:

$$Q = \frac{(C_0 - C_e) \times V}{m} \quad (1)$$

where C_0 and C_e (mg/L) are the initial concentration and the equilibrium concentration of Cr(VI), V (L) is the volume of Cr(VI) solution, and m (mg) is the mass of the

absorbent.

3. Results and discussion

3.1. Characterization of the samples

Fig.2 shows the scanning electron micrographs of degreasing cotton, C-4-APD and C-2-APZ. The surface of the degreasing cotton fiber was smooth and the diameter of the cotton fiber was about 15 μm as seen in Fig. 1A. From Fig. 1B and Fig. 1C, it was observed that the surfaces of both C-4-APD and C-2-APZ become rough, indicating that organic monomers are grafted on the surface of cotton fibers.

Fig.2 SEM images of the degreasing cotton (A), C-4-APD (B) and C-2-APZ (C).

Fig.3 shows the FTIR spectra of degreasing cotton, C-4-APD and C-2-APZ. The FTIR profiles of skimmed cotton: the peaks at 3315 cm^{-1} are caused by stretching vibrations due to the presence of a large number of hydroxyl hydrogen bonds in the cotton fiber; the peaks at 1407 cm^{-1} and 1303 cm^{-1} are caused by the bending vibrations of CH_2 and CH present in large quantities in the cellulose backbone structure, respectively; the characteristic absorption bands at 1149 cm^{-1} and 1019 cm^{-1} are each attributed to the asymmetric stretching vibration of C-O-C and the stretching vibration of C-O in the cellulose six-membered ring structure(Wang et al. 2019). After attachment of 4-aminopyridine/2-aminopyrazine via epichlorohydrin coupling reaction, the spectrum of

1 the modified degreasing cotton exhibits some changes. The peak formed at 3244 cm^{-1}
 2 was an N-H stretching vibration peak in the imine group(Bayramoglu et al. 2016).
 3 Besides, the new characteristic peaks observed at 1643 cm^{-1} , 1638 cm^{-1} , and 1543 cm^{-1}
 4 are caused by C=N and C-N bonds in the aromatic heterocycles, confirming the
 5 successful grafting of pyridine and pyrazine groups on the degreasing cotton surface(Hu
 6 et al. 2014 , Lu et al. 2020).

7
 8 **Fig. 3** FTIR spectra of degreasing cotton, C-4-APD and C-2-APZ.

9 The mass fraction of elements of the degreasing cotton, C-4-APD and C-2-APZ were
 10 determined using XPS to study the amount of aromatic heterocyclic compounds
 11 introduced. As shown in Table 1, the degreasing cotton contains almost no elemental N.
 12 After grafting the 4-aminopyridine and 2-aminopyrazine onto the surface of the
 13 degreasing cotton, the N elemental content of C-4-APD and C-2-APZ increased

significantly, which further proved the successful introduction of 4-aminopyridine and 2-aminopyrazine on the surface of degreasing cotton.

Table 1 The mass fraction of elements of degreasing cotton, C-4-APD and C-2-APZ.

materials	C/%	N/%	O/%
Dgreasing cotton	70.83	0.59	28.58
C-4-Aminopyridine	69.7	5.52	24.78
C-2-Aminopyrazine	65.28	9.69	25.03

3.2. Batch adsorption studies

3.2.1. Effect of pH

Fig.4 shows the difference in the adsorption capacity of C-4-APD and C-2-APZ for Cr(VI) in the range of solution pH from 2 to 8, with an adsorption time of 4 h. In aqueous media, Cr(VI) ions exist mainly as soluble oxides, and the ionic species depend on the pH of the medium and the total concentration of Cr(VI) in the solution, when the solution pH is less than 2.0, the dominant species is H_2CrO_4 . When the solution pH is greater than 7.0, only CrO_4^{2-} is present, while the solution pH is between 2.0 and 6.0, HCrO_4^- and $\text{Cr}_2\text{O}_7^{2-}$ dominate (Bayramoglu et al. 2016). It can be seen from graphs that the adsorption of Cr(VI) by C-4-APD and C-2-APZ increases as the pH decreases, which mainly due to the N atoms in the pyridine, pyrazine and imine groups are prone to binding H^+ under acidic conditions leading to protonation and gravitational binding between them and the negatively charged Cr(VI) anion, resulting in an increase in the removal efficiency of Cr(VI). As shown in Fig.4, the adsorption capacity of the former was higher than that of the latter, which was due to the different electron cloud distribution of the N atoms between the 4-aminopyridin and 2-aminopyrazine. The N atoms of the pyridine group in 4-aminopyridin are in the opposite position of the amino

group, which have stronger ability to bind H^+ when protonated, while the N atoms of pyrazine group in 2-aminopyrazine are in the adjacent and interposition of amino group, respectively, of which the electron cloud distribution was more dispersed, and the ability of binding H^+ was weaker when protonated. At the solution pH less than 2.0, the degreasing cotton skeleton started to be decomposed by corrosion, thus, it was determined that the adsorption capacity of C-4-APD and C-2-APZ for Cr(VI) reached the maximum at pH=2.0, and the subsequent experiments were carried out at this pH value.

9

10 **Fig. 4** Effect of the pH value on the adsorption of Cr(VI) ions by C-4-APD and C-2-APZ.

11 **3.2.2. Adsorption kinetics**

12 Fig. 5A shows the effect of adsorption time on the Cr(VI) ions adsorption capacity
13 of C-4-APD and C-2-APZ. In the first 10 min of the adsorption reaction, the adsorption

1 capacity of Cr(VI) ions by C-2-APZ increased faster, which was due to there are more
2 N atomic sites on the surface of C-2-APZ than C-4-APD. With the increase of time, the
3 N atomic sites slowly reached saturation, and the adsorption of Cr(VI) ions by the
4 adsorbent became very slow and basically reached the adsorption equilibrium state after
5 4 h of adsorption in the solution.

6
7 **Fig. 5** Effect of contact time on the Cr(VI) ions adsorption capacity of C-4-APD and C-2-APZ(A); The
8 curve fitting with pseudo-first-order(B) and pseudo-second-order kinetics model(C).

9 In order to investigate a range of kinetic factors for the adsorption of Cr(VI) ions
10 by C-4-APD and C-2-APZ, pseudo-first-order and pseudo-second-order kinetic models
11 were used to fit the kinetic data:

$$12 \ln(Q_e - Q_t) = \ln Q_e - k_1 t \quad (2)$$

$$\frac{t}{Q_t} = \frac{1}{k_2 Q_e^2} + \frac{1}{Q_e} t \quad (3)$$

where Q_e (mg/g) and Q_t (mg/g) are the adsorption capacities of Cr(VI) ions at equilibrium and time t (min) respectively; k_1 (min^{-1}) and k_2 ((g/mg)/min) are the pseudo-first-order rate constant and pseudo-second-order rate constant, respectively.

Fig.5B and C are the fitted curves of the pseudo-first-order and pseudo-second-order kinetic models for the actual experimental data of C-4-APD and C-2-APZ, and a series of kinetic parameters calculated and fitted by the two adsorption equations are shown in Table 2. As can be seen from the table, for C-4-APD, the correlation coefficient R^2 of the fitted curves of the pseudo-first-order model was higher than that of the fitted curves of the pseudo-second-order model, which was as high as 0.996. However, since both the pseudo-second-order model fit the experimental data of C-4-APD and C-2-APZ well, with correlation coefficients R^2 of 0.983 and 0.986, respectively, it was considered that C-4-APD and C-2-APZ for Cr(VI) ions follow the pseudo-second-order model, and the rate of the adsorption process was influenced by the physicochemical adsorption.

Table 2 Kinetic parameters for Cr(VI) ions uptake by C-4-APD and C-2-APZ.

Absorbent	pseudo-first-order			pseudo-second-order		
	$Q_e(\text{mg/g})$	$k_1(\text{min}^{-1})$	R^2	$Q_e(\text{mg/g})$	$k_2((\text{g/mg})/\text{min})$	R^2
C-4-APD	57.58	0.03773	0.996	65.57	0.00074	0.983
C-4-APZ	48.63	0.28318	0.954	50.37	0.01068	0.986

3.2.3. Adsorption isotherm

Fig.6A shows the adsorption isotherms of Cr(VI) ions by C-4-APD and C-2-APZ. It can be seen from the figure that the adsorption capacities of C-4-APD and C-2-APZ

for Cr(VI) ions were almost the same at the initial concentration of Cr(VI) ions below 60 mg/L. However, as the initial concentration continued to increase, C-4-APD showed better adsorption behavior, which also indicated that C-4-APD had better proton binding ability. When the concentration of Cr(VI) ions solution increased to about 200 mg/L, the adsorption capacities of C-4-APD and C-2-APZ for Cr(VI) ions basically ceased to change. The highest adsorption capacities of C-4-APD and C-2-APZ for Cr(VI) ions were about 73.78 mg/g and 61.34 mg/g, respectively. By comparing with the maximum adsorption capacities of other surface modified biomass materials (Table 3), we can find that the adsorption capacities of C-4-APD and C-2-APZ were better, moreover, C-4-APD and C-2-APZ are very easy to separate from solution, compared to high specific surface area of particulate or nanoparticle materials.

Fig. 6 Cr(VI) ions adsorption isotherms for the C-4-APD and C-2-APZ(A); The curve fitting with

the Langmuir(B) and Freundlich model(C).

Table 3 Comparison of adsorption capacities for Cr(VI) ions on various surface modified biomass materials

Adsorbents	Adsorption capacity (mg/g)	Reference
Pine / TiO2	12.8	(Zhao et al. 2021)
cotton/chitosan	7.5	(Rojas et al. 2018)
Immobilized corn cob	112.49	(Manzoor et al. 2019)
C-4-APD	73.78	this work
C-2-APZ	61.34	this work

Langmuir and Freundlich models were frequently used to evaluate the saturation binding data, the two equations are expressed as follows:

$$\frac{C_e}{Q_e} = \frac{1}{k_L Q_{\max}} + \frac{C_e}{Q_{\max}} \quad (4)$$

$$\ln Q_e = \ln k_F + \frac{1}{n} \ln C_e \quad (5)$$

where Q_e (mg/g) is the amount of Cr(VI) ions bound to the C-4-APD 和 C-2-APZ at equilibrium, C_e (mg/L) is the equilibrium concentration, and $Q_{\max}$ (mg/g) is the apparent maximum adsorption capacity. K_L is the Langmuir constant, K_F and $1/n$ are the Freundlich constants.

The fits of Langmuir and Freundlich isothermal adsorption models for Cr(VI) ions adsorbed by C-4-APD and C-2-APZ were shown in Fig. 6B and C. The isotherm parameters of the two models were listed in Table 4. From the fitted curves, it can be seen that the correlation coefficients R^2 (0.971 and 0.967) of the linear equations after fitting the Langmuir equation were closer to 1 than those of the Freundlich model, which proves that the Langmuir model can describe the experimental measured data

more closely. In addition, the maximum adsorption capacities of C-4-APD and C-2-APZ were calculated as 108.11 mg/g and 82.2 mg/g by taking the experimental data into the equation of Langmuir model, which were different from the experimental adsorption capacity. This was due to the formation of hydrogen bonds between the groups in C-4-APD or C-2-APZ, which occupy the adsorption sites and make the actual maximum adsorption capacity lower than the calculated value. Furthermore, the large size of $\text{Cr}_2\text{O}_7^{2-}$ makes it difficult to enter the adsorption sites, thus limiting the adsorption capacity of $\text{Cr}_2\text{O}_7^{2-}$ (Fenti et al. 2020). These results demonstrate that the adsorption of Cr(VI) ions by C-4-APD and C-2-APZ was the monolayer adsorption process.

Table 4 Parameters for Cr(VI) ions adsorption by C-4-APD and C-2-APZ according to different equilibrium models.

Absorbent	Langmuir				Freundlich	
	$Q_m(\text{mg/g})$	$k_L(\text{mg/L})$	R^2	$1/n$	$k_F((\text{mg/g})/(\text{L/mg}))^{1/n}$	R^2
C-4-APD	108.11	0.00998	0.971	0.50244	4.9163	0.906
C-4-APZ	82.2	0.0141	0.967	0.43877	5.84634	0.9

3.2.4. Reusability studies

Desorption and regeneration of adsorbent is one of the most important properties of adsorption separation technology. In this experiment, a thiourea-hydrochloric acid solution with a mass fraction of 2 wt% (the concentration of HCl was 0.5 mol/L) was chosen as the eluent. The mixed thiourea-hydrochloric acid solution can not only elute the Cr(VI) ions from the binding sites, but also thiourea can reduce Cr(VI) to the less toxic Cr(III) under acidic conditions. To investigate the reusability and stability of C-4-APD and C-2-APZ, we performed six adsorption-desorption processes using the same

1 C-4-APD and C-2-APZ, and the adsorption amounts of the six experiments were in Fig.
 2 7. As can be seen from the figure, the adsorption capacities of C-4-APD and C-2-APZ
 3 for Cr(VI) ions with multiple reuses did not change evidently and remained above 90%
 4 and 80%, which proved that C-4-APD and C-2-APZ have good reusability and stability.
 5 Which was due to the excellent flexibility of degreasing cotton as a substrate, the
 6 adsorption sites were not easily destroyed and deformed. Furthermore, the adsorption
 7 sites encapsulated by hydrogen bonds can replace the destroyed adsorption sites to some
 8 extent after multiple washes. Thus, the multiple adsorption-desorption process has less
 9 effect on the adsorption capacity of C-4-APD and C-2-APZ.

10

11 **Fig. 7** Regeneration of C-4-APD and C-2-APZ.

12 **4. Conclusions**

13 In summary, 4-aminopyridine and 2-aminopyrazine were successfully introduced

to the surface of cotton fiber and used to remove Cr(VI) ions from aqueous solution in this study. SEM, FT-IR and XPS that a large number of amino, pyridine and pyrazine groups were introduced to the surface of cotton fiber after modification by 4-aminopyridine and 2-aminopyrazine. The Cr(VI) ions on the modified cotton fiber adsorption was mainly achieved by electrostatic interactions between the protonated functional groups on the adsorbent and the Cr(VI) anions. The maximum adsorption capacities of C-4-APD and C-2-APZ were 73.78 mg/g and 61.34 mg/g, respectively, at the optimum pH of 2 and an initial concentration of 200 mg/g. Kinetic studies showed that the adsorption process followed the pseudo-second-order kinetic model indicating that the adsorption process was mainly controlled by physicochemical adsorption. The adsorption isotherm analysis showed that the Langmuir model was in good agreement with the adsorption equilibrium data and the adsorption was the monolayer adsorption process. In addition, the adsorption capacities of adsorbents didn't significantly decrease after six times of repeated use, and they decreased gradually in subsequent runs to 90 % and 80 %, respectively. These results indicate the potential application of 4-aminopyridine and 2-aminopyrazine modified cotton fibers in the removal of Cr(VI) ions from aqueous solutions.

Acknowledgments:

The authors appreciate the financial support from the Key Research and Development Plan of Hubei Province(2020BCB068).

Author contributions Conceptualization: ZYH, PW, SHC, XT; Methodology: ZYH; Investigation: ZYH, PW; Formal analysis: ZYH, PW; Writing—original draft

preparation: ZYH; Writing—review and editing: ZYH, PW, XZ, YKY, LF, SHC, XT;
Funding acquisition: SHC, XT, LXW; Resources: SHC, XT, LXW; Supervision: ZYH,
PW, SHC, XT.

Funding the Key Research and Development Plan of Hubei Province (2020BCB068).

Declarations

Conflict of interest

The authors declare that they have no conflicts of interest to declare.

Ethical Standards

This article does not contain any studies with human participants or animals performed
by any of the authors.

Informed consent None.

References

- Bao S, Liu H, Liu Y, Yang W, Wang Y, Yu Y, Sun Y, Li K (2020) Amino-functionalized graphene oxide-supported networked Pd-Ag nanowires as highly efficient catalyst for reducing Cr(VI) in industrial effluent by formic acid. *Chemosphere* 257: 127245. <https://doi.org/10.1016/j.chemosphere.2020.127245>.
- Bayramoglu G, Akbulut A, Arica MY (2016) Aminopyridine modified *Spirulina platensis* biomass for chromium(VI) adsorption in aqueous solution. *Water Sci Technol* 74: 914-926. <https://doi.org/10.2166/wst.2016.281>.
- Elidordio KP, Andolfatto VS, Martins MRG, De Sá BP, Umeki ER, De Araújo Morandim-Giannetti A (2017) Treatment of chromium effluent by adsorption on chitosan activated with ionic liquids. *Cellulose* 24: 2559-2570. <https://doi.org/10.1007/s10570-017-1264-3>.
- Fenti A, Chianese S, Iovino P, Musmarra D, Salvestrini S (2020) Cr(VI) Sorption from Aqueous Solution: A Review. *Applied Sciences* 10: 6477.

- 1 <https://doi.org/10.3390/app10186477>.
- 2 Geng T, Ma L, Chen G, Zhang C, Zhang W, Niu Q (2020) Fluorescent conjugated
3 microporous polymers containing pyrazine moieties for adsorbing and
4 fluorescent sensing of iodine. *Environ Sci Pollut Res Int* 27: 20235-20245.
5 <https://doi.org/10.1007/s11356-019-06534-8>.
- 6 Hu Y, Zhang J, Yu C, Li Q, Dong F, Wang G, Guo Z (2014) Synthesis, characterization,
7 and antioxidant properties of novel inulin derivatives with amino-pyridine
8 group. *Int J Biol Macromol* 70: 44-49.
9 <https://doi.org/10.1016/j.ijbiomac.2014.06.024>.
- 10 Kimbrough DE, Cohen Y, Winer AM, Creelman L, Mabuni C (1999) A Critical
11 Assessment of Chromium in the Environment. *Critical Reviews in*
12 *Environmental Science and Technology* 29: 1-46.
13 <https://doi.org/10.1080/10643389991259164>.
- 14 Kooshki F, Tutunchi H, Vajdi M, Karimi A, Niazkar HR, Shoorei H, Pourghassem
15 Gargari B (2021) A Comprehensive insight into the effect of chromium
16 supplementation on oxidative stress indices in diabetes mellitus: A systematic
17 review. *Clin Exp Pharmacol Physiol* 48: 291-309. [https://doi.org/10.1111/1440-](https://doi.org/10.1111/1440-1681.13462)
18 [1681.13462](https://doi.org/10.1111/1440-1681.13462).
- 19 Li LL, Feng XQ, Han RP, Zang SQ, Yang G (2017) Cr(VI) removal via anion exchange
20 on a silver-triazolate MOF. *J Hazard Mater* 321: 622-628.
21 <https://doi.org/10.1016/j.jhazmat.2016.09.029>.
- 22 Li Y, Zhu H, Zhang C, Cheng M, He H (2018) PEI-grafted magnetic cellulose for Cr(VI)
23 removal from aqueous solution. *Cellulose* 25: 4757-4769.
24 <https://doi.org/10.1007/s10570-018-1868-2>.
- 25 Liang X, Liang B, Wei J, Zhong S, Zhang R, Yin Y, Zhang Y, Hu H, Huang Z (2020) A
26 cellulose-based adsorbent with pendant groups of quaternary ammonium and
27 amino for enhanced capture of aqueous Cr(VI). *Int J Biol Macromol* 148: 802-
28 810. <https://doi.org/10.1016/j.ijbiomac.2020.01.184>.
- 29 Long B, Ye J, Ye Z, He J, Luo Y, Zhao Y, Shi J (2020) Cr(VI) removal by *Penicillium*

1 oxalicum SL2: Reduction with acidic metabolites and form transformation in
2 the mycelium. Chemosphere 253: 126731.
3 <https://doi.org/10.1016/j.chemosphere.2020.126731>.

4 Lu H, Wu F, Yang Y, Li S, Hua Y, Zhu L (2020) Hole transport materials based on a
5 twisted molecular structure with a single aromatic heterocyclic core to boost the
6 performance of conventional perovskite solar cells. Journal of Materials
7 Chemistry C 8: 13415-13421. <https://doi.org/10.1039/d0tc03404e>.

8 Manzoor Q, Sajid A, Hussain T, Iqbal M, Abbas M, Nisar J (2019) Efficiency of
9 immobilized Zea mays biomass for the adsorption of chromium from simulated
10 media and tannery wastewater. Journal of Materials Research and Technology
11 8: 75-86. <https://doi.org/10.1016/j.jmrt.2017.05.016>.

12 Moradi F, Maleki V, Saleh-Ghadimi S, Kooshki F, Pourghassem Gargari B (2019)
13 Potential roles of chromium on inflammatory biomarkers in diabetes: A
14 Systematic. Clin Exp Pharmacol Physiol 46: 975-983.
15 <https://doi.org/10.1111/1440-1681.13144>.

16 Park SH, Shin SS, Park CH, Jeon S, Gwon J, Lee SY, Kim SJ, Kim HJ, Lee JH (2020)
17 Poly(acryloyl hydrazide)-grafted cellulose nanocrystal adsorbents with an
18 excellent Cr(VI) adsorption capacity. J Hazard Mater 394: 122512.
19 <https://doi.org/10.1016/j.jhazmat.2020.122512>.

20 Peng X, Yan Z, Hu L, Zhang R, Liu S, Wang A, Yu X, Chen L (2020) Adsorption
21 behavior of hexavalent chromium in aqueous solution by polyvinylimidazole
22 modified cellulose. Int J Biol Macromol 155: 1184-1193.
23 <https://doi.org/10.1016/j.ijbiomac.2019.11.086>.

24 Rojas SI, Duarte DC, Mosquera SD, Salcedo F, Hinestroza JP, Husserl J (2018)
25 Enhanced biosorption of Cr(VI) using cotton fibers coated with chitosan - role
26 of ester bonds. Water Sci Technol 78: 476-486.
27 <https://doi.org/10.2166/wst.2018.284>.

28 Sharma AK, Devan RS, Arora M, Kumar R, Ma Y-R, Babu JN (2018) Reductive-co-
29 precipitated cellulose immobilized zerovalent iron nanoparticles in ionic

liquid/water for Cr(VI) adsorption. Cellulose 25: 5259-5275.
<https://doi.org/10.1007/s10570-018-1932-y>.

Simonin J-P (2016) On the comparison of pseudo-first order and pseudo-second order rate laws in the modeling of adsorption kinetics. Chemical Engineering Journal 300: 254-263. <https://doi.org/10.1016/j.cej.2016.04.079>.

Singh P, Chowdhuri DK (2017) Environmental Presence of Hexavalent but Not Trivalent Chromium Causes Neurotoxicity in Exposed Drosophila melanogaster. Mol Neurobiol 54: 3368-3387. <https://doi.org/10.1007/s12035-016-9909-z>.

Sun Y, Liu X, Lv X, Wang T, Xue B (2021) Synthesis of novel lignosulfonate-modified graphene hydrogel for ultrahigh adsorption capacity of Cr(VI) from wastewater. Journal of Cleaner Production 295: 126406. <https://doi.org/https://doi.org/10.1016/j.jclepro.2021.126406>.

Vakili M, Deng S, Li T, Wang W, Wang W, Yu G (2018) Novel crosslinked chitosan for enhanced adsorption of hexavalent chromium in acidic solution. Chemical Engineering Journal 347: 782-790. <https://doi.org/10.1016/j.cej.2018.04.181>.

Wang P, Yin Y, Xu J, Chen S, Wang H (2019) Facile synthesis of Cu²⁺-immobilized imprinted cotton for the selective adsorption of bovine hemoglobin. Cellulose 27: 867-877. <https://doi.org/10.1007/s10570-019-02816-z>.

Wei Y, Chen W, Liu C, Wang H (2021) Facial Synthesis of Adsorbent from Hemicelluloses for Cr(VI) Adsorption. Molecules 26: 1443. <https://doi.org/10.3390/molecules26051443>.

Wu Y, Zhang S, Guo X, Huang HJBT (2008) Adsorption of chromium (III) on lignin. 99: 7709-7715.

Xie B, Shan C, Xu Z, Li X, Zhang X, Chen J, Pan B (2017) One-step removal of Cr(VI) at alkaline pH by UV/sulfite process: Reduction to Cr(III) and in situ Cr(III) precipitation. Chemical Engineering Journal 308: 791-797. <https://doi.org/10.1016/j.cej.2016.09.123>.

Xu X, Gao B, Jin B, Yue Q (2016) Removal of anionic pollutants from liquids by biomass materials: A review. Journal of Molecular Liquids 215: 565-595.

1 <https://doi.org/10.1016/j.molliq.2015.12.101>.

2 Yao F, Jia M, Yang Q, Luo K, Chen F, Zhong Y, He L, Pi Z, Hou K, Wang D, Li X

3 (2020) Electrochemical Cr(VI) removal from aqueous media using titanium as

4 anode: Simultaneous indirect electrochemical reduction of Cr(VI) and in-situ

5 precipitation of Cr(III). Chemosphere 260: 127537.

6 <https://doi.org/10.1016/j.chemosphere.2020.127537>.

7 Zhang S, Chen H, Zhang S, Kai C, Jiang M, Wang Q, Zhou Z (2019) Polyethylenimine

8 grafted H₂O₂-oxidized cellulose membrane as a novel biosorbent for Cr(VI)

9 adsorption and detoxification from aqueous solution. Cellulose 26: 3437-3453.

10 <https://doi.org/10.1007/s10570-019-02325-z>.

11 Zhao J, Boada R, Cibin G, Palet C (2021) Enhancement of selective adsorption of Cr

12 species via modification of pine biomass. Sci Total Environ 756: 143816.

13 <https://doi.org/10.1016/j.scitotenv.2020.143816>.

14 Zhao J, Zhang X, He X, Xiao M, Zhang W, Lu C (2015) A super biosorbent from

15 dendrimer poly(amidoamine)-grafted cellulose nanofibril aerogels for effective

16 removal of Cr(vi). Journal of Materials Chemistry A 3: 14703-14711.

17 <https://doi.org/10.1039/c5ta03089g>.

18

Figures

Figure 1

Schematic illustration of the C-4-APD and C-2-APZ preparation process.

Figure 2

SEM images of the degreasing cotton (A), C-4-APD (B) and C-2-APZ (C).

Figure 3

FTIR spectra of degreasing cotton, C-4-APD and C-2-APZ.

Figure 4

Effect of the pH value on the adsorption of Cr(VI) ions by C-4-APD and C-2-APZ.

Figure 5

Effect of contact time on the Cr(VI) ions adsorption capacity of C-4-APD and C-2-APZ(A); The curve fitting with pseudo-first-order(B) and pseudo-second-order kinetics model(C).

Figure 6

Cr(VI) ions adsorption isotherms for the C-4-APD and C-2-APZ(A); The curve fitting with the Langmuir(B) and Freundlich model(C).

Figure 7

Regeneration of C-4-APD and C-2-APZ.