Soil-Water Characteristic Curves And Hydraulic Conductivity of Gaomiaozi Bentonite Pellet-Contained Materials

Jianghong Zhu

Lanzhou University

Zhenyan Su

Lanzhou University

Huyuan Zhang (✉ zhujh17@lzu.edu.cn)

Lanzhou University

Research Article

Keywords: high-level radioactive waste (HLW) disposal, bentonite pellet-contained material (PCM), soil-water characteristic curve (SWCC), hydraulic conductivity, microstructure

Posted Date: July 21st, 2021

DOI: <https://doi.org/10.21203/rs.3.rs-656683/v1>

License: This work is licensed under a Creative Commons Attribution 4.0 International License.

[Read Full License](#)

Version of Record: A version of this preprint was published at Environmental Earth Sciences on January 31st, 2022. See the published version at <https://doi.org/10.1007/s12665-022-10200-7>.

Abstract

The bentonite pellet-contained material (PCM) is a feasible material for the joint sealing of high-level radioactive waste repository. During the operation of the repository, the PCM will be unsaturated for a long time, and its water retention and permeability directly affect the buffer barrier seepage, nuclide migration, and joint healing. Moreover, the particle size of bentonite pellets and dry density are important factors affecting the performance of PCM. In this work, the pressure plate method and vapour equilibrium technique were utilized to test the soil-water characteristic curves (SWCCs) of the PCMs with different particle sizes and dry densities. The unsaturated hydraulic conductivity of the PCMs was predicted by combining the SWCC model and saturated hydraulic conductivity. The results showed that in the low suction range (20–1150 kPa), the dry density and particle size had a negative correlation with the water content at the same suction. In the high suction range (4200–309000 kPa), the dry density and particle size had little effect on the SWCC. The Gardner model was appropriate for describing the SWCC of PCM. In addition, the hydraulic conductivity of the PCM decreased with the increase in dry density, while increased with the increase in particle size. The influence mechanism of the SWCC and hydraulic conductivity was further discussed based on the scanning electron microscopy images and pore size distribution curves.

Introduction

Nuclear energy, with its advantages of cleanliness, safety, and stability, is one of the essential ways to solve the current energy crisis (Peng et al. 2021). However, during the development and utilization of nuclear energy, high-level radioactive waste (HLW) with strong radioactivity, high toxins, and long half-life has been produced, which poses long-term potential ecological risks. The safe, effective, and permanent HLW disposal is an urgent problem for the nuclear industry and science. The deep geological disposal of the multiple buffer barrier systems is considered as the safest method of HLW disposal, which can achieve the purpose of perpetual isolation of HLW from the human living environment (IAEA 2013; Abootalebi and Siemens 2018; Sun et al. 2020). In the HLW disposal, when the buffer barrier is constructed by the prefabricated buffer block masonry method, the joints between the blocks and between the blocks and the surrounding rock will inevitably appear (Wang et al. 2013). These could become potential concentrated seepage channels for groundwater and radionuclide migration, deteriorating the engineering performance of the buffer barrier. To ensure the operational function of the buffer barrier, the joints must be sealed. The bentonite pellet-contained material (PCM) has the advantages of high swelling, low permeability, and irregular voids filling, which is an excellent joint sealing material (Wang 2010; Wang et al. 2021).

Bentonite is different in each country. The main bentonite for the HLW disposal in China is Gaomiaozhi (GMZ) bentonite (Wang et al. 2009; Cui et al. 2012; Xu et al. 2020). The GMZ PCM studied by Chinese scholars is generally a mixture of bentonite pellets with a single particle size and bentonite powder (Ma et al. 2021). Thus, determining the ratio of bentonite pellets to bentonite powder is an important basis for studying the GMZ PCM. The weight percentage of the bentonite pellets in the total weight of the PCM is

defined as the pellet percentage. At present, the optimum pellet percentage of the GMZ PCM with a particle size of 2–5 mm has been studied (Ma et al. 2021), but the optimum pellet percentage of the GMZ PCM with other particle sizes is still unclear. Further related research needs to be carried out. This can provide a basis for sample preparation in the study of water retention and permeability of the GMZ PCM.

During the operation of the repository, the PCM will be eroded by groundwater and radiant heat, and will remain unsaturated for a long time. Its water retention and permeability directly affect the swelling and deformation of the buffer barrier and joints, and then affect the sealing effect of the joints (Tripathy et al. 2014; Fattah et al. 2017; Liu et al. 2020; Sun et al. 2021). The soil-water retention curve (SWCC) reflects the water retention of the soil (Seiphoori, 2016). Therefore, it is necessary to pay attention to the SWCC and hydraulic conductivity of PCM. At present, some achievements have been made on the SWCC and hydraulic conductivity of PCM. Seiphoori et al. (2014) studied the SWCC of MX-80 PCM, and found that the water content of MX-80 PCM was higher than that of MX-80 compacted bentonite under the same suction. Hoffmann et al. (2007) concluded that the hydraulic conductivity of FEBEX PCM was in good agreement with that of FEBEX compacted bentonite. These studies mainly focused on the difference between PCM and compacted bentonite. However, the particle size of bentonite pellets and dry density are important factors affecting the performance of the GMZ PCM. At present, little research has been done on the SWCC and hydraulic conductivity of the GMZ PCM, and there is little research on the influence of particle size and dry density on the SWCC and hydraulic conductivity of the PCM. Furthermore, discussing the influence of particle size and dry density on the SWCC and hydraulic conductivity of GMZ PCM is of great significance to the theoretical analysis and engineering application of joint sealing materials (Lee et al. 1999; Zhang et al. 2016).

Therefore, this work first determined the optimum pellet percentage of the PCM based on the maximum packing density and maximum swelling potential, and made the PCM with the optimum pellet percentage. Then, the pressure plate method and vapour equilibrium technique were used to determine the SWCCs of the PCMs with different particle sizes and dry densities. The saturated hydraulic conductivity of the PCM was measured by the variable head permeability test, and the unsaturated hydraulic conductivity of the PCM was predicted by combining the parameters of the SWCC model. In addition, based on the microstructure, the influence mechanism of dry density and particle size on the SWCC and hydraulic conductivity of PCM was discussed. The results can provide a theoretical basis for screening joint sealing materials and optimizing the joint design of buffer barriers for HLW disposal.

Preparation Of Pcm And Determination Of The Optimum Pellet Percentage

2.1 Test materials

The GMZ bentonite, a Na-bentonite from Inner Mongolia, China, was used in the work. Its main mineral component is montmorillonite, followed by feldspar, quartz, etc. The main physical parameters are shown in Table 1, and the particle size distribution is shown in Fig. 1.

Table 1
Basic properties of the GMZ bentonite

Natural water content / %	Specific gravity	Plastic limit / %	Liquid limit / %	Plasticity index	Montmorillonite content / %
7.8	2.70	32.8	208.1	175.3	44.4

2.2 Preparation of bentonite pellets

Before the preparation of the bentonite pellets, the maximum dry density of the bentonite powder was determined to be 2.0 g/cm^3 , and the optimal water content was 7.3%, almost in line with the natural water content (see Fig. 2). Because of the high dry density required for the bentonite pellets, the bentonite pellets were prepared with the maximum dry density and optimum water content (i.e. natural water content) of the bentonite powder.

The maximum particle size of bentonite pellets was determined by the size of the sample used in the SWCC test. The sample diameter was 50 mm, and the height was 10 mm. It is specified in the Standard for Geotechnical Testing Method (GB/T50123-2019 2019) that the ratio of the sample height to the maximum particle size of the coarse-grained soil should be 4–6. Therefore, 2 mm was set as the maximum particle size of bentonite pellets. Moreover, the particle size was usually larger than 0.25 mm in previous research work (Hoffmann et al. 2007; Seiphoori et al. 2014), and 0.25 mm was also set as the minimum particle size in this work. The preparation methods of bentonite pellets are as follows (Sandén and Börgesson 2014; Liu et al. 2016): firstly, the bentonite cylindrical samples with a height of 20 mm and a dry density of 2.0 g/cm^3 were compacted in a 50 mm diameter compacting cylinder by uniaxial static compaction, and then crushed and sieved to obtain three groups of bentonite pellets with different particle sizes, which were 1–2 mm, 0.5–1 mm and 0.25–0.5 mm, respectively (see Fig. 3).

2.3 Optimum pellet percentage of PCM

In this work, bentonite pellets with a single particle size were mixed with bentonite powder as the PCM (Ma et al. 2021). The pellet percentage ranged from 0–100%, of which 0% and 100% were special cases. When the pellet percentage was 0%, the PCM was all bentonite powder, and when the pellet percentage was 100%, the PCM was all bentonite pellets. The maximum packing density and maximum swelling potential were invoked as the criteria for screening the optimum pellet percentage of the PCM.

2.3.1 Packing density

The determination of the packing density of the PCM was based on the relative density measurement method of sand in the Standard for Geotechnical Testing Method (GB/T50123-2019 2019). The tests were undertaken with a pellet percentage of 0–100% and an interval of 10%. First, 30 g of the PCM was accurately weighed. Then, after the bentonite pellets and bentonite powder were mixed evenly and poured into a calibrated 100 mL measuring cylinder, the measuring cylinder was inverted and vibrated, repeating for 3 times. The packing volume of the PCM was measured several times to obtain the average value,

and the packing density was calculated. The relationship between the packing volume, packing density, and pellet percentage is shown in Fig. 4. The experimental observations found that with the increase in the pellet percentage, the structure of the PCM varied from the particle suspended state (pellet percentage is 0–70%) to the particle contact state (pellet percentage is 80–90%), and then to the particle overhead state (pellet percentage is 100%). The packing volume of the PCM showed a trend of first decreasing and then increasing, while the packing density varied inversely. When the pellet percentage was 70%, the packing volume was the smallest, while the packing density was the highest, ranging from 1.03 to 1.10 g/cm³. And with the increase in particle size, the packing tended to be denser.

2.3.2 Free swelling ratio

The free swelling ratio characterized the swelling potential of PCMs with different pellet percentages. The free swelling ratio test was in accordance with Bentonite (GB/T20973-2020 2020). First, the PCM was dried at 105°C for 24h, and its weight was accurately taken at 2 ± 0.01 g. Then, the PCM was added into a calibrated 100 mL measuring cylinder with 90 mL distilled water several times. To avoid too much PCM to be added at one time and not to fully swell, the amount added per time must not exceed 0.1 g. After all the PCM was added, distilled water was added to the 100 mL mark of the measuring cylinder, and the top of the measuring cylinder was sealed with preservative film. The volume of the PCM was logged every 2 h. The tests were not stopped until the volume remained constant for at least 48 h, and the free swelling ratio was calculated.

It can be seen from Fig. 5 that the free swelling ratio of PCM shows a trend of first increasing and then decreasing with the increase in the pellet percentage. The free swelling ratio reached the maximum when the pellet percentage was 70%, which was consistent with the packing density test results. At the same pellet percentage, the free swelling ratio tended to decrease with the increase in particle size.

The optimum pellet percentage of the PCM was determined by the packing density and free swelling ratio. Therefore, the PCM with a pellet percentage of 70% was selected to determine the SWCC.

Swcc Tests

3.1 Sample preparations

The SWCC was measured in the dehumidification path (Feng et al. 2017; Bai et al. 2020). The PCM was pressed into a ring knife with a diameter of 50 mm and a height of 10 mm according to the set dry density. Table 2 shows the physical parameters of the PCM before saturation. To limit the swelling deformation of the PCM due to water absorption and determine the SWCC of the PCM under the confinement conditions, filter paper and porous stone were placed on and below the PCW, which were clamped together in a steel clamp. The PCM was first vacuumized in a vacuum saturation device, then saturated with distilled water and allowed to stand for 24 h (see Fig. 6).

Table 2
Physical properties of the PCM for the SWCC test

Dry density / (g/cm ³)	Pellet percentage / %	Bentonite pellets	
		Dry density / (g/cm ³)	Particle size / mm
1.50	70	2.00	1–2
	70	2.00	0.5–1
	70	2.00	0.25–0.5
1.60	70	2.00	1–2
	70	2.00	0.5–1
	70	2.00	0.25–0.5
1.80	70	2.00	1–2
	70	2.00	0.5–1
	70	2.00	0.25–0.5

3.2 Test methods

Due to the low hydraulic conductivity of bentonite, the suction can fluctuate from zero to several hundred MPa (Bian et al. 2020; Yoon and Kim 2021). There is no specific technology at this stage to cover this range of suction, so at least two techniques are required to determine it. In this work, the pressure plate method was used in the low suction range (Vaz et al. 2021), and the vapour equilibrium technique was used in the high suction range (Bharat and Gapak 2021). The equipment used in the pressure plate method test was the 15-bar pressure plate extractor (see Fig. 7a). The matrix suction was 20, 30, 50, 70, 100, 200, 300, 500, 700, 1000, and 1150 kPa, respectively during the test. Because the PCM was saturated with distilled water and its water content was high during the measurement, it was considered that the matrix suction measured by the pressure plate method was equal to the total suction, abbreviated as suction (Fredlund and Rahurdjo 1993; Vaz et al. 2021).

After the pressure plate extractor test, the PCM was cut into 7 parts with similar weight, and placed in the vapor equilibrium chamber with a oversaturated salt solution (see Table 3) at the bottom to determine the SWCC of the high suction range(see Fig. 7b). The ambient temperature was controlled at $20 \pm 0.5^\circ\text{C}$, and the sample was weighed every three days. When the weight variation of the sample was less than 0.01 g for three consecutive times, it was considered that the suction of the sample was in equilibrium with the vapor pressure of the corresponding saturated salt solution (Bharat and Gapak 2021). After the equilibrium, the weight of the sample was measured and the final water content was calculated. The equilibrium process took 3 months.

Table 3
Saturated salt solutions and their corresponding suctions at 20°C
(Bharat and Gapak 2021)

Saturated salt solutions	Relative humidity / %	Suction / MPa
K ₂ SO ₄	96.9	4.2
Zn ₂ SO ₄	91.1	12.6
(NH ₄) ₂ SO ₄	83.2	24.9
NaCl	75.5	38.0
NaBr	59.2	71.0
CaCl ₂	35.8	139.0
LiCl	10.2	309.0

3.3 Microstructure tests

After the determination of the SWCC of the PCM, the microstructure of the PCM was examined by mercury intrusion porosimetry (MIP) and scanning electron microscopy (SEM). The pore size distribution curves of the PCMs with different dry densities were quantitatively measured by mercury porosimetry. And SEM was utilized to observe the morphological characteristics of the PCMs with different particle sizes. The influence mechanism of dry density and particle size on the SWCC of PCM was discussed from the micro-level.

Results And Discussion

4.1 Relationship between dry density and SWCC

The SWCCs of PCMs with different dry densities are shown in Fig. 8. In the low suction range (20–1150 kPa), the dry density had a great influence on the SWCC. At the same suction, the water absorbed by the PCM decreased with the increase in dry density. In the high suction range (4200–309000 kPa), the SWCCs of PCMs with different dry densities coincided. In other words, the dry density had little effect on the water retention of the PCM in the high suction range.

4.2 Relationship between particle size of bentonite pellets and SWCC

The SWCCs of PCMs with different particle sizes are illustrated in Fig. 9. In the low suction range (20–1150 kPa), the smaller the particle size, the higher the water content of the PCM with the same suction. However, with the increase in suction, the SWCCs of PCMs with different particle sizes tended to be consistent. In the high suction range (4200–309000 kPa), the particle size had little effect on the water retention of the PCM. The SWCC can reflect not only the relationship between suction and water content,

but also the pore state in soil (Fredlund and Rahurdjo 1993). The SWCCs of PCMs with different particle sizes were different in the low suction range, indicating that although the bentonite pellets became homogeneous with the bentonite powder on the macro-level after saturation, the interior of the PCM was still inhomogeneous on the micro-level.

Hoffmann et al. (2007) analyzed the SWCC of the FEBEX PCM with a dry density of 1.50 g/cm^3 . Zhang et al. (2014) determined the SWCC of the GMZ bentonite-sand mixture with a dry density of 1.50 g/cm^3 and a sand content of 30%. The two curves were compared with the SWCCs of the GMZ PCMs in this work (see Fig. 10). The SWCC of the FEBEX PCM was above the SWCC of the GMZ PCM, but the tendency was similar. The main reason that the SWCCs of these two bentonites could not be completely coincided was due to the inconsistency of mineral composition, resulting in different specific surface areas and surface charge densities of particles (Tripathy et al. 2014; Fattah et al. 2017), which would show different water retention. Furthermore, GMZ bentonite-sand mixture is a feasible buffer backfill block material for the HLW disposal in China (Tan et al. 2019; Zhang et al. 2019; Tan et al. 2020). In the low suction range, the water content of the PCM was more than that of the bentonite-sand mixture under the same suction. However, in the high suction range, there was no significant difference in the water content between the two materials under the same suction. It could be inferred that the PCM as the joint sealing material has better water retention in the low suction range than the buffer backfill block material, and is not prone to shrink and crack in the dry environment of the underground disposal repository. And there is little difference between the water retention of the PCM and that of the buffer backfill block material in the high suction range.

4.3 Hydraulic conductivity

4.3.1 Selection of SWCC model

Three commonly used models, namely Fredlund-Xing model (Fredlund et al. 1994), Gardner model (Gardner 1958), and Van Genuchten model (Genuchten 1980), were selected to fit the SWCC obtained from the test. It was found that the Fredlund-Xing model had a poor fitting effect, and the Gardner model had a good fitting effect, with the correlation coefficients above 0.90, which was the most suitable model for fitting the SWCC of PCM. For space reasons, only the fitting curves of the three models for the SWCC of the PCM with a dry density of 1.60 g/cm^3 and a particle size of 0.5–1 mm are presented in Fig. 11. The correlation coefficient of the Gardner model was 0.997.

The Gardner model is generally applicable to sand, and the Fredlund-Xing model and Van Genuchten model are generally applicable to silt and clay (Gardner 1958; Genuchten 1980; Fredlund et al. 1994). The particle size of bentonite pellets in the PCM was 2 mm maximum and 0.25 mm minimum, and the pellet percentage was 70%, so the PCM belonged to sand. Therefore, the Gardner model was the most suitable model to fit the SWCC of PCM.

The Gardner model is expressed as follows (Gardner 1958):

$$\theta = \frac{\theta_s - \theta_r}{1 + \left(\frac{\varphi}{a}\right)^n} + \theta_r, \quad (1)$$

where φ is the suction, kPa; θ_s is the saturated volumetric water content, %; θ_r is the residual volumetric water content, %; a is the parameter related to the air-entry value; and n is the parameter related to the pore size distribution. The fitting parameters of the Gardner model for the SWCC of the PCM are given in **Table 4**. The dry density and particle size had a great influence on a , but had little effect on n . Among them, with the increase in dry density, a had a greater trend.

Table 4
Fitting parameters of the Gardner model

Particle size of bentonite pellets / mm	Dry density / (g/cm ³)	a	n	R^2
1–2	1.50	20198.26	0.73	0.997
	1.60	17002.92	0.74	0.996
	1.80	31257.96	0.76	0.996
0.5–1	1.50	13615.49	0.78	0.995
	1.60	14041.81	0.78	0.997
	1.80	26422.64	0.71	0.994
0.25–0.5	1.50	16962.26	0.74	0.996
	1.60	17739.19	0.71	0.990
	1.80	41460.37	0.67	0.998

4.3.2 Prediction of unsaturated hydraulic conductivity

Gardner proposed a two-parameter model by considering the pore size distribution and pore geometry (Gardner 1958; Fredlund and Rahurdjo 1993):

$$k(\varphi) = \frac{k_s}{1 + a\varphi^n}, \quad (2)$$

where k_s is the saturated hydraulic conductivity. a and n were obtained by fitting the SWCC of PCM with the Gardner model, and it has just been proved that the Gardner model has a good fit. Therefore, it was feasible to predict the unsaturated hydraulic conductivity of the PCM by using the two-parameter model proposed by Gardner.

The saturated hydraulic conductivity of 6 groups of PCMs was determined by the variable head permeability test as shown in **Table 5**. At the same dry density, the saturated hydraulic conductivity of the PCMs with different particle sizes was in the same order of magnitude. But as the particle size increased,

the saturated hydraulic conductivity of the PCM increased and the impermeability decreased. Moreover, the effect of dry density on the saturated hydraulic conductivity of the PCM was more significant than that of particle size. When the particle size was the same, the dry density of the PCM increased from 1.50 g/cm³ to 1.80 g/cm³, and the saturated hydraulic conductivity of the PCM decreased from 5.31×10⁻¹¹ m/s to 1.61×10⁻¹² m/s, an order of magnitude difference. With the increase in dry density, the saturated hydraulic conductivity decreased and the impermeability increased.

Table 5
Saturated hydraulic conductivity of the PCM

Specimen No.	Particle size of bentonite pellets / mm	Dry density / (g/cm ³)	Saturated hydraulic conductivity / (m/s)
1	1–2	1.60	3.79×10 ⁻¹¹
2	0.5–1	1.60	2.77×10 ⁻¹¹
3	0.25–0.5	1.60	2.38×10 ⁻¹¹
4	0.5–1	1.50	5.31×10 ⁻¹¹
5	0.5–1	1.80	1.61×10 ⁻¹²

The unsaturated hydraulic conductivity of the PCM was obtained by combining the model with the saturated hydraulic conductivity (see Figs. 12 and 13). Ye et al. (2009) carried out an unsaturated hydraulic conductivity test on the compacted GMZ bentonite with a dry density of 1.70 g/cm³, and the unsaturated hydraulic conductivity ranged from 1.13×10⁻¹³ m/s to 8.41×10⁻¹⁵ m/s (see Fig. 12). In this work, the unsaturated hydraulic conductivity of PCMs with a particle size of 0.5-1 mm ranged from 1.27×10⁻¹² m/s to 9.88×10⁻¹⁵ m/s. The unsaturated hydraulic conductivity of the compacted GMZ bentonite with a dry density of 1.70 g/cm³ was between that of the PCM with a dry density of 1.60 g/cm³ and that of the PCM with a dry density of 1.80 g/cm³. Besides, the hydraulic conductivity of the PCM agreed well with that of the compacted bentonite (Hoffmann et al. 2007). Therefore, it could be considered that the method used in this work was reliable to predict the unsaturated hydraulic conductivity of the PCM.

The variation of the unsaturated hydraulic conductivity of the PCM with increasing suction could be divided into two stages (see Figs. 12 and 13). The suction of 0–1000 kPa belonged to the rapid decline stage, and the suction of 1000–30000 kPa belonged to the slow decline stage. In the rapid decline stage, i.e. in the low suction stage, the pore water mainly existed in the inter-aggregate pores, with large pores and good connectivity. When the PCM varied from a saturated state to an unsaturated state, with only a small suction, the pore water in the soil could be discharged quickly, and the unsaturated hydraulic conductivity of the PCM decreased significantly. In the slow decline stage, i.e. in the high suction stage,

the pore water was mainly in the intra-aggregate pores. With the continuous increase in the suction, the flow path of the pore water became smaller and narrower. The pore water was mainly adsorbed on the surface of the soil particles in the form of pellicular water, and the unsaturated hydraulic conductivity of the PCM decreased slowly and smoothly.

The unsaturated hydraulic conductivity of the PCMs with different dry densities and a particle size of 0.5–1 mm ranged from 1×10^{-12} m/s to 1×10^{-15} m/s (see Fig. 12). At the same suction, the unsaturated hydraulic conductivity of the PCMs with dry densities of 1.50 g/cm³ and 1.60 g/cm³ varied in the same order of magnitude, but the unsaturated hydraulic conductivity of the PCM with a dry density of 1.80 g/cm³ was one order of magnitude smaller. The results showed that the dry density had a significant effect on the unsaturated hydraulic conductivity of the PCM. With the increase in dry density, the unsaturated hydraulic conductivity of the PCM decreased.

The unsaturated hydraulic conductivity of the PCMs with a dry density of 1.60 g/cm³ and different particle sizes ranged from 1×10^{-12} m/s to 1×10^{-14} m/s (see Fig. 13). With the increase in particle size, the unsaturated hydraulic conductivity increased. Comparing the variations in Figs. 12 and 13, it could be found that the effect of dry density on the unsaturated hydraulic conductivity was greater than that of particle size.

4.4 Influence mechanism of SWCC and hydraulic conductivity

There are two types of pores in bentonite, i.e. inter-aggregate pores and intra-aggregate pores in the PCM, as shown in Fig. 14 (Lloret and Villar 2007; Agus et al. 2010). The pores with pore sizes larger than 0.2 μ m are inter-aggregate pores, while those with pore sizes smaller than 0.2 μ m are intra-aggregate pores. Figure 15 shows the pore size distribution curves of the PCWs with different dry densities and a particle size of 0.5–1 mm after the SWCC tests. The PCM presented a bimodal pattern in which the intra-aggregate pores and inter-aggregate pores were dominant. The first peak corresponded to the pore size of 0.06 μ m, which was the pore size of the intra-aggregate pores. Compaction did not affect on it, and it did not vary with the dry density. The pore size corresponding to the second peak was 12 μ m, which was the pore size of the inter-aggregate pores. With the decrease in dry density, the size and number of the inter-aggregate pores increased.

The inter-aggregate pores have a great impact on the low suction (Fredlund and Rahurdjo 1993; Hoffmann et al. 2007; Wang et al. 2013). The PCM with low dry density had a lot of large inter-aggregate pores. It could store a large amount of free water and capillary water in the saturated state, and had a high water content in a high saturation state (low suction range). Due to compaction, the size and number of the inter-aggregate pores in the PCM with a high dry density became smaller, and the water content was low at high saturation. In addition, within the high suction range, the pores affecting the water retention and suction are the intra-aggregate pores (Fredlund and Rahurdjo 1993; Hoffmann et al. 2007; Wang et al. 2013). With the variation of dry density, the size and number of intra-aggregate pores

remained unchanged. And in the high suction range, pore water is mainly adsorbed on the mineral surface by intermolecular forces, and compaction can hardly vary the influence of mineral adsorption capacity on water (Fredlund and Rahurdjo 1993). Therefore, in the high suction range, the dry density had little effect on the SWCC of the PCM. Since compaction has no significant effect on the size and number of the intra-aggregate pores in bentonite powder compacted samples after the SWCC test (Zhang et al. 2014), it can be inferred that the compaction has no obvious effect on the size and number of the intra-aggregate pores in bentonite pellets after the SWCC test.

After the SWCC test, the microstructures of the PCMs with a dry density of 1.60 g/cm^3 and different particle sizes are shown in Fig. 16. During the saturation process of the PCM, the high-density bentonite pellets in the PCM were not homogeneous with the surrounding bentonite powder. The results showed that the water molecules did not completely enter into the laminated body of the high-density bentonite pellets, and the internal aggregates of the high-density bentonite pellets did not fully swell, which had the potential of continuous swelling and healing. The microstructure of the saturated FoCa PCM and MX-80 PCM were tested, and similar conclusions were obtained (Pusch et al. 2003; Van Geet et al. 2005). Moreover, the bentonite pellets were not in contact with each other, but were suspended in the bentonite powder and wrapped by the bentonite powder. The interface between the bentonite pellets and powder had no noticeable shrinkage and cracking, indicating that the PCM is effective as a sealing material for the HLW disposal.

The SEM images were binarized to obtain the apparent porosity and average pore area. When the particle size was 1–2, 0.5–1, and 0.25–0.5 mm, respectively, the apparent porosity of the PCM at 500 times magnification was 4.1, 4.5, and 4.7%, respectively, and the average pore area was 138, 112, and $102 \mu\text{m}^2$, respectively. According to the pore size in the SEM images, the pores corresponded to the inter-aggregate pores. Therefore, under the same dry density, as the particle size decreased, the total volume of the inter-aggregate pores did not change significantly, but the average area of the inter-aggregate pores decreased from large to small, thus the water flow of the inter-aggregate pores became more inconvenient and the water retention of the PCM increased. In other words, in the low suction range, the smaller the particle size, the higher the water content of the PCM when the suction was the same. In addition, for the sample preparation of the PCM with the same dry density, the compaction effect was different due to the different particle sizes. However, it was previously found that the compaction had no significant effect on the size and number of intra-aggregate pores in the bentonite powder compacted samples and bentonite pellets after the SWCC test. And the dry density and microstructure of bentonite pellets with different particle sizes before compaction were all consistent. Thus, under the same dry density and different particle sizes of the PCMs, the intra-aggregate pores in the bentonite pellets and bentonite powder were identical. In the high suction range, the particle sizes had little effect on the water retention of the PCM.

After the SWCC test, the PCM was unsaturated, and its microstructure could also be used to analyze the influence mechanism of the unsaturated hydraulic conductivity. The increase in dry density decreased the size and number of inter-aggregate pores in the PCM under compaction, and the intra-aggregate pores did not vary significantly. Therefore, in general, the increase in dry density of the PCM led to the deterioration

of pore connectivity, thus the hydraulic passage per unit section decreased, the unsaturated hydraulic conductivity decreased, and the impermeability increased. Furthermore, with the increase in particle size, although there was no obvious variation in the intra-aggregate pores of the PCM, the area of the inter-aggregate pores increased, resulting in the better connectivity between the inter-aggregate pores and the increase in the hydraulic passage per unit section. Therefore, the unsaturated hydraulic conductivity of the PCM increased and the impermeability decreased.

Conclusions

PCM is a feasible material for the joint sealing of HLW disposal. Its SWCC and hydraulic conductivity are significant theoretical parameters for the hydro-mechanical coupling and long-term safe operation analysis of the HLW disposal. In this work, the optimum pellet percentage of the PCM was determined, the influence of particle size of bentonite pellets and dry density on the SWCC of the PCM was analyzed, and the unsaturated hydraulic conductivity of the PCM was predicted by combining the SWCC model and saturated permeability coefficient. Besides, the influence mechanism of SWCC and hydraulic conductivity was discussed based on the microstructures. The conclusions are as follows:

(1) When the pellet percentage was 70%, the packing density and free swelling ratio of the PCM were the highest. With the same pellet percentage, the packing density increased and the free swelling ratio decreased with the increase in particle size.

(2) In the low suction range (20–1150 kPa), the influence of dry density on the SWCC was more obvious than that of particle size. The dry density and particle size had a negative correlation with the water content at the same suction. In the high suction range (4200–309000 kPa), the dry density and particle size had little effect on the SWCC. The Gardner model was suitable for describing the SWCC of PCM.

(3) The hydraulic conductivity of the PCM decreased with the increase in dry density, but increased with the increase in particle size. The influence of dry density on the hydraulic conductivity was greater than that of particle size.

(4) With the decrease in dry density, the size and number of inter-aggregate pores in the PCM increased. With the decrease in particle size, the total volume of inter-aggregate pores had no discernible variation, and the average area of inter-aggregate pores had a decreasing trend. However, the dry density and particle size had no significant effect on the intra-aggregate pores of the PCM. This can explain the influence mechanism of dry density and particle size on the SWCC and unsaturated hydraulic conductivity.

Declarations

Acknowledgment

The authors are grateful for the financial support from the National Natural Science Foundation of China [Grant No. 41972265 and Grant No. 41672261].

Declaration of interests

We declare that we do not have any commercial or associative interest that represents a conflict of interest in connection with the work submitted.

Data Availability

All data and models generated and used during the study appear in the submitted article.

CRediT author statement

Jianghong Zhu: Conceptualization, Methodology, Investigation, Data Curation, Writing - Original draft preparation.

Zhenyan Su: Writing - Review & Editing.

Huyuan Zhang: Conceptualization, Supervision, Funding acquisition, Project administration, Writing - Review & Editing.

References

1. Abootalebi P, Siemens G., Thermal properties of engineered barriers for a Canadian deep geological repository, *Can. Geotech. J.* 55 (6) (2018) 759–776.
2. Agus S.S., Schanz T., Fredlund D.G., Measurements of suction versus water content for bentonite-sand mixtures. *Can. Geotechn. J.* 47 (5) (2010) 583-594.
3. Bai B., Xu T., Nie Q., Li P., Temperature-driven migration of heavy metal Pb^{2+} along with moisture movement in unsaturated soils, *Int. J. Heat Mass Tran.* 153 (2020) 119573.
4. Bharat T.V., Gapak Y., Soil-water characteristic curves of bentonites in isochoric conditions during wetting: measurement and prediction, *Can. Geotech. J.* 58 (5) (2021) 711-721.
5. Bian X., Cui Y., Zeng L., Li X., State of compacted bentonite inside a fractured granite cylinder after infiltration, *Appl. Clay Sci.* 186 (2020) 105438.
6. Cui S., Zhang H., Zhang M., Swelling characteristics of compacted GMZ bentonite–sand mixtures as a buffer/backfill material in China, *Eng. Geol.* 141-142 (2012) 65-73.
7. Fattah M.Y., Salim N.M., Irshayyid E.J., Determination of the soil-water characteristic curve of unsaturated bentonite–sand mixtures, *Environ. Earth Sci.* 76 (5) (2017) 201.
8. Feng Y., Liu D., Li D., Zhao Q., A Study on Microstructure Composition of Unsaturated Red Mud and its Impact on Hydraulic Characteristics, *Geotechnical and Geological Engineering* 35 (4) (2017) 1357-1367.

9. Fredlund D.G., Rahurdjo H., Soil mechanics for unsaturated soils, John Wiley and Sons, New York, 1993.
10. Fredlund D.G., Xing A., Huang S., Predicting the permeability function for unsaturated soils using the soil-water characteristic curve, *Can. Geotech. J.* 31 (4) (1994) 521-532.
11. Gardner W.R., Some Steady-State Solutions of the Unsaturated Moisture Flow Equation with Application to Evaporation from a Water Table, *Soil Science* 85 (4) (1958) 228-232.
12. Genuchten M.T.V., A closed-form equation for predicting the hydraulic conductivity of unsaturated soils, *Soil Science Society of America Journal* 44 (44) (1980) 892-898.
13. Hoffmann C., Alonso E.E., Romero E., Hydro-mechanical behaviour of bentonite pellet mixtures, *Physics and Chemistry of the Earth, Parts A/B/C* 32 (8-14) (2007) 832-849.
14. IAEA, Characterization of swelling clays as components of the engineered barrier system for geological repositories, IAEA (2013) Austria.
15. Lee H.B., Lee H.K., Shim M.J., Kim S.W., Characteristics of thermal welding at the interface of ABS/bentonite composite, *Mater. Chem. Phys.* 58 (3) (1999) 264-267.
16. Liu J., Ni H., Cao X., Ma L., Guo J., Chen X., Laboratory investigation on gas permeability of compacted GMZ bentonite under a coupled hydraulic-mechanical effect, *Eng. Geol.* 276 (2020) 105761.
17. Liu J., Skoczylas F., Talandier J., Pu H., Dismantling of the EB experiment: Experimental research on the retrieved GBM and bentonite blocks, *Nucl. Eng. Des.* 300 (2016) 297-307.
18. Lloret A., Villar M.V., Advances on the knowledge of the thermo-hydro-mechanical behaviour of heavily compacted "FEBEX" bentonite, *Physics and Chemistry of the Earth, Parts A/B/C* 32 (8-14) (2007) 701-715.
19. Ma G., Zhang H., Ji Z., Tan Y., Comparison of the swelling pressure of bentonite pellet-contained materials and powder, *Constr. Build. Mater.* 281 (2021) 122531.
20. Peng F., Tan Y., Sun D., Thermal conductivity of bentonite-graphite mixture and its prediction for high-level radioactive waste repository, *Ann. Nucl. Energy* 154 (2021) 108142.
21. Pusch R., Bluemling P., Johnson L., Performance of strongly compressed MX-80 pellets under repository-like conditions, *Appl. Clay Sci.* 23 (1-4) (2003) 239-244.
22. Sandén T., Börgesson L., System design of backfill-Methods for water handling, KBSR-14-09, Swedish Nuclear Fuel and Waste Management Company, Sweden, 2014.
23. Seiphoori A., Ferrari A., Laloui L., An insight into the water retention behaviour of MX 80 granular bentonite, *International Conference on the Performance of Engineered Barriers* 2014.
24. Seiphoori A., Laloui L., Ferrari A., Hassan M., Khushefati W.H., Water retention and swelling behaviour of granular bentonites for application in Geosynthetic Clay Liner (GCL) systems, *Soils Found.* 56 (3) (2016) 449-459.
25. Sun W., Xu G., Wei G., Zhang W., Sun D., Effects of ammonium ion and bentonite content on permeability of bentonite-clay mixture, *Environ. Earth Sci.* 80 (4) (2021) 151.

26. Sun Z., Chen Y., Ye W., Cui Y., Wang Q., Swelling deformation of Gaomiaozi bentonite under alkaline chemical conditions in a repository, *Eng. Geol.* 279 (2020) 105891.
27. Tan Y., Zhang H., He D., Zhang G., Deterioration of exposed buffer block: desiccation shrinkage and cracking, *Bull. Eng. Geol. Environ.* 78 (7) (2019) 5431-5444.
28. Tan Y., Zhang H., Wang Y., Evaporation and shrinkage processes of compacted bentonite-sand mixtures, *Soils Found.* 60 (2) (2020) 505-519.
29. The national Standards Compilation Group of People's Republic of China, Standard for geotechnical testing method, GB/T50123-2019, China Planning Press, Beijing, 2019. (in Chinese)
30. The national Standards Compilation Group of People's Republic of China, Bentonite, GB/T20973-2020, China Quality Inspection press, Beijing, 2020. (in Chinese)
31. Tripathy S., Tadza M.Y.M., Thomas H.R., Soil-water characteristic curves of clays, *Can. Geotech. J.* 51 (8) (2014) 869-883.
32. Van Geet M., Volckaert G., Roels S., The use of microfocus X-ray computed tomography in characterising the hydration of a clay pellet/powder mixture, *Appl. Clay Sci.* 29 (2) (2005) 73-87.
33. Vaz E.F., Gitirana G.F.N., Mendes T.A., Rebolledo J.F.R., On the equilibrium of suction and pressure plate tests, *Acta Geotechnica* (2021).
34. Wang J., High-level radioactive waste disposal in China: update 2010, *Journal of Rock Mechanics and Geotechnical Engineering* 2(01) (2010) 1-11.
35. Wang Q., Cui Y., Tang A.M., Barnichon J., Saba S., Ye W., Hydraulic conductivity and microstructure changes of compacted bentonite/sand mixture during hydration, *Eng. Geol.* 164 (2013) 67-76.
36. Wang Q., Minh Tang A., Cui Y., Delage P., Barnichon J., Ye W., The effects of technological voids on the hydro-mechanical behaviour of compacted bentonite-sand mixture, *Soils Found.* 53 (2) (2013) 232-245.
37. Wang S., Dong Y., He M., Chen L., Yu X., Characterization of GMZ bentonite and its application in the adsorption of Pb(II) from aqueous solutions, *Appl. Clay Sci.* 43 (2) (2009) 164-171.
38. Wang Y., Zhang H., Tan Y., Zhu J., Sealing performance of compacted block joints backfilled with bentonite paste or a particle-powder mixture, *Soils Found.* 61 (2) (2021) 496-505.
39. Xu Z., Sun Y., Niu Z., Xu Y., Wei X., Chen X., Pan D., Wu W., Kinetic determination of sedimentation for GMZ bentonite colloids in aqueous solution: Effect of pH, temperature and electrolyte concentration, *Appl. Clay Sci.* 184 (2020) 105393.
40. Ye W., Qian L., Chen B., Wang J., Cui Y., Laboratory test on unsaturated hydraulic conductivity of densely compacted Gaomiaozi Bentonite under confined conditions, *Chinese Journal of Rock Mechanics and Engineering* 31 (1) (2009) 105-108.
41. Yoon S., Kim G., Measuring thermal conductivity and water suction for variably saturated bentonite, *Nucl. Eng. Technol.* 53 (3) (2021) 1041-1048.
42. Zhang H., Tan Y., Zhu F., He D., Zhu J., Shrinkage property of bentonite-sand mixtures as influenced by sand content and water salinity, *Constr. Build. Mater.* 224 (2019) 78-88.

43. Zhang H., Wang W., Liu P., Yan M., Peng Y., Sealing and healing of compacted bentonite block joints in HLW disposal, Chinese Journal of Rock Mechanics and Engineering 35(S2) (2016) 3605-3614.
44. Zhang M., Zhang H., Zhou L., Wang B., Wang S., Hydro-mechanical analysis of GMZ bentonite–sand mixtures in the water infiltration process as the buffer/backfill mixture in an engineered nuclear barrier, Appl. Clay Sci. 97-98 (2014) 115-124.

Figures

Figure 1

Particle size distribution of the GMZ bentonite

Figure 2

Compaction curve of the bentonite powder under a static pressure of 255 MPa

Figure 3

Bentonite pellets with different particle sizes

Figure 4

Variation of packing volume and density of PCM with pellet percentage

Figure 5

Relationship between the free swelling ratio of PCM and pellet percentage

Figure 6

Test apparatus schematic of vacuum saturation

Figure 7

Test apparatus schematic of SWCC (a) Pressure plate method (b) Vapour equilibrium technique

Figure 8

Influence of dry density on the SWCC of PCM (a) Particle size of 1–2 mm (b) Particle size of 0.5–1 mm (c) Particle size of 0.25–0.5 mm

Figure 9

Influence of particle size on the SWCC of PCM (a) Dry density of 1.5 g/cm³ (b) Dry density of 1.6 g/cm³ (c) Dry density of 1.8 g/cm³

Figure 10

Comparison of SWCCs of the GMZ PMC, FEBEX PMC, and GMZ bentonite-sand mixture

Figure 11

Fitting for the SWCC of PCM

Figure 12

Unsaturated hydraulic conductivity of the PCMs with different dry densities

Figure 13

Unsaturated hydraulic conductivity of the PCMs with different particle sizes

Figure 14

Schematic diagram of pore structure in the PCM (Agus et al. 2010)

Figure 15

Pore size distribution curves of the PCWs with different dry densities after SWCC tests

Figure 16

SEM images of the PCMs with different particle sizes after SWCC tests (a) Particle size of 1–2 mm (b) Particle size of 0.5–1 mm (c) Particle size of 0.25–0.5 mm