Fabrication of CdS/Ti₃C₂/g-C₃N₄NS Z-Scheme Composites with Enhanced Visible-Light-Driven Photocatalytic Activity

Ranran Zhang

Hebei Normal University

Jiaying Jin

Hebei Normal University

Lumeng Jia

Hebei Normal University

Bo Shi

Hebei Normal University

Rufen Chen (✉ chenrufen@hebtu.edu.cn)

Hebei Normal University

Research Article

Keywords: CdS/Ti₃C₂/g-C₃N₄NS, Z-scheme heterojunction, Orange G, Degradation

Posted Date: August 2nd, 2021

DOI: <https://doi.org/10.21203/rs.3.rs-683839/v1>

License: This work is licensed under a Creative Commons Attribution 4.0 International License.

[Read Full License](#)

Version of Record: A version of this preprint was published at Environmental Science and Pollution Research on October 14th, 2021. See the published version at <https://doi.org/10.1007/s11356-021-16942-4>.

Abstract

The Ti_3C_2 and $\text{g-C}_3\text{N}_4\text{NS}$ were obtained first, and the $\text{CdS}/\text{Ti}_3\text{C}_2/\text{g-C}_3\text{N}_4\text{NS}$ Z-scheme composites were prepared via a facile hydrothermal synthesis and their photocatalytic properties were investigated. The $\text{g-C}_3\text{N}_4\text{NS}$ with a high surface area displayed higher adsorption and degradation capacity. Compared with $\text{Ti}_3\text{C}_2/\text{g-C}_3\text{N}_4\text{NS}$ and CdS , the optimal ternary composites exhibited significantly enhanced visible light (vis) photocatalytic activity. The Fabrication of $\text{CdS}/\text{Ti}_3\text{C}_2/\text{g-C}_3\text{N}_4\text{NS}$ Z-scheme heterostructure not only enhanced vis absorption, but also improved the separation ability of the photoinduced e^- - h^+ pairs and the redox ability of the catalyst, thereby leading to the improvement of visible-light-driven photocatalytic activity. This finding provides new insights into the construction of high efficiency Z-scheme heterostructure photocatalyst.

Introduction

With the development of industry, water pollution has become a serious problem. Photocatalysis has attracted much attention in resolving water pollution (Xu et al. 2019; Sun et al. 2020). The two-dimensional (2D) layered materials have been widely studied due to their special physical and chemical properties (Zhang et al. 2015; Feng et al. 2018; Low et al. 2018). Ti_3C_2 MXene is a promising 2D-layered photocatalyst material due to its fast electron transfer capability and rich surface properties (Zhang et al. 2018). However, fast charge recombination in Ti_3C_2 catalysts limits its further application. Ti_3C_2 has abundant surface functional groups and can form Schottky junction with some semiconductor materials, which can promote the separation of photogenerated e^- - h^+ pairs (Gao et al. 2015; Zhou et al. 2017; Ai et al. 2019; Xiao et al. 2020;).

Graphitic carbon nitride ($\text{g-C}_3\text{N}_4$) as a nontoxic and accessible semiconductor material, was widely applied in the field of photocatalysis (Koyyada et al. 2021; Ibrahim and Gondal 2021). Furthermore, $\text{g-C}_3\text{N}_4$ nanosheets ($\text{g-C}_3\text{N}_4\text{NS}$) were obtained by treating $\text{g-C}_3\text{N}_4$, and their photocatalytic degradation properties were further improved (Dong et al. 2017; Wu et al. 2019). CdS is an excellent vis-sensitive photocatalyst (Zhou et al. 2015; Zhang et al. 2016). However, the photocatalytic degradation effect of CdS was limited due to the problems of fast recombination of the photoexcited carriers and the photocorrosion (Peng et al. 2019; Zou et al. 2020). The CdS was combined with other semiconductor materials to form composites, which can effectively inhibit the recombination of the photoinduced e^- - h^+ pairs and improve the photocatalytic degradation performance (Kang et al. 2017; Ran et al. 2017; Peng et al. 2019; Zou et al. 2020;).

In addition, the formation of Z-scheme heterojunction in the composite catalyst can also efficiently improve the photocatalytic activity (Zhao et al. 2019). Successful ternary Z-scheme photocatalysts generally utilize noble metals as electron transfer components. Recently, some studies found that the preparation of ternary Z-scheme heterostructure composites using Ti_3C_2 as electron transfer medium can improve the photocatalytic degradation of pollutants (Ai et al. 2019; Li et al. 2019; Ding et al. 2019 Sun et

al. 2020). To further improve visible-light-driven photocatalytic activity, it is still a great challenge to develop novel Z-scheme heterostructure photocatalysts with high efficiency and stability using Ti_3C_2 as a charge transport medium via a simple method.

Herein, the $\text{g-C}_3\text{N}_4\text{NS}$ and Ti_3C_2 were obtained using urea and Ti_3AlC_2 as raw materials, respectively, then a 2D-layered $\text{CdS}/\text{Ti}_3\text{C}_2/\text{g-C}_3\text{N}_4\text{NS}$ Z-scheme photocatalysts were prepared via a facile hydrothermal synthesis. The photocatalytic activity of as-prepared ternary composites was investigated under vis irradiation using orange II as an organic pollutant. This study may provide useful insights into utilizing Ti_3C_2 as the mediator for controlling the transfer of photogenerated carriers in Z-scheme photocatalysis.

Experimental Section

Materials

Ti_3AlC_2 , HF, CdCl_2 , Na_2S , Urea, HCl, orange II, p-benzoquinone (BZQ), tertbutanol (TBA), ethylenediaminetetracetic acid (EDTA), 5,5-dimethyl-1pyrroline Noxide (DMPO), were used. The deionized water (DI) was used to prepare all the solutions.

Preparation of Ti_3C_2 and $\text{g-C}_3\text{N}_4\text{NS}$

Ti_3C_2 was obtained by exfoliating the Al layers from Ti_3AlC_2 with 40 wt% HF at 30°C for 25 h. The precipitates were then filtered, washed with DI, and dried in the oven for 10 h.

Synthesis of the $\text{g-C}_3\text{N}_4\text{NS}$: the urea was calcined at 500° C for 6 h to obtain a $\text{g-C}_3\text{N}_4$ bulk material, and 0.24g of $\text{g-C}_3\text{N}_4$ was added to 60 mL 6M HCl, and treated with ultrasound for 30 min. The mixture was transferred to an autoclave (100mL) and then heated at 110 °C for 7h. The precipitates were centrifuged, washed, and dried at 60°C for 12h in a vacuum oven.

Preparation of $\text{Ti}_3\text{C}_2/\text{g-C}_3\text{N}_4\text{NS}$ and $\text{CdS}/\text{g-C}_3\text{N}_4\text{NS}$ composites

0.5g of Ti_3C_2 (**CdS**) and 0.6g of $\text{g-C}_3\text{N}_4\text{NS}$ samples were added to 50 mL DI under stirring, respectively. The two mixtures were then mixed and sonicated for 1 h. Subsequently, the suspension was heated at 80 °C in a water bath until the solvent was evaporated. The products ($\text{Ti}_3\text{C}_2/\text{g-C}_3\text{N}_4\text{NS}$ and $\text{CdS}/\text{g-C}_3\text{N}_4\text{NS}$) were then dried at 60 °C for 12h in a vacuum oven.

Fabrication of $\text{CdS}/\text{Ti}_3\text{C}_2/\text{g-C}_3\text{N}_4\text{NS}$ composites

The obtained $\text{Ti}_3\text{C}_2/\text{g-C}_3\text{N}_4\text{NS}$ (0.5 g) was dispersed in 60 mL of CdCl_2 solution and further stirred for 15 min, and certain amounts of Na_2S were then added to the mixture solution under stirring. Subsequently, the mixture was transferred to an autoclave (100mL) and then heated at 200 °C for 6h. After the hydrothermal treatment, the precipitates were centrifuged, washed, and then dried at 85 °C for 12 h. The

obtained CdS/Ti₃C₂/g-C₃N₄NS composites by controlling the mass ratio of CdS and Ti₃C₂/g-C₃N₄NS of 2:1, 3:1, 4:1, and 5:1 were denoted as CTN-2:1, CTN-3:1, CTN-4:1, and CTN-5:1, respectively.

Measurement of photocatalytic activity

The photocatalyst (0.04 g) was dispersed in an orange H_2O_2 solutions (100 mL, 20mg/L) at pH 3, and stirred in a dark room for 1h. The 300W Xe lamp was selected as light source. All experimental runs were performed at 20 °C under continuous stirring. During the process of light irradiation, 5 mL suspension were taken out and centrifuged. The concentrations of orange H_2O_2 were determined using a UV-vis spectrometer (UV-8000) at 486nm.

Characterization The characterization and performance of photocatalyst are summarized in the Supporting Information (Table S1).

Results And Discussion

Structures and morphologies of samples

Figure 1 displays the XRD patterns of the as-prepared samples. In Fig. 1a, the peaks at 2θ of 8.84°, 18.4°, 27.5°, and 60.7° correspond to (002), (004), (006), and (110) crystal planes of Ti₃C₂ (Xu et al. 2018; Cai et al. 2018), respectively. In Fig. 1b, the diffraction peaks of the Ti₃C₂ and g-C₃N₄NS were presented (Xu et al. 2019). As shown in Fig. 1c–f, the CdS with cubic phase (JCPDS No 80 – 0019) is obtained in addition to Ti₃C₂ and g-C₃N₄NS phases.

Fig. 2 shows the Raman spectra of the samples. In Fig.2a, the Raman peaks located at 325.5 cm⁻¹ (A_{1g} mode) corresponds to the out-of-plane stretching vibrations of Ti and C (Hu et al. 2015), and the peaks at 1456 and 1519 cm⁻¹ can be attributed to the D-band and G-band of Ti₃C₂ (Naguib et al. 2014). In Fig.2b, the typical peaks at 301.1 and 600.2 cm⁻¹ are assigned to the first-order LO Raman peak and second-order LO phonon vibrational mode of cubic CdS (Rengaraj et al. 2011), respectively. In Fig.2 c, the peak at 474cm⁻¹ is referred as the Raman signal of g-C₃N₄NS (Sutar et al. 2020). As shown in Fig.2d, the Raman peaks of Ti₃C₂, g-C₃N₄NS and CdS are shown, respectively. The XRD and Raman results verify that the ternary composites are composed of Ti₃C₂, g-C₃N₄NS and CdS.

FigureS1 shows the morphologies of g-C₃N₄ and g-C₃N₄NS. g-C₃N₄ shows an irregularly wrinkled morphology, and the prepared g-C₃N₄NS presents a thin sheet shape. Figure 3 presents the morphologies of the Ti₃C₂, Ti₃C₂/g-C₃N₄NS and CdS/Ti₃C₂/g-C₃N₄NS samples. The prepared Ti₃C₂ exhibits a 2D-layered morphology (Fig. 3a). In Fig. 3b, the g-C₃N₄NS is tightly coated around the Ti₃C₂, forming a rough surface. A rough surface facilitates the transmission of photogenerated carriers (Zhang et al. 2020). As shown in Fig. 3c–f, the SEM images of CdS/Ti₃C₂/g-C₃N₄NS composites show that the CdS particles are deposited and tightly attached on the interlayer and surface of Ti₃C₂/g-C₃N₄NS. With the further increase

in CdS amount, the interlayer of the composite occupies a large amount of CdS particles, and the 2D-layered structure of the ternary composite is weakened (Fig. 3f). The EDX spectra and the corresponding elemental mapping were carried out for the CTC-4:1 sample (Fig.S2). Ti, C, N, S, and Cd elements are uniformly distributed in the composite.

The HRTEM image of CTC-4:1 is shown in Fig. 4. The lattice spacings of 0.250 nm and 0.336 nm correspond to the (006) and (111) crystal facets in Ti_3C_2 and CdS (Cao et al. 2013; Ding et al. 2019), respectively. The $\text{g-C}_3\text{N}_4\text{NS}$ with low crystallinity do not show obvious lattice fringes (Wang et al. 2019). A compact and continuous interface exists among Ti_3C_2 , CdS, and $\text{g-C}_3\text{N}_4\text{NS}$, which can provide efficient separation and diffusion of photoinduced carriers (Kang et al. 2017).

Xps Analysis Of Samples

Figure 4 shows the XPS spectra of the CTN-4:1 and CdS. The XPS survey spectrum indicates that the CTN-4:1 is composed of Ti, C, N, S, and Cd elements (Fig. S3).

In the $\text{Ti}2\text{p}$ XPS spectrum of CTN-4:1 (Fig. 5A), the peaks at around 454.7, 458.7 and 463.9 eV are attributed to the Ti-C, $\text{Ti}2\text{p}_{3/2}$ and $\text{Ti}2\text{p}_{1/2}$ in Ti_3C_2 (Yang et al. 2018; He et al. 2020). For the $\text{C}1\text{s}$ spectrum (Fig. 5B), the peaks at approximately 286.26 eV can correspond to C-Ti on the CTN-4:1 surface (Peng et al. 2017), while the peaks at 284.6 and 288.36 eV are attributed to the C-C and C-N = C bonds in $\text{g-C}_3\text{N}_4\text{NS}$ (Diao et al. 2020).

The $\text{S}2\text{p}$ and $\text{Cd}3\text{d}$ XPS spectra of CTN-4:1 and CdS were compared. In the $\text{S}2\text{p}$ and $\text{Cd}3\text{d}$ spectra of CTN-4:1, peaks at 161.9 and 163.2 eV can correspond to $\text{S}2\text{p}_{1/2}$ and $\text{S}2\text{p}_{3/2}$ of S^{2+} (Ai et al. 2019) (Fig. 5C), and the peaks at 412.3 and 405.5 eV can be ascribed to $\text{Cd}3\text{d}_{3/2}$ and $\text{Cd}3\text{d}_{5/2}$ of Cd^{2+} (Ai et al. 2019) (Fig. 5D). Compared with CdS, the binding energies of $\text{S}2\text{p}$ and $\text{Cd}3\text{d}$ in the CTN-4:1 show a shift to the right, suggesting the strong interactions between CdS and $\text{Ti}_3\text{C}_2/\text{g-C}_3\text{N}_4\text{NS}$, forming a heterojunction composite (Wang et al. 2018; Wang et al. 2019).

Bet Analysis Of Samples

The Nitrogen adsorption-desorption isotherms of as-prepared samples are shown in Fig. S4. The specific surface area and pore volume values of all samples are summarized in Table 1. The surface area and pore volume values of obtained $\text{g-C}_3\text{N}_4\text{NS}$ are evidently higher than that of $\text{g-C}_3\text{N}_4$. In contrast to the $\text{Ti}_3\text{C}_2/\text{g-C}_3\text{N}_4\text{NS}$, the CdS-loaded ternary composites increase the surface area and pore volume values. Among the ternary composites, the CTN-4:1 sample presents the largest surface area, which may provide more reactive active sites for photocatalytic degradation (Elfiad et al. 2018).

Table 1
Surface area and pore volume of the samples

Sample	Surface area (m ² /g)	Pore volume (cm ³ /g)
g-C ₃ N ₄	45.09	0.22
g-C ₃ N ₄ NS	70.72	0.53
CdS	54.83	0.30
Ti ₃ C ₂	6.501	0.04
Ti ₃ C ₂ /g-C ₃ N ₄ NS	21.86	0.18
	46.28	0.22
CTN-2:1	51.29	0.24
CTN-3:1	52.99	0.26
CTN-4:1	48.89	0.25
CTN-5:1		

Photocatalytic Activity Of As-prepared Samples

Photocatalytic degradation of orange II

In Fig. S5, the adsorption and degradation curves of orange II exhibit that g-C₃N₄NS has higher adsorption and degradation performances than that of g-C₃N₄, which agrees well with the BET analysis. Figure 6A presents the degradation efficiency (DE) of orange II using different samples as the photocatalysts. And the reaction rate constants in different catalyst systems were calculated by the pseudo-first-order model (Fig. 6B) and listed in Table 2. Ti₃C₂ and CdS show low degradation effect on orange II. Compared with Ti₃C₂/g-C₃N₄NS, the CdS-loaded ternary composites show enhanced photocatalytic degradation activity. Among the ternary composites, the CTN-4:1 exhibits the highest photocatalytic activity. The UV-vis spectral variation of orange II solution with different treatment times in the CTN-4:1 system is exhibited in Fig. 6C. It is clear that the typical adsorption peak of orange II at 486 nm decreased rapidly with the time increasing. Simultaneously, the color of the filtered solution changes from deep to colorless, indicating the degradation of orange II. The TOC removal efficiency of orange II in the CTN-4:1 system is about 76 % at 60 min, indicating that orange II can be effectively mineralized (Fig.S6A). After subsequent reactions under identical conditions, the CTN-4:1 still maintains high catalytic performance after four cycles (Fig.S6B). In Fig.S6C, no evident difference is found for the structure of CTN-4:1 before and after the photocatalytic reaction, which indicates excellent reusability and stability.

Analysis Of Photocatalytic Mechanism

Figure 7A and Fig. S7A present the UV-vis absorption spectra of the samples. Ti_3C_2 shows no obvious absorption edge. Compared with the CdS and $\text{Ti}_3\text{C}_2/\text{g-C}_3\text{N}_4\text{NS}$, all CdS-loaded ternary composites can cause an appropriate shift to long wavelengths. The $(\alpha h\nu)^{1/2}$ versus $h\nu$ plots of the samples are presented in Fig. 7B and Fig. S7B. The band-gap energy (E_g) values of $\text{g-C}_3\text{N}_4$ and $\text{g-C}_3\text{N}_4\text{NS}$ are calculated to be 2.87, 2.77eV, respectively. The E_g of obtained $\text{g-C}_3\text{N}_4\text{NS}$ is lower than that of $\text{g-C}_3\text{N}_4$. And the E_g values of other corresponding samples are summarized in Table 2. Compared with the CdS and $\text{Ti}_3\text{C}_2/\text{g-C}_3\text{N}_4\text{NS}$, the E_g values of the CdS/ $\text{Ti}_3\text{C}_2/\text{g-C}_3\text{N}_4\text{NS}$ composites decrease. Among the ternary composites, the CTN-4:1 has the lowest band-gap energy, which is beneficial improve the absorption of visible light.

Table 2
Reaction rate constant and band-gap energy of the samples

Samples	Reaction rate constant (min^{-1})	Band-gap energy (eV)
Ti_3C_2	3.8×10^{-3}	0.50
CdS	3.9×10^{-3}	2.27
$\text{Ti}_3\text{C}_2/\text{g-C}_3\text{N}_4\text{NS}$	1.3×10^{-2}	2.50
CTN-2:1	1.6×10^{-2}	1.85
CTN3:1	2.3×10^{-2}	1.82
CTN-4:1	4.2×10^{-2}	1.76
CTN-5:1	1.7×10^{-2}	1.89

The PL spectra and transient photocurrent responses of the samples were shown in Fig. 8 (A and B) and Fig.S8 (A and B). The CdS/ $\text{Ti}_3\text{C}_2/\text{g-C}_3\text{N}_4\text{NS}$ composites show lower PL intensity and higher photocurrent density compared with $\text{Ti}_3\text{C}_2/\text{g-C}_3\text{N}_4\text{NS}$ and CdS. Among all samples, CTN-4:1 exhibits the lowest PL intensity and maximum photocurrent intensity, indicating its higher separation efficiency of the photoinduced $\text{e}^- \text{h}^+$ pairs (Liu et al. 2020). As seen in Fig. 8C, by contrast, CTN-4:1 exhibits the smaller impedance radius, indicating the higher charge transfer and separation ability (He et al. 2019). The formation of heterojunction in ternary composites can promote the transfer and separation of photoinduced carries, which leads to the enhancement of photocatalytic activity

Figure 9A shows the trapping experiments for the CTN-4:1degradation system using BZQ, EDTA, and TBA as the scavengers of $\cdot\text{O}_2^-$, h^+ , and $\cdot\text{OH}$ species, respectively. The DEs of orange II decrease after the addition of the scavengers, indicating that the $\cdot\text{O}_2^-$, h^+ , and $\cdot\text{OH}$ species are formed, and $\cdot\text{O}_2^-$ and h^+ species are the main active species in the degradation system. Meanwhile, the EPR spectra of DMPO-

$\cdot\text{O}_2^-$ in the CdS, $\text{Ti}_3\text{C}_2/\text{g-C}_3\text{N}_4\text{NS}$ and CTN-4:1 degradation systems were determined under vis irradiation. As shown in Fig. 9B, the six characteristic peaks corresponding to $\text{DMPO}-\cdot\text{O}_2^-$ are detected in the CTN-4:1 degradation system. The generation efficiency of $\cdot\text{O}_2^-$ in the CTN-4:1 system is slightly higher than those of CdS and $\text{Ti}_3\text{C}_2/\text{g-C}_3\text{N}_4\text{NS}$. On the other hand, the characteristic signal peaks of $\text{DMPO}-\cdot\text{OH}$ signals can also be observed for the CTN-4:1 system (Fig.S9). Under vis irradiation, CTN-4:1 degradation system can promote the production of active species and effectively degrade orange II.

As shown in Fig. S10A, compared with CdS/ $\text{g-C}_3\text{N}_4\text{NS}$ sample, CTN-4:1 catalysis has higher photocatalytic activity for degradation of orange II under the same conditions. The trapping experiments for the CdS/ $\text{g-C}_3\text{N}_4\text{NS}$ system show that both $\cdot\text{O}_2^-$ and h^+ are the major active species during the degradation process (Fig.S10B). As presented in Fig. S10C, the generation efficiency of $\cdot\text{O}_2^-$ in the CdS/ $\text{g-C}_3\text{N}_4\text{NS}$ system is lower than that of CTN-4:1. From Fig.S9 we can see that the $\cdot\text{OH}$ radicals are basically not produced for the CdS/ $\text{g-C}_3\text{N}_4\text{NS}$ degradation system. The formation of CdS/ $\text{Ti}_3\text{C}_2/\text{g-C}_3\text{N}_4\text{NS}$ Z-scheme heterojunction composites using Ti_3C_2 a charge transport bridge, can improve the redox capacity of photocatalysis and promote the production of the active species.

Figure S11 shows the Mott-Schottky plots of the $\text{g-C}_3\text{N}_4\text{NS}$, Ti_3C_2 , and CdS. The slopes of the lines are all positive, implying that the samples belong to n-type semiconductor. The flat potential (E_{fb}) of $\text{g-C}_3\text{N}_4\text{NS}$, Ti_3C_2 , and CdS are estimated to be -1.11, -0.22, and - 0.47 V vs.Ag/AgCl (0.22 V vs. NHE), respectively. Normally, conduction band (E_{CB}) of an n-type semiconductor was about 0.1eV more negative than its E_{fb} (Sun et al. 2014; Ma et al. 2018). Thus, the E_{CB} values of $\text{g-C}_3\text{N}_4\text{NS}$, Ti_3C_2 , and CdS are estimated to be about - 0.99, -0.10, -0.35 V vs.NHE, respectively. According to the band-gap energies of samples, the valence band (E_{VB}) values of $\text{g-C}_3\text{N}_4\text{NS}$, Ti_3C_2 , and CdS are calculated to be 1.78, 0.40, 1.92 V vs.NHE, respectively.

According to the above analysis, the plausible photocatalytic degradation mechanism of the CdS/ $\text{Ti}_3\text{C}_2/\text{g-C}_3\text{N}_4\text{NS}$ catalyst is depicted in Scheme 1. Under vis irradiation, e^- - h^+ pairs can be generated on the CdS/ $\text{Ti}_3\text{C}_2/\text{g-C}_3\text{N}_4\text{NS}$ Z-scheme composite. The E_{CB} of CdS (- 0.35 V vs. NHE) is more negative than that of Ti_3C_2 (- 0.10 V vs. NHE), and the photoinduced electrons in CdS can be transferred to Ti_3C_2 . The E_{VB} of $\text{g-C}_3\text{N}_4\text{NS}$ (1.78V vs. NHE) is higher than that of Ti_3C_2 (0.40 V vs. NHE). The photogenerated holes in $\text{g-C}_3\text{N}_4\text{NS}$ can migrate to the Ti_3C_2 . As a result, the photogenerated carriers can be effectively separated by the Z-scheme heterostructure. Meanwhile, the E_{CB} of $\text{g-C}_3\text{N}_4\text{NS}$ (-0.99 V vs. NHE) is more negative than the potential of superoxide radicals (- 0.046 V) (Kandi et al. 2017), and the dissolved O_2 can combine with the electrons in the E_{CB} of $\text{g-C}_3\text{N}_4\text{NS}$ to produce $\cdot\text{O}_2^-$ in the photodegradation process. In acidic degradation system, some of $\cdot\text{O}_2^-$ radicals may also combine with H^+ to produce $\cdot\text{OH}$ (Cai et al. 2018). At the same time, the holes are accumulated in the E_{VB} of CdS. The CdS/ $\text{Ti}_3\text{C}_2/\text{g-C}_3\text{N}_4\text{NS}$ degradation system can produce additional active species, resulting in high catalytic degradation efficiency of orange II under vis irradiation.

Conclusions

In this work, a novel CdS/Ti₃C₂/g-C₃N₄NS Z-scheme composites with enhanced vis photocatalytic activity were prepared. In contrast to g-C₃N₄, obtained g-C₃N₄NS sample showed improved adsorption and photocatalytic degradation performances. It is found that the CdS/Ti₃C₂/ g-C₃N₄NS Z-scheme heterojunction composites formed by using Ti₃C₂ as a charge transport bridge could improve the vis absorption, enhance the separation ability of the photoexcited carriers, and improve the redox capacity of the composite and promote the production of active species ($\cdot\text{O}_2^-$, h^+ , and $\cdot\text{OH}$), thus enhancing the photocatalytic degradation efficiency of orange II. Among them, the CTN-4:1 sample exhibited the highest vis photocatalytic activity. This study would provide useful insights into utilizing Ti₃C₂ as the electron mediator in Z-scheme photocatalysis.

Declarations

Authors' contributions Ranran Zhang: Data curation, Writing-Original draft preparation. Jiaying Jin: Investigation, Writing-Reviewing and Editing. Lumeng Jia: Writing-Reviewing and Editing. Bo Shi: Software, Validation, Project administration, Resources, Supervision. Rufen Chen: ConceptualizationIdeas, Methodology, Formulation of overarching research goals and aims. Investigation, Project administration, Resources, Supervision, Writing-review & editing.

Funding This work was supported by the National Natural Science Foundation of China (21477032).

Availability of data and materials All data generated or analyzed during this study are included in this published article.

Ethics approval and consent to participate Not applicable.

Consent for publication Not applicable.

Competing interests The authors declare no competing interests

References

1. Ai Z, Shao Y, Chang B, Huang B, Wu Y, Hao X (2019) Effective orientation control of photogenerated carrier separation via rational design of a Ti₃C₂(TiO₂)@CdS/MoS₂ photocatalytic system. Appl Catal B-Environ 242:202-208.
2. Cao S. W, Yuan Y. P, Fang J, Shahjamali M. M, Boey F. Y.C, Barber J, Loo S. C. J, Xue C (2013) In-situ growth of CdS quantum dots on g-C₃N₄ nanosheets for highly efficient photocatalytic hydrogen generation under visible light irradiation. Int J Hydrogen Energy 38 (3): 1258-1266.
3. Cai T, Wang L, Liu Y, Zhang S, Dong W, Chen H, X. Yi H, Yuan J, Xia X, Liu C, Luo S (2018) Ag₃PO₄/Ti₃C₂ MXene interface materials as a Schottky catalyst with enhanced photocatalytic

- activities and anti-photocorrosion performance. *Appl Catal B-Environ* 239: 545-554.
4. Dong G, Jacobs D. L, Zang L, Wang C (2017) Carbon vacancy regulated photoreduction of NO to N₂ over ultrathin g-C₃N₄ nanosheets. *Appl Catal B-Environ* 218:515-524.
 5. Ding X, Li Y, Li C, Wang W, Wang L, Feng L, Han D (2019) 2D visible-light-driven TiO₂@Ti₃C₂/g-C₃N₄ ternary heterostructure for high photocatalytic activity. *J. Mater. Sci.* 54:9385-9396.
 6. Ding X, Li Y, Li C, Wang W, Wang L, Feng L, D. Han (2019) 2D visible-light-driven TiO₂ @Ti₃C₂ /g-C₃N₄ ternary heterostructure for high photocatalytic activity. *J Mater Sci* 54:9385-9396.
 7. Diao Y, Yan M, Li X, Zhou C, Peng B, Chen H, Zhang H (2020) In-situ grown of g-C₃N₄ /Ti₃C₂/TiO₂ nanotube arrays on Ti meshes for efficient degradation of organic pollutants under visible light irradiation. *Colloid Surface A* 594:124511-124521.
 8. Elfiad A, Galli F, Djadoun A, Sennour M, Chegrouche S, Meddour-Boukhobza L, Boffito D.C (2018) Natural α -Fe₂O₃ as an efficient catalyst for the p-nitrophenol reduction. *Mater Sci Eng. B* 229:126-134.
 9. Feng Y, Ding L, Jia D, Wang L, Guo W (2018) Highly rectified ion transport through 2D WSe₂/MoS₂ bilayered membranes. *Chin Chem. Lett* 29:892-894.
 10. Gao Y.P, Wang L.B, Zhou A.G, Li Z.Y, Chen J.K, Bala H, Hu Q.K, Cao X.X (2015) Hydrothermal synthesis of TiO₂/Ti₃C₂ nanocomposites with enhanced photocatalytic activity. *Mater Lett* 150:62-64.
 11. Hu T, Hu M, Li Z, Zhang H, Zhang C, Wang J, Wang X (2015) Covalency-dependent vibrational dynamics in two-dimensional titanium carbides. *J Phys Chem A* 119:12977-12984.
 12. He B, Liu H, Lin Z, Yan L, Ning J, Zhong Y, Zheng C, Zhang Z, Hu Y (2019) A new photocatalyst based on Co(CO₃)_{0.5}(OH)·0.11H₂O/Bi₂WO₆ nanocomposites for high-efficiency cocatalyst-free O₂ evolution. *Chem Eng J* 359:924-932.
 13. He F, Zhu B, Cheng B, Yu J, Ho W, Macyk W (2020) 2D/2D/0D TiO₂/C₃N₄/Ti₃C₂ MXene composite S-scheme photocatalyst with enhanced CO₂ reduction activity. *Appl Catal B-Environ* 272:119006-119018.
 14. Ibrahim Y.O, Gondal M.A (2021) Visible-light-driven photocatalytic performance of a Z-scheme based TiO₂/WO₃/g-C₃N₄ ternary heterojunctions. *Mol Catal* 505: 111494-111507.
 15. Kang P, Zhang L, Cheng B, Yu J (2017) Enhanced charge transfer kinetics of Fe₂O₃/CdS composite nanorod arrays using cobalt-phosphate as cocatalyst. *Appl Catal B-Environ* 218: 570-580.
 16. Kang P, Zhang L, Cheng B, Yu J (2017) Enhanced charge transfer kinetics of Fe₂O₃/CdS composite nanorod arrays using cobalt-phosphate as cocatalyst. *Appl Catal B-Environ* 218: 570-580.
 17. Kandi D, Martha S, Thirumurugan A, Parida K.M (2017) CdS QDs-decorated selfdoped g-Bi₂MoO₆: asustainable and versatile photocatalyst toward photoreduction of Cr(VI) and degradation of phenol. *ACS Omega* 2:9040-9056.

18. Koyyada G, Kumar N S, Al-Ghurabi E H, Asif M, Mallikarjuna K (2021) Enhanced solar-driven photocatalytic performance of a ternary composite of SnO₂ quantum dots//AgVO₃ nanoribbons//g-C₃N₄ nanosheets (0D/1D/2D) structures for hydrogen production and dye degradation. *Environ Sci Pollut Res* 28:31585–31595.
19. Low J, Zhang L, Tong T, Shen B, Yu J (2018) TiO₂/MXene Ti₃C₂ composite with excellent photocatalytic CO₂ reduction activity. *J Catal* 36:1255-266.
20. Li Y, Yin Z, Ji G, Liang Z, Xue Y, Guo Y, Tian J., Wang X, Cui H (2019) 2D/2D/2D heterojunction of Ti₃C₂ MXene/MoS₂ nanosheets/TiO₂ nanosheets with exposed (001) facets toward enhanced photocatalytic hydrogen production activity. *Appl Catal B-Environ* 246:12-20.
21. Liu H, Tong M, Zhu K, Liu H, Chen R (2020) Preparation and photo-Fenton degradation activity of α -Fe₂O₃ nanorings obtained by adding H₂PO₄⁻, SO₄²⁻, and citric acid. *Chem Eng J* 382:123010-123018.
22. Ma Y, Wang Q, Xing S (2018) Insight into the catalytic mechanism of γ -Fe₂O₃/ ZnFe₂O₄ for hydrogen peroxide activation under visible light. *J Colloid Interf Sci* 529: 247-254.
23. Naguib M, Mashtalir O, Lukatskaya M. R, Dyatkin B, Zhang C, Presser V, Gogotsi Y, Barsoum M. W (2014) One-step synthesis of nanocrystalline transition metal oxides on thin sheets of disordered graphitic carbon by oxidation of MXene. *Chem Commun* 50(56): 7420-7423.
24. Peng C, Wang H.J, Yu H, Peng F (2017) (111) TiO₂-x/Ti₃C₂: Synergy of active facets, interfacial charge transfer and Ti³⁺ doping for enhance photocatalytic activity. *Mater Res Bull* 89:16-25.
25. Peng K, Wang H. J, Li X. Y, Wang Ji. W, Xu L, Gao H. F, Niu M, Ma M. B, Yang J (2019) One-step hydrothermal growth of MoS₂ nanosheets/CdS nanoparticles heterostructures on montmorillonite for enhanced visible light photocatalytic activity. *Appl Clay Sci* 175:86-93.
26. Rengaraj S, Venkataraj S, Jee S. H, Kim Y, Tai C, Repo E, Koistinen A, Ferancova A, Sillanpää M (2011) Cauliflower-like CdS microspheres composed of nanocrystals and their physicochemical properties. *Langmuir* 27(1): 352-358.
27. Ran J, Gao G, Li F, Ma T, Du A, Qiao S (2017) Ti₃C₂ MXene co-catalyst on metal sulfide photo-absorbers for enhanced visible-light photocatalytic hydrogen production. *Nat Commun* 8:13907-13916.
28. Sun S. M, Wang W. Z, Li D. Z, Zhang L, Jiang D (2014) Solar light driven pure water splitting on quantum sized BiVO₄ without any cocatalyst. *ACS Catal* 4:3498-3503.
29. Sun M, Yao Y, Ding W, Anandan S (2020) N/Ti³⁺ co-doping biphasic TiO₂/Bi₂WO₆ heterojunctions: hydrothermal fabrication and sonophotocatalytic degradation of organic pollutants. *J Alloy Compd* 820:153172-153180.
30. Sutar R. S, Barkul R. P, Delekar S. D (2020) M. K. Patil, Sunlight assisted photocatalytic degradation of organic pollutants using g-C₃N₄-TiO₂ nanocomposites. *Arab J Chem* 13: 4966- 4977.

31. Wang J, Wang Z, Qu P, Xu Q, Zheng J, Jia S, Chen J, Zhu Z (2018) A 2D/1D TiO₂ nanosheet/CdS nanorods heterostructure with enhanced photocatalytic water splitting performance for H₂ evolution. *Int J Hydrogen energy* 43:7388-7396.
32. Wu X, Wang X, Wang F, Yu H (2019) Soluble g-C₃N₄ nanosheets: Facile synthesis and application in photocatalytic hydrogen evolution. *Appl Catal B-Environ* 247:70-77.
33. Wang J, Wang G, Wang X, Wu Y, Su Y, Tang H (2019) 3D/2D direct Z-scheme heterojunctions of hierarchical TiO₂ microflowers/g-C₃N₄ nanosheets with enhanced charge carrier separation for photocatalytic H₂ evolution. *Carbon* 149:618-626.
34. Wang M, Cui Z, Yang M, Lin L, Chen X, Wang M, Han J (2019) Core/shell structured CdS/polydopamine/TiO₂ ternary hybrids as highly active visible-light photocatalysis. *J Colloid Interf Sci* 544:1-7.
35. Xu Y, Wang S, Yang J, Han B, Nie R, Wang J, Dong Y, Yu X, Wang J, Jing H (2018) Highly efficient photoelectrocatalytic reduction of CO₂ on the Ti₃C₂/g-C₃N₄ heterojunction with rich Ti³⁺ and pyri-N species. *J Mater Chem A* 6 (31): 15213-15220.
36. Xu J, Huang Z, Ji H, Tang H, Tang G, Jiang H (2019) g-C₃N₄ anchored with MoS₂ ultrathin nanosheets as high performance anode material for supercapacitor. *Mater Lett* 241:35-38.
37. Xu C, Anusuyadevi P.R, Aymonier C, Luque R, Marre S (2019) Nanostructured materials for photocatalysis. *Chem Soc Rev* 48:3868-3902.
38. Xiao R, Zhao C, Zou Z, Chen Z, Tian L, Xu H, Tang H, Liu Q, Lin Z, Yang X (2020) In situ fabrication of 1D CdS nanorod/2D Ti₃C₂ MXene nanosheet Schottky heterojunction toward enhanced photocatalytic hydrogen evolution. *Appl Catal B-Environ* 268:118382-118393.
39. Yang C, Liu Y, Sun X, Zhang Y, Hou L, Zhang Q, Chang Y (2018) In-situ construction of hierarchical accordion-like TiO₂/Ti₃C₂ nanohybrid as anode material for lithium and sodium ion batteries. *Electrochim Acta* 271:165-172.
40. Zhang N, Yang M.Q, Liu S.Q, Sun Y.G, Xu Y.J (2015) Waltzing with the versatile platform of graphene to synthesize composite photocatalysts. *Chem Rev* 115:10307-10377.
41. Zhou J.J, Wang R, Liu X.L, Peng F.M, Li C.H, Teng F, Yuan Y.P (2015) In situ growth of CdS nanoparticles on UiO-66 metal-organic framework octahedrons for enhanced photocatalytic hydrogen production under visible light irradiation. *Appl Surf Sci* 346: 278-283.
42. Zhang J, Wageh S, Al-Ghamdi A. A, Yu J (2016) New understanding on the different photocatalytic activity of wurtzite and zinc-blende CdS. *Appl Catal B-Environ* 192: 101-107.
43. Zhou W.J, Zhu J.F, Wang F, Cao M.J, Zhao T (2017) One-step synthesis of Ceria/Ti₃C₂ nanocomposites with enhanced photocatalytic activity. *Mater Lett* 206:237-240.
44. Zhang H.L, Li M, Cao J.L, Tang Q.J, Kang P, Zhu C.X, Ma M.J (2018) 2D α-Fe₂O₃ doped Ti₃C₂ MXene composite with enhanced visible light photocatalytic activity for degradation of Rhodamine B. *Ceram Int* 44:19958-19962.

45. Zhao W, Feng Y, Huang H.B, Zhou P.C, Li J, Zhang L.L, Dai B.L, Xu J.M, Zhu F.X, Sheng N, Leung D.Y.C (2019) A novel Z-scheme $\text{Ag}_3\text{VO}_4/\text{BiVO}_4$ heterojunction photocatalyst: Study on the excellent photocatalytic performance and photocatalytic mechanism. *Appl Catal B-Environ* 245:448-458.
46. Zou L, Wang H. R, Jiang X. Y, Yuan G. L, Wang X (2020) Enhanced photocatalytic efficiency in degrading organic dyes by coupling CdS nanowires with ZnFe_2O_4 nanoparticles. *Sol Energy* 195:271-277.
47. Zhang Q, Liu J.-B, Chen L, Xiao C.X, Chen P, Shen S, Guo J. K, Au C.T (2020) Yin S. F, An etching and re-growth method for the synthesis of bismuth ferrite/MIL-53 (Fe) nanocomposite as efficient photocatalyst for selective oxidation of aromatic alcohols. *Appl Catal B-Environ* 264:118529-118536.

Figures

Figure 1

XRD patterns of samples (a: Ti_3C_2 , b: $\text{Ti}_3\text{C}_2/\text{g-C}_3\text{N}_4\text{NS}$, c: CTN-2:1, d: CTN-3:1, e: CTN-4:1, and f: CTN-5:1)

Figure 2

Raman spectra of samples (a: Ti_3C_2 , b: CdS , c: $\text{g-C}_3\text{N}_4\text{NS}$, and d: CTN-4:1)

Figure 3

SEM images of samples (a: Ti₃C₂, b: Ti₃C₂/g-C₃N₄NS, c: CTC-2:1, d: CTC-3:1, e: CTC-4:1, and f: CTC-5:1)

Figure 4

HRTEM image of CTN-4:1

Figure 5

XPS spectra of the CTN-4:1 composite (A: Ti2p, B: C1s); S2p (C) and Cd3d (D) spectra of CTN-4:1 and CdS

Figure 6

(A) Degradation curves of orange II in the different catalyst systems and (B) the corresponding first-order plots. (C) The UV-vis spectra change of orange II solution in the CTN-4:1 system

Figure 7

(A) UV-vis absorption spectra, (B) band-gap energy of the samples (a: Ti₃C₂, b: CdS, c: Ti₃C₂ / g-C₃N₄NS, d: CTN-2:1, e: CTN-3:1, f: CTN-4:1, and g: CTN-5:1)

Figure 8

(A) PL spectra, (B) transient photocurrent responses and (C) EIS spectra of the samples

Figure 9

(A) Reactive species trapping experiments for the CTN-4:1 degradation system. (B) ESR spectra of DMPO-•O₂- in different systems.

Supplementary Files

This is a list of supplementary files associated with this preprint. Click to download.

- [Scheme1.png](#)
- [supportinginformation.docx](#)