Degradation of Oxytetracycline By Magnetic MOFs Heterojunction Photocatalyst With Persulfate : High Stability And Wide Range

Zhuo Zhang

Changsha University of Science and Technology

Chunyan Du (✉ cydu@csust.edu.cn)

Changsha University of Science and Technology <https://orcid.org/0000-0003-1275-5964>

Yin Zhang

Changsha University of Science and Technology

Guanlong Yu

Changsha University of Science and Technology

Ying Xiong

Changsha University of Science and Technology

Lu Zhou

Changsha University of Science and Technology

Yuanyuan Liu

Changsha University of Science and Technology

Tianying Chi

Changsha University of Science and Technology

Guoliang Wang

Changsha University of Science and Technology

Yihai Su

Changsha University of Science and Technology

Yinchu Lv

Changsha University of Science and Technology

Hao Zhu

Changsha University of Science and Technology

Research Article

Keywords: Antibiotics, Magnetism, Metal-organic frameworks (MOFs), Persulfate, Photocatalysis.

Posted Date: September 13th, 2021

DOI: <https://doi.org/10.21203/rs.3.rs-800618/v1>

License: © ⓘ This work is licensed under a Creative Commons Attribution 4.0 International License.

[Read Full License](#)

Version of Record: A version of this preprint was published at Environmental Science and Pollution Research on January 8th, 2022. See the published version at <https://doi.org/10.1007/s11356-021-17971-9>.

Abstract

Photocatalysis/Persulfate is an effective method of degrading organic pollutants. In this study, $\text{Fe}_3\text{O}_4/\text{MIL-101}(\text{Fe})$, a magnetic heterojunction photocatalyst, was produced by hydrothermal method. The material exhibited excellent removal efficiency for OTC in the coupling of persulfate (87.1%, 1 h). And it has a wide range of applications, with good removal efficiency for OTC concentrations of 30 to 70 mg/L and pH values of 3 to 9. $\cdot\text{SO}_4^-$ and $\cdot\text{OH}$ played a major role in the OTC removal reaction and there was an $\text{Fe}(\text{III})/\text{Fe}(\text{II})$ cycle during the reaction. With excellent stability and recoverability, the OTC removal efficiency decreased by only 4.29% after four cycles, and the Fe leaching did not exceed 0.035 mg/L per cycle. This has a significant implication for the removal of organic pollutants from water bodies.

1. Introduction

Oxytetracycline (OTC) is a broad-spectrum antimicrobial agent of the tetracycline family, widely used in animal and human medicine. It is mostly released in its original form after metabolism in the body, with good water solubility and easy storage and accumulation in the environment (Lin et. al, 2015; Wang et. al, 2017). These residual OTC in the environment can enter the food chain through drinking water, livestock and poultry products, leading to the development of corresponding antibiotic resistance in humans (Wang et. al, 2021; Yang et. al, 2020). Unfortunately, conventional biological treatment, physical adsorption and chemical degradation have various limitations on the removal of OTC, such as secondary contamination, complex processes and high costs (Du et. al, 2021b; Guo et. al, 2021).

Sulphate radical ($\cdot\text{SO}_4^-$) advanced oxidation technology (SR-AOP) is gradually being noticed due to the high redox potential, long half-life and mild generation environment of $\cdot\text{SO}_4^-$ (Chen et. al, 2021).

Persulfates (PS) can be activated by light (Yang et. al, 2021a), heat (Li et. al, 2020), ultrasound (Monteagudo et. al, 2018), transition metal ions (Wang and Wang, 2018), and metal oxides (Do et. al, 2013) to produce $\cdot\text{SO}_4^-$ ($E_0 = 2.5\text{-}3.1\text{V}$) with a redox potential higher than $\cdot\text{OH}$ ($E_0 = 1.9\text{-}2.7\text{V}$).

Metal-organic frameworks (MOFs) are crystalline porous materials that is self-assembled by inorganic metal centres (metal ions or metal clusters) and connected with organic ligands to form a periodic network structure. With large specific surface area, good pore structure, easily adjustable structure and good light response effect, they are one of the excellent catalysts for the combined photo-persulfate degradation of organic pollutants in water (Huang et. al, 2020). Iron-based MOFs are ideal Fenton catalysts for the degradation of organic pollutants in water. They have high surface area and high density of dispersed Fe sites, providing an abundance of adsorption and catalytic metal sites for persulfate activation (Espinosa et. al, 2018).

Material recycling has been one of the main reasons limiting the introduction of photocatalysis into practical applications, and the preparation of magnetic materials is an effective way to address this issue (Du et. al, 2021c). In this study, Fe_3O_4 nanospheres were embedded on MIL-101(Fe) nano-octahedral crystals by hydrothermal method to produce magnetic materials along with the construction of

heterojunctions, and the materials were applied to visible light/PS system to remove OTC in water. The effects of material dosing, pollutant concentration, peroxyxynitrite dosing and pH on the removal of OTC were also investigated. The stability, recyclability and recoverability of the materials were also investigated, and we further explored the mechanism of the $\text{Fe}_3\text{O}_4@\text{MIL-101}/\text{PS}/\text{vis}$ system for the degradation of OTC.

2. Materials And Methods

2.1. Pharmaceuticals

Ferric chloride hexahydrate ($\text{FeCl}_3 \cdot 6\text{H}_2\text{O}$), terephthalic acid (H_2BDC), N,N-dimethylformamide (DMF), ethylene glycol (EG), benzoquinone (BQ), isopropyl alcohol (IPA), methanol (MeOH), sodium chloride (NaCl), potassium persulfates ($\text{K}_2\text{S}_2\text{O}_8$), oxytetracycline (OTC), ammonium acetate (NH_4Ac), and anhydrous ethanol were purchased from Sinopharm Group Co. Ltd (Shanghai, China). All chemicals involved were analytical grade and did not require refining.

2.2. Preparation of catalysts

2.2.1. Preparation of MIL-101

MIL-101 powder was synthesized according to the methods reported previously (Zhao et. al, 2020). In this method, 1.622 g (6 mmol) $\text{FeCl}_3 \cdot 6\text{H}_2\text{O}$ and 0.997 g (6 mmol) H_2BDC were added to 40 mL of DMF solution and stirred for 15 min to obtain a yellow clarified solution, then transferred to a 100 mL Teflon-lined autoclave and heated at 110°C for 20 h. After heating and cooling to room temperature, the yellow-brown liquid was centrifuged to obtain a yellow solid, which was purified using DMF and then washed for 3 h with 100 mL of ethanol at 60°C . Then washed several times alternately with distilled water and anhydrous ethanol. Finally, it was dried at 60°C and ground to obtain a yellow powder.

2.2.2. Preparation of Fe_3O_4

Fe_3O_4 nanosphere was obtained by the traditional hydrothermal method (Shao et. al, 2012). 3.46 g $\text{FeCl}_3 \cdot 6\text{H}_2\text{O}$ was dissolved in 70 mL EG and then 2.66 g NH_4Ac was added under continuous stirring. The solution was subsequently transferred to a Teflon-lined autoclave and heated at 200°C for 8 h. After cooling to room temperature, the powder was filtered, washed, dried and ground to obtain a black powder.

2.2.3. Preparation of MIL-101/ Fe_3O_4

The MIL-101/ Fe_3O_4 heterojunction was prepared by dispersing Fe_3O_4 into DMF solution dissolved in FeCl_3 and H_2BDC , and the subsequent preparation process was identical to that of MIL-101 (Fig. 1). The obtained material was named MF-x depending on the amount of Fe_3O_4 added (x is the mass ratio of FeCl_3 to Fe_3O_4).

2.3. Characterization of catalyst

X-ray photoelectron spectroscopy (XPS) spectrum was obtained from Thermo Scientific K-Alpha Microprobe. X-ray diffraction (XRD) spectrum was captured using a Bruke D8 Advance. Scanning electron microscopy (SEM) images were gained from a Zeiss Sigma300 microscope. UV-vis diffuse diffraction (UV-vis DRS) spectrum was measured on Lambda 750. Electron spin resonance (ESR) spectrum was acquired using a LakeShore 7404. Hysteresis line analysis results came from LakeShore 7404 vibrating sample magnetometer (VSM). EIS (electrochemical impedance spectroscopy) and Mott Schottky testing were performed using an electrochemical workstation (CHI 660E, Chenhua).

2.4. Photocatalytic activity tests

A certain amount of catalyst was added to 100mL of oxytetracycline solution and the reaction was first carried out under dark conditions for 30min to reach the equilibrium of adsorption and desorption. Afterwards, a quantity of $K_2S_2O_8$ was added, and the reaction system was transferred to light conditions using a 300 W xenon lamp with a 420 nm filter. The reaction system was maintained at 25°C throughout the reaction in the presence of circulating water, and stirring was maintained to disperse the material uniformly in the solution. 3mL of the suspension was taken at 10min intervals during the reaction and filtered using a 0.45 μ m filter head to obtain a clarified solution. The concentration of oxytetracycline was later tested using an UV spectrophotometer. The residual ratio of the TC solution was calculated by C/C_0 , where C represented the solution concentration at different times, while C_0 represented the initial solution concentration.

3. Results And Discussion

3.1. Morphological and structural analysis

The SEM images of Fe_3O_4 , MIL-101(Fe) and MF-50 are shown in Fig. 2. It can be clearly seen that Fe_3O_4 is a structure consisting of clusters of nanospheres and MIL-101(Fe) is an octahedral structure, which is similar to that reported previously (Zhang et. al, 2021; Zhao et. al, 2020). For the MF-50 composite, it can be seen that it is still roughly an octahedral-like structure with a few nanospheres on its surface, demonstrating that the Fe_3O_4 and MIL-101(Fe) components are combined and in good contact. EDS supports the study of the chemical composition of MF-50. According to Fig. 2d, C, O and Fe are dispersed uniformly on the surface of MF-50, which proves its successful preparation.

The application of XRD is necessary in order to study the crystal structure and phase composition of the materials. The Fig. 3a shows the XRD spectra of Fe_3O_4 , MIL-101(Fe) and MF-50. The XRD plots of Fe_3O_4 show diffraction peaks at 18.269°, 30.095°, 35.422°, 37.052° and 43.052°, which correspond to the JCPDS 19–0629 standard card for Fe_3O_4 , demonstrating that the preparation of Fe_3O_4 is satisfactory. The XRD plots of MF-50 show peaks of Fe_3O_4 as well as MIL-101, proving that the material has been successfully compounded.

The use of XPS assists in the analysis of the chemical properties of the materials. The survey of XPS spectrum (Fig. 3b) shows that the MF-50 material contains the elements C, O, Fe and Cl. The Fig. 3c shows the Fe 2p spectra, where the area ratio of the Fe 2p 1/2 peak of Fe₃O₄ to the Fe 2p 3/2 peak is 2:1, which is consistent with the Fe(III):Fe(II) = 2:1 feature of Fe₃O₄; as for MIL-101, the difference between the Fe 2p 3/2 (711.2 eV) peak and the Fe 2p 1/2 (724.9 eV) peak is 13.7 eV, which is similar to that previously reported (Zhao et. al, 2020) the spectrum of MF-50 is very similar to that of MIL-101, but its satellite peaks are shifted, demonstrating an interaction between Fe₃O₄ and MIL-101. As shown in the Fig. 2d, the O 1s spectra of both MIL-101 and MF-50 can be divided into three peaks corresponding to C-O, C = O, and Fe-O bonds (Guo et. al, 2020). The Fe-O peak of MIL-101 is lower than that of the C = O bond, while the contrary is observed for MF, indicating that Fe₃O₄ is successfully compounded with MIL-101.

3.2. Analysis of photoelectric properties and energy band structure

The employment of the UV-vis DRS allows exploring the light absorption characteristics of the material and deriving the bandgap energy of the material. As shown in the Fig. 4a, MIL-101 exhibits excellent light absorption in the UV-vis region and when compounded with Fe₃O₄, the absorption in the visible region is improved. This can be attributed to the coupling between Fe₃O₄ and MIL-101 enhancing the efficiency of visible light utilisation. The Kubelka-Munk function for counting the band gap energy of photocatalysts based on UV-vis DRS spectra is as follows: $\alpha h\nu = A(h\nu - E_g)^{n/2}$ (Yang et. al, 2021b). Plotting the light energy $(\alpha h\nu)^2$ versus energy $(h\nu)$, the band gap energy of MIL-101 and Fe₃O₄ are calculated to be 2.54 eV and 1.57 eV (Fig. 4b). The analysis of the XPS valence band spectrum can calculate the valence band potential of the materials. According to Fig. 4c, the valence band potentials of Fe₃O₄ and MIL-101 are 0.99 eV and 2.5 eV, respectively. The test of Mott Schottky can estimate the flat-band potentials. Based on Fig. 4d, the flat-band potentials of Fe₃O₄ and MIL-101 are - 0.45 eV and 0.06 eV, respectively, and both are n-type semiconductors. Typically, the flat-band potentials of n-type semiconductors are slightly higher (0.1–0.2 eV) than the conduction band potential (Yu et. al, 2016). Therefore, the conduction band potentials of Fe₃O₄ and MIL-101 are - 0.58 eV and - 0.04 eV, respectively. The energy band structure of both Fe₃O₄ and MIL-101 are consistent with previous reports (Li et. al, 2019; Wu et. al, 2020).

The determination of EIS allows the charge transfer capability of samples to be studied. The EIS surveys of samples were conducted in NaSO₄ solution (0.20 M) with a frequency range of 10⁻⁵ to 0.01 Hz. Typically, lower EIS curves mean lower resistance and higher charge transfer efficiency (Du et. al, 2021a). As shown in the Fig. 4e, the EIS of MIL-101 is lower than that of Fe₃O₄, and the EIS of the composites of the two is the lowest,, indicating that the heterojunction formed by the two contributes to the separation of photogenerated hole electron pairs.

3.3. Photodegradation performance

The Fig. 5a demonstrates the removal efficiency of OTC in the photo-Fenton system for MF with different Fe_3O_4 compound ratios. The removal efficiency is significantly improved after the Fe_3O_4 compounding because of the formation of heterojunctions and the increase of Fe sites. The highest removal efficiency (87.1%) occurred at MF-50/light/PS.

In order to investigate the role of the components of the reaction, a number of control experiments were carried out. As shown in Fig. 5b, there was no OTC degradation under visible light alone, indicating its structural stability. In the light/PS system, OTC only slightly degraded, demonstrating the ineffectiveness of PS activation by visible light. Also, the removal efficiency of OTC in photocatalytic systems was still relatively low. However, in the Fenton system (MF-50/PS), 61.1% of the OTC was removed, indicating that the sample had a superior activation effect on PS. Notably, in the photo-Fenton system, the synergistic effect of light, MF-50 and PS significantly enhanced the removal efficiency of OTC.

3.3.1. Effect of catalyst dosage

The dosage of catalyst is an important factor affecting the removal efficiency of OTC. We set up parallel experiments with different MF-50 doses (0.05, 0.1, 0.2, 0.3, 0.4 and 0.5 g/L respectively) and the results are shown in the Fig. 5c. The removal efficiency of OTC by the dark reaction increased with the amount of catalyst, because more catalyst provided more adsorption. While in the light reaction, the removal efficiency was well improved when the catalyst dosage was increased from 0.05 g/L to 0.2 g/L, but the removal efficiency was not significantly improved from 0.2 g/L to 0.5 g/L, which may be due to the scattering of light caused by the increase in the amount of catalyst.

3.3.2. Effect of pH

The initial pH value of the solution is an important factor influencing the removal of OTC. Hence, HCl (0.1 mol/L) or NaOH (0.1 mol/L) was adopted to tune the pH value of the OTC solution for investigating the impact of pH value on OTC removal. The Fig. 5d shows the removal efficiency of OTC in the MF/vis/PS system at different initial solution pH values. The dark reaction is less effective in an acidic environment. Combined with the results of zeta potential analysis (Fig. 5g), the zero potential point of the MF material is 9.48, while the OTC molecule exhibits electropositivity at $\text{pH} < 5$ (Sudhaik et. al, 2018) when the surface of the MF material also exhibits electropositivity and homogeneous repulsion. However, in strongly alkaline aqueous solutions, the activity of Fe activated persulfate is reduced, which decreases the removal efficiency of the material in the photoreactive phase. Meanwhile, excessive adsorption can reduce the utilization of light by the samples (Ye et. al, 2019).

3.3.3. Effect of OTC concentration

Investigating the degradation efficiency of MF-50 at different antibiotic concentrations is a major step in testing the suitability of the material. In this study, the removal efficiency of MF-50 coupled with PS was evaluated at OTC concentrations of 30, 40, 50, 60, 70 and 100 mg/L. According to Fig. 5e, MF-50/PS/light has good removal efficiency for OTC from 30 to 70 mg/L. When the concentration of OTC increases to 100 mg/L, the removal efficiency decreases slightly. This can be attributed to the fact that high

concentrations of OTC are more susceptible to light scattering, which reduces the number of photons captured by MF-50. Also the increased competition of OTC molecules is a reason for the low removal efficiency of high OTC concentrations (Jiang et. al, 2018).

3.3.4. Effect of PS concentration

The addition of PS has a non-negligible effect on the removal of OTC, so it is necessary to investigate the optimum amount of persulfate to be added. As shown in the Fig. 5f, the removal rate of OTC increases when the amount of PS increases from 0.1 to 0.5 g/L. This improvement is caused by increased concentrations of active species associated with the conversion of more PS molecules into free radicals (Pan et. al, 2020). However, when the PS continued to increase from 0.5 g/L to 1.0 g/L, the removal efficiency of OTC did not improve, which may be because excessive oxidant would clean up the generated free radicals, resulting in a lower removal efficiency (Heidarpour et. al, 2020).

3.4. Recyclability and stability

Recyclability and stability are two important indicators of the materials' practicality. After each use, the material was recovered with magnets, washed and dried, and then removed the OTC, and so on four times, and the total iron in the water samples at the end of each experiment was measured. As shown in Fig. 6a, after four cycles, the removal efficiency was only reduced by 4.29% and none of the leached iron exceeded 0.035 mg/L. Furthermore, in combination with XPS analysis of the used material (Fig. 3b), the results showed that the structure of the material remained virtually unchanged, demonstrating the excellent stability of the material. The determination of the hysteresis lines helps to characterize the magnetic properties of the material. According to Fig. 6b, MF-50 is paramagnetic with a saturation magnetic strength of 3.52 emu/g.

3.5. Mechanistic analysis

To investigate the role of free radicals in the degradation of oxytetracycline, trapping experiments were carried out. In our work, MeOH (1 mol/L), IPA (1 mol/L), BQ (1 mmol/L), NaCl (1 mmol/L) were used as scavengers for $\cdot\text{SO}_4^-$, $\cdot\text{OH}$, $\cdot\text{O}_2^-$, h^+ , respectively. As shown in the Fig. 7a, the addition of IPA significantly reduced the removal efficiency of OTC, indicating that $\cdot\text{OH}$ was involved in the removal process of OTC. After adding MeOH, the removal efficiency of OTC was further reduced, indicating that $\cdot\text{SO}_4^-$ also played a role in the removal process of OTC. While the addition of BQ and NaCl had no effect on the removal of OTC. In this way, $\cdot\text{SO}_4^-$ and $\cdot\text{OH}$ were the main active substances for OTC degradation. To further verify the reactive oxygen species in AUN-2 photocatalytic system, ESR spin-trap measurement involved 5,5-dimethyl-1-pyrroline N-oxide (DMPO) in aqueous solution. Experiments were conducted in darkness, irradiated with visible light for 5 min. As shown in Fig. 7b, the DMPO $\cdot\text{OH}$ adduct could observe a four-wire ESR signal under light, while the DMPO $\cdot\text{SO}_4^-$ could observe a six-wire ESR signal, indicating that MF-50/light could effectively activate the PDS to produce $\cdot\text{SO}_4^-$ and $\cdot\text{OH}$ radicals, so as to obtain

excellent OTC removal efficiency. In contrast, there was no obvious peak during the dark reaction, which also further illustrated the coupling of photocatalysis with persulfate.

Combined with the analysis of free radicals, the charge transfer paths can be deduced (Fig. 8). According to the analysis results of the material energy band structure, Fe_3O_4 and MIL-101 combine to form a heterojunction structure with interleaved energy levels, so both photocatalysts may form type II heterojunction and Z-type heterojunction structures. MF-50 can generate electron leaps upon photoexcitation for both Fe_3O_4 and MIL-101. Since the conduction band potential of Fe_3O_4 is lower than that of $\text{O}_2/\cdot\text{O}_2^-$ (-0.33 eV vs. NHE), and $\cdot\text{O}_2^-$ does not participate in the degradation of OTC according to the trapping experiments, the electrons on Fe_3O_4 are subsequently transferred to the conduction band of MIL-101, which activates persulfate to generate persulfate. At the same time, h^+ on the valence band of Fe_3O_4 should migrate to the valence band of MIL-101 and convert H_2O to $\cdot\text{OH}$. This is because the valence band potential of Fe_3O_4 is lower than $\cdot\text{OH}/\text{H}_2\text{O}$ (2.38 eV vs. NHE), and h^+ is not the main active substance in the active substance analysis. In addition, comparing $\text{Fe}^{3+}/\text{Fe}^{2+}$ (0.77 eV vs. NHE), the Fe(III) and Fe(II) cycles present during the reaction. This is also evidenced by a new peak of 710.6 eV in the XPS Fe2p pattern of the used material, which corresponds to Fe(II).

4. Conclusion

In summary, magnetic type II heterojunction photocatalyst $\text{Fe}_3\text{O}_4/\text{MIL-101}$ is produced by hydrothermal method and demonstrates excellent degradation performance against OTC in the presence of coupled persulfate. The compounding of Fe_3O_4 not only provides the material with magnetic properties, but also builds heterojunctions to enhance charge conduction and facilitate activation of PS. Furthermore, good adaptability to various operating conditions and environmental fluctuations has been demonstrated. The material has excellent stability, and the structure does not change much after four cycles. Furthermore, only a small amount of Fe is leached out in each cycle. The removal efficiency is reduced to the minimum in each cycle, and the material can be recovered using magnets after each cycle. $\cdot\text{OH}$ and $\cdot\text{SO}_4^-$ are the main active substances attacking the OTC molecules and the Fe(III)/Fe(II) cycle facilitates the charge transfer. Overall, $\text{Fe}_3\text{O}_4/\text{MIL-101}$ photocatalyst coupled with persulfate is an effective method for the degradation of organic pollutants in water bodies.

Declarations

Acknowledgments

This research was funded by Engineering and Technical Center Open Fund of Hunan Provincial Environmental Protection for River-Lake Dredging Pollution Control (EPD202104), Scientific Research Foundation of Hunan Provincial Education Department (18B127, 19A032), National Natural Science Foundation of China (51109016, 51308069, 51809019).

Authors' Contributions

Zhuo Zhang: Writing - Review & Editing, Investigation, Visualization

Chunyan Du: Conceptualization, Project administration, Funding acquisition

Yin Zhang: Conceptualization, Writing - Original Draft, Investigation

Guanlong Yu: Resources, Funding acquisition, Conceptualization

Ying Xiong: Resources

Lu Zhou: Supervision

Yuanyuan Liu: Supervision

Tianying Chi: Formal analysis

Guoliang Wang: Formal analysis

Yihai Su: Validation

Yinchu Lv: Validation

Hao Zhu: Validation

Availability of data and materials

All data generated or analyzed during this study are included in this published article.

Ethics approval and consent to participate

Not applicable

Consent for publication

Not applicable.

Competing interests

The authors declare no competing interests.

References

1. Chen G, Yu Y, Liang L, Duan X, Li R, Lu X et al (2021) Remediation of antibiotic wastewater by coupled photocatalytic and persulfate oxidation system: A critical review. J HAZARD MATER 408:124461

2. Do S, Kwon Y, Bang S, Kong S (2013) Persulfate reactivity enhanced by $\text{Fe}_2\text{O}_3\text{-MnO}$ and $\text{CaO-Fe}_2\text{O}_3\text{-MnO}$ composite: Identification of composite and degradation of CCl_4 at various levels of pH. *CHEM ENG J* 221:72–80
3. Du C, Song J, Tan S, Yang L, Yu G, Chen H et al (2021) Facile synthesis of Z-scheme $\text{ZnO/Ag/Ag}_3\text{PO}_4$ composite photocatalysts with enhanced performance for the degradation of ciprofloxacin. *MATER CHEM PHYS* 260:124136
4. Du C, Zhang Z, Tan S, Yu G, Chen H, Zhou L et al., 2021. Construction of Z-scheme $\text{g-C}_3\text{N}_4 / \text{MnO}_2 / \text{GO}$ ternary photocatalyst with enhanced photodegradation ability of tetracycline hydrochloride under visible light radiation. *ENVIRON RES*:111427
5. Du C, Zhang Z, Yu G, Wu H, Chen H, Zhou L et al (2021) A review of metal organic framework (MOFs)-based materials for antibiotics removal via adsorption and photocatalysis. *CHEMOSPHERE* 272:129501
6. Espinosa J, Catala C, Navalon S, Ferrer B, Alvaro M, Garcia H (2018) Iron oxide nanoparticles supported on diamond nanoparticles as efficient and stable catalyst for the visible light assisted Fenton reaction. *APPL CATAL B-ENVIRON* 226:242–251
7. Guo J, Jiang L, Liang J, Xu W, Yu H, Zhang J et al (2021) Photocatalytic degradation of tetracycline antibiotics using delafossite silver ferrite-based Z-scheme photocatalyst: Pathways and mechanism insight. *CHEMOSPHERE* 270:128651
8. Guo Y, Feng C, Qiao S, Wang S, Chen T, Zhang L et al., 2020. Magnetic Fe_3O_4 -encapsulated VAN@MIL-101 (Fe) with mixed-valence sites and mesoporous structures as efficient bifunctional water splitting photocatalysts. *NANOSCALE*: 12551–12560
9. Heidarpour H, Padervand M, Soltanieh M, Vossoughi M (2020) Enhanced decolorization of rhodamine B solution through simultaneous photocatalysis and persulfate activation over $\text{Fe/C}_3\text{N}_4$ photocatalyst. *CHEM ENG RES DES* 153:709–720
10. Huang D, Zhang G, Yi J, Cheng M, Lai C, Xu P et al (2020) Progress and challenges of metal-organic frameworks-based materials for SR-AOPs applications in water treatment. *CHEMOSPHERE* 263:127672
11. Jiang L, Yuan X, Zeng G, Liang J, Wu Z, Wang H et al (2018) A facile band alignment of polymeric carbon nitride isotype heterojunctions for enhanced photocatalytic tetracycline degradation. *ENVIRON SCI-NANO* 5:2604–2617
12. Li J, Wang L, Peng L, Deng Y, Deng D (2020) A combo system consisting of simultaneous persulfate recirculation and alternating current electrical resistance heating for the implementation of heat activated persulfate ISCO. *CHEM ENG J* 385:123803
13. Li S, Cui J, Wu X, Zhang X, Hu Q, Hou X (2019) Rapid in situ microwave synthesis of $\text{Fe}_3\text{O}_4@\text{MIL-100(Fe)}$ for aqueous diclofenac sodium removal through integrated adsorption and photodegradation. *J HAZARD MATER* 373:408–416

14. Monteagudo J, El-taliawy H, Duran A, Caro G, Bester K (2018) Sono-activated persulfate oxidation of diclofenac: Degradation, kinetics, pathway and contribution of the different radicals involved. J HAZARD MATER 357:457–465
15. Pan Y, Yuan X, Jiang L, Wang H, Yu H, Zhang J (2020) Stable self-assembly AgI/UiO-66 (NH₂) heterojunction as efficient visible-light responsive photocatalyst for tetracycline degradation and mechanism insight. CHEM ENG J 384:123310
16. Shao M, Ning F, Zhao J, Wei M, Evans DG, Duan X (2012) Preparation of Fe₃O₄@SiO₂@Layered Double Hydroxide Core–Shell Microspheres for Magnetic Separation of Proteins. J AM CHEM SOC 134:1071–1077
17. Sudhaik A, Raizada P, Shandilya P, Singh P (2018) Magnetically recoverable graphitic carbon nitride and NiFe₂O₄ based magnetic photocatalyst for degradation of oxytetracycline antibiotic in simulated wastewater under solar light. JOURNAL OF ENVIRONMENTAL CHEMICAL ENGINEERING 6:3874–3883
18. Wang M, Jin C, Kang J, Liu J, Tang Y, Li Z et al (2021) CuO/g-C₃N₄ 2D/2D heterojunction photocatalysts as efficient peroxydisulfate activators under visible light for oxytetracycline degradation: Characterization, efficiency and mechanism. CHEM ENG J 416:128118
19. Wang S, Wang J (2018) Trimethoprim degradation by Fenton and Fe(II)-activated persulfate processes. CHEMOSPHERE 191:97–105
20. Wu Q, Yang H, Kang L, Gao Z, Ren F (2020) Fe-based metal-organic frameworks as Fenton-like catalysts for highly efficient degradation of tetracycline hydrochloride over a wide pH range: Acceleration of Fe(II)/Fe(III) cycle under visible light irradiation. APPL CATAL B-ENVIRON 263:118282
21. Yang J, Zhu M, Dionysiou D (2021) What is the role of light in persulfate-based advanced oxidation for water treatment? WATER RES 189:116627
22. Yang L, Du C, Tan S, Zhang Z, Song J, Chen J et al (2021) Improved photocatalytic properties of Fe(III) ion doped Bi₂MoO₆ for the oxidation of organic pollutants. CERAM INT 47:5786–5794
23. Yang Y, Zeng G, Huang D, Zhang C, He D, Zhou C et al (2020) Molecular engineering of polymeric carbon nitride for highly efficient photocatalytic oxytetracycline degradation and H₂O₂ production. APPL CATAL B-ENVIRON 272:118970
24. Ye S, Yan M, Tan X, Liang J, Zeng G, Wu H et al (2019) Facile assembled biochar-based nanocomposite with improved graphitization for efficient photocatalytic activity driven by visible light. APPL CATAL B-ENVIRON 250:78–88
25. Yu L, Zhang X, Li G, Cao Y, Shao Y, Li D (2016) Highly efficient Bi₂O₂CO₃/BiOCl photocatalyst based on heterojunction with enhanced dye-sensitization under visible light. APPL CATAL B-ENVIRON 187:301–309
26. Zhang H, Zhou C, Zeng H, Wu H, Yang L, Deng L et al (2021) ZIF-8 assisted synthesis of magnetic core-shell Fe₃O₄@CuS nanoparticles for efficient sulfadiazine degradation via H₂O₂ activation: Performance and mechanism. J COLLOID INTERF SCI 594:502–512

27. Zhao F, Liu Y, Ben Hammouda S, Doshi B, Guijarro N, Min X et al (2020) MIL-101(Fe)/g-C₃N₄ for enhanced visible-light-driven photocatalysis toward simultaneous reduction of Cr(VI) and oxidation of bisphenol A in aqueous media. APPL CATAL B-ENVIRON 272:119033

Figures

Figure 1

Preparation process scheme of the samples.

Figure 2

the SEM image of (a) Fe₃O₄, (b) MIL-101, (c) MF-50; (d) the EDS of MF-50

Figure 3

(a) XRD patterns of Fe₃O₄, MIL-101 and MF-50; (b) XPS Survey of Fe₃O₄, MIL-101, fresh MF-50 and used MF-50; (c) Fe 2p; (d) O 1s of MIL-101 and MF-50.

Figure 4

(a) UV-vis diffuse reflectance spectra of as-prepared samples; (b) the transformed diffuse reflectance spectra, (c) the XPS valence band spectra and (d) the Mott-Schottky plots of Fe₃O₄ and MIL-101; (e) the EIS of as-prepared samples.

Figure 5

OTC removal efficiency of (a) MF-x, (b) different systems, (c) different MF-50 dosage, (d) different pH, (e) different OTC concentration, (f) different PS concentration; (g) Zeta potential of MF-50.

Figure 6

(a) Recycle experiments of CMG-10 for the degradation of OTC and the Fe leaching, (b) Magnetization curves of MF-50.

Figure 7

(a) Trapping experiments of MF-50 for OTC degradation in light/PS system, (b) ESR spectra of $\cdot SO_4^-$ and $\cdot OH$.

Figure 8

Schematic diagram of the possible mechanisms of OTC degradation in the MF-50/light/PS system.