Circular economy approach for rice husk modification: Equilibrium, kinetic, thermodynamic aspects and mechanism of Congo red adsorption

Nina Mladenovic

Ss Cyril and Methodius University in Skopje Faculty of Technology and Metallurgy: Saints Cyril and Methodius University in Skopje Faculty of Technology and Metallurgy

Jovana Petkovska

Ss Cyril and Methodius University in Skopje Faculty of Technology and Metallurgy: Saints Cyril and Methodius University in Skopje Faculty of Technology and Metallurgy

Vesna Dimova

Ss Cyril and Methodius University in Skopje Faculty of Technology and Metallurgy: Saints Cyril and Methodius University in Skopje Faculty of Technology and Metallurgy

Dejan Dimitrovski

Ss Cyril and Methodius University in Skopje Faculty of Technology and Metallurgy: Saints Cyril and Methodius University in Skopje Faculty of Technology and Metallurgy

Igor Jordanov (✉ jordanov@tmf.ukim.edu.mk)

Faculty of Technology and Metallurgy, Ss. Cyril and Methodius University <https://orcid.org/0000-0002-9409-8197>

Research Article

Keywords: dye removal, modification, rice husk, circular economy, adsorption

Posted Date: September 24th, 2021

DOI: <https://doi.org/10.21203/rs.3.rs-899831/v1>

License: © ⓘ This work is licensed under a Creative Commons Attribution 4.0 International License.

[Read Full License](#)

Version of Record: A version of this preprint was published at Cellulose on November 19th, 2021. See the published version at <https://doi.org/10.1007/s10570-021-04312-9>.

Circular economy approach for rice husk modification:
Equilibrium, kinetic, thermodynamic aspects and
mechanism of Congo red adsorption

Nina Mladenovic, Jovana Petkovska, Vesna Dimova, Dejan Dimitrovski, Igor Jordanov

Nina Mladenovic

*Faculty of Technology and Metallurgy, Ss. Cyril and Methodius University in Skopje, Ruger
Boskovic 16, 1000 Skopje, Republic of North Macedonia*

Jovana Petkovska

*Faculty of Technology and Metallurgy, Ss. Cyril and Methodius University in Skopje, Ruger
Boskovic 16, 1000 Skopje, Republic of North Macedonia*

Vesna Dimova

*Faculty of Technology and Metallurgy, Ss. Cyril and Methodius University in Skopje, Ruger
Boskovic 16, 1000 Skopje, Republic of North Macedonia*

Dejan Dimitrovski

*Faculty of Technology and Metallurgy, Ss. Cyril and Methodius University in Skopje, Ruger
Boskovic 16, 1000 Skopje, Republic of North Macedonia*

Igor Jordanov

*Faculty of Technology and Metallurgy, Ss. Cyril and Methodius University in Skopje, Ruger
Boskovic 16, 1000 Skopje, Republic of North Macedonia*

+38975223534

jordanov@tmf.ukim.edu.mk

Corresponding author:

Igor Jordanov: jordanov@tmf.ukim.edu.mk

ORCID 0000-0002-9409-8197

Abstract

Equilibrium, kinetic, thermodynamic aspects and mechanism of Congo red adsorption onto rice husk treated with effluent from cotton pre-treatment are examined by altering the initial dye concentration, contact time, temperature, and adsorbent mass. When a lower mass is applied, the treated rice husk adsorbs the Congo red following the Langmuir model, while at a higher mass, the adsorption follows the Freundlich model. A maximum of 149.1 mg/g Congo red is adsorbed with 10 g/L rice husk at 70°C. This capacity of the chemically modified rice husk is one of the better ones found in the literature. The calculated Dubinin–Radushkevich activation energy indicates the physical nature of Congo red adsorption adsorbed under the pseudo-second-order kinetic model. The thermodynamic analysis confirmed spontaneous and endothermic adsorption with physically created Congo red-rice husk bonds. These results showed the applicability of the circular economy concept in the effort to obtain an efficient adsorbent without wasting additional

chemicals and energy that could be used to create a continuous column-mode process of rice husk modification and purification of colored effluent from the textile industry.

Graphical abstract

Key words: dye removal, modification, rice husk, circular economy, adsorption

Highlights

- Treatment of rice husk with effluent from cotton pretreatment.
- Equilibrium, kinetic, thermodynamic and mechanism of adsorption are tested.
- 149.1 mg/g adsorption capacity of treated rice husk.
- The adsorption is physical, spontaneous and endothermic.

Introduction

Direct (substantive) dyes are water-soluble colorants for dyeing cellulosic fabrics when good lightfastness is required, but washing-fastness is not crucial (Broadbend 2001). As sulfonated azo chemicals, they are serious pollutants (Blackburn 2004), because their degradation products are highly carcinogenic (Brown and De Vito 1993). Effluent from dyeing of cellulosic fibers, with 5-30% residual direct dye (Easton 1995) has a negative environmental impact and a toxic influence on aquatic organisms because of its high biochemical oxygen demand that results in the suffocation of aquatic flora and fauna. Several studies for cleaning the colored effluent have been examined. Biological treatment using activated sludge (Abu Elella et al. 2019), chemical treatment with oxidation (Alaton and Teksoy 2007) and ozonation (Ciardelli et al. 2001) and physical methods by implementing membrane technology (Males et al. 2020; Gorgieva et al. 2019), ion-exchange materials (Shao X et al. 2021), polyelectrolytes (Qiao et al. 2021), biomasses (Halysh et al. 2020), nanostructures (Batmaz et al. 2014; Aboamera et al. 2018), cellulose-based hydrogels (Ching et al. 2018; Mohamed et al. 2018) cellulose-based aerogels (Chong et al. 2015) and biopolymers (Perez-Ameneiro et al. 2014) have been explored. Many of these treatments are expensive and have limited effectiveness that requires additional extensive examination. Adsorption of dye molecules is one of the cheapest methods for purifying colored effluent from the textile industry based on employing cheap and highly effective adsorbents. Many adsorbents show effective dye absorbency, but most of them are either expensive or have limited absorptivity. One of the commercially available adsorbents, which possess excellent adsorption ability, is activated carbon (Foo and Hameed 2010). Despite its high efficiency, its expensive fabrication limits its use as a dyed effluent purifier (Abdelwahab et al. 2005).

The latest development in colored effluent cleaning is related to using an agricultural byproduct, or industrial waste, as an adsorbent, that is inexpensive and abundant. Grass waste, leaf, fly ash, sugarcane bagasse, sludge ash, wheat straw, natural fibers, rice husk, etc., have been tested as potential adsorbents (Chakraborty et al. 2011; Gupta et al. 2009; Sanghi and Verma 2013; Sharma et al. 2011; Tarbuk et al. 2020; Toshikj et al. 2019). Some of them are highly efficient, but many require additional modification steps to make them more amenable for dye sorption. Rice husk with its chemical composition containing 32% cellulose, 21% hemicellulose, 21% lignin, 20% silica, 3% crude proteins (Chowdhury et al. 2011), which is similar to the composition of natural cellulose fibers (Ivanovska et al. 2019; Lazic et al. 2018), emphasizes its use as a purifier for colored effluent (Chakraborty et al. 2011; Mladenovic et al. 2020; Shamsollahi and Partovinia 2019). Despite the theoretically good ability for dye adsorption, the content of 21% lignin in its outer protective layer i.e. the hydrophobic lignin-silicone-cellulose shield, makes the rice husk less adsorptive (Ndazi et al. 2007). In order to improve its adsorption capacity, the rice husk was subjected to physical grounding (Vadivelan & Kumar 2005), incineration (Alam et al. 2020), chemical treatments with acids (Abdelwahab et al. 2005), ethylenediamine (Ong et al. 2007) and bases (Chowdhury et al. 2011; Chowdhury et al. 2012). These modifications are effective but require an investment in expensive equipment that operates at high temperatures under pressure.

Alkaline scouring of cotton is a process that uses dilute sodium hydroxide solution and surfactants to remove non-cellulosic hydrophobic components from cotton's cuticle and to make it hydrophilic (Toshikj et al. 2016; Toshikj et al. 2017; Lazic et al. 2018). The circular economy is a new concept opposite to the linear economy one, which is based on production, use, and throwing away of the products. It is mainly focused on using the products and materials over and

over, in a continuous loop. In this system, products and wastes are either reused or recycled. The applicability of the circular economy concept for rice husk modification has been proved in previous research (Mladenovic et al. 2020). In that study, rice husk was treated with cotton scouring effluent as an inexpensive way of successful modification by avoiding the need for additional energy and chemicals. Attenuated total reflectance-infrared spectroscopy (ATR-IR) and scanning electron microscopy-energy dispersive X-ray (SEM-EDX) was used to observe the occurred changes after this modification. The results of these analyzes showed that the treatment with effluent from alkaline scouring effectively removed the lignin-silicone shield from the rice husk surface. Moreover, this treatment increased the percentage of cellulose in the husk and the structure became cellulose-dominant and more amenable for purifying the colored effluent.

The present study explored equilibrium, kinetics, thermodynamics, and the adsorption mechanism of Congo red (CR) onto rice husk modified with cotton scouring effluent (ERH), by the concept of circular economy. The results show that this approach is effective in obtaining an efficient adsorbent for dye removal. Moreover, such modified rice husk has an exceptional absorption capacity higher than other chemically modified rice husks found in the literature.

2. Materials and methods

2.1. Materials

The collected rice husk was sifted through a sieve to eliminate tiny particles with a size less than 1.25 mm and dried at 105 °C for 2 h. Congo red dye - C.I. 20120 (Sigma-Aldrich, Milwaukee, WI) was used as received. All experimental dye solutions with defined concentrations were

prepared by diluting the stock solution which has 1 g/L concentration. Sodium hydroxide and sodium chloride were supplied by Sigma-Aldrich (Milwaukee, WI). Coto blanc HTD-N (CHT Switzerland AG), anionic washing surfactant and Kemonecer NI (Kemo Croatia), nonionic wetting surfactant are used as received.

2.2. Rice husk modification

Rice husk was treated with effluent from cotton scouring. The effluent was obtained after cotton yarn scouring, done with a solution containing 25 g/L of sodium hydroxide, 2 mL/L Coto blanc HTD-N and 1 mL/L Kemonecer NI in a bath with 50:1 liquor ratio at 100°C for 60 min in Ahiba Turbomat TM-6 apparatus. Then, the collected effluent was mixed with the raw rice husk (with a ratio of effluent and husk 20:1) and treated for 30 min in the Linitest apparatus. During this treatment, the effluent temperature decreased from 100°C to 40°C with an average temperature of 70°C. Then, the rice husk was rinsed with effluents from cotton yarn rinsing, performed at 70°C for 15 min (warm rinsing) and 25°C temperature for 15 min (cold rinsing).

2.3. Adsorption studies

The adsorption ability of treated rice husk is examined by employing a batch adsorption process where 2, 4, and 8 g rice husk (i.e. 10, 20, and 40 g/L adsorbent dosage) are added in a 200 mL colored solution (in a glass stoppered Erlenmeyer flask) with an initial dye concentration of 0.1, 0.2, 0.3, 0.4, and 0.5 g/L Congo red, 10 g/L NaCl at pH 7, at 298, 323, and 343 K with constant agitation of 60 min⁻¹ in a GLF-shaking water bath 1083 (EURO lux GmbH & Co. KG Karlstadt-Karlberg, Germany). Pipetting of the dye solution was done at 10, 20, 30, 40, 60, 90, 120, 360,

720, and 1440 min and the concentration of Congo red (max. wavelength at 507 nm) in the supernatant solution was measured with UV/VIS spectrophotometer (Model Hitachi – 2800, United Kingdom). The calculated values are mean values of three measurements. The dye removal efficiency, expressed as a percentage, was determined using Eq. 1.

$$\text{Dye removal (\%)} = \left[\frac{C_0 - C_t}{C_0} \right] * 100 (\%) \quad (1)$$

C_0 (g/L) is the initial concentration of the dye and C_t (g/L) is the concentration of the dye after sorption at any time. The mass balance equation (Eq. 2) was used to calculate the amount of adsorbed dye onto the rice husk Q_e (g/g).

$$Q_e = \frac{(C_0 - C_e) * V}{W} \quad (2)$$

C_0 (g/L) and C_e (g/L) are the initial concentration and the concentration of dye at equilibrium, respectively, V (L) is the volume of the solution and W (g) is the weight of the sorbent used.

3. Results and discussion

The influence of adsorbent dosage, temperature, and initial dye concentration on the adsorption ability of the sorbent has to be inter-correlated to obtain a clear picture of the sorption phenomena for each sorbate-sorbent system. Hence, the adsorption ability of CR employing three masses of ERH, five initial dye concentrations, and three temperatures is examined in this study. The capability of the ERH to remove CR from solution with 0.3 g/L initial dye concentration at 298, 323, and 343 K, tested with 10, 20, and 40 g/L ERH are shown in Fig. 1 (a), (b) and (c), respectively. The increase in the ERH dosage and temperature of the dye solution

increases the percent of removed dye. Increased ERH adsorbent dosage increases the specific area and available adsorption sites, while higher temperatures make the dye molecules more energy-active with a higher potential for adsorption onto the ERH surface. Opposite, a higher initial dye concentration, at a constant adsorbent dosage and temperature of the solution, results in a lower percentage of removed dye (Fig. 2). A constant adsorbent dosage has a defined adsorption ability, so the percentage of removed dye decreases as the initial dye concentration increases. The complete data of the dye removal versus contact time, conducted under all combined parameters, are given as a supplementary file.

Fig. 1 Effect of ERH dosage on dye removal tested with 0.3 g/L CR at 298, 323 and 343 K. (a) 10 g/L, (b) 20 g/L and (c) 40 g/L ERH dosage.

Fig. 2 Influence of initial dye concentration on CR removal tested with 20 g/L ERH at 298 K.

Adsorption isotherms

In order to examine, explain and interpret the used adsorbent-adsorbate sorption system, the adsorbent capacity must first be assessed. Langmuir and Freundlich's isotherms are the most used equilibrium relationships between the adsorbate and adsorbent at a given sorption condition. As such, they are essential for the evaluation of the physicochemical interaction between CR and ERH and the dye adsorption equilibrium analysis. According to the Langmuir theory, dye adsorption is achieved through certain functional groups in the adsorbent. During the reaction, these groups are saturated forming a monolayer, which prevents further absorption of the dye. Also, in the Langmuir equation (Eq. 3), the dye concentration in the adsorbent increases with the dye concentration in the bath but to some extent, i.e. until all active centers of the adsorbent are saturated with dye. This isotherm has a linear form, as expressed in Eq. 4.

$$Q_e = \frac{Q_m K_L C_e}{1 + K_L C_e} \quad (3)$$

$$\frac{C_e}{Q_e} = \frac{1}{K_L Q_m} + \frac{1}{Q_m} C_e \quad (4)$$

Ce (g/L) is the equilibrium concentration of Congo red, Qe (g/g) is the amount of CR adsorbed per unit mass of adsorbent, Qm (g/g) is constant related to adsorption capacity and KL (L/g) is constant related to rate of adsorption. Qm is calculated from the slope of the straight line when Ce/Qe is plotted against Ce.

The Freundlich equation presented in Eq. 5 explain sorption on a heterogeneous surface with sites of varied affinities.

$$Q_e = K_F C_e^{1/n_F} \quad (5)$$

The logarithmic form of Freundlich is given by Eq. 6.

$$\log(Q_e) = \log(K_F) + \frac{1}{n_F} \log(C_e) \quad (6)$$

Qe (g/g) is the equilibrium dye concentration, Ce (g/L) is the equilibrium dye concentration in solution, KF (g/g) (L/g)^{1/n} is the constant related to adsorption capacity, and nF is the adsorption isotherm constant. KF and 1/nF are calculated from the intercept and slope of the straight line of the plot log(Qe) versus log(Ce), respectively.

The Dubinin-Radushkevich (D-R) isotherm, which rules out the homogenous surface or constant sorption potential, is empirical model for the adsorption of the adsorbate to the volume filling of micropores (Dabrowski 2001). This isotherm is very important for determining the adsorption characteristics of most of the industrial adsorbents with a complex and well-developed porous

208 structure, including pores of different shapes and sizes, but micropores play the most significant
 209 role. The non-linear equations of Dubinin-Radushkevich isotherm can be illustrated as Eq. 7 and
 210 8 (Chen 2015).

$$211 \quad Q_e = Q_s \exp(-K_{DR} \varepsilon^2) \quad (7)$$

$$212 \quad \varepsilon = RT \ln \left(1 + \frac{1}{C_e} \right) \quad (8)$$

213 Q_s (g/g) is a constant related to adsorption capacity, K_{DR} (mol²/KJ²) is a constant related to the
 214 mean free energy of adsorption, ε is Polanyi potential, C_e (g/L) is the concentration at
 215 equilibrium, R (J/mol K) is the gas constant, and T (K) is the absolute temperature.

216 The linear expression of Dubinin-Radushkevich isotherm model is shown in Eq. 9.

$$217 \quad \ln Q_e = \ln Q_m - \beta \varepsilon^2 \quad (9)$$

218 Q_m (g/g) is the maximum adsorption capacity and β (mmol²/J²) is a coefficient related to the
 219 mean free energy of adsorption. Q_m and β are calculated from the intercept and slope of the plot
 220 between $\ln Q_e$ and ε^2 , respectively.

221 β is used to calculate E (KJ/mol), the mean free energy of adsorption per mole of the adsorbate,
 222 when the adsorbate is transferred from infinity of the solution to the surface of the solid. The
 223 relation between them is shown in Eq. 10 (El Haddad 2016).

$$224 \quad E = \frac{1}{\sqrt{2\beta}} \quad (10)$$

225 E ranged from 8 to 16 KJ/mol indicates proceeds of the sorption process via chemisorption.
 226 Values of $E < 8$ KJ/mol indicate a physical sorption process (El Haddad 2016).

The experimental adsorption capacity of ERH, the calculated constants of Langmuir, Freundlich and D-R, and the coefficients of correlation between calculated and experimental data are presented in Table 1. The highest adsorption capacity of 149.1 mg/g is achieved when the lowest adsorbent dosage (10 g/L ERH) and the highest temperature of 343 K are applied. The dye removal is directly proportional, while the adsorption capacity of the ERH, at all temperatures is inversely proportional to the adsorbent dosage. Higher dosage reduces the amount of the adsorbed dye per unit weight of the adsorbents. The experimental adsorption capacity of the ERH, tested with 10 and 20 g/L adsorbent dosage, increases by about 63 % as the temperature of the adsorption testing rises from 298 to 343 K. The adsorption capacities tested with 40 g/L ERH are not that temperature-dependent and increase for about 5 % when the temperature of adsorption increases from 298 to 343 K. The calculated coefficients of correlation presented in Table 1 show that the equilibrium data for 10 g/L ERH fits the Langmuir better than the Freundlich isotherm at all tested temperatures, confirming a monolayer coverage of the Congo Red onto ERH when a lower adsorption dosage is used. The adsorption capacity for 20 g/L ERH at 298 and 323 K, fits the Langmuir isotherm, while the one at 343 K fits the Freundlich isotherm model better. The Freundlich isotherm proved to be a better fit for the equilibrium data for 40 g/L ERH at all tested temperatures. A list of published data on adsorption capacities of chemically modified rice husks (Table 2) and the adsorption capacity of Congo red adsorbed onto different renewable adsorbents (Table 3) indicate that capacity of the treated rice husk obtained in this study is one of the better found in the literature.

The Langmuir isotherm could be also used to determine the dimensionless equilibrium separation parameter R_L calculated by Eq. 11 (Omidi and Kakanejadifard 2018).

$$R_L = \frac{1}{1+K_L C_0} \quad (11)$$

K_L (L/g) is the Langmuir constant related to adsorption capacity, while C_0 (g/L) is the initial concentration of the dye solution. When $R_L < 1$, the adsorption is favorable, while for values of $R_L > 1$, it is unfavorable.

The D-R isotherm is employed to calculate the magnitude of E which indicates the type of adsorption. As mentioned above, the value of E higher than 8 KJ/mol is an indicator of chemical ion exchange, while E below 8 KJ/mol indicates physical sorption (Chakraborty et al. 2011). The E values presented in Table 1 are lower than 8 KJ/mol in most cases, confirming the physical sorption of the CR onto ERH.

Table 1 Isotherm parameters for adsorption of Congo red onto ERH

Isotherm	Parameters	Temperature (K)								
		298			323			343		
		Adsorbent dosage (g/L)			Adsorbent dosage (g/L)			Adsorbent dosage (g/L)		
		10	20	40	10	20	40	10	20	40
Langmuir	$Q_{m,exp}$ (g/g)	0.0917	0.0765	0.0579	0.1153	0.0992	0.0608	0.1491	0.1126	0.0610
	Q_m (g/g)	0.0932	0.0759	0.0667	0.1099	0.1011	0.0849	0.1465	0.1264	0.0888
	K_L (l/g)	0.440	0.659	0.719	1.1039	1.5695	1.0279	2.347	1.887	0.968
	R_L ($C_0=0.1$ g/L)	0.9578	0.9382	0.9329	0.9006	0.8643	0.9068	0.8099	0.8413	0.9117
	R^2	0.985	0.988	0.933	0.979	0.987	0.550	0.985	0.930	0.391
Freundlich	K_F (g/g)(l/g) ^{1/n}	0.365	0.365	0.873	0.354	0.615	1.081	0.470	0.906	2.662
	n_F	1.544	1.842	1.436	2.165	1.768	1.461	2.284	1.630	1.438
	R^2	0.6656	0.738	0.976	0.638	0.896	0.989	0.778	0.971	0.983
Dubinin-Radushkevich	Q_m (g/g)	0.205	0.181	0.464	0.211	0.315	0.785	0.268	0.517	0.863
	β (mmol ² /J ²)	1.86x10 ⁻⁸	1.14x10 ⁻⁸	1.76x10 ⁻⁸	0.88x10 ⁻⁸	1.12x10 ⁻⁸	1.61x10 ⁻⁸	0.68x10 ⁻⁸	1.23x10 ⁻⁸	1.51x10 ⁻⁸
	E (KJ/mol ¹)	5.185	6.623	5.330	7.538	6.681	5.573	8.574	6.376	5.754
	R^2	0.409	0.479	0.857	0.391	0.699	0.975	0.521	0.857	0.988

263 **Table 2** Adsorption capacity of chemically treated rice husk for different dyes

Treatment of rice husk	Dye	Adsorption capacity	References
Without any pretreatment	Indigo carmine	65.90 mg/g	Lakshmi et al. (2009)
Citric acid	Direct F. Scarlet	~13 mg/g	Abdelwahab et al. (2005)
H ₃ PO ₄	5G blue dye	3.84 mg/g	Costa Junior et al. (2018)
Thermally treated at 75 °C	Methylene blue	24.48 mg/g	Quansah et al. (2020)
	Crystal violet	25.46 mg/g	Quansah et al. (2020)
Oxalic acid	Methylene blue	53.2 mg/g	Zou et al. (2011)
	Malachite green	54.0 mg/g	Zou et al. (2011)
Sodium hydroxide under pressure	Crystal violet	44.9 mg/g	Chakraborty et al. (2011)
	Safranine	37.9 mg/g	Chowdhury et al. (2012)
	Malachite green	12.6 mg/g	Chowdhury et al. (2011)
HCl	Everdirect Orange-3GL	29.9 mg/g	Safa et al. (2011)
	Direct Blue-67	37.9 mg/g	Safa et al. (2011)
EDTA	Basic blue 3	3.3 mg/g	Ong et al. (2007)
	Reactive orange 16	24.9 mg/g	Ong et al. (2007)
Acetic acid and hydrogen peroxide	Rhodamine B	5.87×10^{-5} mg/g	Jain et al. (2007)
Rise husk ash without pretreatment	Brilliant green	26.20 mg/g	Mane et al. (2007)
Effluent from alkaline scouring of cotton	Congo red	149.1 mg/g	This work

264

265 **Table 3** Adsorption capacity of Congo red onto different renewable adsorbents

Adsorbent	Adsorption capacity of Congo red	References
Rice hull ash	171.00 mg/g	Chou et al. (2001)
Powder from eucalyptus leaf	29.68 mg/g	Kumari et al (2019)
Pellet of rice hull ash, kaolin and starch	21.0 mg/g	Chou et al. (2001)
Hydrothermally treated Shiitake mushroom	217.86 mg/g	Yang et al. (2019)
Egg shell membrane	117.65 mg/g	Parvin et al (2019)
Sulfidogenic sludge	238.90 mg/g	Rasool and Lee (2013)

Raw pine cone	32.65 mg/g	Dawood and Sen (2012)
Acid-treated pine cone	40.19 mg/g	Dawood and Sen (2012)
Clay materials	4.3- 19.9 mg/g	Vimonses et al. (2009)
Rice husk	14.00 mg/g	Han et al. (2008)
Calcium rich - fly ash	4.47×105 mol/g	Acemioğlu (2004)
Ca-bentonite	107.41 mg/g	Lian et al. (2009)
Coir pith	6.72 mg/g	Namasivayam and Kavitha (2002)
Orange peel	22.44 mg/g	Namasivayam et al. (1996)
Powder from jute stick	35.70 mg/g	Panda et al. (2008)
Dead <i>Aspergillus niger</i> fungus	14.72 mg/g	Fu and Viraraghavan (2002)
Modified rice husk	149.1 mg/g	This work

266

267 *Adsorption kinetics*

268 The amount of adsorbed CR versus the contact time serves to evaluate the adsorption kinetics. It
269 is essential for the examination of the mechanism by which the adsorption occurs. Pseudo-first-
270 order (Eq. 12), pseudo-second-order (Eq. 13), Elovich (Eq. 14), intraparticle diffusion (Eq. 15) as
271 well as the liquid film diffusion (Eq. 16) models are employed in this study to evaluate the
272 kinetics of adsorption.

$$273 \quad \log(Q_e - Q_t) = \log Q_e - \frac{k_1}{2.303} t \quad (12)$$

$$274 \quad \frac{t}{Q_t} = \frac{1}{k_2 Q_e^2} + \frac{1}{Q_e} t \quad (13)$$

$$275 \quad Q_t = \frac{1}{\beta} \ln(\alpha\beta) + \frac{1}{\beta} \ln t \quad (14)$$

$$276 \quad Q_t = k_i t^{0.5} \quad (15)$$

$$277 \quad \ln(1 - F) = -k_{fd} t \quad (16)$$

k_1 (min^{-1}) and k_2 (g/gmin) are rate constants for pseudo-first and pseudo-second-order, respectively, Q_e (g/g) is amount of adsorbate at equilibrium and Q_t (g/g) is amount of adsorbate at time t , α (g/gmin) is the initial sorption rate constant, β (g/g) is desorption constant, k_i ($\text{g/gmin}^{0.5}$) is intraparticle diffusion rate constant, F is fractional attainment of equilibrium, equal to Q_t/Q_e and K_{fd} (min^{-1}) is liquid film diffusion rate constant.

The calculated kinetic parameters are presented in Table 4. The coefficients of correlation of the pseudo-second-order vary from 0.9998 to 1, while those of the pseudo-first-order range between 0.1513 and 0.9128. The substantially higher coefficients of correlation of the pseudo-second-order and the small differences between $Q_{m, \text{exp}}$ and $Q_{m, \text{cal}}$ of this kinetic model, reinforce its applicability. The plots t/Q_t versus t of 0.1 to 0.5 g/L initial CR concentration, for 10 g/L adsorbent dosage tested at 298 K show excellent linearity (Fig. 1 in Supplementary file).

Pseudo-second-order rate constant k_2 is calculated from the intercept of the slope t/Q_t versus t . Since k_2 has the highest R^2 , it is then used for calculation of the initial adsorption rate h according to Eq. (17). The k_2 values increase along the adsorbent dosage and temperature of adsorption testing. Increased k_2 at a higher temperature (Table 4) indicates the endothermic process of the adsorption of CR onto ERH when the temperature of adsorption increases (Chowdhury et al. 2011). The h value, which is the initial adsorption rate, is useful for creating a continuous adsorption system in which a higher initial adsorption rate is crucial for the proper selection of the adsorbents. Higher h values at elevated temperature and higher ERH dosage favor building a continuous adsorption system filled with more ERH that will work at a higher temperature.

$$h = k_2 Q_e^2 \quad (17)$$

300 The Elovich model is another kinetic model used to examine adsorption/desorption kinetic on the
301 solid adsorbent. This equation assumes the heterogeneous nature of the solid surface active sites
302 that exhibit different activation energies for chemisorption (Chowdhury et al. 2011). The
303 correlation coefficients R^2 determined from the Q_t vs $\ln(t)$ plots are in the range between 0.4579
304 and 0.9065 (Table 4). In this model, the initial adsorption rate is presented as the constant α ,
305 while β is the surface coverage or desorption constant. These constants are temperature-
306 dependent. An increase in temperature is accompanied by an increase in α and β , indicating that
307 both the initial adsorption and the available adsorption area would increase. Moreover, the
308 adsorbent dosage also influences the values of α and β . More rice husk, at the same initial dye
309 concentration, increases both α and β constants.

310 During the process of dye adsorption onto some adsorbent, the diffusion of the dye from the bulk
311 dye solution to the surface of the rice husk, and the transport from the surface into the solid rice
312 husk may have occurred. Since these mechanisms follow intraparticle diffusion and liquid film
313 diffusion models, these models have been explored to rate CR adsorption onto ERH. The liquid
314 film diffusion parameters calculated from the plots of $\ln(1-F)$ versus t have R^2 between 0.1239
315 and 0.8943 with intercepts ranging from -1.1044 to -4.8625 and k_{fd} ranging from -0.0019 to –
316 0.0071 min^{-1} (Table 4). On the other hand, the intraparticle diffusion parameters calculated from
317 the plots Q_t versus $t^{0.5}$ have R^2 between 0.1238 and 0.5339, intercepts between 0.0097 and
318 0.0837 and k_i ranging from 0.0001 to $0.0073 \text{ g/gmin}^{0.5}$. Both models show that the intercepts of
319 linear plots did not pass through the origin. Theoretically, if one of these models intends to be the
320 sole rate-determining step, the plots must have zero intercept. Since the linear plots of both
321 models do not meet this requirement, the applicability of these models in the present adsorption

system is limited. In that case, during the interaction of CR with ERH, surface adsorption and intraparticle diffusion could both happen.

Table 4 Pseudo-first-order and pseudo-second-order kinetic, Elovich, liquid film diffusion and intraparticle diffusion kinetic parameters for adsorption of Congo red onto ERH

Kinetics	Co g L ⁻¹	Parameters	Temperature (°C)								
			298			323			343		
			Adsorbent dosage (g/L)			Adsorbent dosage (g/L)			Adsorbent dosage (g/L)		
			10	20	40	10	20	40	10	20	40
Pseudo First order	0.1	Q _{m, exp} (g/g)	0.0423	0.0243	0.0122	0.0476	0.0244	0.0123	0.0480	0.0242	0.0122
		Q _{m, calc} (g/g)	0.0070	0.0007	0.0001	0.0047	0.0005	0.0001	0.0035	0.0002	0.0000
		K ₁ (1/min)	0.0094	0.0094	0.0035	0.0085	0.0039	0.0014	0.0092	0.0076	0.0028
		R ²	0.7968	0.4086	0.1513	0.6901	0.3196	0.3043	0.7260	0.5717	0.3854
	0.2	Q _{m, exp} (g/g)	0.0643	0.0455	0.0245	0.0807	0.0483	0.0246	0.0884	0.0480	0.0245
		Q _{m, calc} (g/g)	0.0168	0.0038	0.0006	0.0101	0.0014	0.0003	0.0083	0.0013	0.0002
		K ₁ (1/min)	0.0101	0.0085	0.0060	0.0122	0.0090	0.0030	0.0117	0.0071	0.0058
		R ²	0.9025	0.4530	0.3742	0.6355	0.4318	0.3051	0.6497	0.4875	0.4069
	0.3	Q _{m, exp} (g/g)	0.0740	0.0601	0.0365	0.0907	0.0707	0.0368	0.1183	0.0728	0.0367
		Q _{m, calc} (g/g)	0.0162	0.0093	0.0011	0.0139	0.0079	0.0009	0.0340	0.0038	0.0003
		K ₁ (1/min)	0.0122	0.0157	0.0136	0.0115	0.0120	0.0069	0.0663	0.0092	0.0037
		R ²	0.9128	0.8210	0.5948	0.7789	0.7302	0.5402	0.8485	0.6027	0.3539
	0.4	Q _{m, exp} (g/g)	0.0849	0.0663	0.0480	0.0952	0.0838	0.0489	0.1266	0.0925	0.0489
		Q _{m, calc} (g/g)	0.0240	0.0090	0.0035	0.0129	0.0076	0.0012	0.0112	0.0073	0.0007
		K ₁ (1/min)	0.0111	0.0099	0.0111	0.0131	0.0129	0.0076	0.0117	0.0097	0.0071
		R ²	0.9090	0.6277	0.6477	0.8233	0.6836	0.4537	0.7062	0.6257	0.4877
	0.5	Q _{m, exp} (g/g)	0.0918	0.0765	0.0580	0.1153	0.0993	0.0609	0.1491	0.1127	0.0611
		Q _{m, calc} (g/g)	0.0245	0.0107	0.0056	0.0106	0.0122	0.0023	0.0149	0.0094	0.0010
		K ₁ (1/min)	0.0104	0.0120	0.0092	0.0117	0.0108	0.0083	0.0124	0.0111	0.0064
		R ²	0.8616	0.6595	0.5333	0.6938	0.6140	0.5142	0.6967	0.6084	0.4579
Pseudo Second order	0.1	Q _{m, exp} (g/g)	0.0423	0.0243	0.0122	0.0476	0.0244	0.0123	0.0480	0.0242	0.0122
		Q _{m, calc} (g/g)	0.0426	0.0244	0.0122	0.0478	0.0243	0.0122	0.0489	0.0242	0.0122
		K ₂ (g/g min)	2.5031	11.7048	213.27	3.6212	48.0349	544.69	5.4947	81.2551	792.0172
		h (g/g min)	0.00454	0.00695	0.0317	0.0083	0.0284	0.0815	0.0131	0.0476	0.1176
		R ²	0.9999	0.9999	1	0.9998	1	1	0.9999	1	1
	0.2	Q _{m, exp} (g/g)	0.0643	0.0455	0.0245	0.0807	0.0483	0.0246	0.0884	0.0480	0.0245
		Q _{m, calc} (g/g)	0.0650	0.0458	0.0245	0.0816	0.0484	0.0245	0.0890	0.0480	0.0245
		K ₂ (g/g min)	1.0589	2.8235	27.143	0.9756	7.2143	99.52	1.4852	13.5242	124.6615
		h (g/g min)	0.00447	0.00591	0.0163	0.0065	0.0169	0.0598	0.0117	0.0312	0.0748
		R ²	0.9999	0.9999	1	0.9998	1	1	0.9999	1	1
	0.3	Q _{m, exp} (g/g)	0.0740	0.0601	0.0365	0.0907	0.0707	0.0368	0.1183	0.0728	0.0367
		Q _{m, calc} (g/g)	0.0747	0.0607	0.0366	0.0915	0.0712	0.0368	0.1191	0.0730	0.0367
		K ₂ (g/g min)	1.910	1.6263	9.5558	1.1164	1.8351	20.999	1.2040	4.3465	84.8913
		h (g/g min)	0.00665	0.00597	0.0128	0.0093	0.0093	0.0284	0.0170	0.0231	0.1141
		R ²	0.9999	0.9999	1	0.9999	0.9999	1	0.9999	1	1
	0.4	Q _{m, exp} (g/g)	0.0849	0.0663	0.0480	0.0952	0.0838	0.0489	0.1266	0.0925	0.0489
		Q _{m, calc} (g/g)	0.0859	0.0669	0.0482	0.0959	0.0844	0.0489	0.1273	0.0929	0.0489
		K ₂ (g/g min)	0.7276	1.3883	3.8688	1.3306	1.6509	12.234	1.2279	2.0108	27.7785
		h (g/g min)	0.00537	0.00621	0.0089	0.0122	0.0117	0.0293	0.0199	0.0173	0.0664
		R ²	0.9998	0.9999	1	0.9999	0.9999	1	0.9999	1	1
	0.5	Q _{m, exp} (g/g)	0.0918	0.0765	0.0580	0.1153	0.0993	0.0609	0.1491	0.1127	0.0611
		Q _{m, calc} (g/g)	0.0931	0.0774	0.0583	0.1161	0.1003	0.0610	0.1502	0.1133	0.0611
		K ₂ (g/g min)	0.6251	0.9624	2.3022	1.1533	0.9186	6.3240	0.8527	1.3768	19.2968
		h (g/g min)	0.00541	0.00577	0.0078	0.0155	0.0092	0.0235	0.0192	0.0177	0.0720

		R ²	0.9997	0.9998	0.9999	0.9999	0.9999	1	0.9999	1	1
Elovich	0.1	α (g/g min)	0.0225	0.0316	0.0894	0.0410	0.1475	0.1781	0.0835	0.2119	0.1781
		β (g/g)	169.49	322.58	769.23	158.73	384.61	833.33	166.67	400.00	833.33
		R ²	0.8476	0.7309	0.5261	0.7842	0.561	0.4636	0.7140	0.5169	0.4579
	0.2	α (g/g min)	0.0217	0.0247	0.0804	0.0266	0.0808	0.2389	0.0516	0.1709	0.2804
		β (g/g)	107.53	158.73	357.14	84.745	166.67	400.00	81.967	181.82	400.00
		R ²	0.8977	0.8327	0.6296	0.8781	0.7063	0.5066	0.8270	0.6117	0.4801
	0.3	α (g/g min)	0.0319	0.0276	0.0662	0.0441	0.0437	0.1630	0.0813	0.1335	0.3606
		β (g/g)	95.238	117.65	222.22	78.741	103.09	243.90	62.500	112.36	263.16
		R ²	0.8670	0.8674	0.7011	0.8619	0.8300	0.5917	0.8200	0.7031	0.4984
	0.4	α (g/g min)	0.0241	0.0272	0.0451	0.0576	0.0511	0.1607	0.0886	0.0939	0.3576
		β (g/g)	80.000	105.26	158.73	76.336	86.207	178.57	58.139	83.33	192.31
		R ²	0.9065	0.8703	0.7861	0.8305	0.8182	0.6324	0.8053	0.7827	0.5351
	0.5	α (g/g min)	0.0224	0.0221	0.0375	0.0626	0.0394	0.1123	0.0813	0.0918	0.3658
		β (g/g)	72.464	86.956	126.58	61.728	69.930	133.33	47.847	67.114	151.52
		R ²	0.8983	0.8730	0.8295	0.8119	0.8707	0.6866	0.8271	0.8091	0.5574
Liquid film diffusion	0.1	intercept	-1.376	-3.0671	-4.5824	-2.0285	-3.3218	-3.974	-2.3043	-4.0275	-4.8625
		K _{fd} (min ⁻¹)	-0.0062	-0.0046	-0.0022	-0.004	-0.0022	-0.0012	-0.0044	-0.0039	-0.0019
		R ²	0.666	0.42	0.1663	0.6607	0.2814	0.1239	0.6812	0.4722	0.1854
	0.2	intercept	-1.176	-2.1745	-3.298	-1.8155	-3.0959	-3.7368	-2.0718	-3.1518	-4.3885
		K _{fd} (min ⁻¹)	-0.0046	-0.004	-0.0031	-0.0056	-0.0043	-0.0019	-0.0054	-0.0036	-0.0031
		R ²	0.8822	0.4656	0.3599	0.641	0.4346	0.2315	0.6474	0.4532	0.3329
	0.3	intercept	-1.327	-1.6304	-3.0425	-1.6373	-1.9123	-3.2495	-1.0882	-2.5725	-4.2502
		K _{fd} (min ⁻¹)	-0.0055	-0.0071	-0.0063	-0.0053	-0.0055	-0.0035	-0.029	-0.0043	-0.0023
		R ²	0.8936	0.8158	0.5894	0.7674	0.7199	0.4741	0.8543	0.579	0.2538
	0.4	intercept	-1.1044	-1.7508	-2.2821	-1.7492	-2.104	-3.2266	2.1207	-2.2223	-3.7363
		K _{fd} (min ⁻¹)	-0.005	-0.0046	-0.0052	-0.0059	-0.0059	-0.0038	-0.0054	-0.0045	-0.0037
		R ²	0.8943	0.6286	0.6381	0.8076	0.6793	0.4364	0.6934	0.6132	0.4327
	0.5	intercept	-1.1541	-1.7181	-2.0518	-2.0873	-1.8319	-2.8644	2.0112	-2.1746	-3.6082
		K _{fd} (min ⁻¹)	-0.0047	-0.0055	-0.0043	-0.0054	-0.005	-0.004	-0.0057	-0.0051	-0.0034
		R ²	0.8487	0.6634	0.5556	0.6835	0.6185	0.4954	0.691	0.6075	0.4076
Intraparticle diffusion	0.1	intercept	0.0232	0.0158	0.0094	0.0289	0.0183	0.0097	0.0325	0.0187	0.0097
		K _i (g/g min ^{0.5})	0.0007	0.0004	0.0001	0.0008	0.0003	0.0001	0.0007	0.0002	0.0001
		R ²	0.4284	0.2956	0.1543	0.3500	0.1751	0.1261	0.2831	0.1513	0.1238
	0.2	intercept	0.0313	0.0256	0.0176	0.0397	0.0324	0.019	0.0501	0.0347	0.0193
		K _i (g/g min ^{0.5})	0.0012	0.0008	0.0003	0.0016	0.0007	0.0002	0.0015	0.0006	0.0002
		R ²	0.509	0.4088	0.216	0.4904	0.2736	0.1463	0.4008	0.2102	0.1348
	0.3	intercept	0.0388	0.032	0.0247	0.0488	0.0403	0.0271	0.0688	0.049	0.0286
		K _i (g/g min ^{0.5})	0.0014	0.0011	0.0005	0.0016	0.0012	0.0004	0.002	0.001	0.0004
		R ²	0.4577	0.4559	0.2700	0.4669	0.4024	0.193	0.3899	0.273	0.1412
	0.4	intercept	0.0395	0.0344	0.0295	0.0541	0.0481	0.035	0.0745	0.0572	0.0373
		K _i (g/g min ^{0.5})	0.0073	0.0012	0.0007	0.0016	0.0014	0.0006	0.0021	0.0014	0.0005
		R ²	0.5311	0.4656	0.3498	0.4039	0.3904	0.2192	0.3744	0.347	0.162
	0.5	intercept	0.0412	0.0366	0.0333	0.065	0.0513	0.0415	0.0837	0.0672	0.046
		K _i (g/g min ^{0.5})	0.0019	0.0015	0.001	0.002	0.0019	0.0008	0.0026	0.0018	0.0007
		R ²	0.5339	0.4918	0.4013	0.3911	0.4663	0.2583	0.4031	0.3758	0.1732

327

328

329 *Activation parameters*

330 The activation energy Ea is a crucial parameter for determining the origin of the sorption forces
331 that bind the sorbate and sorbent. Since physical adsorption contains weak forces, Ea is lower
332 than 40 KJ/mol. As chemical adsorption involves much stronger forces than physical adsorption,

Ea is higher than 40 KJ/mol. The activation energy for adsorption of CR onto ERH is determined by the Arrhenius equation (Eq. 17) (Zhu et al 2009).

$$\ln k = \ln A - \frac{E_a}{RT} \quad (17)$$

k is the rate constant, A is the Arrhenius constant, Ea (kJ/mol) is the activation energy, R (8.314 J/mol K) is the gas constant and T (K) is the temperature. In this study, Ea was obtained from the slope of the linear plot of $\ln k_2$ (calculated from the pseudo-second-order kinetic model) versus 1/T.

The Eyring equation (Eq. 18) was also used to determine the standard enthalpy of activation ($\Delta H^\#$), the entropy of activation ($\Delta S^\#$) and free energy of activation ($\Delta G^\#$) in the sorption process (Saha and Chowdhury 2011; Chowdhury et al. 2010):

$$\ln \frac{k}{T} = \ln \frac{k_B}{h} + \frac{\Delta S^\#}{R} - \frac{\Delta H^\#}{RT} \quad (18)$$

where k is the rate constant, T is the temperature (K), k_B is the Boltzman constant (1.3807×10^{-23} J/K), h is the Planck constant (6.6261×10^{-34} J s) and R is the gas constant. By plotting $\ln (k_2/T)$ vs 1/T, the values of $\Delta H^\#$ and $\Delta S^\#$ were determined from the slope and intercept of the plot, respectively. The free energy of activation ($\Delta G^\#$) was calculated by using these values in the following equation:

$$\Delta G^\# = \Delta H^\# - T\Delta S^\# \quad (19)$$

The results of Eyring's thermodynamic parameters and energy of activation shown in Table 5 indicate positive $\Delta G^\#$, positive $\Delta H^\#$, and negative $\Delta S^\#$. Positive $\Delta G^\#$ suggests a requirement of energy to convert reactants into products during the adsorption reaction. The positive $\Delta H^\#$ indicates an endothermic reaction. The negative $\Delta S^\#$ suggests an associative mechanism of CR adsorption onto ERH in which dye molecules are intact. The negative $\Delta S^\#$ values are also an indication of a lack of significant change in the adsorbent's internal structures during the adsorption (Chowdhury et al. 2011; Chowdhury et al. 2012), meaning the ERH can be reused. The obtained Ea values for the adsorption of CR onto ERH, for all initial concentrations (g/L) and adsorbent mass (g), suggest that the adsorption process is, in fact, physisorption.

360 **Table 5** Activation parameters for adsorption of Congo red onto ERH

Model	Initial conc (g/L)	Parameters	Temperature (K)								
			298			323			343		
			Adsorbent dosage (g/L)			Adsorbent dosage (g/L)			Adsorbent dosage (g/L)		
			10	20	40	10	20	40	10	20	40
Eyring	0.1	$\Delta G^\#$ (kJ/mol)	70.77	66.70	59.58	75.70	69.40	62.70	79.65	71.56	65.18
		$\Delta H^\#$ (kJ/mol)	11.98	34.54	22.49						
		$\Delta S^\#$ (J/mol K)	-197.26	-107.93	-124.47						
		Ea (kJ/mol)	14.64	37.18	25.14						
		R ²	0.9809	0.9763	0.9807						
	0.2	$\Delta G^\#$ (kJ/mol)	73.03	70.39	64.53	78.89	74.04	67.68	83.58	76.95	70.20
		$\Delta H^\#$ (kJ/mol)	3.108	26.96	27.03						
		$\Delta S^\#$ (J/mol K)	-234.63	-145.76	-125.84						
		Ea (kJ/mol)	5.76	29.61	29.68						
		R ²	0.4734	0.9999	0.9221						
	0.3	$\Delta G^\#$ (kJ/mol)	72.595	72.09	67.72	78.90	76.88	70.26	83.95	80.72	72.29
		$\Delta H^\#$ (kJ/mol)	-2.61	14.92	37.47						
		$\Delta S^\#$ (J/mol K)	-252.35	-191.84	-101.51						
		Ea (kJ/mol)	0.045	17.57	40.12						
		R ²	0.0009	0.7593	0.9323						
	0.4	$\Delta G^\#$ (kJ/mol)	73.57	72.20	69.64	79.08	77.90	72.58	83.49	82.46	74.93
		$\Delta H^\#$ (kJ/mol)	7.89	4.24	34.55						
		$\Delta S^\#$ (J/mol K)	-220.40	-228.03	-117.74						
		Ea (kJ/mol)	10.54	6.89	37.20						
		R ²	0.7331	0.9803	1						
	0.5	$\Delta G^\#$ (kJ/mol)	73.86	73.25	71.08	79.70	79.10	73.94	84.38	83.78	76.23
		$\Delta H^\#$ (kJ/mol)	4.17	3.54	36.95						
		$\Delta S^\#$ (J/mol K)	-233.84	-233.94	-114.51						
		Ea (kJ/mol)	6.82	6.18	39.60						
		R ²	0.3519	0.5529	0.9827						

362 *Adsorption thermodynamics*

363 Van Hoff's classical equation (Eq. 20) is used to calculate the change in Gibbs free energy which
 364 is crucial for determining the spontaneity of a process (Saha and Chowdhury 2011):

365
$$\Delta G^0 = - RT \ln K_C \quad (20)$$

366 where R (J/mol K) is the universal gas constant, T (K) is the absolute temperature and K_C is the
 367 distribution coefficient for adsorption defined by the Eq. 21:

368
$$K_C = \frac{Ca}{Ce} \quad (21)$$

369 in which Ca (g/L) is the equilibrium dye concentration on the adsorbent and Ce (g/L) is the
 370 equilibrium dye concentration in solution. The enthalpy (ΔH^0) and entropy (ΔS^0) were calculated
 371 using the Eq. 22.

$$\Delta G^0 = \Delta H^0 - T\Delta S^0 \quad (22)$$

By plotting ΔG^0 vs T, the values of ΔH^0 and ΔS^0 were determined from the intercept and slope of the plot, respectively. The calculated values of the thermodynamic parameters for the adsorption of CR onto ERH at all temperatures are listed in Table 6.

Table 6 Thermodynamic parameters for adsorption of Congo red onto ERH.

Model	Initial con. (g/L)	Parameters	Temperature (K)								
			298			323			343		
			Adsorbent dosage (g/L)			Adsorbent dosage (g/L)			Adsorbent dosage (g/L)		
			10	20	40	10	20	40	10	20	40
Thermo dynamic	0.1	K_c	5.46	34.16	38.78	19.41	34.79	44.93	39.81	30.06	38.79
		ΔG^0 (kJ/mol)	-4.21	-8.74	-9.06	-7.96	-9.53	-10.22	-10.51	-9.70	-10.43
		ΔH^0 (kJ/mol)	37.55	2.37	0.0780						
		ΔS^0 (J/mol K)	140.4	21.7	31.07						
		R^2	0.9978	0.9188	0.9046						
	0.2	K_c	1.79	9.91	45.51	4.17	27.98	50.28	7.60	23.39	47.78
		ΔG^0 (kJ/mol)	-1.45	-5.68	-9.46	-3.84	-8.95	-10.52	-5.78	-8.99	-11.03
		ΔH^0 (kJ/mol)	27.24	16.49	0.955						
		ΔS^0 (J/mol K)	96.2	75.8	35.14						
		R^2	1	0.8121	0.9811						
	0.3	K_c	0.97	4.03	36.45	1.53	16.39	50.72	3.73	32.33	43.12
		ΔG^0 (kJ/mol)	0.067	-3.45	-8.91	-1.14	-7.51	-10.54	-3.76	-9.91	-10.73
		ΔH^0 (kJ/mol)	25.20	39.40	3.29						
		ΔS^0 (J/mol K)	83.4	144.3	41.56						
		R^2	0.9269	0.9932	0.8726						
	0.4	K_c	0.74	1.96	23.84	0.91	5.17	42.96	1.72	12.24	43.44
		ΔG^0 (kJ/mol)	0.76	-1.67	-7.86	0.258	-4.41	-10.1	-1.55	-7.14	-10.76
		ΔH^0 (kJ/mol)	15.89	34.53	11.45						
		ΔS^0 (J/mol K)	50.0	121.2	65.42						
		R^2	0.8613	0.996	0.9429						
	0.5	K_c	0.58	1.57	12.66	0.86	3.85	36.88	1.48	9.12	42.10
		ΔG^0 (kJ/mol)	1.35	-1.13	-6.29	0.418	-3.62	-9.69	-1.11	-6.30	-10.66
		ΔH^0 (kJ/mol)	17.59	33.08	22.88						
		ΔS^0 (J/mol K)	54.1	114.4	98.83						
		R^2	0.9593	0.9928	0.9411						

The negative ΔG^0 values for most of the tested samples indicate a spontaneous adsorption process of CR onto ERH. The positive ΔG^0 for ERH tested at 10 g/L adsorption dosage and 0.3, 0.4, and 0.5 g/L initial CR concentration show non-spontaneous adsorption of these samples. The inverse correlation between ΔG^0 and the temperature imply more favorable adsorption at high temperatures. The positive ΔH^0 indicates an endothermic reaction of adsorption. The positive values of ΔS^0 show the modified rice husk's affinity for CR, an increase in the degree of freedom

of the adsorbed dye, and increased randomness at the solid/solution interface (Gedam et al. 2019).

Isosteric heat of adsorption

Isosteric heat of adsorption (ΔH_X , KJ/mol), presented as the heat of adsorption at a constant amount of adsorbed adsorbate, is of great importance for obtaining an optimized adsorption process. The Clausius–Clapeyron equation is used to estimate this thermodynamic quantity (Simsek and Beker 2014).

$$\frac{d(\ln C_e)}{dT} = -\frac{\Delta H_X}{RT^2} \quad (23)$$

In the present study, the calculations for ΔH_X are made at constant surface coverage of $Q_e = 0.04, 0.06, 0.08$ and 0.1 g/g. The $\ln$ of equilibrium concentration (C_e) at a constant amount of adsorbed dye plotted versus $1/T$ is used to determine ΔH_X from the slope of the plots. In the case of physical adsorption, ΔH_X should be below 80 KJ/mol while for chemisorptions, the ΔH_X values range between 80 and 400 KJ/mol (Saha and Chowdhury 2011). The calculated values of isosteric heat of adsorption are presented in Table 7. The values between 2.71 and 72.60 KJ/mol mean physical adsorption of CR onto ERH.

Table 7 Isosteric heat of adsorption of Congo red onto ERH

Model	Constant Surface Coverage Q_e (g/g)	Parameters	Adsorbent dosage (g/L)		
			10	20	40
Clausius-Clapeyron	0.04	ΔH_X (KJ/mol)	21.11	16.32	1.055
		R^2	0.9976	0.6938	0.331
	0.06	ΔH_X (KJ/mol)	15.91	35.98	3.60
		R^2	0.8834	0.9944	0.3526

	0.08	ΔH_x (KJ/mol)	8.11	27.96	11.49
		R^2	0.8279	0.9868	0.8458
	0.1	ΔH_x (KJ/mol)	8.26	25.45	22.49
		R^2	0.931	0.9787	0.9027

400

401 *Mechanism of adsorption of Congo red onto ERH*

402 The results presented above showed physical adsorption of Congo red onto the ERH. Lower
403 values of D-R free energy than 8 KJ/mol, lower energy of activation (E_a) than 40 KJ/mol, and
404 the isosteric heat of adsorption (ΔH_x) below 80 KJ/mol confirm the physical adsorption of CR
405 onto ERH. Congo red is a direct dye that presents Na-salt of diazo dye containing two amino and
406 two sulfonic groups responsible for the creation of hydrogen bonds and determination of the CR
407 solubility, respectively. Theoretically, the adsorption of the direct dye onto cellulose occurs with
408 physical hydrogen bonds (Broadbend, 2001), which confirms the aforementioned statement.
409 Considering the information mentioned above, the proposed schematic of adsorption of CR onto
410 ERH is presented in Fig. 3.

Fig. 3 Mechanism of adsorption of Congo red onto ERH

4. Conclusion

Equilibrium, kinetic, thermodynamic aspects and mechanism of Congo red adsorption onto rice husk treated with effluent from the cotton scouring are explored. The initial dye concentration, contact time, the mass of rice husk and temperature are crucial in determining the adsorption efficiency of treated rice husk. Adsorption of Congo red follows the Langmuir model, when the mass of rice husk is lower, and the Freundlich model when the dosage is high. The dye removal increases with an increase in adsorbent dose, but the adsorption capacity of the ERH, performed at all temperatures, decreases when the adsorbent mass increases. The maximum adsorption capacity of 149.1 mg CR per gram ERH was obtained with 10 g/L ERH at 70°C, which is one of

the more remarkable results mentioned in the literature. The activation energy calculated by the Dubinin–Radushkevich isotherm, indicates the physical nature of CR adsorption onto ERH, while the adsorption kinetics follows the pseudo-second-order model. The Energy of activation, standard enthalpy of activation, the entropy of activation and free energy of activation, calculated using the thermodynamic Arrhenius and Eyring equations, have shown the spontaneous endothermic mechanism of adsorption. The isosteric heats of adsorption, estimated by Clausius–Clapeyron equation, with values below 80 KJ/mol, also confirm the physical bonding of the adsorbed CR onto ERH. This modification, performed according to the circular economy concept, acts as a straightforward process for obtaining a cheap adsorbent capable of removing Congo red from an aqueous solution and presents a solid base for creating a continuous column-mode process of rice husk modification and purifying the colored effluent from the textile industry.

Notes

The authors declare no competing financial interest.

Acknowledgments

References

- Abdelwahab O, El Nemr A, El Sikaily A, Khaled A (2005) Use of rice husk for adsorption of direct dyes from aqueous solution: a case study of direct f. scarlet. *Egypt J Aquat Res* 31:1-11.
- Aboamara NM, Mohamed A, Salama A, Osman TA, Khattab A (2018) An effective removal of organic dyes using surface functionalized cellulose acetate/graphene oxide composite nanofibers. *Cellulose* 25:4155–4166. <https://doi.org/10.1007/s10570-018-1870-8>

445 Abu Elella MH, ElHafeez EA, Goda ES, Lee S, Yoon KR (2019) Smart bactericidal filter
 446 containing biodegradable polymers for crystal violet dye adsorption. *Cellulose* 26:9179-9206.
 447 <https://doi.org/10.1007/s10570-019-02698-1>

448 Acemioglu B (2004) Adsorption of Congo red from aqueous solution onto calcium-rich fly ash. *J*
 449 *Colloid Interface Sci* 274:371–379. <https://doi.org/10.1016/j.jcis.2004.03.019>

450 Alam MM, Hossain MA, Hossain MD, Johir MAH, Hossen J, Rahman MS, Zhou JL, Hasan
 451 ATMK, Karmakar AK, Ahmed MB (2020) The potential of rice husk-derived activated carbon:
 452 From synthesis to application. *Processes* 8, 203. <https://doi.org/10.3390/pr8020203>

453 Alaton IA, Teksoy S (2007) Acid dyebath effluent pretreatment using Fenton's reagent: Process
 454 optimization, reaction kinetics and effects on acute toxicity. *Dyes Pigm* 73:31-39.
 455 <https://doi.org/10.1016/j.dyepig.2005.09.027>

456 Batmaz R, Mohammed N, Zaman M, Minhas G, Berry RM, Tam KC (2014) Cellulose
 457 nanocrystals as promising adsorbents for the removal of cationic dyes. *Cellulose* 21:1655–1665.
 458 <https://doi.org/10.1007/s10570-014-0168-8>

459 Blackburn RS (2004) Natural polysaccharides and their interactions with dye molecules:
 460 applications in effluent treatment. *Environ Sci Technol* 38:4905-4909.
 461 <https://doi.org/10.1021/es049972n>

462 Broadbend AD (2001). Basic principles of textile coloration, Society of Dyers and Colorists,
 463 Bradford, West Yorkshire, England.

464 Brown MA, De Vito SC (1993) Predicting azo dye toxicity. *Crit Rev Environ Sci Technol*
 465 23:249-324. <https://doi.org/10.1080/10643389309388453>

466 Chakraborty S, Chowdhury S, Saha PD (2011) Adsorption of Crystal Violet from aqueous
 467 solution onto NaOH-modified rice husk. *Carbohydr Polym* 86:1533-1541.
 468 <https://doi.org/10.1016/j.carbpol.2011.06.058>

469 Chen X (2015) Modeling of experimental adsorption isotherm data. *Information* 6:14-22.
 470 <https://doi.org/10.3390/info6010014>

471 Ching TW, Haritos V, Tanksale A (2018) Ultrasound-assisted conversion of cellulose into
 472 hydrogel and functional carbon material. *Cellulose* 25:2629-2645.
 473 <https://doi.org/10.1007/s10570-018-1746-y>

474 Chong KY, Chia CH, Zakaria S, Sajab MS, Chook SW, Khiew PS (2015) CaCO₃-decorated
 475 cellulose aerogel for removal of Congo Red from aqueous solution. *Cellulose* 22:2683–2691.
 476 <https://doi.org/10.1007/s10570-015-0675-2>

477 Chou KS, Tsai JC, Lo CT (2001) The adsorption of Congo red and vacuum pump oil by rice hull
 478 ash. *Bioresour Technol* 78:217–219. [https://doi.org/10.1016/S0960-8524\(00\)00116-4](https://doi.org/10.1016/S0960-8524(00)00116-4)

479 Chowdhury S, Mishra R, Saha P, Kushwaha P (2011) Adsorption thermodynamics, kinetics and
 480 isosteric heat of adsorption of malachite green onto chemically modified rice husk. *Desalination*
 481 265:159–168. <https://doi.org/10.1016/j.desal.2010.07.047>

482 Chowdhury S, Mishra R, Kushwaha P, Saha P (2012) Removal of safranin from aqueous
 483 solutions by NaOH-treated rice husk: Thermodynamics, kinetics and isosteric heat of adsorption.
 484 *Asia-Pac J Chem Eng* 7:236–249. <https://doi.org/10.1002/apj.525>

485 Chowdhury S, Mishra R, Kushwaha P, Saha P (2010) Sea shell powder as a new adsorbent to
 486 remove Basic Green 4 (Malachite Green) from aqueous solutions: Equilibrium, kinetic and
 487 thermodynamic studies. *Chem Eng Sci* 164:168–177. <https://doi.org/10.1016/j.ces.2010.08.050>

488

489 Ciardelli G, Capannelli G, Bottino A (2001) Ozone treatment of textile wastewater for reuse.
 490 *Water Sci Technol* 44:61-67. <https://doi.org/10.2166/wst.2001.0252>

491 Costa Junior IL, Finger L, Quitaiski PP, Neitzke SM, Besen JV, Correa MK, Mees JBD (2018)
 492 Biosorption of 5G blue reactive dye using waste rice husk. *Eclet Quim* 43:45-58.
 493 <https://doi.org/10.26850/1678-4618eqj.v43.3.2018.p45-58>

494 Dabrowski A (2001). Adsorption -from theory to practice, *Adv Colloid Interface Sci* 93:135-224.
 495 [https://doi.org/10.1016/S0001-8686\(00\)00082-8](https://doi.org/10.1016/S0001-8686(00)00082-8)

496 Dawood S, Sen TK (2012) Removal of anionic dye Congo red from aqueous solution by raw
 497 pine and acid-treated pine cone powder as adsorbent: Equilibrium, thermodynamic, kinetics,
 498 mechanism and process design. *Water Res* 46:1933–1946.
 499 <https://doi.org/10.1016/j.watres.2012.01.009>

500 Easton JR (1995) Colour in Dyehouse Effluent. In P. Copper (Ed.), *Society of Dyers and*
 501 *Colourists*: Bradford, England.

502 El Haddad M (2016) Removal of Basic Fuchsin dye from water using mussel shell biomass
 503 waste as an adsorbent: Equilibrium, kinetics, and thermodynamics. *J Taibah Univ Sci* 10:664–
 504 674. <https://doi.org/10.1016/j.jtusci.2015.08.007>

505 Foo KY, Hameed BH (2010) An overview of dye removal via activated carbon adsorption
 506 process. *Desalination Water Treat* 19:255–274. <https://doi.org/10.5004/dwt.2010.1214>

507 Fu Y, Viraraghavan T (2002) Removal of Congo red from an aqueous solution by fungus
 508 *Aspergillus niger*. *Adv Environ Re* 7:239– 247. [https://doi.org/10.1016/S1093-0191\(01\)00123-X](https://doi.org/10.1016/S1093-0191(01)00123-X)

509 Gedam VV, Raut P, Chahande A, Pathak P (2019) Kinetic, thermodynamics and equilibrium
510 studies on the removal of Congo red dye using activated teak leaf powder. *Appl Water Sci* 9:55.
511 <https://doi.org/10.1007/s13201-019-0933-9>

512 Gorgieva S, Vogrincic R, Kokol V (2019) The effect of membrane structure prepared from
513 carboxymethyl cellulose and cellulose nanofibrils for cationic dye removal. *J Polym Environ*
514 27:318–332. <https://doi.org/10.1007/s10924-018-1341-1>

515 Gupta VK, Carrot PJM, Ribeiro Carrott MML, Suhas (2009) Low-cost adsorbents: Growing
516 approach to wastewater treatment review. *Crit Rev Environ Sci Technol*, 39:783–842.
517 <https://doi.org/10.1080/10643380801977610>

518 Halysh V, Sevastyanova O, Pikus S, Dobelev G, Pasalskiy B, Gun'ko VM, Kartel
519 M (2020) Sugarcane bagasse and straw as low-cost lignocellulosic sorbents for the removal of
520 dyes and metal ions from water. *Cellulose* 27:8181–8197. [https://doi.org/10.1007/s10570-020-](https://doi.org/10.1007/s10570-020-03339-8)
521 03339-8

522 Han R, Ding D, Xu Y, Zou W, Wang Y, Li Y, Zou L (2008) Use of rice husk for the adsorption
523 of Congo red from aqueous solution in column mode. *Bioresour Technol* 99:2938–2946.
524 <https://doi.org/10.1016/j.biortech.2007.06.027>

525 Ivanovska A, Asanovic K, Jankoska M, Mihajlovski K, Pavun L, Kostic M (2020)
526 Multifunctional jute fabrics obtained by different chemical modifications. *Cellulose* 27:8485–
527 8502. <https://doi.org/10.1007/s10570-020-03360-x>

528 Jain R, Mathur M, Sikarwar S, Mittal A (2007) Removal of the hazardous dye Rhodamine B
529 through photocatalytic and adsorption treatments. *J Environ Manage* 85:956–964.
530 <https://doi.org/10.1016/j.jenvman.2006.11.002>

531 Kumari R, Mohanta J, Dey B, Dey S (2019) Eucalyptus leaf powder as an efficient scavenger for
532 Congo red from water: Comprehensive batch and column investigation. *Sep Sci Technol*
533 55:3047–3059. <https://doi.org/10.1080/01496395.2019.1670208>

534 Lakshmi UR, Srivastava VC, Mall ID, Lataye DH (2009) Rice husk ash as an effective adsorbent:
535 Evaluation of adsorptive characteristics for indigo Carmine dye. *J Environ Manage* 90:710–720.
536 <https://doi.org/10.1016/j.jenvman.2008.01.002>

537 Lazic BD, Pejic BM, Kramar AD, Vukcevic MM, Mihajlovski KR, Rusmirovic JD, Kostic MM
538 (2018) Influence of hemicelluloses and lignin content on structure and sorption properties of flax
539 fibers (*Linum usitatissimum L.*). *Cellulose* 25:697–709. [https://doi.org/10.1007/s10570-017-](https://doi.org/10.1007/s10570-017-1575-4)
540 1575-4

541 Lian L, Guo L, Guo C (2009) Adsorption of Congo red from aqueous solutions onto Ca-
542 bentonite. *J Hazard Mater* 161:126–131. <https://doi.org/10.1016/j.jhazmat.2008.03.063>

543 Males L, Fakin D, Bracic M, Gorgieva S (2020) Efficiency of differently processed membranes
 544 based on cellulose as cationic dye adsorbents. *Nanomaterials* 10:1–18.

545 Mane VS, Mall ID, Srivastava VC (2007) Kinetic and equilibrium isotherm studies for
 546 adsorptive removal brilliant green dye from aqueous solution by rice husk ash. *J Environ*
 547 *Manage* 84:90-400. <https://doi.org/10.1016/j.jenvman.2006.06.024>

548 Mladenovic N, Makreski P, Tarbuk A, Grgic K, Boev B, Mirakovski D, Toshikj E, Dimova V,
 549 Dimitrovksi D, Jordanov I (2020) Improved dye removal ability of modified rice husk with
 550 effluent from alkaline scouring based on the circular economy concept. *Processes* 8:653.
 551 <https://doi.org/10.3390/pr8060653>

552 Mohamed RR, Abu Elella MH, Sabaa MW, Saad GR (2018) Synthesis of an efficient adsorbent
 553 hydrogel based on biodegradable polymers for removing crystal violet dye from aqueous
 554 solution. *Cellulose* 25:6513–6529. <https://doi.org/10.1007/s10570-018-2014-x>

555 Namasivayam C, Kavitha D (2002) Removal of Congo red from water by adsorption onto
 556 activated carbon prepared from coir pith, an agricultural solid waste. *Dyes Pigm* 54:47–58.
 557 [https://doi.org/10.1016/S0143-7208\(02\)00025-6](https://doi.org/10.1016/S0143-7208(02)00025-6)

558 Namasivayam C, Muniasamy N, Gayatri K, Rani M, Ranganathan K (1996) Removal of dyes
 559 from aqueous solutions by cellulosic waste orange peel. *Bioresour Technol* 57:37–43.
 560 [https://doi.org/10.1016/0960-8524\(96\)00044-2](https://doi.org/10.1016/0960-8524(96)00044-2)

561 Ndazi BS, Karlsson S, Tesha JV, Nyahumwa CW (2007) Chemical and physical modifications
 562 of rice husks for use as composite panels. *Compos Part A Appl Sci Manuf* 38:925–935.
 563 <https://doi.org/10.1016/j.compositesa.2006.07.004>

564 Omid S, Kakanejadifard A (2018) Eco-friendly synthesis of graphene–chitosan composite
 565 hydrogel as efficient adsorbent for Congo red. *RSC Adv.* 8:12179.
 566 <https://doi.org/10.1039/c8ra00510a>

567 Ong ST, Lee CK, Zainal Z (2007) Removal of basic and reactive dyes using Ethylenediamine
 568 modified rice hull. *Bioresour Technol* 98:2792–2799.
 569 <https://doi.org/10.1016/j.biortech.2006.05.011>

570 Panda GC, Das SK, Guha AK (2008) Jute stick powder as a potential biomass for the removal of
 571 Congo red and rhodamine B from their aqueous solution. *J Hazard Mater* 164:374– 379.
 572 <https://doi.org/10.1016/j.jhazmat.2008.08.015>

573 Parvin S, Biswas BK, Rahman MA, Rahman MH, Anik MS, Uddin MR (2019) Study on
 574 adsorption of Congo red onto chemically modified egg shell membrane. *Chemosphere*
 575 236:124326. <https://doi.org/10.1016/j.chemosphere.2019.07.057>

576 Perez-Ameneiro M, Vecino X, Barbosa-Pereira L, Cruz JM, Moldes AB (2014) Removal of
 577 pigments from aqueous solution by a calcium alginate–grape marc biopolymer: A kinetic study.
 578 Carbohydr Polym 101:954-960. <https://doi.org/10.1016/j.carbpol.2013.09.091>

579 Qiao L, Wang S, Wang T, Yu S, Guo S, Du K (2021) High-strength and low-swelling
 580 chitosan/cellulose microspheres as a high-efficiency adsorbent for dye
 581 removal. Cellulose **28**:9323–9333. <https://doi.org/10.1007/s10570-021-04111-2>

582 Quansah JO, Hlaing T, Lyonga FN, Kyi PP, Hong S.-H, Lee C.-G, Park S.-J (2020) Nascent
 583 Rice Husk as an Adsorbent for Removing Cationic Dyes from Textile Wastewater. Appl Sci
 584 10:3437. <https://doi.org/10.3390/app10103437>

585 Rasool K, Lee DS (2015) Characteristics, kinetics and thermodynamics of Congo red biosorption
 586 by activated sulfidogenic sludge from an aqueous solution. Int J Environ Sci Technol 12:571–
 587 580. <https://doi.org/10.1007/s13762-013-0462-2>

588 Safa Y, Bhatti HN (2011) Adsorptive removal of direct dyes by low cost rice husk: Effect of
 589 treatments and modifications. Afr J Biotechnol 10:3128–3142.
 590 <https://doi.org/10.5897/AJB10.1302>

591 Sanghi R, Verma P (2013) Decolorisation of aqueous dye solutions by low-cost adsorbents: A
 592 review. Color Technol 129:85–108. <https://doi.org/10.1111/cote.12019>

593 Saha P, Chowdhury S (2011) Insight Into Adsorption Thermodynamics. In M. Tadashi (Ed.),
 594 Thermodynamics, 349-364. IntechOpen Limited, London, UK. <https://doi.org/10.5772/13474>

595 Shamsollahi Z, Partovinia A (2019) Recent advances on pollutants removal by rice husk as a bio-
 596 based adsorbent: A critical review. J Environ Manage 246:314–323.
 597 <https://doi.org/10.1016/j.jenvman.2019.05.145>

598 Shao X, Wang J, Liu Z, Hu N, Liu M, Duan C, Zhang R, Quan C (2021) Cellulose based cation-
 599 exchange fiber as filtration material for the rapid removal of methylene blue from wastewater.
 600 Cellulose 28:9355–9367. <https://doi.org/10.1007/s10570-021-04103-2>

601 Sharma P, Kaur H, Sharma M, Sahore, V (2011) A review on applicability of naturally available
 602 adsorbents for the removal of hazardous dyes from aqueous waste. Environ Monit Assess
 603 183:151-195. <https://doi.org/10.1007/s10661-011-1914-0>

604 Simsek EB, Beker U (2014) Equilibrium arsenic adsorption onto metallic oxides: Isotherm
 605 models, error analysis and removal mechanism. Korean J Chem Eng 31:2057-2069.
 606 <https://doi.org/10.1007/s11814-014-0176-2>

607 Tarbuk A, Grgic K, Toshikj E, Domovic D, Dimitrovski D, Dimova V, Jordanov I (2020)
 608 Monitoring of cellulose oxidation level by electrokinetic phenomena and numeric prediction
 609 model. Cellulose 27:3107-3119. <https://doi.org/10.1007/s10570-020-03028-6>

610 Toshikj E, Tarbuk A, Grgic K, Mangovska B, Jordanov I (2019) Influence of different oxidizing
611 systems on cellulose oxidation level: introduced groups versus degradation model. *Cellulose*
612 26:777-794. <https://doi.org/10.1007/s10570-018-2133-4>

613 Toshikj E, Jordanov I, Dimova V, Mangovska B (2017) Influence of Various Pre-Treatment
614 Processes on Selective Oxidation of Cotton Yarns. *AATCC J Res* 4:22–28.
615 <https://doi.org/10.14504/ajr.4.4.4>

616 Toshikj E, Jordanov I, Dimova V, Mangovska B (2016) The influence of non-selective oxidation
617 on differently pre-treated cotton yarns properties. *Medziagotyra* 22:429-434
618 <https://doi.org/10.5755/j01.ms.22.3.12110>

619 Vadivelan V, Vasanth Kumar K (2005) Equilibrium, kinetics, mechanism, and process design for
620 the sorption of methylene blue onto rice husk. *J Colloid Interface Sci* 286:90-100.
621 <https://doi.org/10.1016/j.jcis.2005.01.007>

622 Vimonses V, Lei S, Jin B, Chow CWK, Saint C (2009) Kinetic study and equilibrium isotherm
623 analysis of Congo red adsorption by clay materials. *Chem Eng J* 148:354–364.
624 <https://doi.org/10.1016/j.cej.2008.09.009>

625 Yang K, Li Y, Zheng H, Luan X, Li H, Wang Y, Du Q, Sui K, Li H, & Xia Y (2019) Adsorption
626 of Congo red with hydrothermal treated shiitake mushroom. *Mater Res Express* 7:015103.
627 <https://doi.org/10.1088/2053-1591/ab5ff3>

628 Zhu CS, Wang LP, Chen WB (2009) Removal of Cu(II) from aqueous solution by agricultural
629 by-product: peanut hull. *J Hazard Mater* 168:739-746.
630 <https://doi.org/10.1016/j.jhazmat.2009.02.085>

631 Zou W, Li K, Bai H, Shi X (2011) Enhanced cationic dyes removal from aqueous solution by
632 oxalic acid modified rice husk. *J Chem Eng Data* 56:1882–1891.
633 <https://doi.org/10.1021/je100893h>

Supplementary Files

This is a list of supplementary files associated with this preprint. Click to download.

- [SupplementaryfileCellulose.docx](#)