Sub-thermionic, ultra-high-gain organic transistors and circuits

Zhongzhong Luo

Nanjing University

Boyu Peng

The University of Hongkong

Junpeng Zeng

Nanjing University

Zhihao Yu

Nanjing University of Posts and Telecommunications

Ying Zhao

Institute of Microelectronics, Chinese Academy of Sciences

Jun Xie

Nanjing Drum Tower Hospital, State Key Laboratory of Pharmaceutical Biotechnology, Medical School of Nanjing University

Longfang Lan

Drum Tower Hospital, Nanjing University Medical School

Zhong Ma

Nanjing University

Lijia Pan

Nanjing University <https://orcid.org/0000-0002-8917-7843>

Ke Cao

Xidian University

Yang Lu

City University of Hong Kong, HK <https://orcid.org/0000-0002-9280-2718>

Daowei He

Nanjing University

Hongkai Ning

Nanjing University

Wanqing Meng

Nanjing University

Yang Yang

Nanjing University

Xiaoqing Chen

Nanjing University

Weisheng Li

Nanjing University

Jiawei Wang

Key Laboratory of Microelectronic Devices & Integrated Technology, Institute of Microelectronics, Chinese Academy of Sciences, Beijing 100029, China

Danfeng Pan

Nanjing University

Xuecou Tu

Nanjing University <https://orcid.org/0000-0001-8357-6221>

Wenxing Huo

Tianjin University

Xian Huang

Department of Biomedical Engineering, Tianjin University, 92 Weijin Road, Tianjin 300072

Dongquan Shi

Nanjing Drum Tower Hospital

Ling Li

Key Laboratory of Microelectronic Devices & Integrated Technology, Institute of Microelectronics, Chinese Academy of Sciences, Beijing 100029, China

Ming Liu

Key Laboratory of Microelectronics Devices and Integrated Technology, Institute of Microelectronics of the Chinese Academy of Science

Yi Shi

Nanjing University <https://orcid.org/0000-0002-1082-0315>

Xue Feng

Tsinghua University

Paddy Kwok Leung Chan

University of Hong Kong <https://orcid.org/0000-0002-3166-2192>

Xinran Wang (✉ xrwang@nju.edu.cn)

Nanjing University <https://orcid.org/0000-0002-3975-1667>

Article

Keywords: organic thin-film transistors (OTFTs), van der Waals device fabrication, sub-thermionic OTFT

Posted Date: October 27th, 2020

DOI: <https://doi.org/10.21203/rs.3.rs-92089/v1>

License: © ⓘ This work is licensed under a Creative Commons Attribution 4.0 International License.

[Read Full License](#)

Version of Record: A version of this preprint was published at Nature Communications on March 26th, 2021. See the published version at <https://doi.org/10.1038/s41467-021-22192-2>.

Sub-thermionic, ultra-high-gain organic transistors and circuits

Zhongzhong Luo^{1,10}, Boyu Peng^{2,10}, Junpeng Zeng^{1,10}, Zhihao Yu^{1,3,10}, Ying Zhao⁴, Jun Xie⁵, Longfang Lan⁵, Zhong Ma¹, Lijia Pan¹, Ke Cao⁶, Yang Lu⁶, Daowei He¹, Hongkai Ning¹, Wanqing Meng¹, Yang Yang¹, Xiaoqing Chen¹, Weisheng Li¹, Jiawei Wang⁴, Danfeng Pan¹, Xuecou Tu¹, Wenxing Huo⁷, Xian Huang⁷, Dongquan Shi⁸, Ling Li⁴, Ming Liu⁴, Yi Shi¹, Xue Feng⁹, Paddy K. L. Chan^{2*}, Xinran Wang^{1*}

¹National Laboratory of Solid-State Microstructures, School of Electronic Science and Engineering and Collaborative Innovation Center of Advanced Microstructures, Nanjing University, China

²Department of Mechanical Engineering, The University of Hongkong, Hong Kong, China

³College of Electronic and Optical Engineering, Nanjing University of Posts and Telecommunications, China

⁴Key Laboratory of Microelectronics Devices and Integrated Technology, Institute of Microelectronics, Chinese Academy of Sciences, China

⁵Department of Cardiology, Nanjing Drum Tower Hospital, The Affiliated Hospital of Nanjing University Medical School, China

⁶Department of Mechanical Engineering, City University of Hong Kong, Hong Kong, China

⁷Department of Biomedical Engineering, Tianjin University, China

⁸Department of Sports Medicine and Adult Reconstructive Surgery, Nanjing Drum Tower Hospital, The Affiliated Hospital of Nanjing University Medical School, China

⁹AML, Department of Engineering Mechanics, Center for Flexible Electronics Technology, Tsinghua University, China

¹⁰These authors contribute equally to this work

*Correspondence to: xrwang@nju.edu.cn, pklc@hku.hk.

The development of organic thin-film transistors (OTFTs) with low power consumption and high gain will advance many flexible electronics applications. Here, by combining

28 solution-processed monolayer organic crystal, ferroelectric HfZrO_x gating and van der
29 Waals device fabrication, we realize flexible OTFTs that simultaneously deliver high
30 transconductance and sub-60mV/dec switching, under one-volt operating voltage. The
31 overall optimization of transconductance, subthreshold swing and output resistance leads to
32 transistor intrinsic gain and amplifier voltage gain over 5.3×10^4 and 1.1×10^4 , respectively,
33 which outperform existing technologies using organics, oxides and low-dimensional
34 nanomaterials. We further demonstrate battery-powered, integrated wearable
35 electrocardiogram (ECG) and pulse sensors that can amplify human physiological signal by
36 900 times with high fidelity. The sensors are capable of detecting extremely weak ECG waves
37 (undetectable even by clinical equipment) and diagnosing arrhythmia and atrial fibrillation.
38 Our sub-thermionic OTFT is promising for battery/wireless powered yet performance
39 demanding applications such as electronic skins, radio-frequency identification tags, among
40 many others.

41
42 OTFTs have been extensively pursued for printable and flexible electronic applications owing
43 to their intrinsic flexibility and low-cost processing¹⁻⁶. Many applications, such as Internet of
44 Things (IoT) and wearable electronics, require low-voltage operation while providing high enough
45 current to drive the circuits or high gain to amplify small signals. So far, however, there exist
46 considerable challenges to make OTFT competitive over carbon nanotube films⁷, two-dimensional
47 (2D) materials⁸ and oxides⁹. First, the mobility of organic semiconductors is generally lower than
48 their inorganic counterparts. This leads to low transconductance (g_m) and intrinsic gain ($A_i = g_m \cdot$
49 r_o , where r_o is output resistance). Second, the contact resistance, which partly arises the vertical
50 access resistance from the finite film thickness and disorders introduced by conventional
51 fabrication processes (such as lithography and metal deposition), is a major limiting factor towards
52 high-frequency operation¹⁰. Third, the switching of OTFTs is often far from ideal, which results
53 in large operating voltage (V_{dd})¹¹. Despite significant efforts it remains a challenge to maintain
54 subthreshold swing (SS) close to the Boltzmann thermionic limit ($\ln(10) \frac{k_B T}{q} \approx 60$ mV/dec,
55 where q is elementary charge, k_B is Boltzmann's constant, and T is temperature) over extended
56 range and V_{dd} low enough for complete battery/wireless operation¹²⁻¹⁴.

Recently, negative capacitance (NC) effect from ferroelectric hafnium oxides provides a promising solution for low-power and complementary metal-oxide-semiconductor (CMOS) compatible electronics¹⁵⁻²⁴. Experimentally, NC transistors have been implemented on silicon²⁵⁻²⁷, germanium²⁸ and 2D materials^{29,30}, showing evidence of sub-60 mV/dec switching and enhanced g_m . Moreover, a transition from negative to positive drain induced barrier lowering (DIBL) was theoretically predicted and experimentally observed in NC transistors^{16,29}. This would lead to infinite r_0 and intrinsic gain near the transition region, which is desirable for high-gain analogue amplifiers. However, this unique advantage of NC transistors has not been fully exploited so far.

Here, we combine solution-processed OTFT with ferroelectric HfZrO_x (HZO) gating to demonstrate flexible sub-thermionic organic transistors as well as ultra-high-gain amplifier circuits. Our technology has several unique features. First, the monolayer organic crystal film ensures excellent gate control while maintaining high channel mobility up to 10.4 cm²V⁻¹s⁻¹. Second, the double-well energy landscape of ferroelectric gating and associated NC effect break the thermionic limit in SS (60 mV/dec) and transconductance efficiency (38.7 S/A) and simultaneously enhances on-current and g_m by saving overdrive voltage loss^{15,23,29,30}. In addition, the negative DIBL introduced by ferroelectric HZO^{16,29} produces extremely large $r_0 \sim 10^{10} \Omega$. Third, the uniform film morphology and van der Waals (vdW) integration of metal electrodes³¹ ensures direct and damage-free contact with the channel, giving contact resistance below 60 $\Omega \cdot \text{cm}$. Together, these systematic optimizations not only significantly improve the performance and power consumption of OTFTs, but also deliver the highest gain for any TFT technologies. Finally, our sub-thermionic OTFTs are low-temperature solution processed, scalable to large area and compatible with flexible substrates, which allow us to fabricate integrated wearable sensors health monitoring and diagnosis.

Device fabrication and characterizations

For device fabrication, we first grew HZO/Al₂O₃ gate dielectrics on highly doped silicon wafers by atomic layer deposition and carried out solution shearing of p-type 2,9-didecyldinaphtho[2,3-b:2',3'-f]thieno[3,2-b]thiophene (C₁₀-DNNTT) as channel material^{32,33} (see Methods for experimental details). The Hf:Zr atomic ratio was close to 1:1 as revealed by X-ray photoelectron spectroscopy (Supplementary Fig. 1b). The HZO showed low surface roughness (~0.3 nm) and ferroelectric properties as confirmed by atomic force microscopy (AFM),

piezoelectric force microscopy (PFM), and polarization-electric field (P-E) loop measurements (Supplementary Fig. 1). Highly uniform monolayer organic films were obtained by optimizing the substrate temperature and blade speed in the shearing process³⁴ (Supplementary Fig. 2). Figure 1a and f show optical images of monolayer C₁₀-DNTT films on 2-inch silicon wafer and polyimide, respectively. The film thickness was characterized by ellipsometry and AFM, both showing ~4 nm (corresponding to monolayer) with excellent wafer-scale uniformity (Fig. 1b, c). The films were highly crystalline with herringbone lattice, consistent with C₁₀-DNTT bulk crystals (Fig. 1d). Under optimized conditions the domain size could reach several millimeters (Fig. 1e), which effectively reduced domain boundaries within device channel. The average field-effect mobility of monolayer OTFTs on Al₂O₃ dielectrics was $8.44 \pm 1.61 \text{ cm}^2\text{V}^{-1}\text{s}^{-1}$, further proving the high quality of C₁₀-DNTT films. On ultra-thin polyimide substrate, the monolayer film was highly transparent (>97%) and conformable to epidermis to allow the construction of skin-like wearable devices (Fig. 1g and Supplementary Fig. 2b).

It is well-known that conventional OTFT fabrication processes can damage the organic films, especially for monolayer³⁵. To this end, we developed solvent-free and low-energy vdW fabrication process as illustrated in Supplementary Fig. 3. This approach is readily scalable to wafer-scale with nearly 100% yield and micrometer resolution (Fig. 2a). Briefly, we first prepared patterned Au contact electrodes on a silicon wafer. The electrodes were mechanically released using PMMA and thermal release tape and gently laminated onto the pre-patterned channel areas. Such low-energy process preserved the integrity of monolayer C₁₀-DNTT channel and contact interface as shown by the cross-sectional transmission electron microscopy image (Fig. 2b). After removing the tape, electron beam lithography was performed to remove the PMMA on probing pads for electrical measurements. The intimate and damage-free contact to the monolayer channel indeed led to contact resistance of $59.4 \pm 5.3 \text{ } \Omega \cdot \text{cm}$ as measured by transfer length method (Supplementary Fig. 4), close to the record for OTFTs (Supplementary Table 1).

Electrical performance of sub-thermionic OTFTs and device modeling

Figure 2c,d presents the room-temperature transfer ($I_{\text{ds}}-V_{\text{gs}}$) and output ($I_{\text{ds}}-V_{\text{ds}}$) characteristics of a typical sub-thermionic monolayer OTFT under $V_{\text{dd}} = 1 \text{ V}$. We observed several remarkable features, including extended subthreshold region with a steep slope, close-to-zero threshold voltage (V_{th}), on/off ratio over 10^8 , excellent saturation behavior, and no hysteresis. The derived

point SS was below 60 mV/dec for more than two decades (Fig. 2e). The average SS was 58.6 mV/dec and 60.9 mV/dec for one and five decades of I_{ds} , respectively. The device also delivered superior on-state performance. In particular, the normalized g_m reached high value of $0.41 \mu\text{S}\mu\text{m}^{-1}\text{V}^{-1}$ under one-volt operation (Supplementary Table 2), suggesting possible radio-frequency applications¹⁰. More importantly, the transconductance efficiency, $\frac{g_m}{I_{ds}} = 41.6 \text{ S/A}$, exceeded the theoretical limit of $\frac{q}{k_B T} = 38.7 \text{ S/A}^4$ imposed by Boltzmann distribution of carriers (Fig. 2e). The high transconductance efficiency was maintained over several orders of I_{ds} , which was desirable in analog circuit design but difficult for CMOS³⁶. To evaluate the device variations, we measured 50 OTFTs (the transfer characteristics and statistics are shown in Supplementary Fig. 5). Figure 2f presents the histogram of SS (over one decade of I_{ds} rather than point SS), showing Gaussian like distribution with 2.5% variation as measured from the full-width at half-maximum. Sub-60 mV/dec switching was observed in 68% (34 out of 50) devices.

To demonstrate the advantage of sub-thermionic OTFTs, we fabricated monolayer OTFTs on 24 nm $\text{Al}_2\text{O}_3/\text{Si}$ substrate (without HZO). The minimum SS of these “normal” devices was 65-75 mV/dec and degraded quickly with I_{ds} (Supplementary Fig. 6a). Consequently, sub-thermionic OTFTs delivered more than one order of magnitude higher on-current and g_m under the same V_{dd} (Supplementary Fig. 6). These observations were consistent with a recent theoretical model based on realistic capacitance analysis²³.

To gain further insight of the device physics, we performed quantitative modeling using an equivalent circuit model in Supplementary Fig. 7. To achieve simultaneous hysteresis-free and sub-thermionic switching, the ferroelectric HZO capacitance (C_{FE}) needs to fall between that of Al_2O_3 (C_{AlOx}) and $C_{\text{MOS}} \approx \left(C_{\text{AlOx}}^{-1} + (C_{j,S} + C_{j,D})^{-1} \right)^{-1}$, where $C_{j,S/D}$ are S/D Schottky junction capacitances (see Supplementary Fig. 7 and Methods)²³. The low dielectric constant and low channel doping of organic channel generate $C_{j,S/D} \approx 6 \times 10^{-7} \text{ F/cm}^2$, which is about one order of magnitude smaller than C_{AlOx} ($3.6 \times 10^{-6} \text{ F/cm}^2$, 2 nm Al_2O_3). This defines an extended design space for C_{FE} . The thin Al_2O_3 also reduces the minimum thickness of HZO to achieve sub-60mV/dec switching. Supplementary Fig. 7d (solid blue line) plots SS as a function of C_{FE}^{-1} using our experimental device geometry. The C_{FE} of 22 nm HZO (derived from fitting of P-E loop, Supplementary Fig. 1d) gives $SS = 56.5 \text{ mV/dec}$ (red star), in good agreement with experimental

data. Furthermore, we quantitatively calculated the transistor characteristics using a compact model incorporating time-dependent depolarization and multi-domain Landau-Khalatnikov theory³⁷. Supplementary Fig. 7e,f shows that the calculated transfer and output curves match experiments very well, which validates the above model analysis.

We further benchmark our sub-thermionic OTFTs with other TFT technologies. Figure 2g compares the g_m and on/off ratio (data from 10 devices) with several representative OTFT technologies, under the same $V_{dd} = 1$ V (see Supplementary Table 2 for details). Our data points are located at the upper right corner of the plot, exhibiting significantly improved g_m while maintaining on/off ratio greater than 10^8 . Figure 2h summarizes the intrinsic gain of various TFT technologies. Our monolayer sub-thermionic OTFTs exhibit the highest A_i of 5.3×10^4 , which is more than one order of magnitude higher than oxides³⁸ and Schottky barrier TFTs^{4,39}, and more than two orders of magnitude higher than 2D materials⁴⁰ and silicon. Other than g_m , an important reason for the high A_i is large $r_0 \sim 10^{10} \Omega$ due to near-zero DIBL in the subthreshold region (Supplementary Fig. 8). This can be understood as a consequence of the transition from negative to positive DIBL, leading to infinite r_0 at the transition (Supplementary Fig. 8). This is a unique property of NC transistors^{16,29} and is also captured by our modeling (Supplementary Fig. 7g). It is important to note that the overall improvement of transistor performance (g_m, r_0, A_i, SS) is accomplished by systematic optimization, including high mobility material, monolayer channel, clean contact interface and ferroelectric dielectrics. To verify the importance of monolayer channel, we fabricated devices with thicker channel and observed inferior SS , on-current and g_m due to poor electrostatics and contact resistance (Supplementary Fig. 6).

The devices also had good temperature and operational stability. The sub-60 mV/dec switching was preserved after two-month storage at room-temperature, with only slight shift of V_{th} and decrease of on-current (Supplementary Fig. 9a). Variable-temperature measurements showed that the SS was below thermionic limit from 250 to 375 K (Supplementary Fig. 9c,d), owing to the high Curie temperature of the HZO¹⁹. In addition, continuous bias stress measurements under $V_{ds} = V_{gs} = -1.5$ V also showed little degradation of device performance after 10^4 seconds (Supplementary Fig. 9b). The stability can be further improved by proper passivation. In terms of frequency limit, previous studies have shown that HZO can properly function up to MHz⁴¹, which is adequate for OTFT applications.

Ultra-high-gain amplifier circuits

By designing proper electrode patterns, we could build functional circuits such as inverter and logic gates using local backgate devices (Fig. 3, Supplementary Fig. 10, see Methods for detailed fabrication processes). There is practically no limit in the circuit complexity by vdW integration as long as the transistors are co-planar. For very large-scale integration that requires multiple layers of interconnects, the upper layers can be fabricated by conventional lithography or printing as they are separated from the channel. Figure 3a shows the circuit and optical image of an enhancement-depletion mode inverter using two sub-thermionic OTFTs with different dimensions (the transfer characteristics are presented in Supplementary Fig. 11a). The inverter exhibited full swing output near zero input voltage with peak power of ~50 nW (Fig. 3b and Supplementary Fig. 11b). Remarkably, we obtained giant voltage gain (A_v) of 4.1×10^3 (1.1×10^4) under $V_{dd} = -1$ V (-3 V) (Fig. 3c). On the other hand, control amplifiers fabricated on $\text{Al}_2\text{O}_3/\text{Si}$ substrate showed 40 times lower A_v (Supplementary Fig. 11c, d). Therefore, we conclude that the high gain is enabled by steep switching in the transistor characteristics, which are unique properties of sub-thermionic OTFTs. Figure 3d benchmarks the A_v of similar amplifier structures based on organics, metal oxides, 2D materials and carbon nanotubes (see Supplementary Table 3 for details). The gain of our devices again outperforms these existing technologies by orders of magnitude while maintaining low V_{dd} , which hold promise for wearable electronics and IoT applications.

Flexible sub-thermionic OTFTs and circuits

For wearable applications, it is important to examine the device performance on flexible substrates. To this end, polyimide was used because it was compatible with the processing temperature of HZO. Spin coated polyimide (~10 μm thick) on sacrificial Si substrate ensured low surface roughness for solution shearing and mechanical reliability under extreme folding or crumpling. Figure 4a illustrates the structure and photograph of device arrays with local backgates. The transfer characteristics of 100 devices exhibit small variations in V_{th} and SS (Fig. 4b, c). Importantly, the steep slope and high gain were preserved on polyimide substrate, with 75% (75 out of 100) devices exhibiting sub-60 mV/dec switching and lowest $SS = 56.5$ mV/dec (Fig. 4c). Figure 4d presents the transfer curves of a flexible inverter with $A_v = 9.7 \times 10^3$, which was comparable to that on Si substrate. Furthermore, the devices were robust under mechanical

bending. Both g_m and SS showed little degradation during 10^4 repeated bending tests to 10 mm radius of curvature (Fig. 4e).

Integrated wearable ECG and pulse sensors

Next, we demonstrated the applications of sub-thermionic OTFT technology in wearable ECG and pulse sensors. Human body constantly produces vital physiological signals, such as biopotentials and metabolites, in the range of microvolt to millivolt⁴²⁻⁴⁵. Therefore, on-site signal amplification using low-voltage and high-gain circuitry is essential for integrated wearable sensors but very challenging. We integrated a flexible enhancement-depletion mode amplifier on a custom-designed flexible circuit board, which could be easily laminated on the front chest (Fig. 5a, b). All the amplifiers were operated under $V_{dd} = -1$ V with the peak A_v greater than 1000. The V_{dd} was supplied either by an external voltage source or a 1.5 V coin battery (Fig. 5c, a voltage divider was used to reduce V_{dd}), showing similar performance (Supplementary Fig. 12). Figure 5d plots the amplified ECG signal of a healthy male subject, clearly showing all the expected waveforms (P, Q, R, S, T and U waves). The signal amplitude was ~ 350 mV, corresponding to an amplification factor of 324. The raw ECG signal could be obtained by deconvoluting the amplifier transfer curve (the blue solid line in Fig. 5e, see Supplementary Fig. 13 for details), which agreed well with the data recorded by a clinical grade commercial equipment (Prince 180B by Heal Force, the grey dashed line in Fig. 5e). Figure 5g, h demonstrates continuous monitoring of ECG over several minutes. The signal fidelity, waveform and amplification factor remained stable during the test, which was essential for long-term health monitoring. To further prove the signal fidelity, we simultaneously measured the ECG signal by our sensor and commercial equipment (Movie S1). Figure 5f compares the power spectral density. We can see that the amplified ECG shares the same wave form with the commercial equipment, with the most prominent peak at 1.29 Hz corresponding to the heart rate of the subject. Importantly, the amplitude of power density was enhanced by $\sim 10^5$ times, consistent with the amplification factor of ~ 300 . Battery-powered ECG also showed similar power spectral density.

With excellent sensitivity and signal fidelity, our ECG sensors are capable of facilitating clinical cardiopathy diagnoses. To this end, two hospital patients were tested. On subject A (female, mid-20s) who was diagnosed with arrhythmia, our sensor clearly captured the irregular heartbeat with a sudden change from 83 to 43 beats per minute (bpm) (Fig. 5i). On subject B (male,

80s) who was diagnosed with atrial fibrillation (AF), our sensor was capable of detecting f wave with a frequency of 357 bpm, which was a direct signature of AF (Fig. 5j lower panel). In contrast, the clinical ECG of same patient did not resolve f wave due to its weak amplitude (Fig. 5j upper panel, taken by NIHON KOHDEN ECG-1350P). Currently, AF is the most common arrhythmia globally associated with the increased risk of stroke and heart failure. The ability to directly identify f wave will significantly increase the sensitivity and specificity of clinical diagnosis. Without any post-processing, the signal-to-noise ratio (SNR) of our ECG signal reached 42 dB, exceeding previously reported results^{46,47}. The improved sensitivity and the ability to detect extremely weak signals are remarkable considering the simple circuitry of our sensors.

As another example, we connected the amplifier to a flexible carbon nanotube sensor to measure wrist pulse signals (Fig. 5k). The pulse pressure induced resistance change in the carbon nanotube film, resulting in a slight shift of amplifier input voltage. Figure 5l shows the measured pulse waveforms of a human subject with ~120 mV peak-to-valley amplitude, corresponding to amplification factor of 900. The details of the pulse waveforms including a systolic peak, a diastolic notch, a reflected systolic peak and an end-diastolic notch were clearly resolved. The higher amplification compared to ECG was due to smaller input signal amplitude (~0.13 mV vs. ~1 mV for ECG), which allowed the amplifier to work at the peak gain point. Compared to literatures, our ECG and pulse sensors show advantages in terms of V_{dd} , gain and SNR (Supplementary Table 4).

Conclusions

We demonstrate the first sub-thermionic flexible OTFT technology by combining solution-processed monolayer organic channel, ferroelectric gate dielectrics and vdW device integration. The devices operate under one-volt and exhibit sub-60mV/dec switching and record-high intrinsic gain. We further build amplifier circuits with extremely high voltage gain of 1.1×10^4 , which outperform existing TFT technologies by more than one order of magnitude. The flexible amplifiers are capable of amplifying human physiological signals by several hundred times with high fidelity, and detecting extremely weak ECG signals to facilitate clinical diagnosis. By developing more robust amplification schemes (such as differential amplification)⁴⁷ and wireless data transmission⁴⁸, we can envision all-organic, battery-powered patches for high-precision health monitoring and real-time cloud-based diagnosis.

Methods

Preparation of HZO/Al₂O₃ dielectrics. The HZO film was deposited by atomic layer deposition (ALD) on p++ silicon (100) substrate at 200 °C and base pressure of ~1 Pa using Tetrakis(dimethylamido) hafnium as Hf source, Tetrakis(dimethylamido) zirconium as Zr source and H₂O as oxidant. We used 20 sccm N₂ as carrier gas. The HfO_x and ZrO_x were deposited sequentially with 1:1 ratio. Then 2 nm AlO_x capping layer was deposited by ALD in-situ for capacitance matching, using trimethylaluminum and H₂O as sources. The pulse/purge time for Hf, Zr and H₂O precursors were 250 ms/30 s, 20 ms/30 s and 30 ms/30 s, respectively. The substrate was undergone 350 °C rapid thermal annealing (RTA) for 1 min in N₂ to crystallize the HZO.

We fabricated the HZO/Al₂O₃ dielectrics on polyimide substrate using the similar method mentioned above. To prepare the polyimide substrate, we spin coated polyimide solution (AA-49, KANEKA) on SiO₂/Si substrate, and then baked at 350 °C for 1 hour on a hotplate.

Solution shearing of monolayer C₁₀-DNTT films. The C₁₀-DNTT powder was dissolved in 1,2,3,4-tetrahydronaphthalene (tetralin) at 85 °C with a concentration of 0.2 mg/mL. The growth of monolayer C₁₀-DNTT was carried out in a home-built solution shearing setup with heaters on both the blade and substrate (Supplementary Fig. 2). The temperature of the blade and substrate was set to 65 °C. 150 µL of C₁₀-DNTT solution was injected for a 2-inch size substrate and a constant shear velocity of 3 µm/s was established by using a linear translation stage during the shearing processes.

Characterizations of C₁₀-DNTT film and OTFTs. We used ellipsometry mapping, high-resolution AFM and cross-polarized optical microscopy to characterize the monolayer C₁₀-DNTT film. The ellipsometry mapping was performed on a Woollam RC2-XI mapping ellipsometer in the wavelength range of 210-2500 nm. For high-resolution AFM, the experiments were conducted on Asylum Cypher under ambient conditions. The cross-polarized optical reflection micrographs were performed by the ScanPro spectro-microscope under the white light. We used cross-sectional transmission electron microscopy (TEM) to characterize the interface and thickness of sub-thermionic OTFTs. The TEM specimens were prepared using a FEI Scois Dualbeam focused ion beam (FIB). After that, the specimens were characterized using a high-resolution JEOL JEM-2100F TEM with acceleration voltage of 200 kV equipped with Energy-dispersive spectroscopy (EDS) detector.

vdW integration of contacts. First, we prepare patterned gold electrodes with 50 nm thickness on a silicon substrate using electron-beam lithography (EBL) and electron-beam evaporation (EBE). Next, a PMMA layer was spin-coated, followed by the lamination of thermal released tape (TRT). The TRT/PMMA/Au electrode stack was carefully released from silicon substrate and was align-transferred to patterned

monolayer C₁₀-DNTT film. Then the TRT was separated at 90 °C. Finally, the PMMA layer was patterned by EBL to remove the PMMA on probing pads for electrical measurements.

Fabrication of amplifiers with local backgate. First, we fabricated 10 nm Ti/20 nm Au backgate electrodes on SiO₂/Si substrate using EBL and EBE. Then, HZO/Al₂O₃ was deposited using ALD. EBL and inductive coupled plasma reactive ion etching (BCl₃ and Cl₂) were adopted to etch HZO/Al₂O₃ and open via holes to backgate electrodes. Then, monolayer C₁₀-DNTT films were grown by the solution shearing process. Finally, the source/drain electrodes (50 nm Au) were align transferred onto the C₁₀-DNTT films. For the device on the polyimide substrate, the processes are similar.

Electrical measurements. Electrical measurements were carried out by an Agilent B1500 semiconductor parameter analyzer in a probe station under ambient conditions.

Electrocardiogram and pulse detection. The flexible amplifier connected with two conventional gel electrodes to obtain the electrocardiogram (ECG) signal. One was placed on the skin above the lower left part of heart and connected to a bias voltage to set the signal at the amplifier optimal work point. And another was placed on the upper right part of the heart as the input signal of the amplifier. We use Agilent B1500 to collect ECG signal and the sampling frequency was 40Hz. Fast Fourier transforms (FFT) was applied to identify the power density of recorded ECG signal.

Inset of Fig. 5k shows the circuit diagram for pulse detection. The resistance of the flexible carbon nanotube sensor is about 1 kΩ. By connecting it with a 1 kΩ divider resistor, the resistance change of the sensor was converted into a voltage signal, then as the input of the amplifier. Agilent B1500 was used to collect the pulse signal.

Data availability

The data that support the plots within this paper and other findings of this study are available from the corresponding author upon reasonable request.

References:

- 1 Sirringhaus, H. 25th Anniversary Article: Organic Field-Effect Transistors: The Path Beyond Amorphous Silicon. *Advanced Materials* **26**, 1319-1335, (2014).
- 2 Kaltenbrunner, M. *et al.* An ultra-lightweight design for imperceptible plastic electronics. *Nature* **499**, 458-463, (2013).
- 3 Wang, S. *et al.* Skin electronics from scalable fabrication of an intrinsically stretchable transistor array. *Nature* **555**, 83, (2018).

- 4 Jiang, C. *et al.* Printed subthreshold organic transistors operating at high gain and ultralow power. *Science* **363**, 719, (2019).
- 5 Klauk, H., Zschieschang, U., Pflaum, J. & Halik, M. Ultralow-power organic complementary circuits. *Nature* **445**, 745, (2007).
- 6 Wang, C., Dong, H., Jiang, L. & Hu, W. Organic semiconductor crystals. *Chemical Society Reviews* **47**, 422-500, (2018).
- 7 Tang, J. *et al.* Flexible CMOS integrated circuits based on carbon nanotubes with sub-10 ns stage delays. *Nature Electronics* **1**, 191-196, (2018).
- 8 Akinwande, D., Petrone, N. & Hone, J. Two-dimensional flexible nanoelectronics. *Nature Communications* **5**, 5678, (2014).
- 9 Myny, K. The development of flexible integrated circuits based on thin-film transistors. *Nature Electronics* **1**, 30-39, (2018).
- 10 Klauk, H. Will We See Gigahertz Organic Transistors? *Advanced Electronic Materials* **4**, 1700474, (2018).
- 11 Liu, A., Zhu, H., Sun, H., Xu, Y. & Noh, Y.-Y. Solution Processed Metal Oxide High- κ Dielectrics for Emerging Transistors and Circuits. *Advanced Materials* **30**, 1706364, (2018).
- 12 Borchert, J. W. *et al.* Flexible low-voltage high-frequency organic thin-film transistors. *Science Advances* **6**, eaaz5156, (2020).
- 13 Ji, D. *et al.* Copolymer dielectrics with balanced chain-packing density and surface polarity for high-performance flexible organic electronics. *Nature Communications* **9**, 2339, (2018).
- 14 Yokota, T. *et al.* Flexible Low-Voltage Organic Transistors with High Thermal Stability at 250 °C. *Advanced Materials* **25**, 3639-3644, (2013).
- 15 Salahuddin, S. & Datta, S. Use of Negative Capacitance to Provide Voltage Amplification for Low Power Nanoscale Devices. *Nano Letters* **8**, 405-410, (2008).

- 16 Pahwa, G. *et al.* Analysis and Compact Modeling of Negative Capacitance Transistor with High ON-Current and Negative Output Differential Resistance—Part II: Model Validation. *IEEE Trans. Electron Devices* **63**, 4986-4992, (2016).
- 17 Khan, A. I. *et al.* Negative capacitance in a ferroelectric capacitor. *Nature Materials* **14**, 182-186, (2015).
- 18 Böске, T. S., Müller, J., Bräuhäus, D., Schröder, U. & Böttger, U. Ferroelectricity in hafnium oxide thin films. *Appl. Phys. Lett.* **99**, 102903, (2011).
- 19 Müller, J. *et al.* Ferroelectricity in Simple Binary ZrO₂ and HfO₂. *Nano Letters* **12**, 4318-4323, (2012).
- 20 Íñiguez, J., Zubko, P., Luk'yanchuk, I. & Cano, A. Ferroelectric negative capacitance. *Nature Reviews Materials* **4**, 243-256, (2019).
- 21 Alam, M. A., Si, M. & Ye, P. D. A critical review of recent progress on negative capacitance field-effect transistors. *Appl. Phys. Lett.* **114**, 090401, (2019).
- 22 Hoffmann, M. *et al.* Unveiling the double-well energy landscape in a ferroelectric layer. *Nature* **565**, 464-467, (2019).
- 23 Cao, W. & Banerjee, K. Is negative capacitance FET a steep-slope logic switch? *Nature Communications* **11**, 196, (2020).
- 24 Wang, H. *et al.* in *2018 IEEE International Electron Devices Meeting (IEDM)*. 31.31.31-31.31.34.
- 25 Li, K. *et al.* in *2015 IEEE International Electron Devices Meeting (IEDM)*. 22.26.21-22.26.24.
- 26 Lee, M. H. *et al.* in *2015 IEEE International Electron Devices Meeting (IEDM)*. 22.25.21-22.25.24.
- 27 Kwon, D. *et al.* Improved Subthreshold Swing and Short Channel Effect in FDSOI n-Channel Negative Capacitance Field Effect Transistors. *IEEE Electron Device Letters* **39**, 300-303, (2018).
- 28 Zhou, J. *et al.* in *2016 IEEE International Electron Devices Meeting (IEDM)*. 12.12.11-12.12.14.

- 29 Si, M. *et al.* Steep-slope hysteresis-free negative capacitance MoS₂ transistors. *Nature Nanotechnology* **13**, 24-28, (2018).
- 30 Yu, Z. *et al.* in *2017 IEEE International Electron Devices Meeting (IEDM)*. 23.26.21-23.26.24.
- 31 Liu, Y., Huang, Y. & Duan, X. Van der Waals integration before and beyond two-dimensional materials. *Nature* **567**, 323-333, (2019).
- 32 Kang, M. J. *et al.* Alkylated Dinaphtho[2,3-b:2',3'-f]Thieno[3,2-b]Thiophenes (Cn-DNTTs): Organic Semiconductors for High-Performance Thin-Film Transistors. *Advanced Materials* **23**, 1222-1225, (2011).
- 33 Peng, B., Huang, S., Zhou, Z. & Chan, P. K. L. Solution-Processed Monolayer Organic Crystals for High-Performance Field-Effect Transistors and Ultrasensitive Gas Sensors. *Advanced Functional Materials* **27**, 1700999, (2017).
- 34 Giri, G. *et al.* Tuning charge transport in solution-sheared organic semiconductors using lattice strain. *Nature* **480**, 504-508, (2011).
- 35 He, D. *et al.* Ultrahigh mobility and efficient charge injection in monolayer organic thin-film transistors on boron nitride. *Science Advances* **3**, e1701186, (2017).
- 36 Terry, S. C. *et al.* Comparison of a BSIM3V3 and EKV MOSFET model for a 0.5 μm CMOS process and implications for analog circuit design. *IEEE Trans. Nucl. Sci.* **50**, 915-920, (2003).
- 37 Zhao, Y. *et al.* in *2019 IEEE International Electron Devices Meeting (IEDM)*. 7.5.1-7.5.4.
- 38 Li, S. *et al.* Nanometre-thin indium tin oxide for advanced high-performance electronics. *Nature Materials* **18**, 1091-1097, (2019).
- 39 Lee, S. & Nathan, A. Subthreshold Schottky-barrier thin-film transistors with ultralow power and high intrinsic gain. *Science* **354**, 302, (2016).
- 40 Chang, H.-Y. *et al.* High-Performance, Highly Bendable MoS₂ Transistors with High-K Dielectrics for Flexible Low-Power Systems. *ACS Nano* **7**, 5446-5452, (2013).

- 41 Yu, Z. *et al.* in *2018 IEEE International Electron Devices Meeting (IEDM)*. 22.24.21-22.24.24.
- 42 Kim, D.-H. *et al.* Epidermal Electronics. *Science* **333**, 838, (2011).
- 43 Chung, H. U. *et al.* Binodal, wireless epidermal electronic systems with in-sensor analytics for neonatal intensive care. *Science* **363**, eaau0780, (2019).
- 44 Ershad, F. *et al.* Ultra-conformal drawn-on-skin electronics for multifunctional motion artifact-free sensing and point-of-care treatment. *Nature Communications* **11**, 3823, (2020).
- 45 Lee, S. *et al.* Ultrasoft electronics to monitor dynamically pulsing cardiomyocytes. *Nature Nanotechnology* **14**, 156-160, (2019).
- 46 Sekitani, T. *et al.* Ultraflexible organic amplifier with biocompatible gel electrodes. *Nature Communications* **7**, 11425, (2016).
- 47 Sugiyama, M. *et al.* An ultraflexible organic differential amplifier for recording electrocardiograms. *Nature Electronics* **2**, 351-360, (2019).
- 48 Fiore, V. *et al.* An Integrated 13.56-MHz RFID Tag in a Printed Organic Complementary TFT Technology on Flexible Substrate. *IEEE Transactions on Circuits and Systems I: Regular Papers* **62**, 1668-1677, (2015).

Acknowledgments

This work is supported by National Natural Science Foundation of China 61734003, 61521001, 61927808, 61851401, 91964202, 61861166001, 51861145202, 61821091, 61888102, 61825403, 11922215; Strategic Priority Research Program of Chinese Academy of Sciences XDB 30000000; General Research Fund (GRF) HKU 17264016, HKU 17204517; Key Laboratory of Advanced Photonic and Electronic Materials, Collaborative Innovation Center of Solid-State Lighting and Energy-Saving Electronics, and the Fundamental Research Funds for the Central Universities, China.

Author contributions

X.W. conceived and supervised the project. Z.L., B.P., J.Z., Z.Y., D.H., H.N., W.M., W.H., X.C., W.L., D.P., X.T., X.H., Y.S. X.F. and P.K.L.C. contributed to sample preparation, characterization, device fabrication, measurements and data analysis. Y.Z., J.W., L. Li and M.L. carried out circuit simulation and theoretical analysis. Z.L., J.Z., J.X., L. Lan, Y.Y. and D.S. performed the clinical electrocardiogram. Z.M. and L.P. fabricated and tested pulse sensors. K.C. and Y.L. performed TEM and data analysis. Z.L., Z.Y., and X.W. co-wrote the manuscript with input from other authors. All authors contributed to discussions.

Competing interests

Authors declare no competing interests.

Fig. 1| Large-area monolayer C₁₀-DNTT films. **a**, Photograph of uniform monolayer C₁₀-DNTT film on 2-inch Si wafer. **b**, The thickness mapping of the sample in **a** using spectral ellipsometry. **c-e**, AFM (**c**), high-resolution AFM (**d**) and cross-polarized optical micrograph (**e**) of the monolayer C₁₀-DNTT film. **f,g**, Photograph of monolayer C₁₀-DNTT film on polyimide substrate (**f**) and flexible device array laminated on a fingertip (**g**).

Fig. 2| Transistor characteristics of sub-thermionic monolayer OTFTs. a, Photographs of device arrays fabricated on silicon substrate. The length to width ratio (L/W) of device channel is $5\mu\text{m}/180\mu\text{m}$. **b,** False-color cross-section TEM image of a device contact region, clearly showing the Au/C₁₀-DNTT/Al₂O₃/HZO/Si stack. **c,** Double-sweep I_{ds} - V_{gs} curves of the sub-thermionic OTFT at $V_{ds} = -0.1$ V (blue) and -1 V (red). No hysteresis is observed. The black dashed line is the gate leakage current. **d,** I_{ds} - V_{ds} curves of the sub-thermionic OTFT. From bottom to top, V_{gs} is from -0.3 to -1 V. **e,** SS (black) and transconductance efficiency (red) as a function of I_{ds} for the device in **c**. **f,** Statistical distributions of one-decade SS for 50 devices. **g,** Comparison of I_{on}/I_{off} and normalized transconductance at $|V_{ds}| = |V_{gs(on)} - V_{gs(off)}| = 1$ V among OTFT technologies using different dielectrics. The extracted data are listed in Supplementary Table 2. **h,** Comparison of intrinsic gain among different TFT technologies.

Fig. 3| Integrated amplifier based on sub-thermionic monolayer OTFTs. a, Equivalent circuit diagram (left) and optical microscope image (right) of an enhancement-depletion mode amplifier. The dotted boxes indicate organic film areas for load and drive transistors. **b**, Voltage transfer characteristics under $V_{dd} = -1, -2$, and -3 V respectively. **c**, A_v as a function of input voltage derived from **b**. **d**, Comparison of A_v among similar amplifier circuits using different materials and processes. The extracted data are listed in Supplementary Table 3.

Fig. 4| Sub-thermionic OTFTs on flexible substrates. **a**, Photograph of OTFT arrays fabricated on 2-inch polyimide substrate (left) and schematic view of the device structure (right). **b**, I_{ds} - V_{gs} curves of 100 devices under $V_{ds} = -1$ V. The L/W of device channel is $5\mu m/180\mu m$. **c**, Statistical distributions of SS for the devices in **b**. **d**, Voltage transfer characteristics (solid lines) and A_v (symbols) of an enhancement-depletion mode amplifier on flexible substrate, under $V_{dd} = -1$ and -3 V. **e**, Bending test of a device on polyimide substrate. Both g_m and SS remain stable during 10^4 bending cycles. Inset shows a photograph of flexible device arrays under bending.

Fig. 5| Low-voltage and high-gain integrated wearable sensors. **a**, Cartoon illustration of the use of amplifier circuit to acquire human ECG signals. **b**, Photograph of a flexible amplifier module attached to a human chest. **c**, Photograph of the amplifier module, with a coin battery, a voltage divider and amplifier circuit integrated on a flexible circuit board. **d**, Amplified ECG signal of a human subject. **e**, Deconvoluted ECG signal using the amplifier's transfer curve (blue solid line) and the ECG signal taken by commercial equipment on the same human subject (black dashed line). **f**, The power spectral density of ECG signals taken by commercial equipment (grey), our amplifier with external voltage source (red) and battery (green) as power supply. **g**, Long-term ECG monitoring using our sensor. **h**, The ECG signal of the 1st (upper panel) and 245th (lower panel) cycle in **g**. **i**, Amplified ECG signal of a human subject with

known arrhythmia history (bottom panel) and the corresponding heart rate (upper panel). **j**, ECG signal of another human subject with AF, recorded by our sensor (bottom panel) and a clinical equipment (upper panel). **k**, Photograph of an integrated pulse sensor using flexible carbon nanotube films and our amplifier circuit. Inset shows the circuit diagram. **l**, Unconditioned and amplified pulse signal taken on the same human subject.

Figures

Figure 1

Large-area monolayer C10-DNTT films. a, Photograph of uniform monolayer C10-DNTT film on 2-inch Si wafer. b, The thickness mapping of the sample in a using spectral ellipsometry. c-e, AFM (c), high-resolution AFM (d) and cross-polarized optical micrograph (e) of the monolayer C10-DNTT film. f,g, Photograph of monolayer C10-DNTT film on polyimide substrate (f) and flexible device array laminated on a fingertip (g).

Figure 2

Transistor characteristics of sub-thermionic monolayer OTFTs. a, Photographs of device arrays fabricated on silicon substrate. The length to width ratio (L/W) of device channel is $5\mu\text{m}/180\mu\text{m}$. b, False-color cross-section TEM image of a device contact region, clearly showing the Au/C₁₀-DNTT/Al₂O₃/HZO/Si stack. c, Double-sweep I_{ds} - V_{gs} curves of the sub-thermionic OTFT at $V_{ds} = -0.1$ V (blue) and -1 V (red). No hysteresis is observed. The black dashed line is the gate leakage current. d, I_{ds} - V_{ds} curves of the sub-thermionic OTFT. From bottom to top, V_{gs} is from -0.3 to -1 V. e, SS (black) and transconductance efficiency (red) as a function of I_{ds} for the device in c. f, Statistical distributions of one-decade SS for 50 devices. g, Comparison of I_{on}/I_{off} and normalized transconductance at $|V_{ds}| = |V_{gs(on)} - V_{gs(off)}| = 1$ V among OTFT technologies using different dielectrics. The extracted data are listed in Supplementary Table 2. h, Comparison of intrinsic gain among different TFT technologies.

Figure 3

| Integrated amplifier based on sub-thermionic monolayer OTFTs. a, Equivalent circuit diagram (left) and optical microscope image (right) of an enhancement-depletion mode amplifier. The dotted boxes indicate organic film areas for load and drive transistors. b, Voltage transfer characteristics under $V_{dd} = -1$, -2 , and -3 V respectively. c, A_v as a function of input voltage derived from b. d, Comparison of A_v among similar amplifier circuits using different materials and processes. The extracted data are listed in Supplementary Table 3.

Figure 4

Sub-thermionic OTFTs on flexible substrates. a, Photograph of OTFT arrays fabricated on 2-inch polyimide substrate (left) and schematic view of the device structure (right). b, I_{ds} - V_{gs} curves of 100 devices under $V_{ds} = -1V$. The L/W of device channel is $5\mu m/180\mu m$. c, Statistical distributions of SS for the devices in b. d, Voltage transfer characteristics (solid lines) and A_v (symbols) of an enhancement-depletion mode amplifier on flexible substrate, under $V_{dd} = -1$ and $-3V$. e, Bending test of a device on polyimide substrate. Both g_m and SS remain stable during 104 bending cycles. Inset shows a photograph of flexible device arrays under bending.

Figure 5

Low-voltage and high-gain integrated wearable sensors. a, Cartoon illustration of the use of amplifier circuit to acquire human ECG signals. b, Photograph of a flexible amplifier module attached to a human chest. c, Photograph of the amplifier module, with a coin battery, a voltage divider and amplifier circuit integrated on a flexible circuit board. d, Amplified ECG signal of a human subject. e, Deconvoluted ECG signal using the amplifier's transfer curve (blue solid line) and the ECG signal taken by commercial equipment on the same human subject (black dashed line). f, The power spectral density of ECG signals taken by commercial equipment (grey), our amplifier with external voltage source (red) and battery (green) as power supply. g, Long-term ECG monitoring using our sensor. h, The ECG signal of the 1st (upper panel) and 245th (lower panel) cycle in g. i, Amplified ECG signal of a human subject with known arrhythmia history (bottom panel) and the corresponding heart rate (upper panel). j, ECG signal of another human subject with AF, recorded by our sensor (bottom panel) and a clinical equipment (upper panel). k, Photograph of an integrated pulse sensor using flexible carbon nanotube films and our amplifier circuit.

Inset shows the circuit diagram. I, Unconditioned and amplified pulse signal taken on the same human subject.

Supplementary Files

This is a list of supplementary files associated with this preprint. Click to download.

- [MovieS1.mp4](#)
- [NCSupplementaryInformation.docx](#)