Quasi-band structure of quantum-confined nanocrystals

Marius Buerkle (✉ marius.buerkle@aist.go.jp)

National Institute of Advanced Industrial Science and Technology (AIST)

Mickäel Lozac'h

National Institute of Advanced Industrial Science and Technology (AIST)

Davide Mariotti

University of Ulster

Vladimir Svrcek

National Institute of Advanced Industrial Science and Technology (AIST)

Research Article

Keywords: nanocrystals, band, structure, discuss, quantum

Posted Date: October 18th, 2021

DOI: <https://doi.org/10.21203/rs.3.rs-964696/v1>

License: © ⓘ This work is licensed under a Creative Commons Attribution 4.0 International License.

[Read Full License](#)

Quasi-band structure of quantum-confined nanocrystals

Marius Bürkle^{1,*}, Mickaël Lozac'h¹, Davide Mariotti², and Vladimir Švrček¹

¹National Institute of Advanced Industrial Science and Technology (AIST), Tsukuba, Japan

²Integrated Bio-Engineering Centre (NIBEC), University of Ulster, UK

*mariaus.buerkle@aist.go.jp

ABSTRACT

We discuss the electronic properties of quantum-confined nanocrystals. In particular, we show how, starting from the discrete molecular states of small nanocrystals, an approximate band structure (quasi-band structure) emerges with increasing particle size. Finite temperature is found to broaden the discrete states in energy space forming even for nanocrystals in the quantum-confinement regime quasi-continuous bands in k-space. These bands can be, to a certain extent, interpreted along the lines of standard band structure theory, while taking also finite size and surface effects into account. We discuss this on various prototypical nanocrystal systems.

Introduction

Nanocrystals (NC) with sizes comparable to their exciton Bohr radius^{1–5} can have very unique electronic properties arising from the interplay between quantum-confinement, finite-size effects, and surface functionalization. The degree of quantum-confinement, which can be for example controlled by the particle diameter as well as different functional groups on the NC's surface, allows to tune electronic and optical properties, such as the electronic gap, absorption and luminescence.^{6–11} Nanocrystals with tailored properties are very attractive for various applications requiring distinct optical and electronic properties, such as fluorescent NC for bio-imaging, light absorbing NC for next-generation photovoltaics or luminescent NC for light emitting devices.^{9, 12–18}

Essentially, quantum-confined NCs are systems that fall somewhere in between the molecular and the bulk world. On the one hand NCs have often a well-defined crystal structure, which remains close to their bulk counterpart and on the other hand the finite surface can have a large effect on the electronic and optical properties. Concepts from both worlds are often used loosely and interchangeably. For example the electronic gap of NCs is usually termed band-gap rather than HOMO-LUMO gap, i.e. the electronic gap between the highest occupied and lowest unoccupied (discrete) molecular orbital, moreover the nature of the band gap is often labeled to be direct or indirect following standard semiconductor theory. These are concepts which are only strictly valid for bulk crystals with a well-defined band structure¹⁹ and do not necessarily correspond to properties of finite-sized systems with broken translational symmetry and discrete energy levels. However, it would be desirable to connect the intuitive picture of band structure theory with nanocrystals while also accounting for finite-size and surface effects. In this work we are going to show how an approximate band structure^{10, 20} (quasi-band structure) can provide a simple and intuitive way to describe nanocrystals. The quasi-band structure stays close to standard band structure theory, while taking finite-size and surface effects into account. In particular, we discuss the effects of (i) size and (ii) surface functionalization on the electronic structure of silicon nanocrystals and (iii) how an approximate band structure emerges from the discrete molecular orbitals with increasing particles size and finite temperature. This is discussed for metallic NCs and semiconducting NCs with indirect and direct band-gap.

Methods

Quasi-band structure

The band structure of bulk crystals is a direct consequence of their translational symmetry and follows from Bloch's theorem.^{19, 21} Concepts from band structure theory, such as band gap, valence band maximum, or conduction band minimum are often used in the context of nanocrystals, however for nanocrystals, as finite-sized objects, they are not (strictly) valid. In particular, quantum confined nanocrystals, while their size is usually much bigger than molecules they are still well-below the bulk limit. On the other hand, NCs have usually a well-defined crystal structure which converges inside the NC to values close to bulk.¹⁰ To connect the molecular limit with the bulk limit we will construct an approximate band structure (quasi-band structure) by considering

the k-space resolved density of states (DOS) for each (molecular) state,^{5,10,20,22} which is closely related to angle-resolved photoemission spectroscopy.²³ By doing so we take surface and finite size into account, while staying as close as possible to the intuitive concept of the standard band structure theory. Following references 10 and 24 the DOS is obtained using a Green's functions technique, where all relevant quantities can be obtained from first-principles calculations. The k-space resolved DOS is obtained from the spectral representation of the Green's function²⁵

$$\hat{G} = \sum_{\mu} \frac{|\mu\rangle\langle\mu|}{E + i\eta - \varepsilon_{\mu}}, \quad (1)$$

here $|\mu\rangle$ is an energy eigenstate of Hamiltonian $\hat{H}$ to the eigenvalue ε_{μ} and $\eta > 0$ is an infinitesimal quantity. Keeping η as a phenomenological parameter finite would allow to account for the finite lifetime (broadening) of the discrete energy eigenstates or more rigorously interaction effects could be introduced by including appropriate self-energy terms into eq. 1. Here, we will neglect interactions, taking only the intrinsic thermal broadening of the DOS into account. From eq. 1 we can directly calculate the (local) DOS $\rho_{\mu}(E) = -\frac{1}{\pi} \text{Im} (G_{\mu\mu}(E))$.²⁵ An approximate representation in k-space is obtained by projecting the molecular states in real space $\phi_{\mu}(\vec{r}) = \langle \vec{r} | \mu \rangle$ onto plane waves $\phi_{\mu}(\vec{k}) = \langle \vec{k} | \mu \rangle = \int d\vec{r} \langle \vec{k} | \vec{r} \rangle \langle \vec{r} | \mu \rangle = \int d\vec{r} e^{i\vec{k}\cdot\vec{r}} \phi_{\mu}(\vec{r})$.²⁰ This allows to write eq. 1 as

$$G(E, \varepsilon_{\mu}; \vec{k}) = \sum_{\mu} \frac{\phi_{\mu}^*(\vec{r}) \phi_{\mu}(\vec{r})}{E + i\eta - \varepsilon_{\mu}} \quad (2)$$

and to obtain the k-space resolved DOS of state μ at temperature $T = 0$ K from

$$\rho(E, \varepsilon_{\mu}; \vec{k}) = -\frac{1}{\pi} \text{Im} [G(E, \varepsilon_{\mu}; \vec{k})]. \quad (3)$$

Whereas off-diagonal terms in k-space arising due to the broken translational symmetry are neglected.²⁶ The thermodynamic density of states $N(E, T) = \partial n(E, T) / \partial E$ at a given finite temperature T is related to the DOS at $T = 0$ K (eq. 1) via the electron density $n(E, T) = \int_{-\infty}^{\infty} dE_1 \rho(E_1) f(E_1 - E, T)$. Hence, the temperature dependent k-space resolved DOS is given by the convolution of the DOS at $T = 0$ K (eq. 3) with the energy derivative of the Fermi function $f'(E - E_1, T) = -\partial f(E - E_1, T) / \partial E$

$$N(E, T; \vec{k}) = \sum_{\mu} \int_{-\infty}^{\infty} dE_1 \rho(E_1, \varepsilon_{\mu}; \vec{k}) \times f'(E - E_1, T). \quad (4)$$

As we will see in the following the thermal broadening will lead, even for small nanocrystals, to the formation of quasi-continuous bands-like features.

First-principles calculations

The electronic and geometrical properties of the NC were obtained within density functional theory (DFT) using the PBE functional²⁷ and a double-zeta basis set with polarization functions for all nonhydrogen atoms.^{28,29} The total energies were converged with a precision of 10^{-7} a.u.. The structures of all NC were fully relaxed, and the optimization was carried out until the maximum norm of the gradient drops below 10^{-5} a.u.. The quantum chemistry package TURBOMOLE³⁰ was used for all calculations.

In the following the nanocrystals are modeled in the first-principles calculations as approximately spherical nanocrystals with under-coordinated atoms removed. For the semiconducting Si and GaAs NCs the surface is fully passivated with hydrogen atoms, for the metallic Pb NC we assume a pristine Pb surface without oxidation as observed in recent experiments.³¹

Results and discussions

Quasi-band structure, size and temperature dependence

First we want to investigate how the quasi-band structure emerges with increasing particle size and how the bands are formed due to finite temperature. Whereas, we purely focus on temperature effects as described by eq. 4, i.e., a smearing of the occupation following the Fermi distribution, renormalization of the orbital energies and finite lifetimes of the molecular states due to e.g. electron-phonon interaction is neglected here, however it would be possible to account for such effects by introducing the corresponding self-energies to the Green's functions which are used to calculate the DOS.

Figure 1. Geometry of the Si-H nanocrystal with an approximate diameter of (a) $d = 1.8$ nm and (b) $d = 2.9$ nm. Quasi-band structure calculated at different temperatures T for (c) Si-H ($d = 1.8$ nm) and (d) Si-H ($d = 2.9$ nm).

We start with a silicon nanocrystal (Si-NC) with very small diameter of $d = 1.8$ nm (Fig. 1a), as here the discrete nature of the energy levels should be clearly evident. The corresponding quasi-band structure for different temperatures is given in Figure (Fig. 1c). The total number of energy eigenstates is limited for the small Si-NC ($d = 1.8$ nm) and their broadening remains small at low temperature ($T = 25$ K) however, while the discrete nature of the eigenvalues is still clearly visible, it is already possible to see the emergence of band-like features. Increasing the temperature broadens the energy levels, and due to the finite overlap between states close in energy, quasi continuous bands start to form. At room temperature ($T = 293$ K) the quasi continuous bands are clearly visible, yet small sub gaps within the bands remain even at room temperature. Increasing the particle size to $d = 2.9$ nm (Fig. 1b) increasing the number of molecular states, which tends to close the sub gaps, as the states become more and more dense in energy space (Fig. 1d). Additionally the bands become more localized in k-space as the surface effects decrease. Lastly, it must be stressed that due to the broken translational symmetry k-points in different Brillouin zones are not equivalent. While for $T = 293$ K the quasi-band structure shows similar feature as the bulk one, i.e. approximate shape of the bands and position of the valance band minimum (X) and conduction band maximum (Γ), the two Γ -points in adjacent reciprocal cells, Γ_0 and Γ_1 are not equivalent. The bands are more pronounced towards Γ_1 while the weight at Γ_0 remains smaller. Nonetheless we clearly see that Si-NC are just as their bulk counter part an indirect band gap materials with a transition between Γ and X point, or to be precise between one of the distinct Γ and one of the X points.

Two more examples for the quasi bandstructure of a semiconducting NC with a direct band gap and a metallic NC, namely a hydrogen terminated GaAs-NC with $d = 3.9$ nm and a Pb-NC with $d = 4.9$ nm are given in figure 2a and 2b. The quasi-band structure is calculated at room temperature ($T = 293$ K). Bulk GaAs is direct band gap material, similarly the GaAs-NC shows also a direct transition at the Γ points. While the weight between the two non-equivalent points Γ varies, the overall shape of the bands remains similar. Additionally, small sub gaps are present at the Γ points (2c), they can likely be attributed to localized surface states.

Bulk Pb is a metal, thus has no band gap and a finite DOS at the Fermi energy. For Pb-NC localization introduced due by the finite NC surface leads naturally to an, albeit possibly small, electronic gap. The HOMO-LUMO gap of the Pb-NC at $T = 0$ K is only 0.05 eV, if we follow the Aufbau principle and assume a Fermi smearing of the occupation we get a broken occupation around the HOMO-LUMO gap and can calculated an effective Fermi-energy which is indicated by the dotted blue line in the quasi-band structure in figure 2d. The bands for the Pb-NC are already well defined as the particle size is relatively big. Accordingly, the Pb-NC is effectively metallic at room temperature. If we move away from the Fermi energy to lower energies we get similarly to bulk Pb a gap in the band structure with a flat band connecting the K and X point.

Surface functionalization

In the following we consider approximate spherical silicon nanocrystals with varying degree of hydroxyl (OH) surface coverage. The modeling here follows our previous theoretical and experimental works.^{8,10} Using plasma processing techniques, it is not only possible to synthesize high quality NC with a narrow size distribution and well-defined crystal structure but also to control the degree of surface functionalization.^{8,9} Depending on the processing time it is possible to replace the initially hydrogen termination of the NC surface (Fig. 3a) gradually with OH groups until the NC surface is completely functionalized by hydroxyl (Fig. 3b).¹⁰

Surface functionalization can have several distinct effects on the NC, (i) chemical effects due to e.g. charge transfer, (ii) change of structural properties due to strain, and (iii) induce localized surface states. Here, charge transfer between the electron withdrawing hydroxyl groups and the silicon atoms of the outer silicon shells plays the main role, while the induced strain remains small and has only minor influence on the electronic properties.¹⁰ In Figure 3c we compare the DOS of Si-NC with full hydrogen coverage to the DOS of the Si-NC with full OH coverage. Introducing hydroxyl on the Si-NC surface has two effects on the DOS it leads to a smearing of the overall DOS and due to the electron donating nature of OH to a shift the orbitals to lower energies, whereas the effect is more pronounced for the unoccupied frontier orbitals which tend to be more localized at the NC's surface. The overall features of the DOS translate accordingly to the quasi-band structure. That is replacing the hydrogen atoms with OH leads, as already suggested from the joined DOS, to a smearing of the bands making them overall more “fuzzy” and more delocalized in k-space (Fig. 3d,e). The energy as well as the shape of the occupied bands remain otherwise largely unchanged as the occupied frontier orbitals tend to be localized within the NC. On the other hand, the unoccupied frontier orbitals tend to be localized on the outer shells of the Si-NC and thus the influence of the surface functionalization is larger on unoccupied states. Accordingly, the unoccupied states are moved down in energy. The energy of lowest unoccupied molecular orbital (LUMO) decreases by around 0.8 eV if the hydrogen coverage is fully replaced by OH groups. This reduction of the electronic gap is consistent with the experimentally observed red shift of the absorbance spectrum with increasing OH coverage.¹⁰ Moreover, additional flat bands in conductance band due to localized surface states are formed at the Γ point (Fig. 3e).

Figure 2. Geometry of (a) the GaAs nanocrystal (gray spheres indicate Ga atoms, purple spheres As atoms, and white spheres H atoms respectively) and (b) the Pb nanocrystal. The corresponding quasi-band structures are given in (c) for GaAs and (d) for Pb, here the dotted blue line indicates the Fermi energy.

Figure 3. Density of states for pristine Si-NC with 0% OH coverage (blue) and Si-NC with full 100% OH coverage (red) for (a) $d = 1.8$ nm and (b) $d = 2.9$ nm. The DOS is calculated by Gaussian broadening (0.025 eV) and superimposing each discrete molecular energy level.

Conclusion

We have introduced the concept of a quasi-band structure which allows us to get an approximate band-like description for objects with sizes falling in between finite-sized molecules and bulk materials. The quasi-band structure allows us to apply, at least approximately, many concepts from standard band structure theory, while at the same time account for finite-size effects. We applied this approach to quantum confined nanocrystals for which surface effects are particular important. Even for small nanocrystals band-like features emerge due to the broadening of the energy eigenstates at finite temperatures. With increasing particle size the band-like features become more and more pronounced. We showed that it is possible to identify clearly the direct and indirect characteristics of band gaps as well as connect the quasi-band structures to features of the corresponding bulk material. Also effects induced by surface functionalization can be readily identified and characterized by means of the quasi-band structure.

Acknowledgements

M.B. and V.S. acknowledge the support by Kakenhi 20H02579 by the Japanese Promotion of Sciences (JSPS), Japan.

Author contributions statement

M.B. performed the calculation and wrote the manuscript. M.B. and V.S. provided funding for this project. All authors contributed to the interpretation and discussion of the result. All authors have read and agreed to the published version of the manuscript.

References

1. Brus, L. E. Electron-electron and electron-hole interactions in small semiconductor crystallites: The size dependence of the lowest excited electronic state. *J. Chem. Phys.* **80**, 4403–4409, DOI: [10.1063/1.447218](https://doi.org/10.1063/1.447218) (1984).
2. Nenadovic, M. T., Rajh, T. & Micic, O. I. Size quantization in small semiconductor particles. *J. Phys. Chem.* **89**, 397–399, DOI: [10.1021/j100249a004](https://doi.org/10.1021/j100249a004) (1985).
3. Bawendi, M. G., Steigerwald, M. L. & Brus, L. E. The quantum mechanics of larger semiconductor clusters ("quantum dots"). *Annu. Rev. Phys. Chem.* **41**, 477–496, DOI: [10.1146/annurev.pc.41.100190.002401](https://doi.org/10.1146/annurev.pc.41.100190.002401) (1990).
4. Bányai, L. & Koch, S. W. *Semiconductor Quantum Dots*, vol. Volume 2 (WORLD SCIENTIFIC, 1993).
5. Hybertsen, M. S. Absorption and emission of light in nanoscale silicon structures. *PRL* **72**, 1514–1517, DOI: [10.1103/PhysRevLett.72.1514](https://doi.org/10.1103/PhysRevLett.72.1514) (1994).
6. Iida, T. Control of plasmonic superradiance in metallic nanoparticle assembly by light-induced force and fluctuations. *J. Phys. Chem. Lett.* **3**, 332–336, DOI: [10.1021/jz2014924](https://doi.org/10.1021/jz2014924) (2012).
7. Murray, C. B., Norris, D. J. & Bawendi, M. G. Synthesis and characterization of nearly monodisperse cde (e = sulfur, selenium, tellurium) semiconductor nanocrystallites. *J. Am. Chem. Soc.* **115**, 8706–8715, DOI: [10.1021/ja00072a025](https://doi.org/10.1021/ja00072a025) (1993).
8. Švrček, V. *et al.* Dramatic enhancement of photoluminescence quantum yields for surface-engineered si nanocrystals within the solar spectrum. *Adv. Funct. Mater.* **23**, 6051–6058, DOI: [10.1002/adfm.201301468](https://doi.org/10.1002/adfm.201301468) (2013).
9. Mariotti, D., Švrček, V., Hamilton, J. W. J., Schmidt, M. & Kondo, M. Silicon nanocrystals in liquid media: Optical properties and surface stabilization by microplasma-induced non-equilibrium liquid chemistry. *Adv. Funct. Mater.* **22**, 954–964, DOI: [10.1002/adfm.201102120](https://doi.org/10.1002/adfm.201102120) (2012).
10. Bürkle, M. *et al.* Bandgap engineering in oh-functionalized silicon nanocrystals: Interplay between surface functionalization and quantum confinement. *Adv. Funct. Mater.* **27**, 1701898, DOI: [10.1002/adfm.201701898](https://doi.org/10.1002/adfm.201701898) (2017).
11. Bürkle, M. *et al.* Tuning the bandgap character of quantum-confined si-sn alloyed nanocrystals. *Adv. Funct. Mater.* **30**, 1907210, DOI: [10.1002/adfm.201907210](https://doi.org/10.1002/adfm.201907210) (2020).
12. Kovalenko, M. V. *et al.* Prospects of nanoscience with nanocrystals. *ACS Nano* **9**, 1012–1057, DOI: [10.1021/nn506223h](https://doi.org/10.1021/nn506223h) (2015).
13. He, Y., Fan, C. & Lee, S.-T. Silicon nanostructures for bioapplications. *Nano Today* **5**, 282–295, DOI: [10.1016/j.nantod.2010.06.008](https://doi.org/10.1016/j.nantod.2010.06.008) (2010).
14. Erathodiyil, N. & Ying, J. Y. Functionalization of inorganic nanoparticles for bioimaging applications. *Acc. Chem. Res.* **44**, 925–935, DOI: [10.1021/ar2000327](https://doi.org/10.1021/ar2000327) (2011).

15. Macias-Montero, M. *et al.* Energy band diagram of device-grade silicon nanocrystals. *Nanoscale* **8**, 6623–6628, DOI: [10.1039/C5NR07705B](https://doi.org/10.1039/C5NR07705B) (2016).
16. Peng, F. *et al.* Silicon nanomaterials platform for bioimaging, biosensing, and cancer therapy. *Acc. Chem. Res.* **47**, 612–623, DOI: [10.1021/ar400221g](https://doi.org/10.1021/ar400221g) (2014).
17. Sun, K. *et al.* Enabling silicon for solar-fuel production. *Chem. Rev.* **114**, 8662–8719, DOI: [10.1021/cr300459q](https://doi.org/10.1021/cr300459q) (2014).
18. Xiao, Z. & Farokhzad, O. C. Aptamer-functionalized nanoparticles for medical applications: Challenges and opportunities. *ACS Nano* **6**, 3670–3676, DOI: [10.1021/nn301869z](https://doi.org/10.1021/nn301869z) (2012).
19. Ashcroft, N. W. & Mermin, N. D. *Solid State Physics* (Holt-Saunders, 1976).
20. Hapala, P., Kůsová, K., Pelant, I. & Jelínek, P. Theoretical analysis of electronic band structure of 2- to 3-nm si nanocrystals. *PRB* **87**, 195420, DOI: [10.1103/PhysRevB.87.195420](https://doi.org/10.1103/PhysRevB.87.195420) (2013).
21. Kittel, C. *Introduction to Solid State Physics* (Wiley, 2004), 8 edn.
22. Kůsová, K. *et al.* Direct bandgap silicon: Tensile-strained silicon nanocrystals. *Adv. Mater. Interfaces* **1**, 1300042, DOI: [10.1002/admi.201300042](https://doi.org/10.1002/admi.201300042) (2014).
23. Damascelli, A., Hussain, Z. & Shen, Z.-X. Angle-resolved photoemission studies of the cuprate superconductors. *RMP* **75**, 473–541, DOI: [10.1103/RevModPhys.75.473](https://doi.org/10.1103/RevModPhys.75.473) (2003).
24. Buerkle, M., Lozach, M., McDonald, C., Mariotti, D. & Svrcek, V. (invited) electronic and optical properties of quantum-confined nanoparticles. *ECS Trans.* **102**, 67–73, DOI: [10.1149/10201.0067ecst](https://doi.org/10.1149/10201.0067ecst) (2021).
25. Doniach, S. & Sondheimer, E. H. *Green's Functions for Solid State Physicists* (PUBLISHED BY IMPERIAL COLLEGE PRESS AND DISTRIBUTED BY WORLD SCIENTIFIC PUBLISHING CO., 1998).
26. Ku, W., Berlijn, T. & Lee, C.-C. Unfolding first-principles band structures. *PRL* **104**, 216401, DOI: [10.1103/PhysRevLett.104.216401](https://doi.org/10.1103/PhysRevLett.104.216401) (2010).
27. Perdew, J. P., Burke, K. & Ernzerhof, M. Generalized gradient approximation made simple. *PRL* **77**, 3865–3868, DOI: [10.1103/PhysRevLett.77.3865](https://doi.org/10.1103/PhysRevLett.77.3865) (1996).
28. Dunning, T. & Hay, P. *Methods of Electronic Structure Theory, Vol. 3; III, H. F. S., Ed.*; (Plenum Press, 1977).
29. Wadt, W. R. & Hay, P. J. Ab initio effective core potentials for molecular calculations. potentials for main group elements na to bi. *J. Chem. Phys.* **82**, 284–298, DOI: [10.1063/1.448800](https://doi.org/10.1063/1.448800) (1985).
30. Turbomole 6.4, turbomole gmbh karlsruhe, <http://www.turbomole.com>. turbomole is a development of university of karlsruhe and forschungszentrum karlsruhe 1989-2007, turbomole gmbh since 2007.
31. Kano, J., Kizuka, T., Shikanai, F. & Kojima, S. Pure lead nanoparticles with stable metallic surfaces, on perovskite lead strontium titanate particles. *Nanotechnology* **20**, 295704, DOI: [10.1088/0957-4484/20/29/295704](https://doi.org/10.1088/0957-4484/20/29/295704) (2009).